



Standard Specification for Polyethylene (PE) Plastic Pipe (SDR-PR) Based on Outside Diameter¹

This standard is issued under the fixed designation F714; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers polyethylene (PE) pipe made in dimensions based on outside diameters of 90 mm (3.500 in.) and larger.

1.2 Three standard outside diameter sizing systems are detailed: one known as the ISO metric system, one known as the IPS system, and the other known as the DIPS system. See 5.2.5 for guidelines for special sizes.

1.3 The piping is intended for new construction and insertion renewal of old piping systems used for the transport of water, municipal sewage, domestic sewage, industrial process liquids, effluents, slurries, etc., in both pressure and nonpressure systems.

NOTE 1—The user should consult the manufacturer to ensure that any damage to the polyethylene pipe caused by the material being transported will not affect the service life beyond limits acceptable to the user.

1.4 All pipes produced under this specification are pressure-rated. See Appendix X5 for information on pressure rating.

NOTE 2—References and material descriptions for PE2406, PE3406, PE3408 and materials having a HDB of 1450 psi have been removed from Specification F714 due to changes in Specification D3350 and PPI TR-3. For removed designations, refer to previous editions of Specification F714, Specification D3350, PPI TR-3 and PPI TR-4. The removal of these materials does not affect pipelines that are in service. See Notes 9 and 10.

1.5 This specification includes criteria for choice of raw material, together with performance requirements and test methods for determining conformance with the requirements.

1.6 Quality-control measures are to be taken by manufacturers. See Appendix X4 for general information on quality control.

1.7 In referee decisions, the SI units shall be used for metric-sized pipe and inch-pound units for pipe sized in the IPS system (ANSI B36.10) and DIPS system. In all cases, the values given in parentheses are provided for information only.

¹ This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.26 on Olefin Based Pipe.

Current edition approved March 1, 2008. Published March 2008. Originally approved in 1981. Last previous edition approved in 2006 as F714 – 06a. DOI: 10.1520/F0714-08.

1.8 The following safety hazards caveat pertains only to the test methods portion, Section 6, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

D1598 Test Method for Time-to-Failure of Plastic Pipe Under Constant Internal Pressure

D1599 Test Method for Resistance to Short-Time Hydraulic Pressure of Plastic Pipe, Tubing, and Fittings

D1600 Terminology for Abbreviated Terms Relating to Plastics

D2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings

D2290 Test Method for Apparent Hoop Tensile Strength of Plastic or Reinforced Plastic Pipe by Split Disk Method

D2321 Practice for Underground Installation of Thermoplastic Pipe for Sewers and Other Gravity-Flow Applications

D2412 Test Method for Determination of External Loading Characteristics of Plastic Pipe by Parallel-Plate Loading

D2837 Test Method for Obtaining Hydrostatic Design Basis for Thermoplastic Pipe Materials or Pressure Design Basis for Thermoplastic Pipe Products

D3350 Specification for Polyethylene Plastics Pipe and Fittings Materials

F412 Terminology Relating to Plastic Piping Systems

F585 Practice for Insertion of Flexible Polyethylene Pipe Into Existing Sewers

2.2 ANSI Standard:

B36.10 Standard Dimensions of Steel Pipe (IPS)³

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

2.3 ISO Standards:

161 Thermoplastic Pipe for the Transport of Fluids - Nominal Outside Diameters and Nominal Pressures⁴

3607 Polyethylene Pipe: Tolerances on Outside Diameters and Wall Thicknesses⁴

4427 Polyethylene Pipes and Fittings for Water Supply Specification⁴

2.4 Federal Standard:

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)⁵

2.5 Military Standard:

MIL-STD-129 Marking for Shipment and Storage⁵

2.6 Canadian Standard:

CGSB 41 GP-25M Pipe, Polyethylene for the Transport of Liquids⁶

2.7 NSF/ANSI Standards:

Standard No. 14 for Plastic Piping Components and Related Materials⁷

Standard No. 61 for Drinking Water Systems Components—Health Effects⁷

2.8 Other Documents:

PPI TR-3 Policies and Procedures for Developing Hydrostatic Design Basis (HDB), Pressure Design Basis (PDB), Strength Design Basis (SDB), and Minimum Required Strength (MRS) Ratings for Thermoplastic Piping Materials or Pipe⁸

PPI TR-4 HDB/SDB/PDB/MRS Listed Materials, PPI Listing of Hydrostatic Design Basis (HDB), Strength Design Basis (SDB), Pressure Design Basis (PDB), and Minimum Required Strength (MRS) Ratings for Thermoplastic Piping Materials or Pipe⁸

3. Terminology

3.1 Unless otherwise specified, definitions are in accordance with Terminology **F412** and abbreviations are in accordance with Terminology **D1600**.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *relation between dimension ratio, hydrostatic design stress, and hydrostatic pressure:*

$$P = \frac{2S}{(D_o/t) - 1}$$

where:

S = hydrostatic design stress, psi (or kPa or MPa),

P = pressure rating, psi (or kPa or MPa),

D_o = average outside diameter, in. (or mm),

t = minimum wall thickness, in. (or mm), and

D_o/t = dimension ratio.

3.2.2 *relations between hydrostatic design basis and hydrostatic design stress*—the hydrostatic design stress, S , is deter-

⁴ Available from International Organization for Standardization (ISO), 1 rue de Varembe, Case postale 56, CH-1211, Geneva 20, Switzerland, <http://www.iso.ch>.

⁵ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.

⁶ Available from Canadian Standards Association (CSA), 5060 Spectrum Way, Mississauga, ON L4W 5N6, Canada, <http://www.csa.ca>.

⁷ Available from NSF International, P.O. Box 130140, 789 N. Dixboro Rd., Ann Arbor, MI 48113-0140, <http://www.nsf.org>.

⁸ Available from Plastics Pipe Institute (PPI), 105 Decker Court, Suite 825, Irving, TX 75062, <http://www.plasticpipe.org>.

mined by multiplying the hydrostatic design basis (HDB) by a design factor, DF that has a value less than 1.0.

NOTE 3—Hydrostatic design stress (HDS) ratings for PE materials are in accordance with Test Method **D2837** and **PPI TR-3** and are listed in **PPI TR-4**.

4. Materials

4.1 *Polyethylene Compound*—Polyethylene material compounds suitable for use in the manufacture of pipe under this specification shall meet Specification **D3350** and shall meet the Specification **D3350** classification and property requirements in **Table 2**, and shall have PPI TR-4 HDB and HDS listings at 73°F (23°C) and HDB listings 140°F (60°C) in accordance with **Table 2**. See S1.

4.2 *Color and Ultraviolet (UV) Stabilization*—Polyethylene material compounds shall meet Specification **D3350** code C or E. Code C material compounds shall have 2 to 3 percent carbon black. Code E material compounds shall be colored with UV stabilizer.

4.3 *Rework Material*—Clean polyethylene compound from the manufacturer's own pipe production that met 4.1 and 4.2 as virgin material is suitable for reextrusion into pipe, either alone or blended with new compound of the same cell classification or material designation. Pipe containing the rework material shall meet the material and product requirements of this specification.

5. Requirements

5.1 *Workmanship*—The pipe shall be homogeneous throughout and essentially uniform in color, opacity, density, and other properties. The inside and outside surfaces shall be semimatte or glossy in appearance (depending on the type of plastic) and free of chalking, sticky, or tacky material. The surfaces shall be free of excessive bloom, that is, slight bloom is acceptable. The pipe walls shall be free of cracks, holes, blisters, voids, foreign inclusion, or other defects that are visible to the naked eye and that may affect the wall integrity. Holes deliberately placed in perforated pipe are acceptable. Bloom or chalking may develop in pipe exposed to direct rays of the sun (ultraviolet radiant energy) for extended periods and, consequently, these requirements do not apply to pipe after extended exposure to direct rays of the sun.

5.2 Dimensions and Tolerances:

5.2.1 *Outside Diameters*—These shall be in accordance with **Table 3** (SI units), **Table 4** (inch-pound units) or **Table 5** (inch-pound units) when measured in accordance with Test Method **D2122** at any point not closer than 300 mm (11.8 in.) to the cut end of a length of pipe. Conditioning to standard temperature without regard to relative humidity is required.

5.2.2 *Wall Thicknesses*—The minimum thicknesses shall be in accordance with **Table 6**, **Table 7**, or **Table 8** when measured in accordance with Test Method **D2122**. Conditioning to standard temperature without regard to relative humidity is required.

5.2.3 *Eccentricity*—The wall thickness variability as measured and calculated in accordance with Test Method **D2122** in any diametrical cross section of the pipe shall not exceed 12 %.

5.2.4 *Toe-In*—When measured in accordance with 5.2.1, the outside diameter at the cut end of the pipe shall not be more

TABLE 1 Elevated Temperature Sustained Pressure Test Requirements

Condition	PE, 2606, PE2706, PE2708, PE3608, PE3708, PE4608, PE4708			PE3710, PE4710	
	Test Temperature °F (°C) ^A	Test Pressure Hoop Stress ^B psi (kPa) ^A	Minimum Average Time Before Failure Hours	Test Pressure Hoop Stress ^B psi (kPa) ^A	Minimum Average Time Before Failure Hours
1	176 (80)	670 (4620)	170	750 (5170)	200
2	176 (80)	650 (4480)	340	730 (5020)	400
3	176 (80)	630 (4345)	510	705 (4870)	600
4	176 (80)	610 (4210)	680	685 (4715)	800
5	176 (80)	590 (4070)	850	660 (4565)	1000
6	176 (80)	580 (4000)	1000	640 (4415)	1200

^ATest temperature tolerance $\pm 3.6^{\circ}\text{F}$ ($\pm 2^{\circ}\text{C}$). Test pressure tolerance ± 5 psi (± 35 kPa); test pressure hoop stress values are rounded to the nearest 5 psi or 5 kPa.

Note: **Table 2** conditions are based on PE validation requirements per PPI TR-3 with Condition 6 being 85% of Condition 1 test pressure hoop stress and six times greater minimum average time before failure. Conditions 2 through 5 are linear stress and time interpolations between Conditions 1 and 6. The intent of multiple conditions is to maintain equivalent performance criteria, but provide for retest in the event of ductile failure. The test pressure hoop stress levels for Conditions 2-5 are linear interpolations for arbitrarily chosen time increments. An equivalent performance requirement, however, may be determined by arbitrarily choosing a test pressure hoop stress between Conditions 1 and 6 and linearly interpolating the minimum average time before failure. For example for PE3710 and PE4710 material, at 670 psi test pressure hoop stress, the minimum average time before failure would be $927 \text{ hours} (200 + (750 - 670) \cdot ((1200 - 200) / (750 - 640))) = 927$.

^BCalculate internal test pressure in accordance with:

$$P = \frac{2s}{\left(\frac{D_o}{t} - 1\right)}$$

Where:

P = test pressure, psig (kPa)

S = test pressure hoop stress, psi. (kPa)

D_o = measured outside diameter, in. (mm)

t = measured minimum wall thickness, in (mm)

TABLE 2 Specification D3350 Classification and Properties for Polyethylene Pipe Materials

Physical Properties	Cell Classification Number or Property Value							
	PE2606	PE2706	PE2708	PE3608	PE3708	PE3710	PE4708	PE4710
Density	2	2	2	3	3	3	4	4
Melt index	3 or 4	3 or 4	3 or 4	4	4	4	4	4
Flexural modulus	≥ 4	≥ 4	≥ 4	≥ 4	≥ 4	≥ 4	≥ 4	≥ 5
Tensile strength	≥ 3	≥ 3	≥ 3	≥ 4	≥ 4	≥ 4	≥ 4	≥ 4
Slow crack growth resistance (F1473)	6	7	7	6	7	7	7	7
Hydrostatic strength classification	3	3	3	4	4	4	4	4
Color and UV Stabilizer ^A	C or E _B	C or E _B	C or E _B	C or E _B	C or E _B	C or E _B	C or E _B	C or E _B
HDB at 140°F (60°C), PPI TR-4, psi (MPa)								
HDS at 73°F (23°C); PPI TR-4, psi (MPa)	630 (4.34)	630 (4.34)	800 (5.52)	800 (5.52)	800 (5.52)	1000 (6.90)	800 (5.52)	1000 (6.90)

^A See 4.2.

^BListing required; consult manufacturer for listed value

than 1.5 % smaller than the undistorted outside diameter. Measurement of the undistorted outside diameter shall be made no closer than 1.5 pipe diameters or 11.8 in. (300 mm), whichever distance is less, from the cut end of the pipe. Undistorted outside diameter shall meet specifications in **Table 3**, **Table 4**, or **Table 5**.

5.2.5 Special Sizes—Where existing system conditions or special local requirements make other diameters or dimension ratios necessary, other sizes or dimension ratios, or both, shall be acceptable for engineered applications when mutually agreed upon by the customer and the manufacturer, if the pipe is manufactured from plastic compounds meeting the material requirements of this specification, and the strength and design requirements are calculated on the same basis as those used in this specification. For diameters not shown in **Table 3**, **Table 4**, or **Table 5**, the tolerance shall be the same percentage as that used in the corresponding table for the next smaller listed size. Minimum wall thicknesses for DRs not shown in **Table 6**, **Table 7**, or **Table 8** shall be determined by dividing the average outside diameter by the DR and rounding to three decimal

places for inch sized pipes or two decimal places for metric sized pipes, and the tolerance shall comply with **5.2.3**.

5.3 Pressure Test Performance—All pipe shall meet the requirements of **5.3.2** and either **5.3.1** or **5.4**.

NOTE 4—The requirements of **5.3.1** and **5.3.2** are for laboratory proof-testing only and should not be interpreted as applicable to in situ testing for acceptance of installed systems. See appropriate installation and leak testing standards or manufacturer’s recommendations for field testing procedure.

5.3.1 Short-Term Pressurization—Quick burst or non-failure testing shall be conducted per **5.3.1.1** or **5.3.1.2**. Test pressure shall be determined per **3.2.1** except that S shall be the prescribed hoop stress value, and P shall be test pressure.

5.3.1.1 Quick Burst—For pipe nominal 12-in. (315 mm) and smaller diameter, rupture shall be ductile when tested in accordance with **6.1**. The minimum hoop stress shall be 2500 psi for **Table 2** density cell 2 materials and 2900 psi for **Table 2** density cell 3 and 4 materials.

5.3.1.2 Non-Failure—When raised to test pressure and held at test pressure for five (5) seconds, pipe shall not rupture, leak,

TABLE 3 Outside Diameters and Tolerances

ISO Sizing System (ISO 161/1)			
Nominal Pipe Size	Equivalent	Outside Diameter, D _o , mm	
		min	max ^A
mm	in.		
90	3.543	90	90.8
110	4.331	110	111.0
160	6.299	160	161.4
200	7.874	200	201.8
250	9.843	250	252.3
280	11.024	280	282.5
315	12.402	315	317.8
355	13.976	355	358.2
400	15.748	400	403.6
450	17.717	450	454.1
500	19.685	500	504.5
560	22.047	560	565.0
630	24.803	630	635.7
710	27.953	710	716.4
800	31.496	800	807.2
900	35.433	900	908.1
1000	39.370	1000	1009.0
1200	47.244	1200	1210.8
1400	55.118	1400	1412.6
1600	62.992	1600	1614.4

^A As specified in ISO 3607.

TABLE 5 Outside Diameters and Tolerances

DIPS Sizing System			
Nominal DIPS Sizes, in.	Equivalent, mm	Actual Outside Diameters, in.	
		Average	Tolerance ± in.
3	100.6	3.96	0.016
4	121.9	4.80	0.022
6	175.3	6.90	0.031
8	229.9	9.05	0.041
10	281.9	11.10	0.050
12	385.3	13.20	0.059
14	388.6	15.30	0.069
16	442.0	17.40	0.078
18	495.3	19.50	0.088
20	548.6	21.60	0.097
24	655.3	25.80	0.116
30	812.8	32.00	0.144
36	972.8	38.30	0.172
42	1130.3	44.50	0.200
48	1290.3	50.80	0.229

TABLE 6 Minimum Wall Thickness ISO 161 Sizing System, mm

DR Nominal Pipe Size	Actual Outside Diameters, in.						
	41	32.5	26	21	17	11	
90	3.5	4.3	5.3	8.2	
110	...	3.4	4.2	5.2	6.5	10.0	
160	...	4.9	6.2	7.6	9.4	14.5	
200	...	6.2	7.7	9.5	11.8	18.2	
250	...	7.7	9.6	11.9	14.7	22.7	
280	...	8.6	10.8	13.3	16.5	25.5	
315	...	9.7	12.1	15.0	18.5	28.6	
355	...	10.9	13.7	16.9	20.9	32.3	
400	...	12.3	15.4	19.0	23.5	36.4	
450	...	13.8	17.3	21.4	26.5	...	
500	...	15.4	19.2	23.8	29.4	...	
560	...	17.2	21.5	26.7	32.9	...	
630	...	19.4	24.2	30.0	37.1	...	
710	...	21.8	27.3	33.8	41.8	...	
800	...	24.6	30.8	38.1	47.1	...	
900	...	27.7	34.6	42.9	
1000	24.4	30.8	38.5	47.6	
1200	29.3	36.9	46.2	
1400	34.1	43.1	
1600	39.0	49.2	

TABLE 4 Outside Diameters and Tolerances IPS Sizing System (ANSI B36.10)

Nominal Pipe Size, in.	Equivalent, mm	Actual Outside Diameters, in.	
		Average	Tolerance ± in.
3	88.9	3.500	0.016
4	114.3	4.500	0.020
5 ^A	136.5	5.375	0.025
5	141.3	5.563	0.025
6	168.3	6.625	0.030
7 ^A	181.0	7.125	0.034
8	219.1	8.625	0.039
10	273.1	10.750	0.048
12	323.8	12.750	0.057
13 ^A	339.7	13.375	0.060
14	355.6	14.000	0.063
16	406.4	16.000	0.072
18	457.2	18.000	0.081
20	508.0	20.000	0.090
21.5 ^A	546.1	21.500	0.097
22	558.8	22.000	0.099
24	609.6	24.000	0.108
26	660.4	26.000	0.117
28	711.2	28.000	0.126
30	762.0	30.000	0.135
32	812.8	32.000	0.144
34	863.6	34.000	0.153
36	914.4	36.000	0.162
42	1066.8	42.000	0.189
48	1219.2	48.000	0.216
54	1371.6	54.000	0.243

^A Irregular size.

nor exhibit localized deformation when tested in accordance with 6.1 at a test pressure determined using 2500 psi hoop stress for Table 2 density cell 2 materials, and 3200 psi hoop stress for Table 2 density cell 3 and 4 materials.

5.3.2 Elevated Temperature Sustained Pressure—Elevated-temperature sustained-pressure test for each Table 2 polyethylene pipe material (material designation) used in production at the facility shall be conducted per 6.2.

NOTE 5—Elevated temperature sustained pressure tests are intended to

verify extrusion processing and are conducted in accordance with the manufacture’s quality program.

5.3.2.1 Passing results are (1) non-failure for all three specimens at a time equal to or greater than the Table 1 “minimum average time before failure”, or (2) not more than one ductile specimen failure and the average time before failure for all three specimens shall be greater than the specified “minimum average time before failure” for the selected Table 1 Condition. If more than one ductile failure occurs before the Table 1 “minimum average time before failure”, it is permissible to conduct one retest at a Table 1 Condition of lower stress and longer minimum average time before failure for the material designation except that for Table 1 Condition 6 no retest is permissible. Brittle failure of any specimen in the test sample when tested at Table 1 Condition 1 through 6 constitutes failure to meet this requirement and no retest is allowed.

5.3.2.2 Provision for retest (if needed)—The retest sample shall be three specimens of the same pipe or tubing size and

**TABLE 7 Minimum Wall Thickness
IPS Sizing System, in. (ANSI B36.10)**

Nominal IPS Pipe Size	Actual Pipe Size	Dimension Ratio											
		41	32.5	26	21	17	15.5	13.5	11	9.3	9	8.3	7.3
3	3.500	0.085	0.108	0.135	0.167	0.206	0.226	0.259	0.318	0.376	0.389	0.422	0.479
4	4.500	0.110	0.138	0.173	0.214	0.265	0.290	0.333	0.409	0.484	0.500	0.542	0.616
5 ^A	5.375	0.131	0.165	0.207	0.256	0.316	0.347	0.398	0.489	0.578	0.597	0.648	0.736
5	5.563	0.136	0.171	0.214	0.265	0.327	0.359	0.412	0.506	0.598	0.618	0.670	0.762
6	6.625	0.162	0.204	0.255	0.315	0.390	0.427	0.491	0.602	0.712	0.736	0.798	0.908
7 ^A	7.125	0.174	0.219	0.274	0.340	0.420	0.460	0.528	0.648	0.766	0.792	0.858	0.976
8	8.625	0.210	0.265	0.332	0.411	0.507	0.556	0.639	0.784	0.927	0.958	1.039	1.182
10	10.750	0.262	0.331	0.413	0.512	0.632	0.694	0.796	0.977	1.156	1.194	1.295	1.473
12	12.750	0.310	0.392	0.490	0.607	0.750	0.823	0.944	1.159	1.371	1.417	1.536	1.747
13 ^A	13.375	0.326	0.412	0.514	0.637	0.787	0.863	0.991	1.216	1.438	1.486	1.611	1.832
14	14.000	0.341	0.431	0.538	0.667	0.824	0.903	1.037	1.273	1.505	1.556	1.687	1.918
16	16.000	0.390	0.492	0.615	0.762	0.941	1.032	1.185	1.455	1.720	1.778	1.928	2.192
18	18.000	0.439	0.554	0.692	0.857	1.059	1.161	1.333	1.636	1.935	2.000	2.169	2.466
20	20.000	0.488	0.615	0.769	0.952	1.176	1.290	1.481	1.818	2.151	2.222	2.409	...
21.5 ^A	21.500	0.524	0.662	0.827	1.024	1.265	1.387	1.593
22	22.000	0.537	0.677	0.846	1.048	1.294	1.419	1.630	2.000	2.366	2.444
24	24.000	0.585	0.738	0.923	1.143	1.412	1.548	1.778	2.182	2.581	2.667
26	26.000	0.634	0.800	1.000	1.238	1.529	1.677	1.926	2.364	2.796
28	28.000	0.683	0.862	1.077	1.333	1.647	1.806	2.074	2.545	3.011
30	30.000	0.732	0.923	1.154	1.429	1.765	1.935	2.222	2.727	3.226
32	32.000	0.780	0.985	1.231	1.524	1.882	2.065	2.370	2.909
34	34.000	0.829	1.046	1.308	1.619	2.000	2.194	2.519	3.091
36	36.000	0.878	1.108	1.385	1.714	2.118	2.323	2.667	3.273
42	42.000	1.024	1.292	1.615	2.000	2.471	2.710
48	48.000	1.171	1.477	1.846	2.286	2.824	3.097
54	54.000	1.317	1.662	2.077	2.571	3.176

^A Irregular size.

TABLE 8 Minimum Wall Thickness

Nominal DIPS Pipe Size	Actual OD ^A Pipe Size	DIPS Sizing System, in.						
		Dimension Ratio						
		41	32.5	26	21	17	13.5	11
3	3.96	...	0.122	0.153	0.189	0.233	0.294	0.360
4	4.80	0.117	0.148	0.185	0.229	0.283	0.356	0.437
6	6.90	0.168	0.213	0.266	0.329	0.406	0.512	0.628
8	9.05	0.221	0.279	0.348	0.431	0.533	0.670	0.823
10	11.10	0.236	0.342	0.427	0.529	0.653	0.823	1.009
12	13.20	0.322	0.407	0.508	0.629	0.777	0.978	1.200
14	15.30	0.373	0.471	0.589	0.729	0.900	1.134	1.391
16	17.40	0.424	0.536	0.670	0.829	1.024	1.289	1.582
18	19.50	0.463	0.600	0.750	0.929	1.147	1.445	1.773
20	21.60	0.527	0.665	0.831	1.029	1.271	1.600	1.964
24	25.80	0.629	0.794	0.993	1.229	1.518	1.912	2.346
30	32.00	0.780	0.985	1.231	1.524	1.883	2.371	2.909
36	38.30	0.934	1.179	1.473	1.824	2.253	2.837	3.482
42	44.50	1.085	1.370	1.712	2.119	2.618	3.297	4.046
48	50.80	1.239	1.563	1.954	2.419	2.989	3.763	4.619

^A In accordance with Table 6.

compliance with Section 5, Requirements, it is acceptable to test individual samples.

NOTE 6—Manufacturers conduct appropriate quality control tests at a frequency appropriate to their manufacturing operations. See Appendix X4.

6. Test Methods

6.1 *Short-Term Pressurization Tests*—When tested to rupture, this test is applicable to nominal 12-in. (315-mm) and smaller pipes and is conducted in accordance with Test Method D1599. When tested for non-failure, this test is applicable to all pipe sizes and is conducted in accordance with Test Method D1598 except that no failure will have occurred when tested at the test pressure and duration per 5.3.1.2. The test shall be conducted at 73.4 ± 3.6°F (23 ± 2°C) without regard to relative humidity.

NOTE 7—**Warning:** Pressurization of specimens being tested under 6.1 should not commence until it is certain that all entrapped air has been bled from the water-filled specimens.

6.2 *Elevated Temperature Sustained Pressure Test*—The “test sample” shall be three specimens of a generally representative pipe or tubing size produced at the manufacturer’s facility using the Table 2 polyethylene pipe material (material designation). Select one Table 1 Condition for the Table 2 polyethylene pipe material (material designation) and test the three specimen test sample in accordance with Test Method D1598 using water as the internal test medium.

6.3 *Apparent Tensile Properties*—The procedure and test equipment shall be as specified in Test Method D2290. Cut specimens from pipe. Test a minimum of five specimens at 73.4 ± 3.6°F (23 ± 2°C) without regard to relative humidity.

material designation from the same time frame as the test sample per 6.2. For the retest, any specimen failure before the “minimum average time before failure” at the retest condition of lower stress and longer minimum average time before failure constitutes failure to meet this requirement.

5.4 *Apparent Tensile Strength at Yield*—For pipe nominal 3-in. (90-mm) diameter and larger, Short-Term Pressurization requirement, 5.3.1, may be replaced by the apparent tensile strength at yield requirement, 5.4. The minimum apparent tensile strength at yield when determined in accordance with 6.3 shall be 2520 psi (17.4 MPa).

5.5 *Quality Control*—To determine compliance with Section 5, the number of samples specified in the test method shall be tested. For quality control purposes, not for determining

This test is applicable to all pipe of nominal 3-in. (90-mm) outside diameter and larger.

7. Retest and Rejection

7.1 Except as required in 5.3.2.1 or 5.3.2.2, if the results of any test(s) do not meet the requirements of this specification, the test(s) may be conducted again in accordance with an agreement between the purchaser and the seller. There shall be no agreement to lower the minimum requirement of the specification by such means as omitting tests that are a part of the specification, substituting or modifying a test method, or by changing the specification limits. In retesting, the product requirements of this specification shall be met, and the test methods designated in the specification shall be followed. If, upon retest, failure occurs, the quantity of product represented by the test(s) does not meet the requirements of this specification.

8. Certification

8.1 When specified in the purchase order or contract, a manufacturer's certification shall be furnished to the purchaser that the material was manufactured, sampled, tested, and inspected in accordance with this specification, and has been found to meet the requirements. When specified in the purchase order or contract, a report of the test results shall be furnished. Each certification so furnished shall be signed by an authorized agent of the manufacturer.

9. Marking

9.1 Marking on the pipe shall include the following and shall be spaced at intervals of not more than 5 ft (1.5 m).

9.1.1 Markings placed at each end of each shipped length are acceptable by agreement between the manufacturer and the purchaser.

NOTE 8—End of pipe markings are intended for use only per a manufacturer-purchaser agreement where pipe is to be used as a subcomponent by the purchaser for the manufacture of another product such as fabricated fittings, transition fittings, coupling devices or other piping appurtenances where continuous markings along the pipe length may be undesirable. Where pipe is used as the fluid transporting conduit in a piping system, continuous marking per 9.1 is used.

9.1.2 The letters ASTM followed by the designation number of this specification.

9.1.3 The letters PE followed by the Specification D3350 cell classification number of the raw material compound used in accordance with Table 2. Where applicable, the standard thermoplastic pipe materials designation code may be used as an alternative marking.

NOTE 9—The manufacturer determines the thermoplastic material des-

ignation code for the material per Section 4 and Terminology F412. Not all potential combinations are possible, for example, Specification D3350 density cell 2 materials typically qualify for HDB cell 3, but not HDB cell 4. Typical thermoplastic material designation codes are PE2606, PE2708, PE3608, PE3708, PE3710, PE4708 and PE4710.

NOTE 10—Earlier editions of Specification F714 included PE material designations PE2406, PE3406, PE3407 and PE3408. Changes to Specification D3350 and PPI TR-3 led to changes in thermoplastic material designation codes, resulting in material designation PE2406 being superseded by material designations PE2606 and PE2708, material designation PE3406 being superseded by PE3606, material designation PE3407 being discontinued, and material designation PE3408 being superseded by material designations PE3608, PE3708, PE3710, PE4708 and PE4710. Recognizing that a period of time is necessary for the dissemination of information and to update specifications and literature, during the transitional period, product markings that include both older and newer materials designations, for example PE2406/PE2606, may occur.

9.1.4 Nominal pipe outside diameter in mm or inches in accordance with Table 3, Table 4, or Table 5, and the designated sizing system: "XX mm ISO," or "XX in IPS," or "XX in DIPS." For metric outside diameter pipe, "ISO" may be omitted, and for inches outside diameter pipe, "in" may be replaced with a double-quotation mark ("").

9.1.5 Dimension ratio, DR, or pressure rating, or both, in kilopascals or pound-force per square inch shown as "XXX kPa" or "XXX psi" where "XXX" is the numerical value of the pressure rating for water at 80°F (27°C) and lower. See Appendix X5.

9.1.6 Name or trademark of the manufacturer.

9.1.7 Production code from which location and date of manufacturer can be identified.

9.1.8 Pipe intended for the transport of potable water shall also include the seal or mark of the accredited laboratory. (See 4.3.)

9.2 *Using Color to Identify Piping Service*—It is not mandatory to use color to identify piping service, but when color is applied expressly to identify piping service, such as with stripes, a color shell or solid color, blue is used for potable water; green is used for sewer; and purple (violet, lavender) is used for reclaimed water.

10. Quality Assurance

10.1 When the product is marked with this designation, ASTM F714, the manufacturer affirms that the product was manufactured, inspected, sampled, and tested in accordance with this specification and has been found to meet the requirements of this specification.

11. Keywords

11.1 industrial pipe; non-pressure pipe; plastic pipe; polyethylene pipe; pressure pipe; sewer pipe; water pipe