
**Plastics piping systems for the supply
of gaseous fuels — Unplasticized
polyamide (PA-U) piping systems
jointed by solvent cement —**

**Part 2:
Pipes**

iTeh STANDARD PREVIEW

(standards.iteh.ai)
*Systèmes de canalisations en matières plastiques pour la distribution
de combustibles gazeux — Systèmes de canalisations en polyamide
non plastifié (PA-U) avec assemblage par collage —*

ISO 17467-2:2012

Partie 2: Tuyauteries

<https://standards.iteh.ai/catalog/standards/sist/1a35e3-2ed3-453e-bb35-ca8a76285f66/iso-17467-2-2012>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 17467-2:2012

<https://standards.iteh.ai/catalog/standards/sist/c1a35e3-2ed3-453e-bb35-ca8a76285f66/iso-17467-2-2012>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions, symbols and abbreviated terms.....	2
4 Material.....	2
5 Appearance.....	2
6 Geometrical characteristics.....	2
6.1 Measurement of dimensions.....	2
6.2 Mean outside diameters, out-of-roundness and their tolerances.....	2
6.3 Wall thicknesses and tolerances.....	3
7 Mechanical characteristics.....	5
7.1 Conditioning.....	5
7.2 Requirements.....	5
8 Physical characteristics.....	8
8.1 Conditioning.....	8
8.2 Requirements.....	8
9 Marking.....	9

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 17467-2:2012](https://standards.iteh.ai/catalog/standards/sist/c1a35e3-2ed3-453e-bb35-ca8a76285f66/iso-17467-2-2012)

<https://standards.iteh.ai/catalog/standards/sist/c1a35e3-2ed3-453e-bb35-ca8a76285f66/iso-17467-2-2012>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17467-2 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 4, *Plastics pipes and fittings for the supply of gaseous fuels*.

This first edition of ISO 17467-2 cancels and replaces the first edition of ISO 15439-2:2007, which has been technically revised.

ISO 17467 consists of the following parts, under the general title *Plastics piping systems for the supply of gaseous fuels — Unplasticized polyamide (PA-U) piping systems jointed by solvent cement*:

- Part 1: General
- Part 2: Pipes
- Part 3: Fittings

iTeh STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/c1a35e3-2ed3-453e-bb35-ca8a76285f66/iso-17467-2-2012>

Introduction

Thin wall thickness unplasticized polyamide (PA-U) pipes and solvent cement joints are used typically for low pressures, while thicker wall thickness pipes and butt fusion, electrofusion or mechanical joints are typically used for high pressures.

For technical and safety reasons, it is not possible to mix the components of the two types of piping system (thin wall thickness pipes cannot be jointed by butt fusion or mechanical joints and vice versa). In particular, solvent cement joints must not be used for jointing for high pressure piping systems.

So for the time being, the standardisation programme dealing with unplasticized polyamide (PA-U) piping systems for the supply of gaseous fuels is split into two series of International Standards, with one series (ISO 17467) covering piping systems the components of which are connected by solvent cement jointing and the other (ISO 16486) the components of which are connected by fusion jointing and/or mechanical jointing. When more experience will be gained from the field, it might be reasonable to merge ISO 17467 series and ISO 16486 series in one single series applicable to PA-U piping systems.

A similar series (ISO 17135) of International Standards for fusion and mechanically jointed plasticized polyamide (PA-P) piping systems is in preparation.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 17467-2:2012](https://standards.iteh.ai/catalog/standards/sist/c1a35e3-2ed3-453e-bb35-ca8a76285f66/iso-17467-2-2012)

<https://standards.iteh.ai/catalog/standards/sist/c1a35e3-2ed3-453e-bb35-ca8a76285f66/iso-17467-2-2012>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 17467-2:2012

<https://standards.iteh.ai/catalog/standards/sist/c1a35e3-2ed3-453e-bb35-ca8a76285f66/iso-17467-2-2012>

Plastics piping systems for the supply of gaseous fuels — Unplasticized polyamide (PA-U) piping systems jointed by solvent cement —

Part 2: Pipes

1 Scope

This part of ISO 17467 specifies the physical and mechanical properties of pipes made from unplasticized polyamide (PA-U) in accordance with Part 1, intended to be buried and used for the supply of gaseous fuels for maximum operating pressure up to and including 4 bar.

It also specifies the test parameters for the test methods to which it refers.

In addition, this part of ISO 17467 lays down dimensional characteristics and requirements for the marking of pipes.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 161-1, *Thermoplastics pipes for the conveyance of fluids — Nominal outside diameters and nominal pressures — Part 1: Metric series*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 307, *Plastics — Polyamides — Determination of viscosity number*

ISO 1167-1, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method*

ISO 1167-2, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces*

ISO 2505, *Thermoplastics pipes — Longitudinal reversion — Test method and parameters*

ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions*

ISO 3127, *Thermoplastics pipes — Determination of resistance to external blows — Round-the-clock method*

ISO 4065, *Thermoplastics pipes — Universal wall thickness table*

ISO 6259-1, *Thermoplastics pipes — Determination of tensile properties — Part 1: General test method*

ISO 6259-3, *Thermoplastics pipes — Determination of tensile properties — Part 3: Polyolefin pipes*

ISO 11922-1:1997, *Thermoplastics pipes for the conveyance of fluids — Dimensions and tolerances — Part 1: Metric series*

ISO 13477, *Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Small-scale steady-state test (S4 test)*

ISO 13479, *Polyolefin pipes for the conveyance of fluids — Determination of resistance to crack propagation — Test method for slow crack growth on notched pipes*

ISO 13480, *Polyethylene pipes — Resistance to slow crack growth — Cone test method*

ISO 17467-1:2012, *Plastics piping systems for the supply of gaseous fuels — Unplasticized polyamide (PA-U) piping systems jointed by solvent cement — Part 1: General*

3 Terms and definitions, symbols and abbreviated terms

For the purposes of this document, the terms and definitions, symbols and abbreviated terms given in ISO 17467-1 apply.

4 Material

The pipes shall be made from virgin PA-U material. Own and external reprocessible materials and recyclable material shall not be used.

The compound from which the pipes are made shall conform to ISO 17467-1.

5 Appearance

When viewed without magnification, the internal and external surfaces of pipes shall be smooth, clean and free from scoring, cavities and other surface defects which may affect pipe performance. The pipe ends shall be cut cleanly and square to the axis of the pipe.

ITeC STANDARD PREVIEW
(standards.iteh.ai)

6 Geometrical characteristics

ISO 17467-2:2012

<https://standards.iteh.ai/catalog/standards/sist/c1a35e3-2ed3-453e-bb35-ca8a76285f66/iso-17467-2-2012>

6.1 Measurement of dimensions

Dimensions shall be measured in accordance with ISO 3126 at (23 ± 2) °C, after being conditioned for at least 4 h. The measurement shall not be made less than 24 h after manufacture.

6.2 Mean outside diameters, out-of-roundness and their tolerances

The mean outside diameters of the pipe d_{em} and their tolerances shall conform to Table 1.

For maximum mean outside diameter, grade B tolerances, conforming to ISO 11922-1, shall apply.

The maximum absolute out-of-roundness is not applicable for this part of ISO 17467 because the socket re-rounds the pipe spigot when solvent cement jointed.

Table 1 — Mean outside diameters

Dimensions in millimetres

Nominal outside diameter	Mean outside diameter	
	$d_{em,min}$	$d_{em,max}$
12	12,0	12,2
16	16,0	16,3
18	18,0	18,2
20	20,0	20,3
23	23,0	23,2

Table 1 (continued)

Nominal outside diameter	Mean outside diameter	
25	25,0	25,3
32	32,0	32,3
40	40,0	40,4
50	50,0	50,4
63	63,0	63,4
75	75,0	75,5
90	90,0	90,6
110	110,0	110,7
125	125,0	125,8
140	140,0	140,9
160	160,0	161,0
180	180,0	181,1
200	200,0	201,2
225	225,0	226,4
250	250,0	251,5

6.3 Wall thicknesses and tolerances

6.3.1 Minimum wall thickness

ISO 17467-2:2012

<https://standards.iteh.ai/catalog/standards/sist/c1a35e3-2ed3-453e-bb35-c18a76285f66/iso-17467-2:2012>

The minimum wall thickness e_{\min} shall conform to Table 2. Small diameter pipes are characterized by wall thickness. Large diameter pipes are characterized by SDR.

The use of any SDR derived from the pipe series S given in accordance with ISO 4065 and ISO 161-1 is permitted.

NOTE To minimize the possibility of damage to small diameter gas pipes by external influences, the use of pipes with a wall thickness not less than 1,0 mm, even if this is a higher value than according to the minimal SDR value, can be considered.

Table 2 — Minimum wall thickness

Dimensions in millimetres

Nominal outside diameter	Minimum wall thickness	
	e_{\min}	
d_n	SDR 26	SDR 33
12	1,0	1,0
16	1,0	1,0
18	1,0	1,0
20	1,0	1,0
23	1,0	1,0
25	1,0	1,0
32	1,3	1,0