



## Standard Guide for Universal Oxidation/Thermal Stability Test Apparatus<sup>1</sup>

This standard is issued under the fixed designation D 4871; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This guide describes an apparatus used to measure the oxidation or thermal stability of liquids by subjecting them to temperatures in the range from 50 to 375°C in the presence of air, oxygen, nitrogen, or other gases at flow rates of 1.5 to 13 L/h, or in the absence of gas flow. Stability may be measured in the presence or absence of water or soluble or insoluble catalysts. Gases evolved may be allowed to escape, condensed and collected, or condensed and returned to the test cell.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

- D 91 Test Method for Precipitation Number of Lubricating Oils<sup>2</sup>
- D 156 Test Method for Saybolt Color of Petroleum Products (Saybolt Chromometer Method)<sup>2</sup>
- D 445 Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and the Calculation of Dynamic Viscosity)<sup>2</sup>
- D 664 Test Method for Acid Number of Petroleum Products by Potentiometric Titration<sup>2</sup>
- D 974 Test Method for Acid and Base Number by Color-Indicator Titration<sup>2</sup>
- D 1500 Test Method for ASTM Color of Petroleum Products (ASTM Color Scale)<sup>2</sup>
- D 3339 Test Method for Acid Number of Petroleum Products by Semi-Micro Color Indicator Titration<sup>3</sup>
- D 5770 Test Method for Semi-quantitative Micro Determination of Acid Number of Lubricating Oils During Oxidation Testing<sup>4</sup>

<sup>1</sup> This guide is under the jurisdiction of ASTM Committee D02 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.09 on Oxidation.

Current edition approved June 10, 2000. Published July 2000. Originally published as D 4871 - 88. Last previous edition D 4871 - 95.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 05.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 05.02.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 05.03.

### 3. Summary of Guide

3.1 An apparatus is described in which a sample of test fluid, typically from 100 ml or 100 g, is subjected to thermal or oxidative degradation or both. Insoluble or soluble catalyst may be added. Gas may be bubbled through the liquid to provide agitation or to promote oxidation or both. Water or water vapor may be added. At the end of the test or at intervals throughout the test, the liquid is monitored for change in neutralization number, viscosity, weight loss, formation of sludge, or for other parameters. The corrosivity of the fluid toward any catalyst metals can be determined from the appearance and weight change of the metal test specimens, if present, or by monitoring the oil and any sludge or water for metal content. The test is terminated after a fixed time period or when a selected parameter reaches a condemning value.

NOTE 1—The volume of liquid at test temperature should be sufficient to cover the catalysts and should not extend beyond the heated portion of the bath.

### 4. Significance and Use

4.1 This standard describes an apparatus that provides the versatility required to conduct oxidation or thermal stability tests on liquids using a wide variety of test conditions. It is sufficiently flexible so that new test conditions can be chosen in response to the changing demands of the marketplace.

### 5. Apparatus<sup>5</sup>

5.1 *Heating Block*, as shown at the lower right in Fig. 1, to provide a controlled constant temperature for conducting tests.

5.1.1 Test cells are maintained at constant elevated temperature by means of a heated aluminum block which surrounds each test cell.

5.1.2 Holes in the aluminum block to accommodate the test cells shall provide 1.0 mm max clearance for 38-mm outside diameter glass tubes. The glass test cells shall fit into the block to a depth of  $225 \pm 5$  mm.

NOTE 2—The original test blocks were made with spaces for ten test

<sup>5</sup> A standard commercial apparatus has been found satisfactory for the purpose of this guide. This apparatus, including heating block, temperature control system, flow control system and glassware, is available from Falex Corp., 1020 Airpark Drive, Sugar Grove, IL 60554. Glassware for the Universal Oxidation test apparatus is also available from W. A. Sales, Ltd., 419 Harvester Court, Wheeling, IL 60090.



FIG. 1 Universal Oxidation Test Apparatus

cells. Blocks with different number of holes are acceptable if other requirements are met.

5.1.3 The heating system shall be geometrically and thermally balanced. For thermal balance, sizes and locations of the heaters are proportioned against heat losses.

5.1.4 The block is cylindrical and constructed from forged aluminum. The block has a minimum thickness of 38 mm of insulation on all sides, top and bottom. An insulation of thermally efficient ceramic fiber material is suggested.

5.1.5 The exterior jacket, sides and top are stainless steel or equivalent.

5.1.6 The block is equipped with a well for a thermocouple for temperature control and measurement, and a thermometer well for temperature calibration.

5.2 *Temperature Control System*, as shown at lower left in Fig. 1, to maintain the heating block at a set temperature.

5.2.1 The temperature controller shall be capable of maintaining the block temperature within  $\pm 0.5^\circ\text{C}$  of the desired test temperature for the duration of the test. The preferred control-

ler shall have proportional and integral control modes, and a heater malfunction alarm.

5.2.2 The range for operation is from at least  $50^\circ\text{C}$  to  $375^\circ\text{C}$ . (**Warning**—An adjustable deviation alarm that automatically shuts down the system if temperature varies outside preset limits is desirable as a safety feature and to avoid erroneous test results. A separate adjustable high temperature monitor and shutoff is desirable as a safety device.)

5.2.3 Temperature control and uniformity is the most important parameter affecting test result precision. Therefore, the heating system design is critical. Temperature from hole-to-hole and at all sides of each hole in the block shall be uniform within the  $0.5^\circ\text{C}$  tolerance of the total system.

5.3 *Gas Flow Control System*, as shown in Fig. 1, to provide air or other gases to each test cell.

5.3.1 A gas flow controller is required for each test cell, to provide air or other desired gases. (**Warning**—If reactive gases are to be used in the test procedure, all fittings in the gas control system must be compatible with these gases.)