



Designation: ~~A 203/A 203M-97(Reapproved 2003)~~ Designation: A 203/A 203M - 97 (Reapproved 2007)

Standard Specification for Pressure Vessel Plates, Alloy Steel, Nickel¹

This standard is issued under the fixed designation A 203/A 203M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification² covers nickel-alloy steel plates intended primarily for welded pressure vessels.

1.2 Plates under this specification are available with four strength levels and two nickel compositions as follows:

Nominal
Yield
Tensile
Nickel
Strength,
Strength,
Content
min, ksi
min, ksi

Grade%	[MPa] Nominal Nickel Content %	[MPa] Yield Strength, min, ksi [MPa]	Tensile Strength, min, ksi [MPa]
A	A	2.25	37 [255]
B	2.25	40 [275]	70 [485] —D
D	3.50	37 [255]	65 [450] —E
E	3.50	40 [275]	70 [485] —F
F	3.50	40 [275]	70 [485] —F
— 2 in. [50 mm] and under		55 [380]	80 [550]
— 2 in. [50 mm] and under		55 [380]	80 [550] cccc
— Over 2 in. [50 mm]		50 [345]	75 [515]
— Over 2 in. [50 mm]		50 [345]	75 [515]

1.3 The maximum thickness of plates is limited only by the capacity of the composition to meet the specified mechanical property requirements. However, current practice normally limits the maximum thickness of plates furnished under this specification as follows:

Grade	Maximum Thickness, in. [mm]
-	Maximum Thickness, in. [mm]
Grade	
A	6 [150]
B	6 [150]
D	4 [100]
E	4 [100]
F	4 [100]

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents. Therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with this specification.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved Sept. 10, 2003. Published October 2003. Originally approved in 1937. Last previous edition approved in 1997 as A203/A203M-97.

Current edition approved Nov. 1, 2007. Published March 2008. Originally approved in 1937. Last previous edition approved in 2003 as A 203/A 203M - 97 (2003).

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-203/SA-203M in Section II of that Code.

2. Referenced Documents

2.1 ASTM Standards:³

A 20/A 20M [Specification for General Requirements for Steel Plates for Pressure Vessels](#)

A 435/A 435M [Specification for Straight-Beam Ultrasonic Examination of Steel Plates](#)

A 577/A 577M [Specification for Ultrasonic Angle-Beam Examination of Steel Plates](#)

A 578/A 578M [Specification for Straight-Beam Ultrasonic Examination of ~~Plain and Clad~~ Rolled Steel Plates for Special Applications](#)

3. General Requirements and Ordering Information

3.1 Material supplied to this material specification shall conform to Specification A 20/A ~~20M/A20M~~. These requirements outline the testing and retesting methods and procedures, permissible variations in dimensions and mass, quality and repair of imperfections, marking, loading, etc.

3.2 Specification A 20/A ~~20M/A20M~~ also establishes the rules for the basis of purchase that should be complied with when purchasing material to this specification.

3.3 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements. These include:

3.3.1 Vacuum treatment,

3.3.2 Additional or special tension testing,

3.3.3 Impact testing, and

3.3.4 Nondestructive examination.

3.4 The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification A 20/A ~~20M/A20M~~.

3.5 If the requirements of this specification are in conflict with the requirements of Specification A 20/A ~~20M/A20M~~, the requirements of this specification shall prevail.

4. Materials and Manufacture

4.1 *Steelmaking Practice*—The steel shall be killed and shall conform to the fine grain size requirement of Specification A 20/A 20M.

5. Heat Treatment

5.1 All plates shall be thermally treated as follows:

5.1.1 All plates of Grades A, B, D, and E shall be normalized except as permitted by 5.1.1.1.

5.1.1.1 If approved by the purchaser for Grades A, B, D, and E, cooling rates faster than air cooling are permissible for improvement of the toughness, provided the plates are subsequently tempered at not less than 1100°F [595°C] for not less than ½ h. <https://standards.iteh.ai/catalog/standards/sist/9e390247-19f4-4bab-a485-a61c27fd3740/astm-a203-a203m-972007>

5.1.2 All plates of Grade F shall be heat treated by heating into the austenitic range, quenching in water, and tempering at not less than 1100°F [595°C] for not less than ½ h.

6. ~~Chemical Composition~~ Chemical Composition

6. Chemical Composition

6.1 The steel shall conform to the chemical requirements shown in Table 1 unless otherwise modified in accordance with Supplementary Requirement S17, Vacuum Carbon-Deoxidized Steel, in Specification A ~~20A~~ 20/A ~~20M/A20M~~.

7. Mechanical Properties

7.1 *Tension Test Requirements*—The material as represented by the tension test specimens shall conform to the requirements shown in Table 2.

7.1.1 For plates that have been heat treated in accordance with 5.1.1.1 or 5.1.2 and have a nominal thickness of ¾ in. [20 mm] and under, the 1½-in. (40-mm) wide rectangular specimen may be used for the tension test, and the elongation may be determined in a 2-in. [50-mm] gage length that includes the fracture and that shows the greatest elongation. When this specimen is used, the elongation shall be not less than 23 %.

7.2 *Impact Test Requirements:*

7.2.1 Plates of Grades A, B, D, and E that have been heat treated in accordance with 5.1.1.1 shall be Charpy V-notch impact tested. The impact test shall meet 20 ft · lbf [27 J]. The test temperature and orientation shall be a matter of agreement between the purchaser and supplier.

³ Annual Book of ASTM Standards, Vol 01.04.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.