This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: A 225/A 225M-03 Designation: A225/A225M - 03 (Reapproved 2007)

Standard Specification for Pressure Vessel Plates, Alloy Steel, Manganese-Vanadium-Nickel¹

This standard is issued under the fixed designation A225/A225M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification² covers manganese-vanadium-nickel alloy steel plates intended primarily for welded layered pressure vessels.

1.2 Plates under this specification are available in two grades having different strength levels as follows: - Grade

Tensile Strength, ksi [MPa]		
Grade	e	Tensile Strength, ksi [MPa]
	Ð	
Grade		Tensile Strength, ksi [MPa]
C		105–135 [725–930]
D		105–135 [725–930]
3 in. [75		
mm] and		
under		
- Over 3 in.		
[75 mm]		
		80-105 [550-725]
		US <u>-75-100 [515-690]</u> 80-105 [550-725]
3 in. [75 mm] and under		80–105 [550–725]
Over 3 in. [75 mm]		75–100 [515–690]
· · · · · · · · · · · · · · · · · · ·		ten all ' '

1.3 The maximum thickness of plates is limited only by the capacity of the chemical composition to meet the specified mechanical property requirements; however, current mill practice normally limits Grade C to 0.58 in. [15 mm] maximum and Grade D to 6 in. [150 mm] maximum.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

https://standards.iteh.ai/catalog/standards/sist/ec889ca2-afd2-4aee-99e0-8e7b41fc66d7/astm-a225-a225m-032007

*A Summary of Changes section appears at the end of this standard.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless <u>Steel</u>, <u>Steel</u> and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved Sept. 10, 2003. Published October 2003. Originally approved in 1939. Last previous edition approved in 1999 as A 225/A 225M-93 (1999). Current edition approved Nov. 1, 2007. Published March 2008. Originally approved in 1939. Last previous edition approved in 2003 as A225/A225M – 03. DOI: 10.1520/A0225 A0225M-03R07.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-225/SA-225M in Section II of that Code.

A225/A225M – 03 (2007)

2. Referenced Documents

2.1 ASTM Standards:³

A20/A20M Specification for General Requirements for Steel Plates for Pressure Vessels

A435/A435M Specification for Straight-Beam Ultrasonic Examination of Steel Plates

A577/A577M Specification for Ultrasonic Angle-Beam Examination of Steel Plates

A578/A578M Specification for Straight-Beam Ultrasonic Examination of Plain and Clad Rolled Steel Plates for Special Applications

3. General Requirements and Ordering Information

3.1 Plates supplied to this product specification shall conform to Specification A 20A20/A20M/A 20M, which outlines the testing and retesting methods and procedures, permissible variations in dimensions and mass, quality and repair of defects, marking, loading, etc.

3.2 Specification A 20A20/A20M/A 20M also establishes the rules for ordering information that should be complied with when purchasing plates to this specification.

3.3 In addition to the basic requirements of this specification, certain supplementary requirements are available where additional control, testing, or examination is required to meet end use requirements.

3.4 The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification A 20A20/A20M/A = 20M.

3.5 Coils are excluded from qualification to this specification until they are processed into finished plates. Plates produced from coil means plates that have been cut to individual lengths from coil. The processor directly controls, or is responsible for, the operations involved in the processing of coils into finished plates. Such operations include decoiling, leveling, cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

NOTE 1—For plates produced from coil and furnished without heat treatment or with stress relieving only, three test results are reported for each qualifying coil. Additional requirements regarding plates from coil are described in Specification A20/A20M.

leh Standards

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards Vol 01.04.volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Chemical Requirements				
Elements	Composition,	Composition,- %		
	Grade C	Grade D		
Carbon, max ^A	ASTM 0.2525/A225M-03(2007)	0.20		
Manganese, max:	standards/sist/ec889ca2-afd2-4aee-99e0-8e7b4	1fc66d7/astm-a225-a225m-0320		
Manganese, max: Manganese, max: Heat analysis	1.60	1.70		
- Product analysis	1.72	1.70		
Heat analysis	1.60	1.70		
Product analysis	1.72	1.84		
Phosphorus, max^{A}	0.035	0.035		
Sulfur, max ^A	0.035	0.035 0.035		
Silicon:	0.035			
Sulfur, max ^A	0.035	0.035		
Silicon:				
Heat analysis	0.15-0.40	0.10-0.50		
- Product analysis	0.13 0.45			
Vanadium:				
Heat analysis	0.15-0.40	0.10-0.50		
Product analysis	0.0.45	0.08-0.56		
Product analysis	0.13–0 <u>.45</u>	<u>0.0</u> 8–0.56		
Vanadium:				
Heat analysis	0.13-0.18	0.10-0.18		
- Product analysis	0.11–0.20			
Nickel:				
Heat analysis	0.13-0.18	0.10-0.18		
Product analysis	0.0.20	0.08-0.20		
Product analysis	0.11–0 <u>.20</u>	<u>0.0</u> 8–0.20		
Nickel:				
Heat analysis	0.40-0.70	0.40-0.70		
- Product analysis	0.37–0.73			
Heat analysis	0.40-0.70	0.40-0.70		
Product analysis	0.37-0.73	0.37-0.73		

^A Applies to both heat and product analyses.