



~~Designation: A 2-02~~ **Designation: A2 – 02 (Reapproved 2008)**

Standard Specification for Carbon Steel Girder Rails of Plain, Grooved, and Guard Types¹

This standard is issued under the fixed designation A2; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers carbon steel girder rails² of three classes based on type or type and weight, and chemistry defined as follows and in Table 1:

1.1.1 Unless otherwise specified by the purchaser, girder-guard rails shall be Class A.

1.1.2 Plain and grooved-girder rails under 135 lb/yd (67.1 kg/m) in weight shall be specified by the purchaser as either Class A or Class B.

1.1.3 Plain and grooved-girder rails of 135 lb/yd in weight and heavier shall be Class C, unless otherwise specified.

1.2 The values states in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

2.1 *ASTM Standards:*³

A700 [Practices for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipments](#)—[Shipment](#)

E10 [Test Method for Brinell Hardness](#)—[Hardness of Metallic Materials](#)

3. Classification of Rails

3.1 *No. 1 Rails*—Rails that are free of injurious imperfections and flaws of all kinds.

3.2 *No. 2 Rails*—Rails that contain surface imperfections in such number or of such character that shall not, in the judgment of the inspector, render them unfit for recognized uses.

4. Ordering Information

4.1 Orders for girder rails under this specification shall include the following information as appropriate:

4.1.1 ~~ASTM designation and date of issue;~~ ~~issue;~~

4.1.2 Quantity (tons or pieces as appropriate);

4.1.3 Complete identification of section with dimensional drawing if ~~required;~~ required;

4.1.4 Arrangement of bolt holes, bond holes, and tie rod holes with dimensional drawings, if ~~required;~~ required;

4.1.5 Class (in accordance with 1.1 and Table 1); and

4.1.6 Certification and Test Report (see 12.1).

5. Manufacture

5.1 *Melting Practice*—The steel shall be made by any of the following processes: open-hearth, basic-oxygen, or electric-furnace.

5.1.1 The steel may be cast by a continuous ~~process;~~ process or in ingots.

5.2 *Discard*—Sufficient discard shall be made to secure freedom from injurious segregation and piping.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.01 on Steel Rails and Accessories.

~~Current edition approved November 10, 2002. Published December 2002. Originally approved in 1912. Last previous edition approved in 1990 as A 31-90 (1997).~~

~~Current edition approved March 1, 2008. Published March 2008. Originally approved in 1912. Last previous edition approved in 2002 as A2-02. DOI: 10.1520/A0002-02R08.~~

² Design details for carbon steel girder rails are indicated in the girder rail catalogs of individual manufacturers.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards*—~~Vol 01-05~~—volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Chemical Requirements, %

	Class A	Class B	Class C
Carbon	0.60–0.75	0.70–0.85	0.75–0.90
Manganese	0.60–0.90	0.60–0.90	0.60–0.90
Phosphorus, max	0.04	0.04	0.04
Silicon	0.10–0.40	0.10–0.40	0.10–0.40

6. Chemical Composition

6.1 *Heat or Cast Analysis*—An analysis for each heat or cast of steel shall be made by the manufacturer to determine the percentage of the elements specified in Table 1. The analysis shall be made from a test sample representing the heat or cast and shall conform to the requirements in Table 1.

6.2 Upon request by the purchaser, similar samples shall be provided to verify the heat or cast analysis as determined in 6.1.

6.3 *Product Analysis*—When ladle tests are not available, finished material representing the heat may be product tested. The product analysis allowance beyond the limits of the specified ladle analysis shall be within the limits for product analyses specified in Table 2.

7. Hardness Properties

7.1 Test Specimens:

7.1.1 Three representative sections of rail from each heat shall be selected as test specimens.

7.1.2 Excess scale and decarburization shall be removed from the test area of the head or web of the selected specimens.

7.2 Procedure:

7.2.1 The test shall be conducted in accordance with Test Method E10.

7.3 Requirements:

7.3.1 Class A rail shall have a Brinell hardness of 248 to 293, and Classes B and C shall have hardnesses of 269 to 321.

7.4 *Retests*—If the average depth of the impressions obtained on the head of the three specimens from any heat fails to conform to the requirements specified in 7.3, the manufacturer may at his option retest the specimens, or each rail from that heat. Rails represented by retests which conform to the requirements of 7.3 shall be accepted.

8. Permissible Variations of Dimension, Weight, and Other Physical Attributes

8.1 Section:

8.1.1 The section of the rail shall conform to the design specified by the purchaser.

8.1.2 A variation of $\frac{1}{64}$ in. (0.4 mm) less or $\frac{1}{32}$ in. (0.8 mm) greater than the specified height will be permitted.

8.1.3 A variation of $\frac{1}{8}$ in. (3.2 mm) from the specified overall width of the head and tram will be permitted, but any variation that would affect the gage line more than $\frac{1}{32}$ in. (0.8 mm) will not be permitted.

8.1.4 The overall width of the base shall not vary under that specified more than $\frac{1}{8}$ in. (3.2 mm) for widths less than $6\frac{1}{2}$ in. (165 mm), $\frac{3}{16}$ in. (4.8 mm) for a width of $6\frac{1}{2}$ in., and $\frac{1}{4}$ in. (6.35 mm) for a width of 7 in. (178 mm).

8.1.5 No variation will be permitted in dimensions affecting the fit of the joint bars, except that the fishing template approved by the purchaser may stand out laterally not more than $\frac{3}{32}$ in. (2.4 mm).

8.1.6 The base of the rail shall be at right angles to the web, and the convexity shall not exceed $\frac{1}{32}$ in. (0.8 mm).

8.1.7 When necessary, because of the type of track construction, and notice to that effect has been given to the manufacturer, the position of the gage line with respect to the outer edge of the base shall not vary more than $\frac{3}{64}$ in. (1.2 mm).

8.2 *Weight*—The weight of the rails per yard as calculated, shall be maintained as nearly as possible after conforming to the requirements specified in 8.1.

8.3 Length:

8.3.1 Unless otherwise specified, the standard length of rail shall be 39 ft (11.9 m) where measured at a temperature of 60°F (15°C).

8.3.2 All standard 39-ft lengths may be specified; or

8.3.3 Standard 39-ft lengths with up to 11 % of the entire order in lengths shorter than standard, varying by 1 ft (0.3 m) from 38 to 24 ft (11.6 to 7.3 m) may be specified; or

TABLE 2 Product Analysis—Allowance Beyond Limits of Specified Chemical Analysis

	Allowance Under Minimum Limit, %	Allowance Over Maximum Limit, %
Carbon	0.04	0.04
Manganese	0.06	0.06
Phosphorus	...	0.008
Silicon	0.02	0.02 ^A

^A Continuously cast allowances shall be 0.05 % over maximum for silicon.