



**Designation: ~~B296-96~~ Designation: B 296 – 03 (Reapproved 2008)**

## **Standard Practice for Temper Designations of Magnesium Alloys, Cast and Wrought<sup>1</sup>**

This standard is issued under the fixed designation B 296; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### **1. Scope**

1.1 This practice covers a system for designating the tempers of magnesium alloys, cast and wrought. The designations used in ASTM specifications under the jurisdiction of Committee ~~B-7B07~~ for magnesium alloy castings and wrought ~~products; products~~ conform to this practice.<sup>2</sup>

### **2. Basis of Codification**

2.1 The designations for temper are used for all forms of magnesium and magnesium-alloy products except ingots and are based on the sequence of basic treatments used to produce the various tempers.

2.2 The temper designation follows the alloy designation, the two being separated by a dash.

2.3 Basic temper designations consist of letters. Subdivisions of the basic tempers, where required, are indicated by a digit or digits following the letter. These designate specific sequences of basic treatments, but only operations recognized as significantly influencing the characteristics of the product are indicated. Should some other variation of the same sequence of basic operations be applied to the same alloy, resulting in different characteristics, then additional digits are added to the designation.

NOTE 1—In material specifications containing reference to two or more tempers of the same alloy which result in identical mechanical properties, the distinction between the tempers should be covered in suitable explanatory notes.

2.4 The temper designations and the subdivisions are fully defined and explained in Table 1. A brief outline for quick reference is given in Table 2.

standards.iteh.ai  
(<https://standards.iteh.ai>)  
Document Preview

ASTM B296-03(2008)

<https://standards.iteh.ai/catalog/standards/sist/aa4def8a-104a-494b-8313-0c43e9d05de2/astm-b296-032008>

<sup>1</sup> This practice is under the jurisdiction of the ASTM Committee ~~B-7B07~~ on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.04 on Magnesium Alloy Cast and Wrought Products.

Current edition approved ~~April 10, 1996; March 1, 2008~~. Published ~~June 1996; March 2008~~. Originally published as ~~B296-54; approved in 1954~~. Last previous edition ~~B296-67(1990); approved in 2003 as B 296 – 03~~.

<sup>2</sup> The designations used in ASTM Committee ~~B-7B07~~ specifications for aluminum-alloy wrought and cast products conform to the American National Standard H 35.1/H 35.1(M).