

INTERNATIONAL STANDARD

ISO
1436

Third edition
1991-09-15

Rubber hoses and hose assemblies — Wire-reinforced hydraulic type — Specification

iTeh STANDARD PREVIEW
*Tuyaux et flexibles en caoutchouc — Type hydraulique à armature de fils
métalliques — Spécifications*
(standards.iteh.ai)

ISO 1436:1991

<https://standards.iteh.ai/catalog/standards/sist/3c5c0b24-2255-48be-bd11-51ffä2f3277e/iso-1436-1991>

INTERNATIONAL

ISO



Reference number
ISO 1436:1991(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 1436 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Sub-Committee SC 1, *Hoses (rubber and plastics)*.

<https://standards.iteh.ai/catalog/standards/sist/3c5c0b24-2255-48be-bd11-5111d23277e4/iso-1436-1991>

This third edition cancels and replaces the second edition (ISO 1436:1978), of which it constitutes a technical revision.

© ISO 1991

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Rubber hoses and hose assemblies — Wire-reinforced hydraulic type — Specification

1 Scope

This International Standard specifies requirements for six types of wire-reinforced hose and hose assembly of internal diameter from 5 mm to 63 mm, for use with common hydraulic fluids, such as mineral oils, soluble oils, oil and water emulsions, aqueous glycol solutions, and water, at temperatures ranging from $-40\text{ }^{\circ}\text{C}$ to $+100\text{ }^{\circ}\text{C}$.

The standard does not include requirements for end fittings. It is limited to the performance of the hoses and hose assemblies.

NOTE 1 The hoses are not suitable for use with castor-oil-based and ester-based fluids. Operating temperatures in excess of $93\text{ }^{\circ}\text{C}$ may materially reduce the life of the hose.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 1402:1984, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*.

ISO 1817:1985, *Rubber, vulcanized — Determination of the effect of liquids*.

ISO 4671:1984, *Rubber and plastics hose and hose assemblies — Methods of measurement of dimensions*.

ISO 4672:1988, *Rubber and plastics hoses — Sub-ambient temperature flexibility tests*.

ISO 6803:1984, *Rubber or plastics hoses and hose assemblies — Hydraulic pressure impulse test without flexing*.

ISO 7326:1991, *Rubber and plastics hoses — Assessment of ozone resistance under static conditions*.

ISO 7751:—¹⁾, *Rubber and plastics hoses and hose assemblies — Ratios of proof and burst pressure to design working pressure*.

ISO 8033:1985, *Rubber and plastics hose — Determination of adhesion between components*.

3 Types

Hoses shall be one of the following six types:

- Type 1A hose: with a single wire braid reinforcement;
- Type 2A hose: with two braids of wire reinforcement;
- Type 2B hose: with two spiral plies and one braid of wire reinforcement.

Types 1AT, 2AT, and 2BT shall be of the same reinforcement construction as types 1A, 2A and 2B, except that they shall have thinner covers designed to assemble with fittings which do not require removal of the cover or a portion thereof.

4 Materials and construction

4.1 The hoses shall consist of an oil- and water-resistant synthetic rubber tube, one or more layers of high tensile steel wire and an oil- and weather-resistant rubber cover.

1) To be published. (Revision of ISO 7751:1983)

4.2 The hose shall be concentric in accordance with the following:

The measurements of the wall thickness at different points shall not differ by more than the following values:

- up to and including 6,3 mm nominal bore: 0,8 mm;
- over 6,3 mm up to and including 22 mm nominal bore: 1,0 mm;
- over 22 mm nominal bore: 1,3 mm.

5 Dimensions

The bore diameter, diameter over reinforcement and outside diameter of the hose shall meet the requirements of table 1, when measured in accordance with ISO 4671.

NOTE 2 ISO 1307:1983, *Rubber and plastics hoses — Bore diameters and tolerances on length*, has not been followed for nominal bore or permitted range. The dimensions adopted in table 1 are to ensure compatibility with fittings that are in wide use throughout the world.

Table 1 — Bore diameter, diameter over reinforcement and outside diameter of hose

Dimensions in millimetres

Nominal bore	All types		Type 1A				Type 1AT			Types 2A and 2B				Types 2AT and 2BT		
	Bore diameter		Diameter over reinforcement		Outside diameter of hose		Outside diameter of hose	Cover thickness		Diameter over reinforcement		Overall diameter of hose		Outside diameter of hose	Cover thickness	
	min.	max.	min.	max.	min.	max.	max.	min.	max.	min.	max.	min.	max.	max.	min.	max.
5	4,5	5,4	8,9	10,1	11,9	13,5	12,5	0,76	1,52	10,6	11,7	15,1	16,7	14,1	0,76	1,52
6,3	6,1	6,9	10,6	11,7	15,1	16,7	14,1	0,76	1,52	12,1	13,3	16,7	18,3	15,7	0,76	1,52
8	7,7	8,5	12,1	13,3	16,7	18,3	15,7	0,76	1,52	13,7	14,9	18,3	19,8	17,3	0,76	1,52
10	9,3	10,1	14,5	15,7	19,1	20,6	18,1	0,76	1,52	16,1	17,3	20,6	22,2	19,7	0,76	1,52
10,3	9,9	11,1	15,3	16,4	19,8	21,4	18,9	0,76	1,52	—	—	—	—	—	—	—
12,5	12,3	13,5	17,5	19,1	22,2	23,8	21,5	0,76	1,52	19,0	20,6	23,8	25,4	23,1	0,76	1,52
16	15,4	16,7	20,6	22,2	25,4	27	24,7	0,76	1,52	22,2	23,8	27	28,6	26,3	0,76	1,52
19	18,6	19,8	24,6	26,2	29,4	31	28,6	0,76	1,52	26,2	27,8	31	32,5	30,2	0,76	1,52
22	21,8	23,0	27,8	29,4	32,5	34,1	31,8	0,76	1,52	29,4	31	34,1	35,7	33,4	0,76	1,52
25	25,0	26,4	32,5	34,1	36,9	39,3	36,6	0,76	1,52	34,1	35,7	38,5	40,9	38,9	1,07	2,16
31,5	31,3	33,0	39,3	41,7	44,5	47,6	44,8	1,02	2,03	43,3	45,6	49,2	52,4	49,6	1,27	2,54
38	37,7	39,3	45,6	48	50,8	54	52,0	1,27	2,54	49,6	52	55,6	58,7	56,0	1,27	2,54
51	50,4	52,0	58,7	61,9	65,1	68,3	65,9	1,27	2,54	62,3	64,7	68,3	71,4	68,6	1,27	2,54
63	63,1	65,1	—	—	—	—	—	—	—	74,6	77,8	80,9	84,1	—	—	—

6 Hydrostatic requirements

6.1 The design working pressure of the hose shall comply with the requirements of table 2 when tested in accordance with ISO 1402. The ratios of design working pressure to proof pressure and to minimum burst pressure shall be in accordance with category No. 3 of ISO 7751.

Table 2 — Design working pressure

Nominal bore	Design working pressure			
	Types 1A and 1AT		Types 2A, 2AT 2B and 2BT	
	MPa	bar	MPa	bar
mm				
5	21,0	210	35,0	350
6,3	20,0	200	35,0	350
8	17,5	175	29,5	295
10	16,0	160	28,0	280
10,3	16,0	160	—	—
12,5	14,0	140	25,0	250
16	10,5	105	20,0	200
19	9,0	90	17,5	175
22	8,0	80	14,0	140
25	7,0	70	14,0	140
31,5	4,4	44	11,0	110
38	3,5	35	9,0	90
51	2,6	26	8,0	80
63	—	—	7,0	70

6.2 When tested in accordance with ISO 1402, the change in length of hose at the design working pressure shall not exceed + 2 % to - 4 %.

7 Minimum bend radius

The hose shall be capable of performing at design working pressure when curved to a radius not less than that given in table 3 as measured on the inside of the bend.

NOTE 3 Should any portion of the hose be curved to a radius less than the specified bend radius, performance capability of the hose is reduced.

Table 3 — Minimum bend radius

Dimensions in millimetres

Nominal bore	Bend radius
5	90
6,3	100
8	115
10	130
10,3	140
12,5	180
16	205
19	240
22	280
25	300
31,5	420
38	500
51	630
63	760

8 Tolerance on hose length

8.1 The hose shall be supplied in lengths as specified by the purchaser, subject to a tolerance on the specified lengths of $\pm 1\%$ or ± 3 mm, whichever is the greater.

8.2 When no specific hose lengths have been ordered, the percentages of different lengths in any given delivery shall be as follows:

- over 13 m: not less than 65 % of total length;
- 7,5 m to 13 m: not more than 35 % of total length;
- 1 m to 7,5 m: not more than 10 % of total length.

No length shall be less than 1 m.

9 Impulse test requirements

9.1 Four unaged samples of hose with end fittings shall be tested in accordance with the method specified in ISO 6803.

9.2 Type 1 hose, when tested at 125 % of the design working pressure for hoses of nominal bore 25 mm and smaller, and at 100 % of the design working pressure for nominal bore 31,5 mm and above, at a temperature of $93\text{ °C} \pm 3\text{ °C}$, shall withstand a minimum of 150 000 impulse cycles.

Type 2 hose, when tested at 133 % of the working pressure, at a temperature of $93\text{ °C} \pm 3\text{ °C}$, shall withstand a minimum of 200 000 impulse cycles.

There shall be no leakage or other malfunction after the specified number of cycles.

Leakage at the end-fitting, fitting blow-off or rupture of the hose adjacent to the fitting shall be considered as failures in the performance of the assembly. Such failures do not necessarily demonstrate an inability of the hose to meet the specified requirements with an alternative fitting.

The mode and position of any failures shall be recorded.

NOTE 4 If an impulse test is unavoidably stopped for a period of more than 24 h before completion of the minimum number of cycles, slight seepage of test fluid may occur at the hose/fitting junction upon restarting the test. Such seepage, provided that it seals itself within 30 min of the re-start, is not deemed to constitute a failure.

10 Leakage

Unaged hose assemblies on which the end fittings have been attached not over 30 days shall be subjected to a hydrostatic pressure equal to 70 % of the specified minimum burst pressure for a period of 5 min to 5,5 min and then reduced to zero, after which the 70 % of minimum burst pressure shall be reapplied for another 5 min. There shall be no leakage or evidence of failure. This test shall be considered a destructive test and the sample shall be destroyed.

11 Cold flexibility requirements

When tested in accordance with method B of ISO 4672 at a temperature of $-40\text{ °C} \pm 2\text{ °C}$, there shall be no cracking of the lining or cover. The test piece shall not leak or crack when subjected to a proof pressure test (see 6.1) after regaining ambient temperature.

12 Oil resistance

The lining and cover, when tested by the method specified in ISO 1817, immersed in oil No. 3 for $(72 \pm 2)\text{ h}$ at a temperature of $100\text{ °C} \pm 1\text{ °C}$, shall

show no shrinkage and shall not show volume swelling greater than 100 %.

13 Ozone resistance

When tested in accordance with ISO 7326, no cracking or deterioration of the cover shall be visible at a magnification of $\times 2$, after exposure to an ozone concentration of $50\text{ pphm (V/V)} \pm 5\text{ pphm (V/V)}$ at $40\text{ °C} \pm 2\text{ °C}$ for $(72 \pm 2)\text{ h}$.

14 Adhesion between components

When tested in accordance with ISO 8033, adhesion between lining and reinforcement, and between cover and reinforcement, shall be not less than 2,5 kN/m. Test pieces shall be type 5 for lining and reinforcement and type 2 or 6 for cover and reinforcement as described in the table for test piece selection in ISO 8033.

15 Marking

Hoses and hose assemblies complying with this International Standard shall be marked with at least the following information:

- a) the number of this International Standard (ISO 1436);
- b) the hose type;
- c) the nominal bore size;
- d) the manufacturer's name or trademark;
- e) the date of manufacture, i.e. quarter and last two digits of year of manufacture.

EXAMPLE: ISO 1436/2AT/16/XXXX/4.91

Other information as agreed between the purchaser and the manufacturer shall be included, if requested.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

This page intentionally left blank

ISO 1436:1991

<https://standards.iteh.ai/catalog/standards/sist/3c5c0b24-2255-48be-bd11-51ffa2f3277e/iso-1436-1991>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 1436:1991

<https://standards.iteh.ai/catalog/standards/sist/3c5c0b24-2255-48be-bd11-51ffa2f3277e/iso-1436-1991>

UDC 621.643.3-036.4:621.8.032

Descriptors: hydraulic systems, rubber products, hoses, rubber hoses, specifications, dimensions, marking.

Price based on 4 pages
