



Designation: D3345 – 08

# Standard Test Method for Laboratory Evaluation of Wood and Other Cellulosic Materials for Resistance to Termites<sup>1</sup>

This standard is issued under the fixed designation D3345; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the laboratory evaluation of treated or untreated cellulosic material for its resistance to subterranean termites. This test should be considered as a screening test for treated material and further evaluation by field methods is required.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. (Warning—See 6.1.4.)*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D1413 Test Method for Wood Preservatives by Laboratory Soil-Block Cultures

2.2 *Other Documents:*<sup>3</sup>

AWPA E10 Testing Wood Preservatives by Laboratory Soil-Block Cultures

## 3. Apparatus

3.1 *Containers, Glass or Clean Plastic*, with loosely fitting tops with liners removed, 220 to 450 cm<sup>3</sup> (8 to 16 oz).

3.1.1 If volatile chemicals are to be tested, a 4.8 mm (No. 12 or approximately  $\frac{3}{16}$  in.) hole is drilled in the center of the top.

3.2 *Tray*, enamel, stainless steel, or plastic, 0.25 m by 0.51 m (10 by 20 in.) and bucket.

3.3 *Paper Towels*.

## 4. Reagents and Materials

4.1 *Benzalkonium Chloride Solution (1+750)*—Add 1 part benzalkonium chloride to 750 parts water. A comparable surface antiseptic is satisfactory.

4.2 *Distilled Water*.

4.3 *Sand*, brown or white, screened, washed, and heat-sterilized.

4.4 *Southern Yellow Pine (SYP) (Pinus spp.)* measuring 25.4 mm (1.00 in.) square by 6.4 mm (0.25 in.) in the tangential direction. Sapwood, no visible defects, smoothed surfaces equivalent to planed or sanded, 2 to 3 rings/cm (4 to 6 rings/in.). All test samples should come from same parent board.

4.4.1 Other wood species may be used, but in each separate test using other species as the major test wood, five SYP sapwood blocks should be used as additional controls to permit the correlation of test results among laboratories.

4.5 *Subterranean Termites*—Use a major common species of the region being studied.

4.5.1 Specific identification of any termites used shall be obtained and reported with the test data.

## 5. Determination of Sand Water-Holding Capacity

5.1 Determine the quantity of distilled water to be added to the sand during the test as follows:

5.1.1 Place 100 g of oven-dry sand in a beaker and determine the volume of water required to saturate the sand. The saturation point is defined as the point when the addition of more water will result in free water on the surface of the sand.

5.1.2 Calculate the percent saturation as follows:

$$\% \text{ Saturation} = (\text{weight of water/oven dry weight of sand}) \times 100 \quad (1)$$

5.1.3 Add water to the sand as follows:

$$\% \text{ water to add} = \text{saturation} - 7.0 \quad (2)$$

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D07 on Wood and is the direct responsibility of Subcommittee D07.06 on Treatments for Wood Products.

Current edition approved March 1, 2008. Published April 2008. Originally approved in 1974. Last previous edition approved in 1999 as D3345 – 74 (1999). DOI: 10.1520/D3345-08.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from the American Wood Protection Association (AWPA), PO Box 361784, Birmingham, AL 35236-1784, http://www.awpa.com.

5.1.4 For example, the saturation point was reached at 20 mL of water:

$$\text{Saturation} = (20/100) \times 100 = 20.0\% \quad (3)$$

$$\% \text{ Water to add} = 20.0 - 7.0 = 13.0\%$$

## 6. Collection of Termites

6.1 *Subterranean Termites*, for example, (*Reticulitermes*, *Coptotermes*, spp.)—Collect from a large colony (over 50 000) in a natural forest situation, for example, from fallen logs, stumps, and so forth, or from strong laboratory cultures.

6.1.1 Remove short log sections to the laboratory cultures and split them. Shake the insects out onto a tray or trays. After distributing the debris and insects evenly on the tray(s), lay damp paper towels, sheets of kraft paper, and so forth, over the debris. The termites will cling to the damp paper after a few minutes.

6.1.2 Prepare an 8 to 11-L (2 to 3-gal) pail by placing about ten unfolded, slightly crumpled, damp paper towels in the bottom of the pail. Rinse these towels in distilled water and squeeze damp a number of times. Cover these towels with about ten unfolded, dry paper towels.

6.1.3 Shake the damp towels covering the tray debris into the above described pail. After 2 to 4 h, remove the dry towels and any insects and debris on them from the pail and discard. Use insects clinging to the lower, damp towels in the test.

6.1.4 Do not hold termites in the pail longer than 24 h before using. (**Warning**—Exercise reasonable care to ensure that any termites discarded (for example, 6.1.3) are dead. Oven-drying debris and towels used at 100°C for 6 h is sufficient. When a test is finished, reasonable care should also be exercised that living insects are not discarded.)

## 7. Weathering of Test Blocks

7.1 If the test material is weathered prior to exposure to the insects, report the complete details on the weathering.

7.2 The ASTM weathering procedure for the soil-block test is recommended (see Test Method D1413).

## 8. Conditioning of the Test Blocks

8.1 Condition all test blocks, following weathering if used, to a constant weight within the equilibrium moisture content range from 6 to 14 % moisture content to ensure that all solvent is removed prior to exposure to insects.

8.2 The ASTM soil-block conditioning procedure is recommended (see Test Method D1413).

## 9. Block Quantity and Identifications

9.1 Prepare five replicate blocks for each variable under test, for example, for each retention of each preservative or chemical to be tested.

9.2 Use five untreated blocks as described in 9.1 as controls for each separate study.

9.3 If SYP is not used as the species in 9.1 and 9.2, then add five blocks of untreated SYP to each study to permit a comparison to studies using SYP as the major species.

9.4 Identify all blocks with a number in a suitable manner.

## 10. Assembling Containers

10.1 Prior to using, wash all containers rinsed in the surface antiseptic solution, and dry.

10.2 Place the test block in the bottom of the container with one edge of the block up against the side of the container.

10.3 Add 200 g of sand to each container.

10.4 Use suitable numbers on each container.

10.5 Add sufficient distilled water to each container as determined in Section 4. After addition of the water, allow the containers to stand overnight.

10.6 Assemble five containers with sand, water, and termites but without test blocks.

## 11. Adding Termites

11.1 Weigh out  $1 \pm 0.05$  g of subterranean termites (Section 6) and add to each of the previously prepared containers. Select the termites so that about 90 % are workers.

11.2 Replace the container tops loosely.

## 12. Container Storage and Inspections

12.1 Select five test containers randomly and weigh individually. Maintain all containers at 25.5 to 27.7°C (78 to 82°F) for four weeks.

12.2 At the end of the first and fourth weeks, examine the containers and record the presence of tunneling, termite mortality, and position of the termites in the container as follows:

12.2.1 After one week, containers assembled in accordance with 10.6 should show virtually complete survival, thereby indicating that test procedures have been followed and vigorous termites used.

12.2.2 *Tunneling Present*—Yes or no. (Tunneling indicates vigor of insects.)

12.2.3 *Majority Termite Position*—(On or beneath surface. Position on surface suggests response of termites to an antagonizing effect such as repellency of preservative.)

12.2.4 *Approximate Termite Mortality*—Slight (0 to 33 %), moderate (34 to 66 %), heavy (67 to 99 %), complete (100 %).

12.2.5 Weekly reweigh the five selected containers (12.1) and add distilled water to all containers if the moisture content of the sand drops below two percentage points of the original moisture content (see Section 5).

## 13. Container Disassembly

13.1 After four weeks disassemble the containers and remove and clean the blocks. Prior to and during the disassembly, note the items in 12.2. Discard the used sand and termites (**Warning**— See 6.1.4.) and do not reuse for subsequent tests.

## 14. Block Evaluation

14.1 Examine and visually rate each block using the following rating system: