INTERNATIONAL STANDARD

ISO 17730

First edition 2014-11-01

Dentistry — Fluoride varnishes

Médecine bucco-dentaire — Vernis fluorés

iTeh STANDARD PREVIEW (standards.iteh.ai)



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 17730:2014 https://standards.iteh.ai/catalog/standards/sist/9d312d21-bcb4-4788-afd6-2e5832916f31/iso-17730-2014



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Con	itents	Page
Forev	word	iv
Intro	duction	v
1	Scope	1
2	Normative references	1
3	Terms and Definitions	1
4	Requirements 4.1 Total fluoride content	2
5	Sampling	2
6	Test method 6.1 Test for total fluoride content 6.2 Test conditions	2
7	Test report	4
8	Instructions for use	4
9	Packaging, labelling, and marking 9.1 Packaging 9.2 Labelling	5
Biblio	ography iTeh STANDARD PREVIEW	6
	(standards.iteh.ai)	

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword — Supplementary information.

The committee responsible for this document is ISO/TC 106, Dentistry, Subcommittee SC7, Oral care products.

Introduction

Fluoride varnishes are used in dentistry primarily for caries prevention and reduction of dentine hypersensitivity. Fluoride varnishes are applied in the oral cavity directly on the outer surfaces of teeth and fillings, and are intended to remain at least for several hours.

Specific qualitative and quantitative test methods for demonstrating freedom from unacceptable biological hazard are not included in this International Standard, but it is recommended that, for the assessment of possible biological or toxicological hazards, reference should be made to ISO 10993-1 and ISO 7405.

iTeh STANDARD PREVIEW (standards.iteh.ai)

iTeh STANDARD PREVIEW (standards.iteh.ai)

Dentistry — Fluoride varnishes

1 Scope

This International Standard specifies requirements and their test methods for total digestible fluoride content in dental varnishes containing fluoride, intended for use in the oral cavity directly on the outer surfaces of teeth and fillings. It also specifies the requirements for their packaging and labelling, including the instructions for use. This International Standard covers fluoride varnishes to be applied by dental health care workers.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1942, Dentistry — Vocabulary

ISO 3696, Water for analytical laboratory use — Specification and test methods

ISO 8601, Data elements and interchange formats — Information interchange — Representation of dates and times (standards.iteh.ai)

Terms and Definitions

ISO 17730:2014

For the purposes of this document, the definitions given in ISO 1942 and the following apply. 26583291631/iso-17730-2014

3.1

consumer packaging

retail packaging sales packaging

package, with labelling and contents as a sales unit to the user or consumer at the point of retail

Note 1 to entry: A consumer packaging can consist of a secondary packaging wrapping or container covering one or more primary packaging elements or, it can consist of a single primary packaging element containing the product.

Note 2 to entry: Adapted from ISO 21067:2007, definition 2.2.5.

3.2

fluoride varnish

dental product, in paintable liquid form containing fluoride compound for topical application to the outer surfaces of teeth and fillings, intended primarily to prevent tooth caries or reduce dentine hypersensitivity

3.3

total fluoride

mass percent of fluoride in the fluoride varnish

4 Requirements

4.1 Total fluoride content

The total fluoride content shall not deviate by more than 20 % from the stated amount on the package when tested in accordance with 6.1 or other validated methods for total fluoride content.

5 Sampling

Use packages prepared for retail sale from the same batch containing enough material to carry out the specified tests, plus an allowance for repeat tests, if necessary.

6 Test method

6.1 Test for total fluoride content.

6.1.1 Chemicals and solutions

6.1.1.1 Total ionic strength adjusting buffer (TISAB) solution, described in ASTM D1179-10:2010 18.1 or alternative.

NOTE TISAB II: Sodium chloride 5,8 % (w/v), acetic acid 5,7 % (w/v), CDTA 0,4 % (w/v) adjust to pH 5 to pH 5,5 with sodium hydroxide (5 mol/L). Examples are TISAB II® (Orion Research). An acceptable product (TISAB II®) is available from Thermo Fisher Scientific, Beverly, MA 01915 USA. This information is given only for the convenience of users of this document and does not constitute an endorsement by ISO of this product.

- **6.1.1.2 50 % Diluted TISAB solution**, dilute TISAB with delonized water 1:1 by volume.
 - https://standards.iteh.ai/catalog/standards/sist/9d312d21-bcb4-4788-afd6-
- **6.1.1.3 Fluoride standard solution**, commercially available or prepared with sodium fluoride at 0,10 mol/L.
- **6.1.1.4 Chloroform**, reagent grade.
- **6.1.1.5 Deionized water**, in accordance with ISO 3696:1987, grade 2.
- 6.1.1.6 Potassium hydroxide at 1 mol/L.
- 6.1.2 Apparatus
- **6.1.2.1 Chloroform resistant vials and caps**, 25 mL or more capacity.
- 6.1.2.2 Balance accurate to 0,000 1 g.
- 6.1.2.3 Magnetic stir bar.
- 6.1.2.4 Magnetic stir plate.
- **6.1.2.5 Pipette**, capable of measuring 1 mL to 0,01 mL.
- **6.1.2.6 Fluoride ion selective electrode (F-ISE)**, with reference electrode, or combination F-ISE/reference electrode pair.

6.1.2.7 Plastic vial (or beaker or small container), 25 mL or more capacity.

6.1.2.8 pH/mV electrometer (pH meter), with a sensitivity of ± 0,1 mV.

Perform tests on "as received" samples.

6.2 Test conditions

Perform tests at room temperature with no more than 2 °C variation.

6.2.1 Preparation of standard solution

Make successive dilutions of the fluoride standard solution to obtain a set of working standard solutions that are 10^{-2} , 10^{-3} , 10^{-4} , 10^{-5} mol/L NaF.

6.2.2 Preparation of calibration curve

- a) Pipette 5,0 mL of each standard solution into a separate plastic vial (or beaker or small container).
- b) Add 5,0 mL of TISAB solution, add a magnetic stir bar to each plastic vial. Mix thoroughly.
- c) Insert the fluoride ion selective and reference electrodes into the liquid in the plastic vial containing the first standard solution.
- d) Record the millivolt reading to 0,1 mV at the steady potential difference with the mV electrometer.
- e) Conduct at least two measurements for millivolt readings until the difference between the two readings is less than 0,2 mV.
- f) Repeat steps (c) to (e) for each of the other/standard solutions.
- g) Construct a calibration curve of millivolts/iversus/the log of the fluoride ion concentration of the standard.

NOTE The slope of the calibration curve should be linear and no less than 55 mV per decade ($-\log_{10} [F]$), and the l c coefficient of determination (r^2) should be greater than 0,98.

6.2.3 Sample preparation

- a) Place open chloroform resistant vial that can be capped, such as a scintillation vial, on balance and tare to zero.
- b) Dispense 1 to 3 drops (0,05 g to 0,15 g) of varnish product onto the bottom of the container.
- c) Determine and record the mass of the amount of varnish [Varnish_{mass}] added to \pm 0,000 1 g.
- d) If the varnish sample contains fluorosilane, add 1,0 mL of 1 mol/L KOH to the varnish in the container and mix for 5 min. If the varnish sample does not contain fluorosilane then skip this step.
- e) Add (4 ± 0.5) mL of chloroform into the container and stir.
- f) Add $(10,0 \pm 0,1)$ mL of TISAB buffer to the chloroform + sample.
- g) Cap and vigorously shake the mixture to dissolve the resin into the chloroform and all the fluoride into the TISAB. Be careful to allow the pressure in the vial to escape by loosening the cap briefly and retightening.
- h) Add magnetic stir bar.
- i) Stir for at least 1,5 h at room temperature.