

SLOVENSKI STANDARD SIST-TP CEN/TR 16895:2016

01-december-2016

Jeklene in železove litine - Ugotavljanje svinca, kadmija, živega srebra, šestvalentnega kroma, polibromiranih bifenilov (PBB) in polibromiranih difeniletrov (PBDE) v zvezi z direktivami 2011/65/EU (RoHS) in 2000/53/ES (ELV) -**Omejitve**

Steels and cast irons - Determination of lead, cadmium, mercury, hexavalent chromium, polybrominated biphenyls (PBB) and polybrominated diphenylethers (PBDE) with regard to directives 2011/65/EU (RoHS) and 2000/53/EC (ELV) - Limitations

iTeh STANDARD PREVIEW

(standards.iteh.ai)

SIST-TP CEN/TR 16895:2016
Aciers et fontes - Déterminations du plomb du cadmium, du mercure du chrome hexavalent, des diphényles polybromés (RBB) et des diphenyléthers polybromés (PBDE) en relation avec les directives 2011/65/EU (RoHS) et 2000/53/EC (ELV) - Limites

Ta slovenski standard je istoveten z: CEN/TR 10364:2016

ICS:

77.040.30 Kemijska analiza kovin Chemical analysis of metals Železne kovine na splošno 77.080.01 Ferrous metals in general

SIST-TP CEN/TR 16895:2016 en,fr,de **SIST-TP CEN/TR 16895:2016**

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST-TP CEN/TR 16895:2016</u> https://standards.iteh.ai/catalog/standards/sist/31665977-85be-45ed-b888-1a90a900dbae/sist-tp-cen-tr-16895-2016

TECHNICAL REPORT RAPPORT TECHNIQUE TECHNISCHER BERICHT

CEN/TR 10364

March 2016

ICS 77.040.30; 77.080.01

English Version

Steels and cast irons - Determination of lead, cadmium, mercury, hexavalent chromium, polybrominated biphenyls (PBB) and polybrominated diphenylethers (PBDE) with regard to directives 2011/65/EU (RoHS) and 2000/53/EC (ELV) - Limitations

Aciers et fontes - Déterminations du plomb, du cadmium, du mercure, du chrome hexavalent, des diphényles polybromés (PBB) et des diphenyléthers polybromés (PBDE) en relation avec les directives 2011/65/EU (RoHS) et 2000/53/EC (ELV) - Limites

Stahl und Gusseisen - Bestimmung von Blei, Cadmium, Quecksilber, sechswertigem Chrom, polybromierten Biphenylen (PBB) und polybromierten Diphenylethern im Hinblick auf EU-Direktiven 2011/65/EU (RoHS) und 2000/53/EC (ELV) - Beschränkungen

This Technical Report was approved by CEN on 29 September 2015. It has been drawn up by the Technical Committee ECISS/TC 102.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom. https://standards.iteh.ai/catalog/standards/sist/31665977-85be-45ed-b888-

1a90a900dbae/sist-tp-cen-tr-16895-2016



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

SIST-TP CEN/TR 16895:2016

CEN/TR 10364:2016 (E)

Contents		Page
Europ	oean foreword	3
1	Scope	4
2	Requirements and applicability	4
2.1	General	4
2.2	Bulk materials	4
2.2.1	Lead (Pb)	4
2.2.2	Cadmium (Cd) and mercury (Hg)	5
2.2.3	Hexavalent chromium [Cr (VI)]	5
2.2.4	Polybrominated biphenyls (PBB) and polybrominated diphenylethers (PBDE)	5
2.3	Surface	5
2.3.1		
2.3.2	iTeh STANDARD PREVIEW Hexavalent chromium [Cr (VI)]	5
3	(standards.iteh.ai) Recommendation	<i>6</i>
Biblio	SIST-TP CEN/TR 16895;2016 https://standards.jten.al/catalog/standards/sist/31665977-85be-45ed-b888-	7
	1.00.000	

1a90a900dbae/sist-tp-cen-tr-16895-2016

CEN/TR 10364:2016 (E)

European foreword

This document (CEN/TR 10364:2016) has been prepared by Technical Committee ECISS/TC 102 "Methods of chemical analysis for iron and steel", the secretariat of which is held by SIS.

This project was submitted to the vote with document reference FprCEN/TR 16895.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST-TP CEN/TR 16895:2016</u> https://standards.iteh.ai/catalog/standards/sist/31665977-85be-45ed-b888-1a90a900dbae/sist-tp-cen-tr-16895-2016

CEN/TR 10364:2016 (E)

1 Scope

The present Technical Report gives guidance regarding the chemical composition controls of steels (except chrome plated products) and cast irons in respect of the European legislation, namely Directives 2011/65/EU (RoHS) [1], repealing 2002/95/EU and 2000/53/EC (ELV) [2].

These directives require the characterization of these materials for Cadmium (Cd), hexavalent chromium (Cr (VI)), mercury (Hg), Lead (Pb), polybrominated biphenyls (PBB) and polybrominated diphenylethers (PBDE). Nevertheless, the directives do not reflect the correspondence between these elements/compounds and the normal composition of each material concerned. In other words, for every material there is an obligation to determine all the compounds listed, independently of the relevance of such controls.

2 Requirements and applicability

2.1 General

Directive 2011/65/EU, article 4, restricts the following substances to the maximum concentration values to the following concentrations:

— Lead: 0.1 %:

— Mercury: 0,1 %;

iTeh STANDARD PREVIEW (standards.iteh.ai)

— Cadmium: 0,01 %;

(Standards.itch.ar)

— Hexavalent chromium: 0,1 %;

SIST-TP CEN/TR 16895:2016

- Polybrominated biphenyls (PBB): 0,1 % joa900dbae/sist-tp-cen-tr-16895-2016
- Polybrominated diphenyl ethers (PBDE): 0,1 %.

Steel and cast iron manufacturers are often required to state/provide compliance with the directives above and submit analytical results for each of those elements/compounds. However, due to the manufacturing processes and the inherent properties of the steels and cast irons, the determination of most of the compounds listed is not applicable or relevant.

Subclauses 2.2 and 2.3 details the relevance of these requirements.

2.2 Bulk materials

2.2.1 Lead (Pb)

Due to a 1 755 °C boiling point, lead is the single element among the six compounds specified in the directives which can be present in the steels and cast irons.

NOTE For stainless steel production using the Argon Oxygen Decarburization (AOD) converter process or equivalent, the lead content in the alloy will be considerably decreased to orders of magnitude below the directives requirements levels.

In contrast to cadmium and mercury, lead is also possible to detect and quantify on a reproducible base by using standardized methods as EN 10181 [3], EN 62321 [4], EN 62321-1 [5] or ISO 16918-1 [6].

2.2.2 Cadmium (Cd) and mercury (Hg)

With high temperature required during the melting processes and because of their physic-chemical properties, cadmium (Cd) and mercury (Hg) are normally absent in steels and cast irons.

The temperature required for melting iron based alloys is at least 1 400 °C, whereas the boiling temperatures of Cadmium (Cd) and mercury (Hg) are 767 °C and 357 °C respectively. In other words, these elements will evaporate during the melting process and cannot be present in an easily quantifiable amount in the steels and cast irons.

There are analytical techniques available and appropriate for the determination of both these elements below

 $1~\mu g/g$ as, for example, inductively coupled plasma mass spectrometry (ICP-MS), cold vapour atomic absorption spectrometry or electrothermal atomic absorption spectrometry (ETAAS). However for the physical reasons above, i.e. the "absence of content", it remains impossible to verify the robustness of the procedures for such aims: this includes selecting the most appropriate dissolution procedures and also the unavailability of appropriate reference materials.

2.2.3 Hexavalent chromium [Cr (VI)]

According to the document "hexavalent chromium in steels, cobalt, nickel and zirconium based alloys" [7] the occurrence of hexavalent chromium (Cr (VI)) in steel is purely hypothetical. This is due to the physical nature of metallic bonding where ions cannot exist.

2.2.4 Polybrominated biphenyls (PBB) and polybrominated diphenylethers (PBDE)

The most common types of polybrominated biphenyls (PBB) and polybrominated diphenylethers (PBDE) homologues are penta-, octo- and deca- bromodiphenyl ethers. They are extremely stable compounds with boiling points in the range of about 300 to 500 °C. Investigations [8] have shown that polybrominated biphenyls (PBB) decompose by pyrohydrolysis at temperatures ranging from 600 to 900 °C, i.e. significantly lower than in the steel making process and that the main part of polybrominated diphenylethers (PBDE) in fly ash from electric arc furnaces are destroyed or removed by thermal treatment at

1 450 °C [9].

Thus it shall be concluded that these compounds cannot be present in the steel (or cast iron) itself.

2.3 Surface

2.3.1 General

The as-delivered products from the steel plants or foundries are controlled and protected.

However, as for any material, the surface of steel and cast iron products may get contaminated or may undergo surface reactions. In some circumstances, due to further processing or treatments, this may result in presence of un-wanted substances on the surface.

2.3.2 Hexavalent chromium [Cr (VI)]

Due to some surface treatment, hexavalent chromium (Cr (VI)) is the single substance among the six elements/compounds specified in the directives which may be found on the surface of the steels and cast irons.

However a positive detection of this ion on the surface of any steel or cast iron shall not be put in correspondence with the bulk material composition. For the control of this ion, standardized methods are available as, for example, EN 62321.

CEN/TR 10364:2016 (E)

3 Recommendation

When receiving requirements related with Directives 2011/65/EU (RoHS), 2002/95/EU and 2000/53/EC, it is recommended to take the information given in the present Technical Report into account.

In other words, the single compounds relevant to be determined are:

- lead in the bulk materials (see NOTE in 2.2.1);
- hexavalent chromium (Cr (VI)) on the surface of some products (see 2.3.2).

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST-TP CEN/TR 16895:2016 https://standards.iteh.ai/catalog/standards/sist/31665977-85be-45ed-b888-1a90a900dbae/sist-tp-cen-tr-16895-2016