



SLOVENSKI STANDARD
oSIST prEN 13523-21:2016
01-julij-2016

Prevljučene kovine, ki se navijajo - Preskusne metode - 21. del: Vrednotenje preskušancev, izpostavljenih zunanjemu okolju

Coil coated metals - Test methods - Part 21: Evaluation of outdoor exposed panels

Bandbeschichtete Metalle - Prüfverfahren - Teil 21: Bewertung von freibewitterten Probenplatten

Tôles prélaquées - Méthodes d'essais - Partie 21 : Évaluation des panneaux exposés en extérieur

[SIST EN 13523-21:2017](https://standards.iteh.ai/catalog/standards/sist/a47f0085-573a-41c8-93d9-7c815aa86927/sist-en-13523-21-2016)

[https://standards.iteh.ai/catalog/standards/sist/a47f0085-573a-41c8-93d9-](https://standards.iteh.ai/catalog/standards/sist/a47f0085-573a-41c8-93d9-7c815aa86927/sist-en-13523-21-2016)

[7c815aa86927/sist-en-13523-21-2016](https://standards.iteh.ai/catalog/standards/sist/a47f0085-573a-41c8-93d9-7c815aa86927/sist-en-13523-21-2016)

Ta slovenski standard je istoveten z: prEN 13523-21

ICS:

25.220.60 Organske prevleke Organic coatings

oSIST prEN 13523-21:2016 **en**

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 13523-21

June 2016

ICS 25.220.60

Will supersede EN 13523-21:2010

English Version

Coil coated metals - Test methods - Part 21: Evaluation of outdoor exposed panels

Tôles prélaquées - Méthodes d'essais - Partie 21 :
Évaluation des panneaux exposés en extérieur

Bandbeschichtete Metalle - Prüfverfahren - Teil 21:
Bewertung von freibewitterten Probenplatten

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 139.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	3
Introduction	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	6
4 Principle	7
5 Apparatus and materials.....	8
6 Sampling.....	8
7 Test panels.....	8
8 Procedure.....	8
8.1 General.....	8
8.2 Preparation	8
8.3 Evaluation	9
8.3.1 General.....	9
8.3.2 Panel 1 (45° panel)	9
8.3.3 Panel 2 (90° panel)	9
8.3.4 Panel 3 (5° panel).....	10
9 Expression of results.....	11
10 Precision.....	11
11 Test report.....	12
Bibliography.....	16

European foreword

This document (prEN 13523-21:2016) has been prepared by Technical Committee CEN/TC 139 “Paints and varnishes”, the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 13523-21:2010.

The main changes compared to the previous edition are:

- a) a “terms and definitions” clause has been added containing all terms and definitions from EN ISO 4628-8 and a definition for edge;
- b) “corrosion” and “delamination” was changed to “corroded area” and “delaminated area”, where appropriate;
- c) the first inspection after 6 months was deleted;
- d) the inspection of defects using a $\times 10$ magnification was amended;
- e) a reference to EN ISO 4628-8 was amended for evaluation of delamination and corrosion around the scribe;
- f) the text has been revised editorially and the normative references have been updated.

The EN 13523 series, *Coil coated metals — Test methods*, consists of the following parts:

- *Part 0: General introduction*
- *Part 1: Film thickness*
- *Part 2: Gloss*
- *Part 3: Colour difference — Instrumental comparison*
- *Part 4: Pencil hardness*
- *Part 5: Resistance to rapid deformation (impact test)*
- *Part 6: Adhesion after indentation (cupping test)*
- *Part 7: Resistance to cracking on bending (T-bend test)*
- *Part 8: Resistance to salt spray (fog)*
- *Part 9: Resistance to water immersion*
- *Part 10: Resistance to fluorescent UV radiation and water condensation*
- *Part 11: Resistance to solvents (rubbing test)*
- *Part 12: Resistance to scratching*
- *Part 13: Resistance to accelerated ageing by the use of heat*

prEN 13523-21:2016 (E)

- *Part 14: Chalking (Helmen method)*
- *Part 15: Metamerism*
- *Part 16: Resistance to abrasion*
- *Part 17: Adhesion of strippable films*
- *Part 18: Resistance to staining*
- *Part 19: Panel design and method of atmospheric exposure testing*
- *Part 20: Foam adhesion*
- *Part 21: Evaluation of outdoor exposed panels*
- *Part 22: Colour difference — Visual comparison*
- *Part 23: Resistance to humid atmospheres containing sulfur dioxide*
- *Part 24: Resistance to blocking and pressure marking*
- *Part 25: Resistance to humidity*
- *Part 26: Resistance to condensation of water*
- *Part 27: Resistance to humid poultice (Cataplasma test)*
- *Part 29: Resistance to environmental soiling (Dirt pick-up and striping)*

<https://standards.iteh.ai/catalog/standards/sist/a47f0085-573a-41c8-93d9-7c815ae86927/sist-en-13523-21-2017>

Introduction

Pressure generated within a coil or a stack of sheets can affect the coating surface and cause marks of gloss transfer, plasticizer migration, etc. and even blocking/sticking.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 13523-21:2017](https://standards.iteh.ai/catalog/standards/sist/a47f0085-573a-41c8-93d9-7c815ae86927/sist-en-13523-21-2017)

<https://standards.iteh.ai/catalog/standards/sist/a47f0085-573a-41c8-93d9-7c815ae86927/sist-en-13523-21-2017>

prEN 13523-21:2016 (E)**1 Scope**

This part of the EN 13523 series specifies the procedure for evaluating the behaviour of an organic coating on a metallic substrate during and after outdoor exposure. Panel design, preparation and the procedure for outdoor exposure are performed in accordance with EN 13523-19.

After washing of the panel, some dirt can remain on the panel. This remaining dirt can influence the accuracy and precision of readings of gloss and colour, performed on exposed panels, although carried out in accordance with the standards. Unlike other precise measurements, the objective of this European Standard is to report on trends in the corrosion and/or paint degradation behaviour of coil coated panels.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1396, *Aluminium and aluminium alloys - Coil coated sheet and strip for general applications - Specifications*

EN 10169, *Continuously organic coated (coil coated) steel flat products — Technical delivery conditions*

EN 13523-0, *Coil coated metals - Test methods - Part 0: General introduction*

EN 13523-2, *Coil coated metals - Test methods - Part 2: Gloss*

EN 13523-3, *Coil coated metals - Test methods - Part 3: Colour difference - Instrumental comparison*

EN 13523-14, *Coil coated metals - Test methods - Part 14: Chalking (Helmen method)*

EN 13523-19, *Coil coated metals - Test methods - Part 19: Panel design and method of atmospheric exposure testing*

EN ISO 4628-2, *Paints and varnishes - Evaluation of degradation of coatings - Designation of quantity and size of defects, and of intensity of uniform changes in appearance - Part 2: Assessment of degree of blistering (ISO 4628-2)*

EN ISO 4628-3, *Paints and varnishes - Evaluation of degradation of coatings - Designation of quantity and size of defects, and of intensity of uniform changes in appearance - Part 3: Assessment of degree of rusting (ISO 4628-3)*

EN ISO 4628-4, *Paints and varnishes - Evaluation of degradation of coatings - Designation of quantity and size of defects, and of intensity of uniform changes in appearance - Part 4: Assessment of degree of cracking (ISO 4628-4)*

EN ISO 4628-5, *Paints and varnishes - Evaluation of degradation of coatings - Designation of quantity and size of defects, and of intensity of uniform changes in appearance - Part 5: Assessment of degree of flaking (ISO 4628-5)*

EN ISO 4628-8, *Paints and varnishes - Evaluation of degradation of coatings - Designation of quantity and size of defects, and of intensity of uniform changes in appearance - Part 8: Assessment of degree of delamination and corrosion around a scribe or other artificial defect (ISO 4628-8)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13523-0 and the following apply.

3.1

holiday

absence of a paint film from certain areas of a coated substrate

[SOURCE: EN ISO 4628-8:2012, 3.1]

3.2

artificial defect

holiday through a coating, deliberately introduced in order to expose the underlying metal substrate prior to exposure to a corrosive environment

[SOURCE: EN ISO 4628-8:2012, 3.2]

3.2.1

circular defect

circular holiday through a coating, deliberately introduced in order to expose the underlying metal substrate prior to exposure in a corrosive environment

[Source: EN ISO 4628-8:2012, 3.3]

3.2.2

scribe

linear holiday through a coating, deliberately introduced in order to expose the underlying metal substrate prior to exposure in a corrosive environment

[SOURCE: EN ISO 4628-8:2012, 3.6]

3.2.3

edge

unprotected cut edge, deliberately introduced in order to expose the underlying metal substrate prior to exposure in a corrosive environment

3.3

corroded area

area around a defect where the substrate has been attacked by corrosion

[SOURCE: EN ISO 4628-8:2012, 3.4]

3.4

delaminated area

area around a defect where loss of adhesion of a coating from a substrate or an underlying coating has occurred

[SOURCE: EN ISO 4628-8:2012, 3.5]

4 Principle

The behaviour of the test panels exposed in accordance with EN 13523-19 is evaluated. Any degradation in the relevant area is reported, using the relevant parts of the EN 13523 series and appropriate EN ISO Standards.

In cases where the inspection area is limited (e.g. at screws and bends), the evaluation method described in the EN ISO 4628 series is replaced by an easier and more suitable measurement of the degradation in millimetres.

Where possible, the results of symmetrical areas, e.g. left and right edges, are combined and the average value is reported.

prEN 13523-21:2016 (E)

The inspection of the 45° panel (panel 1) will focus on paint degradation, whereas the 90° panel (panel 2) and the 5° panel (panel 3) are mainly evaluated for corrosion.

NOTE 1 Panel designations (1, 2, 3) are as defined in EN 13523-19.

NOTE 2 Due to restrictions in the available flat area, the number of recommended readings might vary from other parts of the EN 13523 series and relevant EN ISO Standards.

It is strongly recommended to take a photograph of each exposed panel at each inspection.

5 Apparatus and materials

5.1 Gloss meter, in accordance with EN 13523-2.

5.2 Apparatus for colour measurement, in accordance with EN 13523-3.

5.3 Apparatus for measurement of chalking, in accordance with EN 13523-14.

5.4 Washing solution, containing 0,5 % (by mass) of a mild non-reactive detergent (pH 6 to 7) in water.

5.5 Cloth or sponge, non-abrasive and smooth.

6 Sampling

See EN 13523-0.

7 Test panels

See EN 13523-0.

8 Procedure

8.1 General

Evaluate the coating properties at ambient temperature.

The panels shall be inspected yearly and for a minimum duration as specified in EN 1396 or EN 10169. Colour measurements on metallics as well as gloss and colour measurements on textured and embossed surfaces are only indicative.

8.2 Preparation

8.2.1 Ensure that results of the measurements of gloss in accordance with EN 13523-2 and colour in accordance with EN 13523-3 are available before exposure of the test panels.

When using reference panels, these panels shall be kept in an envelope and not exposed to any light source.

8.2.2 Some measurements require a washed area prior to inspection. Washing shall be performed as follows:

Wash the upper 1/3 part of the 45° panel with washing solution (5.4) at ambient temperature. Use the cloth or sponge (5.5) to gently clean the surface. Rinse with water at ambient temperature and air dry at ambient temperature.

Washing should be carried out in such a way that the other 2/3 of the panel is not affected.