



Designation: ~~C1315-07~~ Designation: C 1315 – 08

Standard Specification for Liquid Membrane-Forming Compounds Having Special Properties for Curing and Sealing Concrete¹

This standard is issued under the fixed designation C 1315; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification provides requirements for membrane-forming liquids suitable for use as curing compounds and sealers on freshly placed concrete and as sealers on hardened concrete. These membranes have special properties, such as, alkali resistance, acid resistance, adhesion-promoting qualities, and resistance to degradation by UV light.

NOTE 1—For liquid membrane-forming curing compounds specified primarily by their ability to retain water in newly placed concrete (and by drying time, and for white pigmented products, reflectance), see Specification C 309.

1.2 The values stated in SI units are to be regarded as the standard. (Inch pound units are shown in parentheses).

1.3 The following precautionary caveat pertains only to the test methods portion, Section 8, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 This is a performance specification. The allowable composition of products covered by this specification is limited by various local, regional, and national regulations. Issues related to air quality (solvent emission), worker exposure, and other hazards are not addressed here. It is the responsibility of the producers and users of these materials to comply with pertinent regulations.

Warning—Some VOC exempt solvents used to meet the regulations are extremely flammable with low auto ignition temperatures and rapid evaporation rates. Consult the manufacturer's product information sheet for important application and safety information.

2. Referenced Documents

2.1 ASTM Standards:²

C 156 Test Method for Water Retention by Liquid Membrane-Forming Curing Compounds for Concrete

C 309 Specification for Liquid Membrane-Forming Compounds for Curing Concrete

D 869 Test Method for Evaluating Degree of Settling of Paint

D 1308 Test Method for Effect of Household Chemicals on Clear and Pigmented Organic Finishes

D 1309 Test Method for Settling Properties of Traffic Paints During Storage

D 1544 Test Method for Color of Transparent Liquids (Gardner Color Scale)

D 1734 Practice for Making Cementitious Panels for Testing Coatings

D 2369 Test Method for Volatile Content of Coatings

D 2371 Test Method for Pigment Content of Solvent-Reducible Paints

D 3723 Test Method for Pigment Content of Water-Emulsion Paints by Low-Temperature Ashing

D 4541 Test Method for Pull-Off Strength of Coatings Using Portable Adhesion Testers

E 1347 Test Method for Color and Color-Difference Measurement by Tristimulus Colorimetry

G 154 Practice for Operating Fluorescent Light Apparatus for UV Exposure of Nonmetallic Materials

2.2 Other Standard:

ANSI A136.1-1992 Type I Organic Adhesives for Installation of Ceramic Tile³

3. Classification

3.1 The following types of liquid membrane-forming compounds are included:

¹ This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.22 on Materials Applied to New Concrete Surfaces.

Current edition approved ~~June~~ March 1, 2007-2008. Published ~~July~~ 2007-April 2008. Originally approved in 1995. Last previous edition approved in 2006-2007 as ~~C1315-06~~ C 1315 – 07.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ American National Standard Specifications for the Installation of Ceramic Tile, 1992, Tile Council of America, P.O. Box 1787, Clemson, SC 29633-1787.

*A Summary of Changes section appears at the end of this standard.

3.1.1 *Type I*—Clear or translucent, and

3.1.2 *Type II*—White pigmented.

3.2 The curing compound shall conform to one of the following classes:

3.2.1 *Class A* curing compounds conform to the requirements of 6.4.1, and are essentially non-yellowing,

3.2.2 *Class B* curing compounds conform to the requirements of 6.4.2, where moderate yellowing is not prohibited, and

3.2.3 *Class C* curing compounds are not restricted with regard to yellowing or darkening, and are for use where the color changes are acceptable.

NOTE 2—Polymer materials known to satisfy the durability requirements of this document include, but are not limited to, chlorinated rubbers, styrene-acrylate and styrene-butadiene copolymers. These polymers have demonstrated their durability by their ability to adhere to concrete and not be affected by the alkalis from cement.

NOTE 3—Pigmented colors other than white, or other special attributes, are beyond the scope of this specification and are subject to negotiation between the purchaser and the supplier.

4. Ordering Information

4.1 The purchaser shall include the following information in the purchase order when applicable:

4.1.1 Type and class of liquid membrane-forming compound to be furnished,

4.1.2 Rate of application to be used to determine conformance to this specification,

4.1.2.1 For Type I compounds if not specified, the liquid membrane-forming material shall be applied by uniform spraying at a rate of 7.4 m²/L (300 ft²/gal) for testing purposes.

4.1.2.2 For Type II compounds, if not specified, the liquid membrane-forming material shall be applied by uniform spraying at a rate of 5.0 m²/L (200 ft²/gal) for testing purposes.

NOTE 4—The application rate used for testing may or may not be the same as the rate used for field application. Many agencies use the same rate for field application on relatively smooth surfaces as the rate used for testing, while requiring a substantially greater application rate on deeply textured surfaces.

4.1.3 The intended method of application (for example: spraying, brushing, or by roller). If not specified, materials shall be of a sprayable consistency.

5. General Requirements

5.1 Type I liquid membrane-forming compound shall be clear or translucent and have a minimum of 25 % solids by mass when tested in accordance with 8.5.

5.2 Type II liquid membrane-forming compound shall consist of finely divided white pigment and vehicle integrally ready mixed for immediate use as is and have a minimum of 25 % vehicle solids by mass when tested in accordance with 8.6. The membrane-forming compound shall present a uniform white appearance when applied uniformly to a new concrete surface at the specified rate of application.

NOTE 5—Although this is a performance specification, a minimum vehicle solids content is specified in order to provide an approximately 0.025 mm (1 mil) thick dry film at the specified rate of application. This film thickness is considered necessary to achieve the desired characteristics.

5.3 Liquid membrane-forming compounds shall be of such a consistency that they can be readily applied by spraying, or by brushing or rolling, to form a uniform coating at temperatures above 4 °C (40 °F).

NOTE 6—For uniform application in the field on vertical concrete surfaces, the specified rate of application may be achieved by two coats, each applied at one half the normal rate with approximately 1 h drying time between coats or in accordance with manufacturer's recommendations.

5.4 Liquid membrane-forming compounds shall adhere to freshly-placed concrete that has stiffened or set sufficiently to resist marring during application. Liquid membrane-forming compounds shall also adhere to damp or dry, hardened concrete surfaces. In every case, the compound shall form a continuous film after application at the specified rate.

5.5 Liquid membrane-forming compounds shall not react deleteriously with concrete. Deleterious reactions are detected by scratching the surface of a mortar specimen used for the water-retention test with a knife or screwdriver, not less than 72 h after application, and comparing with the surface hardness similarly determined on a similar specimen that has been moist cured for one half the time. Any softening of the treated surface shall be considered sufficient cause for rejection of the compound.

5.5.1 Testing for deleterious reactions is not needed on a routine basis. However, it must be done when testing compounds of a new or unknown composition.

5.6 Liquid membrane-forming compounds shall be storable for at least 6 months without deterioration. Compounds of the water emulsion type shall not be exposed to freezing. Type II liquid membrane-forming compounds shall be capable of being mixed to a uniform consistency by stirring or agitation. When tested for long term settling, as is stated in 8.4, the compound shall have a rating of not less than 4.

6. Specific Characteristics

6.1 *Water Retention*—Liquid membrane-forming compounds, when tested in accordance with 8.1 shall restrict the loss of water to not more than 0.40 g/m² in 72 h.

6.2 *Reflectance*—Type II liquid membrane-forming compounds, when tested in accordance with 8.2 shall exhibit a daylight reflectance of not less than 65 %. Reflectance properties are only for white pigmented materials.

6.3 *Drying Time*—Liquid membrane-forming compounds, when tested in accordance with 8.3 shall dry to touch in not more than 4 h.

6.4 *Ultraviolet Light (UV) Degradation-Yellowing* — When tested in accordance with 8.7.6, compounds shall be durable and remain as a complete film, free of blisters, peeling, or flaking on the surface of the mortar panel.

6.4.1 Class A Type I or Type II compounds shall have a color equal to or lighter than Gardner Color Standard No. 1 when tested in accordance with 8.7.6.

6.4.2 Class B Type I or Type II compounds shall have a color equal to or lighter than Gardner Color Standard No. 3 when tested in accordance with 8.7.6.

6.4.3 Class C shall not be tested for yellowing.

6.5 *Acid and Alkali Resistance* :

6.5.1 The cured membrane, when tested in accordance with 8.7.7 for 48 h, shall not pin-hole, blister or disintegrate.

6.6 *Adhesion*—This requirement is to assure that the product being specified does not reduce the bonding effectiveness of adhesives commonly used to adhere flooring materials such as ceramic tile, resilient tile, wood flooring and carpet to concrete.

6.6.1 When tested in accordance with 8.8, surfaces coated with the membrane-forming compound shall pass the performance requirement of 8.8.5.

7. Sampling

7.1 Samples shall be taken either at the plant or warehouse prior to delivery, or at the point of delivery, at the option of the purchaser. If sampling is done prior to shipment, the inspector representing the purchaser shall have free access to the materials being sampled and shall be afforded all reasonable facilities for inspection and sampling.

7.2 Thoroughly shake or stir liquid membrane-forming compounds before taking a sample. Take one sample for each lot, batch, or other unit of production in a shipment. If the liquid membrane-forming compound is in mixing tanks or vats, one third of the sample shall represent the material coming from the tank at the beginning of the filling operation, one third shall represent the material coming at the middle of the filling operation, and one third shall represent the material coming at the end of the filling operation. If the liquid membrane-forming compound to be sampled is in containers, obtain a sample by taking a portion out of a number of containers equal in number to the next integer larger than the cube root of the total number of containers in the lot.

7.3 Seal all of the filled containers represented by the sample to prevent leakage, substitution or dilution. The sampling agency shall mark each container represented by the sample with a suitable identification mark for later identification and correlation.

8. Test Methods

8.1 *Water Retention Test*—~~Using Test Method C156 at an application rate of 7.4 m²/L (300 ft²/gal) for Type I compounds and 5.0 m²/L (200 ft²/gal) for Type II compounds, test for water retention.~~ —Perform as per Test Method C 156. Unless otherwise specified by the manufacturer, use an application rate of 7.4 m²/L (300 ft²/gal) for Type I compounds and 5.0 m²/L (200 ft²/gal) for Type II compounds.

8.2 *Reflectance Test*—Using Test Method E 1347, determine the daylight reflectance of Type II membrane-forming compound on a mortar specimen after completion of the water retention test.

8.3 *Drying Time Test*:

8.3.1 *Scope*—This test method is used to determine the length of time for a liquid membrane-forming curing compound to dry to the touch.

8.3.2 *Significance and Use*—The ability of a liquid membrane-forming compound to dry in a suitable length of time enables the user the ability to perform other tasks on the concrete, such as sawing joints, and the like without lifting the membrane from the concrete by tracking.

8.3.3 *Procedure*—Apply the membrane-forming compound to a fresh mortar specimen at the specified rate of application and expose it to air at 23 ± 2 °C (73 ± 4 °F), 50 ± 10 % relative humidity and at an air velocity of approximately 180 m/min (600 ft/min) horizontally across the surface of the test specimen. Test the film with a finger using moderate pressure. Consider the film to be dry when the soft tacky condition no longer exists and the film feels firm.

8.3.4 *Precision and Bias*—The precision of the procedure for measuring the drying time of liquid membrane-forming compounds is being determined. The test method has no bias because there is not any acceptable reference material.

8.4 *Long Term Settling Test*—Use Test Method D 1309 for routine testing. In the case of dispute, use Test Method D 869.

8.5 *Solids Test (Type I)*—Test in accordance with Test Method D 2369.

8.6 *Vehicle Solids Test (Type II)*— Determine total nonvolatile content in accordance with Test Method D 2369, and pigment solids in accordance with Test Method D 2371 for solvent-borne products or Test Method D 3723 for water-borne products. Calculate percent vehicle solids as percent total solids minus percent pigment solids.

NOTE 7—This procedure is not satisfactory for water-borne products containing organic colorants or filler, or pigments which dehydrate or decompose below 230 °C (450 °F).

8.7 *UV Degradation, Yellowing, Acid, and Alkali Resistance*:

8.7.1 *Scope*—This procedure is used to evaluate the resistance of the membrane to the effects of UV radiation, acid, and alkali.