



Designation: ~~D3206-92 (Reapproved 2002)~~ Designation: D 3206 – 08

Standard Test Method for Soil Resistance of Floor Polishes¹

This standard is issued under the fixed designation D 3206; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of soil resistance of floor polishes on test tile only. A carpet covered roller is used to simulate the action of foot traffic. A synthetic soil is employed in conjunction with the roller.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

D 1436 Test Methods for Application of Emulsion Floor Polishes to Substrates for Testing Purposes

D 3153 Test Method for Recoatability of Water-Emulsion Floor Polishes

~~E 97 Test Method for Directional Reflectance Factor, 45-deg 0-deg, of Opaque Specimens by Broad-Band Filter Reflectometry Method of Test for Directional Reflectance Factor, 45-deg, 0-deg, of Opaque Specimens by Broad-Band Filter Spectrometry³~~

3. Significance and Use

3.1 This test method measures the ability of a floor polish to resist soiling by a standard soil that approximates dirt carried in from the outside.

4. Apparatus

4.1 *Official Vinyl Composition Tile (OVCT)*⁴—white, 304.8 by 304.8 mm (12 by 12 in.).

4.2 *Washability Apparatus*—The Gardner straight line washability machine.

4.3 *Roller*.⁴

4.4 *Carpeting*.⁵

4.5 *Soil*—Standard Soiling Compound—A soiling compound, such as AATCC (American Association of Textile Colorist and Chemist) synthetic soil formula.⁶

4.6 *Reflectometer*, equipped with a search unit for measuring diffused reflectance and a green filter.

4.7 *Pipet*, 2 mL.

5. Procedure

5.1 Clean the test tile in accordance with Test Method D 3153, paragraph 9.1.2. Rinse well and allow to dry. Apply 2 mL of

⁴ This test method is under the jurisdiction of ASTM Committee D21 on Polishes and is the direct responsibility of Subcommittee D21.04 on Performance Tests. Current edition approved Aug. 15, 1992. Published October 1992. Originally published as D3206-73. Last previous edition D3206-87.

¹ This test method is under the jurisdiction of ASTM Committee D21 on Polishes and is the direct responsibility of Subcommittee D21.04 on Performance Tests. Current edition approved March 1, 2008. Published April 2008. Originally approved in 1973. Last previous edition approved in 2002 as D 3206 – 92(2002).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards*, Vol 15.04, volume information, refer to the standard's Document Summary page on the ASTM website.

³ Annual Book of ASTM Standards, Vol 06.01.

⁴ Withdrawn.

⁵ The sole source of supply of the apparatus known to the committee at this time is Chemical Specialties Manufacturers Assn., 1913 Eye St., N.W., Washington, DC 20006. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.

⁶ Obtain tight weave short pile carpet from local store.

⁶ The sole source of supply of the apparatus known to the committee at this time is Rohm and Haas, Norristown and McKean Roads, Springhouse, PA 19477. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.

⁶ Prepared soils are available from Textile Innovations Corporation, P.O. Box 8, Windsor NC 27983 or SDL Atlas Textile Testing Solutions: SDL Atlas LLC, 3934 Airway Drive, Rock Hill, SC 29732.