INTERNATIONAL STANDARD

First edition 2018-10

Petroleum, petrochemical and natural gas industries — Scheme for conformity assessment of manufacturers of special materials

Industries du pétrole, de la pétrochimie et du gaz naturel — Système d'évaluation de la conformité des fabricants de matériaux spéciaux **iTeh STANDARD PREVIEW**

(standards.iteh.ai)

ISO 17782:2018 https://standards.iteh.ai/catalog/standards/sist/48e86801-653d-4cd1-8601f75c9a27cd09/iso-17782-2018



Reference number ISO 17782:2018(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 17782:2018</u> https://standards.iteh.ai/catalog/standards/sist/48e86801-653d-4cd1-8601f75c9a27cd09/iso-17782-2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Contents

Page

Forew	ord		v		
Introd	luction		vi		
1	Scope				
2	Norm	ativa rafarancas	1		
2	-		I		
3	Terms	, definitions and abbreviated terms	2		
	3.1 2.2	Terms and definitions	Z		
	5.2	Addreviated terms	4		
4	Respo	nsibilities	5		
	4.1	Purchaser's responsibilities	5		
	4.2	Manufacturer's responsibilities	5 r		
	4.3	Qualitying company's responsibilities			
5	Conformity assessment of manufacturers				
	5.1	Conformity assessment	6		
	5.2	Basis for assessment of manufacturers			
	5.3 5.4	Evaluation for conformity	/ 7		
	5.4	Statement of conformity			
	5.5				
6	Validit	ty of the manufacturer procedure conformity record (MPCR)			
	6.1 6.2	Ierm of Valletty and	/ 7		
	63	Transitional requirements (arc)s. iten.al)			
_	0.5				
7	Gener	al requirements	8		
	/.1	Knowledge and relevant experience 2010 7.1 https://standarda.teh.ai/catalog/standards/sist/48e86801-653d-4cd1-8601-	о8 о		
		7.1.2 Relevant experience 2009/iso-17782-2018	0 Q		
	7.2	Manufacturing facilities and equipment	8		
	7.3	Subcontractors and suppliers			
	7.4	Quality requirements for test laboratories and manufacturers of welded products	9		
		7.4.1 Test laboratories	9		
		7.4.2 Manufacturers of welded products	9		
8	Manufacturing procedure summary (MPS)				
	8.1	General	9		
	8.2	Content of the manufacturing procedure summary (MPS)	9		
		8.2.1 Scope of the manufacturing procedure summary	9		
		8.2.2 Manufacturing procedure summary requirements	10		
9	Heat treatment				
	9.1	Facilities and equipment	12		
		9.1.1 General	12		
		9.1.2 Foundries	12		
		9.1.3 Heat treatment furnaces	12		
		9.1.4 Thermocouples and pyrometers	13		
		9.1.5 Quencing baths 9.1.6 Loading of components	13		
		9.1.7 Transfer time between furnace and ouenching bath			
		9.1.8 Continuous, semi-continuous and induction furnaces			
	9.2	Heat treatment procedure			
		9.2.1 General	14		
		9.2.2 Heat treatment facilities and equipment	14		
		9.2.3 Loading and unloading of components and transfer between furnace and			
		quenching bath	14		
		9.2.4 Description of neat treatment cycle	14		

		9.2.5 Production testing and traceability	15			
		9.2.6 Documentation of heat treatments	15			
	9.3	Verification of heat treatment procedures	15			
		9.3.1 General	15			
		9.3.2 Objective	16			
		9.3.3 EXTENT OF VERIFICATION	16			
		9.3.4 Procedure for verification	10			
		9.5.5 Reporting	17 18			
4.0		J.J. G. A. I	10			
10	Verifi	Cation of the manufacturing process	10			
	10.1	Objective of verification testing	10			
	10.2	10.2.1 Congral	10 18			
		10.2.1 Central	18			
		10.2.3 Fittings	18			
		10.2.4 Forgings	18			
		10.2.5 Heat treatment				
		10.2.6 Hot forming	19			
		10.2.7 Hot isostatic pressed (HIP) products	20			
		10.2.8 Induction bending				
		10.2.9 Manufacture at different plants and/or locations	20			
		10.2.10 Manufacturing equipment				
		10.2.11 Material grade	20			
		10.2.12 Melting and refining process.	20			
		10.2.13 Start materials				
		10.2.14 Strain hardening standards.iteh.ai)	21			
		10.2.15 Thickness and mass limitations	22			
	10.2	Ouclification testing	23			
	10.5	10.2.1 Colottos/standards.itchaideatalegastenderds/sist/48e86801-653d-4cd1-8601-	43 22			
		10.3.2 Testing f75c9a27cd09/iso-17782-2018	23			
		10.3.2 Additional testing	25			
	10.4	Welding procedure qualifications				
11	Мари	facturing procedure conformity record (MPCP)	20			
11	11.1	General	29			
	11.2	Content of manufacturing procedure conformity record (MPCR)	29			
	11.3	Required copies and distribution of manufacturing procedure conformity record				
Anne	x A (info	ormative) Manufacturing Procedure Summary front page and examples	32			
A	D (max	mative) Temperature Uniformity Currery Additional requirements to				
Annez	Annes	Mative) remperature officially survey — Additional requirements to	38			
Anne		rmative) verification of the neat treatment procedure — Example	40			
Annex	x D (noi	mative) Fasteners	41			
Anne	x E (nor bend	mative) Induction bending — Testing for qualification of bends without post -	47			
Anne	F (nor	mative) Assessment of testing laboratories	4.8			
Annex G (normative) Manufacturing Procedure Conformity Record (MPCR) front page 57						
Dibliography						
bibliography						

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see <u>www.iso</u> .org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 67, Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <u>www.iso.org/members.html</u>.

Introduction

This document is based on NORSOK M-650, 4th edition, which was developed by the Norwegian petroleum industry to ensure adequate safety, value added and cost effectiveness for petroleum industry developments and operations.

The conformity assessment requirements provide a Scheme for manufacturers to demonstrate their competence and experience to manufacture the relevant material grades and product forms. The intention is that a manufacturing procedure conformity record (MPCR) accepted by one customer should also be acceptable for other customers, within the essential variables of this document.

This document includes the following annexes that are either normative or informative:

- <u>Annex A</u> provides the Manufacturing Procedure Summary front page and examples (informative);
- <u>Annex B</u> contains the Temperature Uniformity Survey with additional requirements to Annex M of ISO 10423:2009 and ASTM A991-10 (normative);
- <u>Annex C</u> provides an example of verification of the heat treatment procedure (informative);
- <u>Annex D</u> contains requirements related to fasteners (normative);
- <u>Annex E</u> contains requirements related to induction bending in the case of testing for qualification of bends without post-bend heat treatment (normative);
- <u>Annex F</u> contains requirements for the assessment of testing laboratories (normative);
- <u>Annex G</u> provides the Manufacturing Procedure Conformity Record front page (normative).

<u>ISO 17782:2018</u> https://standards.iteh.ai/catalog/standards/sist/48e86801-653d-4cd1-8601f75c9a27cd09/iso-17782-2018

Petroleum, petrochemical and natural gas industries — Scheme for conformity assessment of manufacturers of special materials

1 Scope

This document establishes a procedure for verifying that the manufacturer of special materials for the petroleum, petrochemical and natural gas industries has sufficient competence and experience of the relevant material grades of metal, and the necessary facilities and equipment, to manufacture these materials in the required shapes and sizes with acceptable properties according to the applicable standard, material specification and/or material data sheet specified by the purchaser.

This document is applicable to manufacturers of various materials, product forms and manufacturing processes when specified by the purchaser. This document has been established considering especially, but not exclusively:

- a) duplex stainless steel;
- b) high alloyed austenitic stainless steel;
- c) nickel-based alloy**i**;**Teh STANDARD PREVIEW**
- d) titanium and its alloys. (standards.iteh.ai)

This document is also applicable to the processes of induction bending and strain-hardened products.

https://standards.iteh.ai/catalog/standards/sist/48e86801-653d-4cd1-8601f75c9a27cd09/iso-17782-2018

2 Normative references f75c9a27cd09/iso-177

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3834-2, Quality requirements for fusion welding of metallic materials — Part 2: Comprehensive quality requirements

ISO 9000, Quality management systems — Fundamentals and vocabulary

ISO 10423:2009, Petroleum and natural gas industries — Drilling and production equipment — Wellhead and christmas tree equipment

ISO 10474, Steel and steel products — Inspection documents

ISO 14343, Welding consumables — Wire electrodes, strip electrodes, wires and rods for arc welding of stainless and heat resisting steels — Classification

ISO 15590-1, Petroleum and natural gas industries — Induction bends, fittings and flanges for pipeline transportation systems — Part 1: Induction bends

ISO 15614-1, Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys

ISO/IEC 17000:2004, Conformity assessment — Vocabulary and general principles

ISO/IEC 17025, General requirements for the competence of testing and calibration laboratories

ASME Boiler and Pressure Vessel Code, Section II, Materials, Part C, *Specifications for welding rods, electrodes, and filler metals* (also referred to ASME II Part C)

ASME Boiler and Pressure Vessel Code, Section IX: *Welding and Brazing Qualifications* (also referred to ASME IX)

ASTM A370-14, Standard Test Methods and Definitions for Mechanical Testing of Steel Products

ASTM A991-10, Standard Test Method for Conducting Temperature Uniformity Surveys of Furnaces Used to Heat Treat Steel Products

ASTM E407, Standard Practice for Microetching Metals and Alloys

EN 10204, Metallic products — Types of inspection documents

3 Terms, definitions and abbreviated terms

For the purposes of this document, the terms and definitions given in ISO 9000, ISO/IEC 17000 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <u>https://www.iso.org/obp</u>
- IEC Electropedia: available at <u>http://www.electropedia.org/</u>

iTeh STANDARD PREVIEW 3.1 Terms and definitions

3.1.1

conformity assessment

demonstration that specified requirements relating to a product, process, system, person or body are fulfilled f75c9a27cd09/iso-17782-2018

(standards.iteh.ai)

[SOURCE: ISO/IEC 17000:2004, 2.1]

3.1.2

continuous furnace

furnace in which the item/product to be heat treated is loaded and heat treated in a continuous cycle

3.1.3

company

owner or organization that is responsible for development of and/or operation of an installation/facility

Note 1 to entry: For the purposes of this document, the company is normally an oil company.

3.1.4

equalization time

time used to ensure a uniform pre-set temperature throughout a heat treatment load and/or throughout all section thicknesses of a component

3.1.5

heat sink

separate block used to monitor temperature during heat treatment and made from the same generic type of material as the parts being heat treated

3.1.6

high alloyed austenitic stainless steel (SS)

austenitic stainless steel typically having PREN \ge 40 or [%Ni + 2(%Mo)] > 30 where %Mo > 2, all mass fractions expressed as percent

EXAMPLE UNS S31254, UNS N08367, UNS N08926, UNS S31266, UNS S32654, UNS S34565, J93254.

3.1.7

holding time

time from when the controlling thermocouple(s) [normally the furnace thermocouple(s)] has reached set temperature until the specified soaking time is completed

Note 1 to entry: See also <u>Annex C</u>.

Note 2 to entry: Holding time consists of equalization time + soaking time. Holding time is not applicable to continuous and semi-continuous furnaces.

3.1.8

main contractor

party which carries out all or part of the design, engineering, procurement, construction, commissioning or management of a project, or operation or maintenance of a facility, on a contract awarded by the company

3.1.9

manufacturer

party, including subcontractors, which carries out operations that affect the material properties of the finished product

Note 1 to entry: A manufacturer should have minimum one operation, which affects material properties in-house.

Note 2 to entry: These operations can include forming, heat treatment, etc.

3.1.10 pitting resistance equivalent number DARD PREVIEW PREN

number indicating the resistance of stainless steel to pitting corrosion and related to chemical composition

Note 1 to entry: PREN is calculated from one of the following equations: d-4cd1-8601-

a) PREN = %Cr + 3,3 %Mo + 16 %N $f^{75c9a27cd09/iso-17782-2018}$

b) PREN = %Cr + 3,3 %(Mo + 0,5 W) + 16 %N

where all mass fractions are expressed as a percentage.

Note 2 to entry: The requirement for the minimum PREN value applies to the applicable material specification, MDS and/or material standard as specified by purchaser.

3.1.11

purchaser

party which purchases a product from a manufacturer

Note 1 to entry: Company (end user), main contractor and buyer are purchasers in the context used in this document.

3.1.12

Qualifying Company

body or person that performs *conformity assessment activity* (3.1.13)

3.1.13

second-party conformity assessment activity

conformity assessment activity that is performed by a person or organization that has a user interest in the object

Note 1 to entry: Persons or organizations performing second-party conformity assessment activities include, for example, purchasers or users of products, or potential customers seeking to rely on a supplier's management system, or organizations representing those interests.

[SOURCE: ISO/IEC 17000:2004, 2.3]

3.1.14

semi-continuous furnace

furnace for which the load to be heat treated is prepared as a batch in front of the furnace and then passed in a continuous way through the furnace

3.1.15

soaking time

time that the entire part/section being heat treated (throughout its cross-sections) remains within the specified soaking (material) temperature range

Note 1 to entry: See also <u>Annex C</u>.

3.1.16

soaking zone

zone in a continuous/semi-continuous heat treatment furnace where the material is maintained within the specified soaking temperature range

3.1.17

SS type 22Cr duplex

ferritic/austenitic stainless steel alloys with 30,0 < PREN < 40,0 and $Cr \ge 19$ % (mass fraction)

EXAMPLE UNS S31803 and UNS S32205.

3.1.18

SS type 25Cr duplex

ferritic/austenitic stainless steel alloys with $40.0 \le PREN < 48.0$ (mass fraction)

Note 1 to entry: This alloy is often referred to as "super duplex". (Standards.iteh.ai

EXAMPLE UNS S S32505, UNS S32550, UNS S32750, UNS S32760 and UNS S39274.

3.1.19

test direction https://standards.iteh.ai/catalog/standards/sist/48e86801-653d-4cd1-8601-

direction in which testing is carried out as defined relative to the geometry of the component to be tested

ISO 17782:2018

Note 1 to entry: For the purposes of this document, the definitions given in ASTM A370-14, section 5, apply, with axial defined as the longitudinal axis of the test specimen located parallel to the main axis of the component.

3.1.20

third-party conformity assessment activity

conformity assessment activity that is performed by a person or organization that is independent of the person or organization that provides the object, and of user interest in that object

Note 1 to entry: Criteria for the independence of the conformity assessment bodies and accreditation bodies are provided in the International Standards and Guides applicable to their activities [see Bibliography (in ISO/IEC 17000)].

[SOURCE: ISO/IEC 17000:2004, 2.4]

3.2 Abbreviated terms

- AOD argon oxygen decarburization
- API American Petroleum Institute
- ASTM American Society for Testing and Materials
- EN European Standard
- HIP hot isostatic pressed

HV	Vickers hardness
MDS	material data sheet
МОМ	minutes of meeting
MPCR	manufacturing procedure conformity record
MPS	manufacturing procedure summary
NDE	non-destructive examination
NORSOK	Industry Standards for the Competitive Standing of the Norwegian Offshore Sector
PED	Pressure Equipment Directive
PREN	pitting resistance equivalent number
PWHT	post-weld heat treatment
SS	stainless steel
UNS	unified numbering system
VOD	vacuum oxygen decarburization
WPQR	welding procedure qualification record PREVIEW
WPS	welding procedure specificationards.iteh.ai)

4 Responsibilities standards.iteh.ai/catalog/standards/sist/48e86801-653d-4cd1-8601-

f75c9a27cd09/iso-17782-2018

4.1 Purchaser's responsibilities

The purchaser is responsible for ensuring that the manufacturers engaged for a project are qualified within the essential variables of this document. Existing manufacturer's procedure conformity records (MPCRs) shall be reviewed for conformance with this document. Manufacturers unknown to the purchaser should in addition be visited.

Acceptance of an MPCR and the manufacturer chosen are at the discretion and determination of the purchaser.

The purchaser is not exempted from his responsibility for quality surveillance of his subcontractors, even if these fulfil the requirements of this document.

4.2 Manufacturer's responsibilities

The manufacturer is responsible for establishing and maintaining required documentation and carrying out verification and testing in accordance with this document.

A manufacturer conforming to this document assumes the obligation to carry out manufacturing and establish material/test certificates of products in accordance with the qualified Manufacturing Procedure Summary (MPS), including all referenced procedures. If an order requiring conformance with this document is outside the qualified range as defined in <u>10.2.15</u>, the purchaser shall be informed.

4.3 Qualifying Company's responsibilities

The Qualifying Company shall monitor the conformity assessment activities, review and finally approve the resulting MPCR by signing and stamping the MPCR front page (see <u>Annex G</u>).

The Qualifying Company person signing the MPQR shall have the following,

- a) a relevant education on bachelor level from a university college or equal;
- b) good knowledge of metallurgical aspects of the applicable alloys, which shall be evaluated, including phase and transformation diagrams, effects of hot forming, welding, heat treatment, testing, etc.;
- c) relevant knowledge of the manufacturing process(es) to be evaluated;
- d) in-depth knowledge and understanding of this document;
- e) previous experience with this document or received guidance/supervision from a person with previous qualification experience with this document.

The Qualifying Company shall be independent of the manufacturer.

NOTE Qualification (conformity assessment) experience with NORSOK M-650 Ed. 4 is considered equal to conformity assessment experience with this document.

5 Conformity assessment of manufacturers

5.1 Conformity assessment

The conformity assessment shall be carried out in cooperation with and verified by the Qualifying Company. The conformity assessment shall be carried out as either

- a) a second-party conformity assessment activity (see definition in <u>3.1.13</u>), or
- b) a third party conformity assessment activity (see definition in <u>3.1.20</u>), but only where the third party is accepted as a competent Qualifying Company by Company, Main Contractor or Purchaser.

A Qualifying Company can be engaged: iteh.ai/catalog/standards/sist/48e86801-653d-4cd1-8601-

f75c9a27cd09/iso-17782-2018

- a) through projects for which the manufacturer has specific orders; that is, through contact between the manufacturer and the Companies, Main Contractors or Purchasers;
- b) through a third party in cases where manufacturer wants to be evaluated without having any specific orders. In such cases the acceptance of the Qualifying Company and of the MPCR shall be by future customers prior to purchase order placement. Acceptance may be indicated by counter signature of the MPCR front page as specified in <u>5.5</u>.

5.2 Basis for assessment of manufacturers

The manufacturer, including any nominated subcontractors, shall have:

- a) knowledge and relevant manufacturing experience with the type of material to be qualified (see <u>Clause 7</u>);
- b) acceptable manufacturing facilities and equipment (see <u>Clauses 7</u> and <u>9</u>);
- c) an established MPS (procedure) covering all manufacturing steps from melting or start material, as defined in <u>Table 1</u>, column "Type of start material", to finished product (see <u>Clause 8</u>);
- d) an established heat treatment procedure (see <u>Clause 9</u>);
- e) a management system that conforms with the requirements of ISO 9001 or equivalent;
- f) satisfactory verification test results in conformance with this document (see <u>Clause 10</u>).

5.3 Evaluation for conformity

The Qualifying Company shall carry out a review and inspection of the manufacturing facilities, equipment, implementation of procedures and documentation, as required by this document, on the premises of the manufacturer and his subcontractors.

The results of the evaluation shall be documented in an evaluation report or minutes of meeting (MOM).

5.4 Review of manufacturing procedure conformity record (MPCR)

A complete MPCR with content in accordance with Clause 11 shall be established for review.

The only way to qualify a manufacturing procedure is to fulfil all the requirements of this document. It is not possible to deviate from this document with respect to being qualified. When all requirements in this document are fulfilled, the MPCR front page (see <u>Annex G</u>) shall be signed off and stamped by the Qualifying Company.

5.5 Statement of conformity

The original MPCR front page (see <u>Annex G</u>), completed with all data indicated in <u>Annex G</u> and signed by the Qualifying Company, is the only valid proof of conformity in accordance with this document.

Where a party authorized by the Company, Main Contractor or Purchaser is used as the Qualifying Company, the Company, Main Contractor or Purchaser who has given the authorization shall co-sign the MPCR front page to confirm their acceptance of the MPGR FVIEW

NOTE ISO does not keep any listing of qualified manufacturers who are accepted in accordance with this document.

6 Validity of the manufacturer procedure conformity record (MPCR)

f75c9a27cd09/iso-17782-2018

6.1 Term of validity

The manufacturer's MPCR is valid for a maximum of five years starting from the date of signing and stamping of the MPCR front page. For new manufacturers, see <u>7.1.2</u>.

For renewal of an existing MPCR according to <u>6.2</u>, the renewal is valid for a maximum of five years starting from the expiry date of the original conformity assessment.

The conformity assessment is valid within the parameters specified in 10.2.

6.2 Renewal of the MPCR

The MPCR from a manufacturer with regular production of the originally conformity assessed products and alloys to a valid MPS is considered renewed without additional testing provided that production testing records are retained that demonstrate continued conformance to the specifications employed for the original conformity assessment. It is a prerequisite that applicable requirements of this document are complied with.

A renewal shall be initiated prior to the expiry date of the existing MPCR. If this is not the case, a complete new conformity assessment shall be carried out.

The following actions shall be executed for a renewal of the conformity assessment:

- a) evaluating and reviewing the manufacturer's and subcontractors' premises according to <u>5.3</u> by the Qualifying Company;
- b) reviewing and updating the MPS and referred procedures and making a decision whether retesting is required;

- c) reviewing the heat treatment procedure and its corresponding verification (see 9.3) and making a decision whether a new verification is required;
- d) the renewed MPCR shall contain a MOM, which describes the actual parts of the MPCR, which shall be updated, and the conditions for the renewal of the conformity assessment;
- e) establishing and properly signing a new MPCR front page with new revision number.

6.3 Transitional requirements

A valid NORSOK M-650 Ed. 4 QTR, which complies with the essential variables of this document, is considered equivalent to this document provided the original material specification, e.g. NORSOK M-630 MDS, remains applicable.

Renewal of a NORSOK M-650 QTR to an ISO 17782 MPCR shall be in accordance with <u>6.2</u>.

7 General requirements

7.1 Knowledge and relevant experience

7.1.1 Knowledge

The manufacturer shall have in-house knowledge of the relevant metallurgical aspects of the alloys to be qualified, including phase transformation diagrams, effects of hot forming, welding, and heat treatment parameters, etc. as applicable to the manufacturing processes employed. (standards.iteh.ai)

7.1.2 Relevant experience

The manufacturer shall have relevant experience with manufacture of the type of material to be qualified. f75c9a27cd09/iso-17782-2018

Relevant experience shall be demonstrated by statistical data presented in the form of a histogram for key properties, e.g. tensile strength, impact toughness, corrosion resistance, etc. In addition, a relevant reference list from the last two years' production for the products, materials and the range of sizes to be qualified shall be included.

New manufacturers with less than two years of documented production for actual product and material may be qualified to this Scheme, but with a validity period limited to two years, after which a renewal according to <u>6.2</u> shall be carried out. The reason for the limited validity period shall be included on the MPCR front page.

7.2 Manufacturing facilities and equipment

Facilities and equipment shall be fit for purpose, regularly maintained and calibrated in conformance with pertinent International Standards and other requirements specific to the processes employed or the material grade being manufactured as specified in this document.

Requirements for heat treatment facilities and equipment are further described in <u>9.1</u>.

7.3 Subcontractors and suppliers

The manufacturer is responsible for ensuring that subcontracted services shall meet the requirements of this document for all manufacturing steps performed by the subcontractor.

The manufacturer shall demonstrate adequate and consistent control of supply chain regarding purchase of start materials as defined in <u>Table 1</u>, column "Type of start material".

7.4 Quality requirements for test laboratories and manufacturers of welded products

7.4.1 Test laboratories

Test laboratories shall operate in accordance with ISO/IEC 17025 for the applicable test methods.

Conformance to ISO/IEC 17025 shall be documented by,

- a) a national accreditation certificate with definition of the scope of the certificate, issued by an ISO/ IEC 17011 conforming national accreditation body or;
- b) the test laboratory shall complete and sign the form in <u>Annex F</u>. The form shall be presented to the Qualifying Company for evaluation. In such cases,
 - 1) the Qualifying Company shall carry out an assessment of the laboratory to review listed procedures and how they are implemented.
 - 2) In addition, microstructure examination, as applicable, shall be demonstrated to the Qualifying Company's satisfaction.
 - 3) The results of the assessment shall be documented by a statement of conformity, which shall be signed by the laboratory and the Qualifying Company. The statement of conformity shall be attached to the filled in form in <u>Annex F</u>.

7.4.2 Manufacturers of welded products

iTeh STANDARD PREVIEWManufacturers of welded products shall conform to ISO 3834-2 or equivalent, as accepted by the
Qualifying Company.(standards.iteh.ai)

8 Manufacturing procedure summary (MPS)

nttps://standards.iteh.ai/catalog/standards/sist/48e86801-653d-4cd1-8601f75c9a27cd09/iso-17782-2018

8.1 General

The manufacturer shall have an MPS for each production route, type of product, grade of material and size range.

NOTE Sometimes it can be convenient to combine several production routes, types of product and/or grades of material into one MPS, e.g. as shown in the flow chart in <u>Annex A</u>.

The MPS shall describe, step by step in a logical and correct sequence, all important manufacturing activities with reference to detailed procedures. A short description and the main parameters for each activity shall be included. Each production route shall be illustrated with a flow chart.

If the manufacturer has different plants or different production routes for a product, separate documentation is required for each of these. If essential parts of the work, e.g. forming, heat treatment, pickling, etc., are subcontracted, this shall be identified in the documentation. The documentation shall then include the name and address of each subcontractor and the relevant documentation from the subcontractor's equipment and procedures.

The MPS is the property of the manufacturer. Distribution is at the manufacturer's discretion.

8.2 Content of the manufacturing procedure summary (MPS)

8.2.1 Scope of the manufacturing procedure summary

The scope of the MPS shall be clearly defined, stating:

a) name and address of the manufacturer;