



Designation: B136 – 84 (Reapproved 2008)^{ε1}

Endorsed by American
Electroplaters' Society
Endorsed by National
Association of Metal Finishers

Standard Method for Measurement of Stain Resistance of Anodic Coatings on Aluminum¹

This standard is issued under the fixed designation B136; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

^{ε1} NOTE—The units statement in subsection 1.6 was corrected editorially in April 2008.

1. Scope

1.1 This method is intended to determine whether anodic oxide coatings on aluminum and its alloys, that have undergone a sealing treatment and contact with an acid solution, are stainproof or nonadsorptive with respect to dyes.

1.2 Coatings that have been properly sealed should be proof against adsorption of coloring materials and, hence, “nonstaining” in many types of service.

1.3 This method is applicable to anodic coatings intended for applications where they are exposed to the weather, or for protective purposes in corrosive media, and where resistance to staining is important.

NOTE 1—Performance in this test is predictive only of susceptibility to stain by dyes. It is not intended to be predictive of other factors in service performance such as pitting or general corrosion.

NOTE 2—For Aluminum Association Class I and II architectural anodic coatings that are sealed in solutions containing less than 15 ppm silicates or 3 ppm phosphates, the acid pretreatment may be omitted.

1.4 In the case of coatings colored in deep shades, where estimation of the intensity of any residual dye stain is difficult, interpretation of the test is based on whether or not the original color has been affected by the action of the test.

1.5 This method is not applicable to:

1.5.1 Chromic acid type anodic coatings.

1.5.2 Anodic coatings on aluminum alloys containing more than 2 mass % Cu or 4.5 mass % Si.

1.5.3 Anodic coatings that have been sealed only in dichromate solutions.

1.5.4 Anodic coatings that have undergone a treatment to render them hydrophobic.

1.6 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of whoever uses this standard to consult and establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Summary of Test Method

2.1 The method depends upon the observation that a non-sealed or poorly sealed anodic coating is attacked by acid and easily colored by dye, while an adequately sealed coating is not appreciably attacked and does not retain any dye stain.

2.2 The method comprises contacting the test area of the anodized specimen with nitric acid solution and, after rinsing and drying, applying a special dye solution followed by rinsing and rubbing the test area with pumice powder, drying, and visual examination of the test area for retention of dye stain. Coatings that exhibit no dye stain or change in color are considered to have passed the test.

3. Reagents

3.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society,² where such specifications are available. Other grades may be used, provided it is first ascertained that the reagent is of

¹ This method is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.07 on Conversion Coatings.

Current edition approved April 1, 2008. Published April 2008. Originally approved in 1940. Last previous edition approved in 2003 as B136 – 84 (2003). DOI: 10.1520/B0136-84R08E01.

² *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.