This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: D3766-86 (Reapproved 2007) Designation: D 3766 - 08

Standard Terminology Relating to Catalysts and Catalysis¹

This standard is issued under the fixed designation D 3766; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This terminology covers definitions of terms related to catalysts and catalysis.

NOTE 1—The Manual of Symbols and Terminology for Physicochemical Quantities and Units presents authoritative descriptions of many terms used in the field of catalysis.²

2. Terminology

2.1 Definitions:

activity activity, n—of a catalyst, the measure of the rate of a specific catalytic reaction conducted in the presence of a catalyst.
catalyst bed support calcine, v—in catalysis, to heat a material to a high temperature causing a physical or chemical change, for example, loss of moisture and volatile matter, or a phase change, or both.

<u>catalyst bed support, n</u>—an essentially inert plate, grid, particulate bed, or other structural component designed to hold up or bear a quantity of catalyst in a catalytic reactor.

catalyst carrier<u>catalyst carrier</u>, <u>n</u>—a solid, generally porous material upon the surface or into the voids of which catalytic materials are placed to create the desired catalyst.

DISCUSSION—A carrier may have or contribute to catalytic activity.

catalyst substrate catalyst substrate, *n*—less preferred alternative term for *catalyst carrier*. catalyst carrier .

catalyst support— less preferred alternative term for **catalyst carrier**. <u>catalyst support</u>, <u>n</u>—less preferred alternative term for **catalyst carrier**.

crush strength, *n*—*in catalysis*, a measure of the resistance of a single particle of a formed catalyst<u>formed catalysts or catalyst</u> <u>carriers</u>, either singly or in bulk, to loss of form when subjected to a compressive force.

DISCUSSION—Formed catalysts may include tablets, spheres, extrudates, rings, pellets, etc. and should be distinguished from powders and granules.

density, packing (bulk)<u>density, packing (bulk)</u>, <u>n</u>—the ratio of the mass of a collection of discrete pieces of solid material to the sum of the volumes of: the solids in each piece, the voids within the pieces, and the voids among the pieces of the particular collection.

density, particle (envelope)<u>density, particle</u> (envelope), <u>n</u>—the ratio of the mass of a particle to the sum of the volumes of: the solid in each piece and the voids within each piece, that is, within close-fitting imaginary envelopes completely surrounding each piece.

density, skeletal<u>density, skeletal, *n*</u>—the ratio of the mass of discrete pieces of solid material to the sum of the volumes of: the solid material in the pieces and closed (or blind) pores within the pieces.

- **density, theoretical**<u>density, theoretical, *n*—the ratio of the mass of a collection of discrete pieces of solid material to the sum of the volumes of said pieces, the solid material having an ideal regular arrangement at the atomic level.</u>
- envelope<u>envelope</u>, <u>n</u>—of a particle in catalysis, a theoretical surface that encloses the particle and that bridges openings to the interior of the particle.

porepore, <u>n</u>—in catalysis, a small opening in a material permitting admission, adsorption, or passage of a fluid.

pore size distribution pore size distribution, *n*— *in catalysis*, the volume of pores of a material expressed or displayed as a function of pore diameters.

pore volume distribution pore volume distribution, *n*—in catalysis, an alternative term for pore size distribution.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

¹ This terminology is under the jurisdiction of ASTM Committee D32 on Catalysts and is the direct responsibility of Subcommittee D32.92 on Nomenclature and Definitions.

Current edition approved Nov. 15, 2007. April 1, 2008. Published January April 2008. Originally approved in 1979. Last previous edition approved in 20022007 as D 3766–86(20027).

² "The Manual of Symbols and Terminology for Physicochemical Quantities and Units—Appendix II. Definitions, Terminology and Symbols in Colloid and Surface Chemistry. Part II: Heterogeneous Catalysis," Pure and Applied Chemistry, Vol 46, No. 1, 73–90(1976).