



Designation: ~~D5648-94~~ Designation: D 5648 – 01 (Reapproved 2008)

Standard Test Method for Torque-Tension Relationship of Adhesives Used on Threaded Fasteners (Lubricity)¹

This standard is issued under the fixed designation D 5648; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the torque-tension relationship (lubricity) of adhesives used for locking and sealing threaded fasteners.

~~1.2~~

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 *ASTM Standards:*²

D 907 Terminology of Adhesives

2.2 *Society of Automotive Engineers Standards:*

SAE J174 Torque Tension Test Procedure for Steel Threaded Fasteners³

SAE J429 Mechanical and Material Requirements for Externally Threaded Fasteners³

2.3 *Federal Specification:*

FF-N-836 Nut: Square, Hexagon, Cap, Slotted, Castle, Knurled, Welding and Single Ball Seat⁴

3. Terminology

3.1 *Definitions*—Many of the terms in this test method are defined in Terminology D 907.

4. Summary of Test Method

4.1 This test method consists of applying adhesive to a threaded fastener and measuring the developed tension applied to the fastener at specified torques. Alternatively, the torque required to reach specified levels of bolt tension may be measured.

5. Significance and Use

5.1 On some applications of threaded fasteners, it is desirable to control either the amount of developed tension when a specified range of torque has been applied or the torque required to develop a specified range of tension. This test method is used to determine the effect of using adhesives on the torque-tension relationship of threaded fasteners.

5.2 Accurate torque-tension relationships may be measured only by defining and controlling the many related test parameters.

6. Apparatus

6.1 *Tension-Measuring Device*, capable of measuring the axial tension induced in the bolt as it is tightened. ~~This device shall be accurately tightened, having an accuracy within ± 5 % of the test load.~~

¹ This test method is under the jurisdiction of ASTM Committee D-14 on Adhesives and is the direct responsibility of Subcommittee D14.80 on Metal Bonding Adhesives. Current edition approved Dec. 15, 1994. Published February 1995.

¹ This test method is under the jurisdiction of ASTM Committee D14 on Adhesives and is the direct responsibility of Subcommittee D14.60 on Adhesive Material Classification System

Current edition approved April 1, 2008. Published April 2008. Originally approved in 1994. Last previous edition approved in 2001 as D 5648 - 01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards*, Vol 15.06, volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from the Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

⁴ Available from the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20403.

⁴ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.