

---

---

**Plastics — Determination of burning  
behaviour by oxygen index —**

**Part 1:  
General requirements**

*Plastiques — Détermination du comportement au feu au moyen de  
l'indice d'oxygène —*

*Partie 1: Exigences générales*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[ISO 4589-1:2017](https://standards.iteh.ai/catalog/standards/sist/55fb278b-6d87-4c0f-b98c-6994e980356e/iso-4589-1-2017)

<https://standards.iteh.ai/catalog/standards/sist/55fb278b-6d87-4c0f-b98c-6994e980356e/iso-4589-1-2017>



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 4589-1:2017](https://standards.iteh.ai/catalog/standards/sist/55fb278b-6d87-4c0f-b98c-6994e980356e/iso-4589-1-2017)

<https://standards.iteh.ai/catalog/standards/sist/55fb278b-6d87-4c0f-b98c-6994e980356e/iso-4589-1-2017>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
[copyright@iso.org](mailto:copyright@iso.org)  
[www.iso.org](http://www.iso.org)

# Contents

	Page
Foreword .....	iv
Introduction .....	v
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principles of the test</b> .....	<b>2</b>
<b>5 Applicability of the test</b> .....	<b>2</b>
<b>6 Specimen preparation</b> .....	<b>3</b>
<b>7 Apparatus</b> .....	<b>3</b>
7.1 General .....	3
7.2 Measuring device .....	3
7.3 Column design .....	3
7.4 Sample holder .....	3
<b>8 Operating conditions</b> .....	<b>3</b>
8.1 Calibration .....	3
8.2 Flame application time .....	4
8.3 Gas flow .....	4
8.4 Elevated-temperature routine .....	4
8.5 Pass/fail criteria .....	4
<b>9 Conclusions</b> .....	<b>5</b>
<b>Bibliography</b> .....	<b>6</b>
	<a href="https://standards.iteh.ai/catalog/standards/sist/55fb278b-6d87-4c0f-b98c-6994e980356e/iso-4589-1-2017">https://standards.iteh.ai/catalog/standards/sist/55fb278b-6d87-4c0f-b98c-6994e980356e/iso-4589-1-2017</a>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html). (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 4, *Burning behaviour*.

<https://standards.iteh.ai/catalog/standards/sist/55fb278b-6d87-4c0f-b98c-589f68102161/iso-4589-1:2017>

This second edition cancels and replaces the first edition (ISO 4589-1:1996), which has been technically revised.

A list of all parts in the ISO 4589 series can be found on the ISO website.

## Introduction

The oxygen index (OI) test at ambient temperature was first described by Fenimore and Martin<sup>[3]</sup> in 1966. The first use of the method in standards was ASTM D2863:1970<sup>[2]</sup> and it has since been published in a wide range of national and international standards. It was published as ISO 4589 in 1984 and has now been revised as ISO 4589-2. The OI test at elevated temperatures is described in ISO 4589-3.

In the period since ASTM D2863 became a standard, a considerable number of papers have been published about this test. An example is the review in Reference [6] relating to the relevance of the test to real fire situations. Other papers have suggested empirical formulae relating OI to the amounts of added fire retardant, or describe practical investigations on the equipment performance (see Reference [7]). A clear consensus on the value of the two variants of the test has emerged, however, and it is the purpose of this document to discuss the use of the equipment and the applicability of both test methods.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 4589-1:2017

<https://standards.iteh.ai/catalog/standards/sist/55fb278b-6d87-4c0f-b98c-6994e980356e/iso-4589-1-2017>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 4589-1:2017

<https://standards.iteh.ai/catalog/standards/sist/55fb278b-6d87-4c0f-b98c-6994e980356e/iso-4589-1-2017>

# Plastics — Determination of burning behaviour by oxygen index —

## Part 1: General requirements

### 1 Scope

This document specifies the general requirements for the oxygen index (OI) test which are further described in ISO 4589-2 and ISO 4589-3 as follows:

- ISO 4589-2 describes a method for determining the minimum volume fraction of oxygen in a mixture of oxygen and nitrogen introduced at  $23\text{ °C} \pm 2\text{ °C}$  that will just support combustion of a material under specified test conditions;
- ISO 4589-3 describes methods of carrying out the same determination over a range of temperatures typically between  $25\text{ °C}$  and  $150\text{ °C}$  (although temperatures up to  $400\text{ °C}$  can be used).

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4589-2:2017, *Plastics — Determination of burning behaviour by oxygen index — Part 2: Ambient-temperature test*

ISO 4589-3:2017, *Plastics — Determination of burning behaviour by oxygen index — Part 3: Elevated-temperature test*

ISO 13943, *Fire safety — Vocabulary*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 13943 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

#### 3.1

**oxygen index**

**OI**

**limiting oxygen index**

**LOI**

minimum volume fraction of oxygen in a mixture of oxygen and nitrogen, at  $23\text{ °C} \pm 2\text{ °C}$ , that just supports flaming combustion of a material under specified test conditions

Note 1 to entry: It is expressed as a percentage, e.g. OI = 34,6 %.

[SOURCE: ISO 13943:2008, 4.248, modified — Note 1 to entry has been revised.]

## 4 Principles of the test

In ISO 4589-2, the material can be tested either as a rigid specimen or as a flexible specimen in a specified holder which is mounted in a transparent chimney in which a mixture of oxygen and nitrogen flows upwards in a laminar flow pattern. After specimen conditioning, the test is carried out at room temperature. This constitutes the test in its simplest form. In the top-surface ignition procedure, the applied flame is allowed to impinge on the top surface of the specimen for a maximum time of 30 s coupled with periodic removal of the flame every 5 s to check if the specimen is burning. This also ensures that the specimen temperature does not rise excessively, since this would normally lower the OI value. In the propagating-ignition procedure, the flame is allowed to impinge to a depth of approximately 6 mm down the vertical sides of the specimen. In the thin-film procedure, the film is wrapped in a 45° spiral around a rod and taped, after which the rod is withdrawn and the top end of the specimen is cut off at a distance of 20 mm from the top.

In ISO 4589-3, the material is tested in an identical manner, except that the test takes place in a heated column in which both the incoming gas and the gas passing up the column are heated. At the start of the test, the specimen and specimen holder are preheated in the gas flow for  $240 \text{ s} \pm 10 \text{ s}$  to allow them to reach temperature equilibrium prior to testing. The flame is applied for the same length of time as in ISO 4589-2.

## 5 Applicability of the test

The test is used for the quality control of materials, particularly to check the incorporation of flame retardants in the material under test, and for research and development. This test is often used for inclusion in material data sheets. This test, in isolation, is insufficient to evaluate the burning behaviour and should not be used for regulations relating to safety control and consumer protection. The test provides a sensitive measure of burning materials under controlled laboratory conditions. The results are dependent upon the specimen size, shape and orientation. Aside from these restrictions, the OI test is widely used in the polymer industry as well as by cable-manufacturing companies and by those manufacturing flame retardants.

The elevated-temperature test (ISO 4589-3) provides information on the effect of a range of temperatures on the OI value. As a result, the value of the test is different from that of the single-point measurement at room temperature in that it gives an understanding of the behaviour of materials over a temperature range. This is of particular value in detecting, for example, the potential loss of effectiveness of some added flame retardant or of some technology which has been shown to be significant in certain cases. It is also useful in monitoring any chemical changes taking place at the higher temperatures which can serve to enhance or reduce the tendency to burn.

The flammability temperature test (ISO 4589-3:2017, Annex A) provides a means for assessing the way in which materials behave in a normal atmosphere by determining the temperature at which the OI of a specimen is 20,9 %.

ISO 4589-2 and ISO 4589-3 can be used to compare the particular burning characteristics of a series of plastic materials. The burning characteristics of a material are complex, and one test alone is insufficient to evaluate the material behaviour. It should be stressed that a number of tests are required to describe all the burning characteristics of a material.

It is essential that these small-scale laboratory tests be regarded as material tests only. They are primarily for assistance in development, monitoring consistency and/or pre-selection of materials, and are not for use as the sole means of assessing the potential fire hazard of a material in use.

The specific requirements of different industries have resulted in the issue of a number of similar standards, but they are not completely identical, often using different burners and conditions of ignition. These different burners and conditions may give different test results and care should be exercised in comparing results from these tests when conducted in accordance with different standards.



## 6 Specimen preparation

Specimen preparation should always be carried out carefully. It is important to ensure that the surfaces are clean and free from any flaws, as failure to observe these precautions can profoundly affect the burning behaviour. No shortcuts should be taken in conditioning of specimens.

## 7 Apparatus

### 7.1 General

Several types of apparatus exist that meet the specifications of ISO 4589-2 and ISO 4589-3. Some models have flow meters, valves or oxygen analysers. Some models are modular and allow upgrading to a heated model at a later date. A full description of apparatus can be found in ISO 4589-2:2017, Clause 5 and ISO 4589-3.

### 7.2 Measuring device

ISO 4589-2 indicates that measurement may be made either by the use of flow meters or by the use of an oxygen analyser. It is essential to use the proper calibration information for flow meters and to calibrate oxygen analysers using a standard gas. It is also necessary to check the overall equipment from time to time at the intervals specified in ISO 4589-2 to ensure that there are no leaks in the system. This is critical if for any reason the equipment is dismantled and reassembled.

### 7.3 Column design

The preferred inside diameter of the column for the ambient test (ISO 4589-2) is 75 mm to 100 mm. The reason for this was clearly identified in Reference [8] which showed that there was entrainment of air from outside the column. In the case of ISO 4589-3, it is recommended that a 75 mm minimum diameter column be used, again with a restricted aperture since entrainment of air was more of a problem in this equipment. Without the aperture, there would be errors introduced into the oxygen index values for particular materials. The preferred shape and size of the opening to eliminate this effect is given in ISO 4589-2 and ISO 4589-3.

### 7.4 Sample holder

There are two types of holder, depending on the specimen: one for rigid specimens, the other for flexible specimens. Care should be taken to ensure that the specimen holder cools to ambient temperature in ISO 4589-2 testing. Alternatively, a second holder can be used.

The elevated-temperature test (ISO 4589-3) encounters a number of problems, one of which relates to the sample holder for flexible thermoplastic materials. The recommended wire cage support (see ISO 4589-3:2017, Figure 5) is not optimum for some products. Another practice is to support the test piece between two capillary glass tubes, the assembly being lightly bound together with a single tie of fine nichrome or stainless-steel wire (nominally 200 µm gauge) and held in a small standard clamp. This non-standard practice should be used carefully and recorded in the test report.

## 8 Operating conditions

### 8.1 Calibration

The importance of following the calibration procedures as specified in both ISO 4589-2 and ISO 4589-3 cannot be stressed too highly. It is recommended that a regular check be carried out by testing a specified material, such as poly(methyl methacrylate) (PMMA), and that records of all values obtained should be kept. If there is any significant change in these values then the complete calibration procedure should be carried out to determine the cause of the change.