

ISO/TC 183

Secretariat: SA

Voting begins on:
2020-06-22

Voting terminates on:
2020-08-17

Copper and nickel sulfide ores and concentrates — Determination of total chlorine content — Alkaline fusion and potentiometric titration method

Minerais et concentrés de cuivre et de nickel — Détermination de la teneur en chlore - Détermination de la teneur en chlore total

ITEH STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sis/4a19c916-6bfd-4a0a-bb45-a17ce5349c03/iso-fdis-15661>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number
ISO/FDIS 15661:2020(E)

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/4a19c91d-6bfd-4a0a-bb45-a17ce5349c03/iso-fdis-15661>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Reagents	2
6 Apparatus	4
7 Instrument operating parameters	4
8 Sample	4
8.1 Laboratory sample	4
8.2 Test sample	5
9 Procedure	5
9.1 Number of blank testing	5
9.2 Number of determinations	5
9.3 Determination	5
9.3.1 General	5
9.3.2 Decomposition of the test portion by fusion with a mixture of carbonate salts	5
9.3.3 Decomposition of the test portion by fusion with a mixture of potassium salts	6
9.3.4 Oxidation of sulfide	7
9.3.5 Preparation of solution for titration	7
9.3.6 Potentiometric titration	7
10 Expression of results	8
11 Precision and accuracy	9
11.1 Expression of precision	9
11.2 Method for obtaining the final result	10
11.3 Precision between laboratories	10
11.4 Check of trueness	11
12 Test report	12
Annex A (informative) Procedure for the preparation and determination of the mass of a predried test portion	13
Annex B (normative) Flow chart of the procedure for the acceptance of analytical values for test samples	15

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 183, *Copper, lead, zinc and nickel ores and concentrates*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Copper and nickel sulfide ores and concentrates — Determination of total chlorine content — Alkaline fusion and potentiometric titration method

CAUTION — The use of this document can involve hazardous materials, operations and equipment. This document does not purport to address all of the safety issues associated with its use. It is the responsibility of the user of this document to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to its use.

1 Scope

This document specifies an analytical method for the determination of total chlorine content using alkaline fusion and potentiometric titration.

This method is applicable to copper and nickel sulfide ores and concentrates having chlorine content in the following ranges:

- a) Method 1: 80 µg/g to 4 300 µg/g
- b) Method 2: 70 µg/g to 4 300 µg/g

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385, *Laboratory glassware — Burettes*

ISO 648, *Laboratory glassware — Single volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 4787, *Laboratory glassware — Volumetric instruments — Methods for testing of capacity and for use*

ISO 9599, *Copper, lead, zinc and nickel sulfide concentrates — Determination of hygroscopic moisture content of the analysis sample — Gravimetric method*

ISO 12743, *Copper, lead, zinc and nickel concentrates — Sampling procedures for determination of metal and moisture content*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

The test portion is decomposed by fusion with a mixture of sodium carbonate and potassium carbonate or with a mixture of potassium nitrate and potassium hydroxide. The fusion mixture is dissolved in water and the sulfide contained is oxidized with hydrogen peroxide.

At the acid pH, the chloride content is determined by potentiometric titration with silver nitrate solution after a known addition of the analyte.

5 Reagents

During the analysis, use only reagents of recognized analytical reagent grade and water that conforms with grade 2 of ISO 3696. Particular care should be taken to ensure all reagents are high purity.

5.1 Sodium carbonate (Na_2CO_3), high purity.

5.2 Potassium carbonate (K_2CO_3), high purity.

5.3 Potassium nitrate (KNO_3), high purity.

5.4 Potassium hydroxide (KOH), high purity.

5.5 Sodium chloride (NaCl), high purity.

5.6 Sodium bromide (NaBr), high purity.

5.7 Silver nitrate (AgNO_3), high purity.

5.8 Flux mixture.

Mix one portion of anhydrous sodium carbonate ([5.1](#)) and one portion of potassium carbonate ([5.2](#)).

If the grain size of some reagent is significantly different from the other, a size reduction and homogenization could be necessary.

Preferably use anhydrous reagent.

5.9 Methyl orange ($\text{C}_{14}\text{H}_{14}\text{N}_3\text{NaO}_3$), high purity.

5.10 Nitric acid (HNO_3), $\rho_{20} = 1,4$ g/ml, AR grade.

5.11 Hydrogen peroxide (H_2O_2), 30 % purity.

5.12 Nitric acid solution (HNO_3), volume fraction 1:1.

To a 1 000 ml volumetric flask add approximately 400 ml of deionized water and then 500 ml of concentrated nitric acid ([5.10](#)). Cool to room temperature, dilute to volume and homogenize.

5.13 Sodium chloride solution (NaCl), 0,01 mol/l.

Weigh 0,584 4 g of sodium chloride ([5.5](#)), oven-dried at 105 °C for approximately 1 h, and transfer to a 50 ml beaker. Adjust the mass before weighing according to the purity of the reagent used (mass = $0,584\ 4 \times 100/\text{purity}$). Transfer to a glass volumetric flask of 1 000 ml using deionized water. Dissolve, dilute to volume with deionized water and homogenize.

5.14 Sodium bromide solution (NaBr), 0,01 mol/l.

Weigh 1,028 9 g of sodium bromide (5.6), oven-dried at 105°C for approximately 1 h, and transfer to a 50 ml beaker. Adjust the mass to weigh according to the purity of the reagent used ($m = 1,028\ 9 \times 100/\text{purity}$). Transfer to a glass volumetric flask of 1 000 ml using deionized water. Dissolve and dilute to volume with deionized water and homogenize.

5.15 Methyl orange solution, 0,1 % mass fraction.

Dissolve 0,5 g of methyl orange (5.9) into a 500 ml flask with deionized water.

5.16 Deionized water.**5.17 Silver nitrate solution** (AgNO₃), 0,01 mol/l.

Dissolve 1,698 7 g of silver nitrate (5.7) in 1 l of deionized water. Stir to dissolve and allow to cool. Standardize this solution as specified in 5.18.

Adjust the mass to weigh according to a purity of the reagent used ($m = 1,698\ 7 \times 100/\text{purity}$).

This standard solution should be prepared at the same ambient temperature as that at which the determinations will be conducted.

5.18 Standardization — Determination of the titration factor of the silver nitrate solution

Add to three separate 250 ml beakers 2 ml of 0,01 mol/l sodium bromide solution (5.14) and 4 ml of 0,01 mol/l sodium chloride solution (5.13) and dilute to 200 ml with deionized water.

Add some drops of methyl orange solution (5.15) and adjust the pH with drops of nitric acid solution (5.12) until the colour changes from yellow to red. Add 2 ml extra.

Insert the electrode for chloride titration (6.12) in the titration solution, stir at a constant rate and wait about 3 min before titration.

Carry out the titration with 0,01 mol/l silver nitrate solution (5.17).

The end point (E) is detected automatically by the potentiometric sensor. The first end point represents the consumption of silver nitrate solution (5.17) due to the bromide ion ($E1$) and the second due to the chloride ion plus the bromide ion ($E2$). Calculate the volumes due to only the titration of chloride to each replicate V_1 , V_2 and V_3 using Formulae (1) to (3):

$$V_1 = E2_1 - E1_1 \quad (1)$$

$$V_2 = E2_2 - E1_2 \quad (2)$$

$$V_3 = E2_3 - E1_3 \quad (3)$$

Calculate the standardization factors f_1 , f_2 and f_3 using Formulae (4) to (6):

$$f_1 = V_{\text{NaCl}}/V_1 \quad (4)$$

$$f_2 = V_{\text{NaCl}}/V_2 \quad (5)$$

$$f_3 = V_{\text{NaCl}}/V_3 \quad (6)$$

where

ISO/FDIS 15661:2020(E)

V_{NaCl} is the volume of solution (5.13) added in ml, which in this case is equal to 4 ml.

Calculate to four significant figures the mean standardization factor, f , for the silver nitrate standard solution, provided that the range of the values of f_1 , f_2 and f_3 , does not exceed 0,02. If this range is exceeded, repeat the standardization or preparation of solutions.

It is desirable that the titration factor is in the range 0,99 to 1,01.

Use this factor at expression of results (see [Clause 10](#)) to obtain the total chlorine content of the samples.

6 Apparatus

All laboratory glassware and equipment shall be shown to be free of chlorine contamination.

Use ordinary laboratory apparatus and the following:

6.1 Volumetric glassware, of class A conforming with ISO 385, ISO 648 and ISO 1042 and used in accordance with ISO 4787.

6.2 Glassware beakers, 250 ml and 400 ml.

6.3 Zirconium crucibles, capacity of 80 ml with caps.

6.4 Nickel crucibles, capacity of 80 ml with caps (desirable).

6.5 Weighing device, capable of weighing the test sample and test portions to an accuracy of 0,000 1 g.

6.6 Oven, capable of being maintained at $105\text{ °C} \pm 5\text{ °C}$.

6.7 Gas burner.

6.8 Muffle furnace, capable of being maintained at $340\text{ °C} \pm 20\text{ °C}$ and $800\text{ °C} \pm 50\text{ °C}$.

6.9 Magnetic stirrer with hot plate.

6.10 Filter paper, sufficient retention capacity for filtration to clear solution.

6.11 Potentiometric titrator, commercially available.

6.12 Silver electrode for chloride titration (single-rod measuring cell).

7 Instrument operating parameters

Refer to the manufacturer's instructions for optimizing electrode and potentiometric titrator operation.

8 Sample

8.1 Laboratory sample

The laboratory sample shall be taken and prepared in accordance with the procedures described in ISO 12743.

8.2 Test sample

Prepare an air-equilibrated test sample in accordance with ISO 9599.

NOTE A test sample is not required if pre-dried test portions are used, see [Annex A](#).

9 Procedure

9.1 Number of blank testing

Carry out two blank tests in parallel with the analysis using the same quantities of all reagents but omitting the test sample as described in [9.3](#).

NOTE Blank tests in this method are used to subtract the known addition of bromide and chloride to the test samples.

9.2 Number of determinations

Carry out the determinations at least in duplicate, as far as possible under repeatability conditions, on each test sample.

NOTE Repeatability conditions exist where mutually independent test results are obtained with the same method on identical test material in the same laboratory by the same operator using the same equipment, within short intervals of time.

9.3 Determination

9.3.1 General

This item specifies two fusion methods for test sample preparation analysis: the decomposition of the test portion by fusion with a mixture of carbonate salts ([9.3.2](#)) or potassium salts ([9.3.3](#)). The choice of method depends on materials, reagents and time available for performing the procedure.

9.3.2 Decomposition of the test portion by fusion with a mixture of carbonate salts

9.3.2.1 Decomposition

Taking multiple increments, extract a representative test portion from the test sample. Weigh to the nearest 0,1 mg approximately 5 g of test sample.

Transfer the test portion to a zirconium crucible ([6.3](#)).

Add to the crucible 25 g of the flux mixture ([5.8](#)) and mix gently, taking care to avoid projections.

Cover with a cap.

Place the crucibles in a muffle furnace ([6.8](#)) at 800 °C. The zirconium crucibles may have a short shelf life when subjected to 800 °C.

After 20 min to 30 min of heating, remove each crucible individually and swirl well, spreading through the walls of the crucibles before the melt solidifies.

Place the crucibles in order on a metal or ceramic plate and allow to cool.

9.3.2.2 Dissolution of the test sample

Wash the crucible outside with deionized water and place in a 400 ml beaker ([6.2](#)).

Add deionized water to the beaker until the crucible is submerged. Be careful not to exceed the 200 ml graduation of the beaker.

Insert a magnetic bar into the crucible.

Place the beaker containing the crucible in the magnetic stirrer with hot plate (6.9). Warm and stir gently overnight so that the residue is completely digested.

Allow to cool.

Transfer the entire contents of the crucible to a 250 ml volumetric flask (6.1) and wash well with deionized water. Be sure that no residue remains in the crucible.

Fill to the mark with deionized water and homogenize well.

Proceed with solids separation by filtration or centrifugation.

Take 100 ml from the liquid part of the sample using volumetric equipment and transfer to a 250 ml beaker (6.2).

9.3.3 Decomposition of the test portion by fusion with a mixture of potassium salts

9.3.3.1 Decomposition

Place 4 g of potassium hydroxide (5.4) in a nickel crucible (6.4).

Taking multiple increments, extract a representative test portion from the test sample. Weigh to the nearest 0,1 mg approximately 2 g of test sample.

Transfer the test portion to the nickel crucible (6.4) containing potassium hydroxide (5.4).

Add to the crucible 2 g of potassium nitrate (5.3) and another 4 g of potassium hydroxide (5.4). Mix gently.

Provide pre-fusion in the gas burner for approximately 60 seconds to obtain as homogeneous a mix as possible, taking care to avoid projections.

The addition of fluxes should be carried out immediately before performing the pre-fusion.

Place the crucibles in a muffle furnace (6.8) at 340 °C.

After 30 minutes of heating, remove each crucible individually and swirl well, spreading through the walls of the crucibles before the melt solidifies.

Place the crucibles in order on a metal or ceramic plate and allow to cool.

9.3.3.2 Dissolution of the test sample

Wash the crucible outside with deionized water and place on a stable and clean surface.

Fill the crucible with deionized water and wait about 2 h for complete dissolution of the melt.

Multiple increments of water can be used to promote dissolution, if desired, to make the process faster.

Transfer, with the aid of a rubber tip, the entire contents of the crucible to a 200 ml volumetric flask (6.1). Wash well with deionized water. Be sure that no residue remains in the crucible.

Fill to the mark with deionized water and homogenize well.

Proceed with solids separation by filtration or centrifugation.

Take 100 ml from the liquid part of the sample using volumetric equipment and transfer to a 250 ml beaker (6.2).