



# Standard Specification for Cold-Expansion Fittings With Metal Compression-Sleeves for Cross-Linked Polyethylene (PEX) Pipe<sup>1</sup>

This standard is issued under the fixed designation F2080; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers cold-expansion fittings using metal compression-sleeves for use with cross-linked polyethylene (PEX) plastic pipe in  $\frac{3}{8}$ -in.,  $\frac{1}{2}$ -in.,  $\frac{5}{8}$ -in.,  $\frac{3}{4}$ -in., 1-in.,  $1\frac{1}{4}$ -in.,  $1\frac{1}{2}$ -in., and 2 in. nominal diameters, whereby the PEX pipe is cold-expanded before fitting assembly. These cold-expansion fittings and metal compression-sleeves are intended for use in residential and commercial, hot and cold, potable water distribution systems, as well as sealed central heating, including under-floor heating systems, with continuous operation at pressures up to and including 100 psi (690 kPa), and at temperatures up to and including 180°F (82°C).

1.2 Included in this specification are the requirements for materials, workmanship, dimensions, and markings to be used on the fittings and compression-sleeves. Performance requirements are as referenced in Specification F877.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 The following precautionary caveat pertains only to the test method portion, Section 10, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- A108 Specification for Steel Bar, Carbon and Alloy, Cold-Finished
- A269 Specification for Seamless and Welded Austenitic

### Stainless Steel Tubing for General Service

- A276 Specification for Stainless Steel Bars and Shapes
  - A312/A312M Specification for Seamless, Welded, and Heavily Cold Worked Austenitic Stainless Steel Pipes
  - A519 Specification for Seamless Carbon and Alloy Steel Mechanical Tubing
  - A584 Specification for Aluminum-Coated Steel Woven Wire Fence Fabric<sup>3</sup>
  - B16/B16M Specification for Free-Cutting Brass Rod, Bar and Shapes for Use in Screw Machines
  - B62 Specification for Composition Bronze or Ounce Metal Castings
  - B140/B140M Specification for Copper-Zinc-Lead (Red Brass or Hardware Bronze) Rod, Bar, and Shapes
  - B283 Specification for Copper and Copper-Alloy Die Forgings (Hot-Pressed)
  - B689 Specification for Electroplated Engineering Nickel Coatings
  - B851 Specification for Automated Controlled Shot Peening of Metallic Articles Prior to Nickel, Autocatalytic Nickel, or Chromium Plating, or as Final Finish
  - D1600 Terminology for Abbreviated Terms Relating to Plastics
  - D2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings
  - F412 Terminology Relating to Plastic Piping Systems
  - F876 Specification for Crosslinked Polyethylene (PEX) Tubing
  - F877 Specification for Crosslinked Polyethylene (PEX) Plastic Hot- and Cold-Water Distribution Systems
- ### 2.2 ASME Standards:
- B1.20.1 Pipe Threads General Purpose (Inch)<sup>4</sup>
  - B16.18 Cast Copper Alloy Solder Joint Pressure Fittings (Inch)<sup>4</sup>
  - B16.22 Wrought Copper Alloy Solder Joint Pressure Fittings (Inch)<sup>4</sup>

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.10 on Fittings. Current edition approved April 15, 2008. Published April 2008. Originally approved in 2001. Last previous edition approved in 2005 as F2080 – 05. DOI: 10.1520/F2080-08.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Withdrawn. The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

<sup>4</sup> Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

### 2.3 NSF Standards:

**Standard No. 14** for Plastic Piping Components and Related Materials<sup>5</sup>

**Standard No. 61** for Drinking Water System Components—Health Effects<sup>5</sup>

### 2.4 MSS Standard:

**SP-104** Wrought Copper Solder Joint Pressure Fittings<sup>6</sup>

### 2.5 EN Standards:

**EN 12164** Copper and Copper Alloys—Rod for Free Machining Purposes<sup>7</sup>

**EN 12165** Copper and Copper Alloys—Wrought and Unwrought Forging Stock<sup>7</sup>

## 3. Terminology

3.1 *Definitions*—Definitions of terms used in this specification are in accordance with Terminology **F412**, and abbreviations are in accordance with Terminology **D1600**, unless otherwise indicated.

### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *cross-linked polyethylene, n*—plastics prepared by cross-linking (curing) polyethylene compounds (PEX).

3.2.2 *fitting assembly, n*—comprised of a cold-expansion fitting and a metal compression-sleeve, whereby the PEX pipe is cold-expanded before fitting insertion, and the compression-sleeve is pulled over the PEX pipe.

## 4. Classification

4.1 This specification covers one class of metal and plastic cold-expansion fittings with metal compression-sleeves suitable for use with PEX pipe that meets the requirements of Specifications **F876** and **F877**.

## 5. Materials and Manufacture

5.1 *Fittings*—Cold-expansion fittings shall be made from one of the following materials:

5.1.1 *Machined Brass*—Machined brass cold-expansion fittings shall be made from material meeting the requirements of Specification **B16/B16M**, copper-alloy UNS C36000, or Specification **B140/B140M**, copper alloy UNS C31400, or Specification **B283**, copper-alloy UNS C89844, or Standard **EN 12164**, Copper Alloy CW614N.

5.1.2 *Machined Stainless Steel*—Machined stainless steel cold-expansion fittings shall be made from material meeting the requirements of Specification **A312/A312M**, stainless steel alloy 304L or 316L, or Specification **A269**, stainless steel alloy 304L or 316L, or Specification **A276**, stainless steel alloy 304L or 316L.

5.1.3 *Machined Carbon Steel*—Machined carbon steel cold-expansion fittings shall be made from material meeting the requirements of Specification **A108**, Carbon Steel Alloy 1020 or 1025, or Specification **A519**, Carbon Steel Alloy 1020, or 1025 or 1026.

<sup>5</sup> Available from NSF International, P.O. Box 130140, 789 N. Dixboro Rd., Ann Arbor, MI 48113-0140, <http://www.nsf.org>.

<sup>6</sup> Available from Manufacturer's Standardization Society of the Valve and Fittings Industry, 5203 Leesburg Pike, Suite 502, Falls Church, VA 22041.

<sup>7</sup> Available from European Committee for Standardization (CEN), 36 rue de Stassart, B-1050, Brussels, Belgium, <http://www.cenorm.be>.

5.1.4 *Forged Brass*—Forged brass cold-expansion fittings shall be made from material meeting the requirements of Specification **B283**, copper-alloy UNS C37700 or UNS C89844, or Standard **EN 12165**, Copper Alloy CW617N.

5.1.5 *Cast Copper Alloys*—Cast copper alloy cold-expansion fittings shall be made from material meeting the requirements of Specification **B62** copper alloy UNS C83600, or Specification **A584**, copper-alloy UNS C83800, C84400 or C89844.

5.2 *Compression-Sleeves*—Metal compression-sleeves shall be made from one of the following materials:

5.2.1 *Machined Brass*—Machined brass compression-sleeves shall be made from material meeting the requirements of Specification **B16/B16M** copper-alloy UNS C36000, or Standard EN 12168, Copper Alloy CW614N, or Standard **EN 12165**, Copper Alloy CW617N.

5.2.2 *Machined Stainless Steel*—Machined stainless steel compression-sleeves shall be made from material meeting the requirements of Specification **A312/A312M**, stainless steel alloy 304L or 316L, or Specification **A269**, stainless steel alloy 304L or 316L, or Specification **A276**, stainless steel alloy 304L or 316L.

5.3 *Plating*—Plating of either fitting component with nickel or chrome, or other metal is optional and must fall within the dimensional tolerances of this specification. Plating can not negatively affect the quality of markings or the ability to meet S1.2.

5.3.1 *Nickel Plating*—Application of electroplated nickel coating shall meet the requirements of Specifications **B689** and **B851**.

5.3.2 *Chrome Plating*—Application of electroplated chrome coating shall meet the requirements of Specification **B851**.

## 6. Performance Requirements

6.1 *General*—All performance tests shall be conducted on assemblies of fittings (cold-expansion fittings and compression-sleeves) and PEX pipe. Fittings shall meet the material and dimensional requirements of this specification. PEX pipe shall meet the requirements of Specifications **F876** and **F877**. Assembly of test specimens shall be in accordance with **9.3**. Each assembly shall contain at least two joints. Use separate sets of assemblies for each performance test requirement.

6.2 Fittings shall comply with the following performance requirements of Specification **F877**. When a section with an identical title appears in this Specification, it contains additional requirements that supplement those found in Specification **F877**.

6.2.1 Requirements,


6.2.2 Test Methods, and

6.2.3 Retest and Rejection.

## 7. Dimensions

7.1 *Dimensions and Tolerances*—The dimensions and tolerances of the cold-expansion fittings and compression-sleeves, when measured in accordance with **10.1**, shall be as shown in **Figs. 1 and 2**.

7.1.1 *Alignment*—The maximum angular variation of any opening shall not exceed 1° off the true centerline axis.



Note 1—All dimensions shall be measured with appropriate micrometers, such as pin or ball micrometers for wall thickness, and outside-diameter micrometers with flat anvils, or vernier calipers, to measure outside diameter and width of cold-expansion fittings and compression-sleeves.  
 Note 2—The average measurement is obtained from measurements taken in at least four locations spaced at approximately 45° around the circumference, in accordance with 10.1.

Size	A <sup>A</sup>	B	C	D	E	F	G	H	I	J <sup>B</sup>	K <sup>C</sup>	L	M	R <sub>1</sub>	R <sub>2</sub>	R <sub>3</sub>	S
3/8 in.	0.745 <sup>+</sup>	0.408	0.451	0.408	0.385	0.280	0.516	0.034	0.034	0.023	0.059	0.055	0.407	0.008	0.005	0.005	0.000
		0.420	0.461	0.418	0.395	0.292	0.536	0.044	0.044	0.033	0.069	0.065	0.419	0.020	0.010	0.015	0.010
1/2 in.	0.840 <sup>+</sup>	0.538	0.578	0.540	0.515	0.390	0.700	0.034	0.034	0.026	0.098	0.055	0.585	0.008	0.005	0.005	0.000
		0.550	0.590	0.552	0.525	0.402	0.720	0.044	0.044	0.036	0.110	0.065	0.600	0.020	0.010	0.015	0.010
5/8 in.	1.110 <sup>+</sup>	0.596	0.671	0.634	0.605	0.480	0.820	0.034	0.034	0.026	0.133	0.055	0.700	0.008	0.005	0.005	0.000
		0.608	0.683	0.646	0.615	0.492	0.840	0.044	0.044	0.036	0.145	0.065	0.715	0.020	0.010	0.015	0.010
3/4 in.	1.110 <sup>+</sup>	0.703	0.778	0.742	0.715	0.590	0.820	0.034	0.034	0.026	0.134	0.055	0.700	0.008	0.005	0.005	0.000
		0.715	0.790	0.754	0.725	0.602	0.840	0.044	0.044	0.036	0.146	0.065	0.715	0.020	0.010	0.015	0.010
1 in.	1.375 <sup>+</sup>	0.900	0.988	0.944	0.908	0.768	1.070	0.054	0.034	0.034	0.180	0.062	0.915	0.008	0.005	0.005	0.000
		0.918	1.000	0.956	0.918	0.780	1.090	0.064	0.044	0.044	0.192	0.072	0.930	0.020	0.010	0.017	0.010
1 1/4 in.	1.600 <sup>+</sup>	1.110	1.159	1.157	1.110	0.923	1.316	0.005	0.034	0.034	0.189	0.113	1.016	0.018	0.005	0.005	0.253
		1.128	1.171	1.169	1.122	0.938	1.336	0.017	0.044	0.044	0.207	0.123	1.031	0.030	0.010	0.017	0.268
1 1/2 in.	1.910 <sup>+</sup>	1.327	1.377	1.375	1.327	1.133	1.322	0.005	0.046	0.046	0.177	0.125	1.016	0.034	0.005	0.005	0.253
		1.345	1.389	1.387	1.339	1.145	1.342	0.017	0.056	0.056	0.195	0.135	1.031	0.048	0.010	0.017	0.268
2 in.	2.300 <sup>+</sup>	1.727	1.797	1.795	1.727	1.493	1.595	0.005	0.058	0.058	0.212	0.156	1.239	0.034	0.005	0.005	0.288
		1.745	1.809	1.807	1.739	1.508	1.615	0.017	0.068	0.068	0.238	0.166	1.254	0.048	0.010	0.017	0.306

<sup>A</sup> "A" dimensions (OD) are minimums. No maximum OD is specified, as this is a function of assembly tool geometry.  
<sup>B</sup> J dimensions 3 PLS.  
<sup>C</sup> K dimensions 3 PLS.

FIG. 1 Cold-Expansion Fittings Dimensions and Tolerances, in.

7.1.2 *Fittings with Solder-Joint Ends*—Solder-joint end dimensions shall be in accordance with ASME B16.18, ASME B16.22, or MSS SP-104.

7.1.3 *Tapered Threaded-Ends*—Fitting threads shall be right-hand, conforming to ASME B1.20.1, and shall be tapered threads (NPT).

7.1.4 *Straight Threaded-Ends*—Fitting threads shall be right-hand, conforming to ASME B1.20.1, and shall be straight mechanical threads (NPSM).

7.1.5 *Inside Diameter*—The minimum inside diameter, listed as Dimension F in Fig. 1, applies to the entire fitting not just the insert area. When fitting has ends that are of different sizes or configurations (for example, threaded, solder), or both, the minimum ID applies to entire insert area.

8. Workmanship, Finish and Appearance

8.1 The fittings shall be made from materials that are homogeneous throughout. All sealing surfaces shall be smooth

and free of foreign material. The walls of cold-expansion fittings and compression-sleeves shall be free of cracks, holes, blisters, voids, foreign inclusions, or other defects that are visible to the unaided eye and that affect wall integrity.

8.2 *Flash*—Except for the insert, molded polymer fittings shall be free of flash in excess of 0.005 in. On the insert, molded polymer fittings shall be free of flash in excess of 0.002 in. Flash, mismatch, and witness mark requirements for the insert shall be in accordance with Figs. 3 and 4.

8.3 *Splay*—Molded polymer fittings shall be free of visible splay excepting some light blushing at the gate location.

9. Assembly

9.1 Joints:

9.1.1 *Cold-Expansion Joints*—Fittings shall be joined to PEX pipe by first expanding the end of the pipe with the expander tool, inserting the cold-expansion fitting into expanded pipe, then pulling the compression-sleeve over the PEX