



Designation: B 806 – 08

Standard Specification for Copper Alloy Permanent Mold Castings for General Applications¹

This standard is issued under the fixed designation B 806; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification establishes requirements for copper alloy² permanent mold castings for general applications. Nominal compositions of the alloys under this specification are shown in **Table 1**.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form part of this specification to the extent referenced herein:

2.2 *ASTM Standards*:³

B 208 Practice for Preparing Tension Test Specimens for Copper Alloy Sand, Permanent Mold, Centrifugal, and Continuous Castings

B 824 Specification for General Requirements for Copper Alloy Castings

E 527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

3. Ordering Information

3.1 Orders for casting under this specification shall include the following information:

3.1.1 Quantity of castings required,

3.1.2 Copper Alloy UNS number (**Table 2**) and temper (as-cast, heat-treated, and so forth), (4.2),

3.1.3 Specification number, title, and year of issue.

3.1.4 Pattern or drawing number, and condition (cast, machined, and so forth),

3.1.5 Pressure test requirements, if specified in the purchase order (**Specification B 824**),

3.1.6 Soundness requirements, if specified in the purchase order (**Specification B 824**),

3.1.7 Repair of castings (**Section 7**),

3.1.8 Certification, if specified in the purchase order (**Specification B 824**),

3.1.9 Foundry test report, if specified in the purchase order (**Specification B 824**),

3.1.10 Witness inspection, if specified in the purchase order (**Specification B 824**),

3.1.11 Product marking, if specified in the purchase order (**Specification B 824**), and

3.1.12 Castings for Seawater Service (**Section 4**).

3.2 When material is purchased for agencies of the U.S. government, the Supplementary Requirements of **Specification B 824** may be specified.

4. Materials and Manufacture

4.1 For better corrosion resistance in sea water applications, castings in Copper Alloy UNS No. C95800 shall be given a temper anneal heat treatment at 1250 ± 50°F (675 ± 10°C) for 6 h minimum. Cooling shall be the fastest means possible that will not cause excess distortion or cracking. Propeller castings shall be exempt from this requirement.

5. Chemical Composition

5.1 The castings shall conform to the chemical requirements specified in **Table 2**.

5.2 These specification limits do not preclude the presence of other elements. Limits may be established for unnamed elements by agreement between the manufacturer and the supplier and the purchaser. Copper or zinc may be given as the remainder and may be taken as the difference between the sum of all the elements analysed and 100 %.

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.05 on Castings and Ingots for Remelting.

Current edition approved April 1, 2008. Published May 2008. Originally approved in 1990. Last previous edition approved in 2006 as B 806 – 06.

² The UNS system for copper and copper alloys (see Practice **E 527**) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00”. The suffix can be used to accommodate composition variations of the base alloy.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Nominal Composition

Classification	Copper Alloy UNS No.	Nominal Composition								
		Copper	Aluminum	Iron	Manganese	Nickel (incl Cobalt)	Silicon	Lead	Zinc	Tin
Aluminum bronze	C95300	89.0	10.0	1.0
	C95400	85.0	11.0	4.0
	C95410	84.0	10.0	4.0	...	2.0
Nickel aluminum bronze	C95500	81.0	11.0	4.0	...	4.0
	C95800	81.3	9.0	4.0	1.2	4.5
Silicon brass	C87500	82.0	4.0	...	14.0	...
	C87800	82.0	4.0	...	14.0	...
	C87850 ^A	76.0	3.0	...	20.9	...
Lead-free yellow brass ^B	C89540	61.0	0.40	0.30	...	0.5	36.0	0.8

^A Phosphorus 0.12.

^B Bismuth 0.9; selenium 0.03.

TABLE 2 Chemical Requirements

Classification	Copper Alloy UNS No.	Composition, % max except as indicated									Copper + Sum of named elements, min
		Copper	Aluminum	Iron	Manganese	Nickel (incl Cobalt)	Silicon	Lead	Zinc	Tin	
Aluminum bronze	C95300	86.0 min	9.0–11.0	0.75–1.5	99.0
	C95400	83.0 min	10.0–11.5	3.0–5.0	0.25	1.5	99.5
	C95410	83.0 min	10.0–11.5	3.0–5.0	0.25	1.5–2.5	99.5
Nickel aluminum bronze	C95500	78.0 min	10.0–11.5	3.0–5.0	1.0	3.0–5.5	99.5
	C95800	79.0 min	8.5–9.5	3.5–4.5 ^A	0.8–1.5	4.0–5.0 ^A	0.10	0.03	99.5
Silicon brass	C87500	79.0 min	0.5	3.0–5.0	0.50	12.0–16.0	...	99.5
	C87800	80.0 min	0.15	0.15	0.15	0.20	3.8–4.2	0.09	12.0–16.0	0.25	99.8 ^B
	C87850 ^C	74.0–78.0	...	0.10	0.10	0.20	2.7–3.4	0.10	Remainder	0.30	99.5
Lead-free yellow brass ^D	C89540	58.0–64.0	0.10–0.60	0.50	...	1.0	...	0.10	32.0–38.0	1.2	99.5

^A Iron content shall not exceed the nickel content.

^B Antimony 0.05 %; arsenic 0.05 %; magnesium 0.01 %; phosphorus 0.01 %; and sulfur 0.05 % max.

^C Antimony 0.10 %; phosphorus is a major element at 0.05–0.20 %.

^D Bismuth 0.6–1.2; selenium 0.10.

6. Mechanical Properties

6.1 Mechanical properties shall be determined from separately cast test bar castings and shall meet the requirements shown in **Table 3**.

7. Casting Repair

7.1 Alloys included in this specification are generally weldable. Weld repairs may be made at the manufacturer's discretion.

7.2 The castings shall not be impregnated without approval of the purchaser (3.1.7).

8. General Requirements

8.1 Material furnished under this specification shall conform to the applicable requirements of Specification **B 824**.

9. Sampling

9.1 A lot shall be as defined in Specification **B 824** with the exception that a lot shall consist of not more than 1000 lbs (455 kg) of castings (gates and risers removed).

9.2 Test bar castings shall be cast to the form and dimensions shown in Figs. 8 or 10 using the dies shown in Figs. 7 or 9 of Practice **B 208**.

10. Keywords

10.1 copper alloy castings; copper-base alloy castings; permanent mold castings

TABLE 3 Mechanical Requirements

Copper Alloy UNS No.	Tensile Strength, min ksi ^A (MPa) ^B	Yield Strength, min ^C ksi (MPa)	Elongation in 2 in. (50.8 mm) min, %
C95300	80 (550)	30 (205)	20
C95400	100 (690)	40 (275)	10
C95410	100 (690)	40 (275)	10
C95500	110 (760)	60 (415)	5
C95800 ^D	90 (620)	40 (275)	15
C87500	80 (550)	30 (205)	15
C87800	80 (550)	30 (205)	15
C87850	64 (440)	32 (220)	16
C89540	35 (240)	21 (140)	5

^A ksi = 1000 psi.

^B See **Appendix X1**.

^C Yield strength shall be determined as the stress producing an elongation under load of 0.5 %, that is, 0.01 in. in a gage length of 2 in.

^D As cast or temper annealed.