
**Electrolytic tin-coated cold-reduced
carbon steel sheet of commercial and
drawing qualities**

*Tôles en acier au carbone laminées à froid, revêtues en continu
d'un dépôt électrolytique d'étain, de qualités commerciale et pour
emboutissage*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 5950:2012](https://standards.iteh.ai/catalog/standards/sist/cdf0b83d-2c63-49cf-bd03-fc94406cc4ae/iso-5950-2012)

[https://standards.iteh.ai/catalog/standards/sist/cdf0b83d-2c63-49cf-bd03-
fc94406cc4ae/iso-5950-2012](https://standards.iteh.ai/catalog/standards/sist/cdf0b83d-2c63-49cf-bd03-fc94406cc4ae/iso-5950-2012)



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 5950:2012

<https://standards.iteh.ai/catalog/standards/sist/cdf0b83d-2c63-49cf-bd03-fc94406cc4ae/iso-5950-2012>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Designation system	2
5 Dimensions	2
6 Conditions of manufacture	2
6.1 Chemical composition	2
6.2 Coating mass	3
6.3 Weldability	4
6.4 Fabrication qualities	4
6.5 Mill passivation	4
6.6 Coating condition	4
6.7 Application	5
6.8 Mechanical properties	5
6.9 Surface finish	5
6.10 Oiling	5
7 Dimensional tolerances	5
8 Sampling	6
8.1 Tensile test	6
8.2 Tests for mass of coating	6
9 Test methods	6
9.1 Tensile test (base metal)	6
9.2 Coating tests	6
10 Retests	6
10.1 Machining and flaws	6
10.2 Additional tests	6
11 Resubmission	7
12 Workmanship	7
13 Inspection and acceptance	7
14 Coil size	7
15 Marking	7
16 Information to be supplied by the purchaser	8
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 5950 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 12, *Continuous mill flat rolled products*.

This fifth edition cancels and replaces the fourth edition (ISO 5950:2008), which has been technically revised.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 5950:2012](https://standards.iteh.ai/catalog/standards/sist/cdf0b83d-2c63-49cf-bd03-fc94406cc4ae/iso-5950-2012)

<https://standards.iteh.ai/catalog/standards/sist/cdf0b83d-2c63-49cf-bd03-fc94406cc4ae/iso-5950-2012>

Electrolytic tin-coated cold-reduced carbon steel sheet of commercial and drawing qualities

1 Scope

1.1 This International Standard applies to cold-reduced carbon steel sheet of commercial and drawing qualities coated in coil or cut length forms by electro-deposition of tin. The product is commonly known as electrolytic tin-coated sheet and is used where solderability is desired, appearance is important, or a degree of corrosion resistance under specific conditions is advantageous and coating mass can be specified. The coating is expressed as the total coating on both surfaces, in grams per square metre. The coating mass specified should be compatible with the desired service life, thickness of the base metal and the forming requirements involved. A designation system (Clause 4) includes the coating designation, coating condition and quality.

1.2 This International Standard does not cover tinplate and blackplate.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 16162, *Cold-rolled steel sheet products — Dimensional and shape tolerances*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

electrolytic tin-coated sheet

product obtained by electrolytic deposition of tin on cold-reduced steel sheet on a continuous electrolytic tinning line to produce either tin-coated coils or tin-coated cut lengths

3.2

skin pass

light cold-rolling of the cold-reduced and annealed sheet prior to electro-tinning

NOTE The purposes of skin passing are one or more of the following:

- to minimize the appearance of coil breaks, stretcher strains and fluting;
- to control the shape;
- to obtain the required surface finish.

An increase in hardness and some loss in ductility will result from skin passing.

3.3

aluminum killed

steel which has been deoxidized with aluminum sufficient to prevent the evolution of gas during solidification

4 Designation system

The as-produced electrolytic tin-coated sheet coatings are designated as SN as shown in Table 4. The coating mass designation follows the SN and three spaces are allocated for coating mass designation. If only two spaces are required, such as for designation 56, then the 56 is preceded by a “0” to fill computer space and is shown as “056”. Since this product is always skin-passed, the section in this designation system usually reserved for S or N will be used to indicate where the tin has been reflowed, or whether it is “matt” or not reflowed (see 6.6 and 6.9). Therefore, the designations for this tin condition will be

- BR: Bright reflowed, fused, melted,
- MA: Matt, dull, not reflowed, unmelted.

The numbers 01, 02, 03 and 04 are common to other standards indicating the qualities of commercial, drawing, deep drawing, and deep drawing aluminium killed.

EXAMPLE SN056BR03 is a complete designation, including coating, coating mass, coating condition and quality signifying:

- SN: Tin coating,
- 056: Coating designation (Table 4),
- BR: Bright; tin has been reflowed,
- 03: Deep drawing quality.

iTeh STANDARD PREVIEW (standards.iteh.ai)

5 Dimensions

Electrolytic tin-coated sheet is normally produced in thicknesses from 0,50 mm to 0,85 mm and widths of 600 mm to 1 050 mm, in coils and cut lengths. [ISO 5950:2012](https://standards.iteh.ai/catalog/standards/sist/cdf0b83d-2c63-49cf-bd03-1c74406c74ac/iso-5950-2012)

NOTE Some world markets define “electrolytic tinplate” as having a maximum thickness of 0,38 mm, in which case, the thickness range for “electrolytic tin-coated sheet” will have a minimum of 0,38 mm.

6 Conditions of manufacture

6.1 Chemical composition

The chemical composition (heat analysis) shall not exceed the values given in Tables 1 and 2. On request, a report of the heat analysis shall be made to the purchaser.

Each of the elements listed in Table 2 shall be included in the report of the heat analysis. When the amount of copper, nickel, chromium or molybdenum present is less than 0,02 %, the analysis result may be reported as “< 0,02 %”.

A verification analysis may be made by the purchaser to verify the specified analysis of the product and shall take into consideration any normal heterogeneity. Non-killed steels (such as rimmed or capped steels) are not technologically suited to product analysis. For killed steels, the sampling method and deviation limits shall be agreed upon between the interested parties at the time of ordering. The product analysis tolerances are shown in Table 3.

The processes used in making the steel and in manufacturing tin-coated sheet are left to the discretion of the manufacturer. When requested, the purchaser shall be informed of the steel-making process used.

Table 1 — Chemical composition (heat analysis)

Mass fractions in percent

Quality		C max.	Mn max. ^a	P max. ^a	S max.
Designation	Name				
01	Commercial	0,15	0,60	0,03	0,035
02	Drawing ^b	0,10	0,50	0,03	0,035
03	Deep drawing ^b	0,08	0,45	0,02	0,03
04	Deep drawing aluminum killed ^b (non-ageing)	0,06	0,45	0,02	0,03

^a Higher maximum required for certain applications subject to agreement.

^b If interstitial free (IF Steel) is to be applied to 02, 03 and 04 orders, the values of 0,15 % maximum Ti and 0,10 % maximum Nb and V are acceptable to ensure that the carbon and nitrogen are fully stabilized.

Table 2 — Limits on additional chemical elements

Mass fractions in percent

Elements ^a	Heat analysis max.	Product analysis max.
Cu ^b	0,20	0,23
Ni ^b	0,20	0,23
Cr ^{b,c}	0,15	0,19
Mo ^{b,c}	0,06	0,07
Nb ^d	0,008	0,018
V ^d	0,008	0,018
Ti ^d	0,008	0,018

^a Each of the elements listed in this table shall be included in the report of the heat analysis. When the amount of copper, nickel, chromium or molybdenum present is less than 0,02 %, the analysis may be reported as "< 0,02 %".

^b The sum of copper, nickel, chromium and molybdenum shall not exceed 0,50 % on heat analysis. When one or more of these elements is specified, the sum does not apply; in which case, only the individual limits on the remaining elements will apply.

^c The sum of chromium and molybdenum shall not exceed 0,16 % on heat analysis. When one or more of these elements is specified, the sum does not apply; in which case, only the individual limits on the remaining elements will apply.

^d For stabilized steels, the maximum for titanium is 0,15 %, and the maximum for each of niobium and vanadium is 0,10 %, to ensure that the carbon and nitrogen are fully stabilized.

Table 3 — Product analysis tolerances

Mass fractions in percent

Element	Maximum of specified element	Tolerance over maximum specified
Carbon	0,15	0,03
Manganese	0,60	0,03
Phosphorus	0,03	0,01
Sulfur	0,035	0,01

NOTE The maximum tolerance in this table is the allowable excess over the specified requirement and not the heat analysis.

6.2 Coating mass

The coating mass shall conform to the requirements presented in Table 4 for the specific coating designation. The coating mass is the total amount of the tin, including both sides of the sheet, expressed

in grams per square metre (g/m²) of sheet. Methods for checking that the material complies with this International Standard are given in 8.2 and 9.2.

Table 4 — Mass of coating (total both sides)

Coating designation	Nominal coating g/m ²	Minimum coating mass limits	
		Triple spot test check limits g/m ² (of sheet)	Single spot test check limits g/m ² (of sheet)
SN056	5,6	3,7	2,8
SN112	11,2	7,3	5,6
SN168	16,8	11,0	8,2
SN224	22,4	14,6	11,0

Because of the many variables and changing conditions that are characteristic of continuous tin coating, the mass of coating is not always evenly divided between the two surfaces of a tin-coated sheet, neither is the tin coating evenly distributed from edge to edge. However, it can normally be expected that not less than 40 % of the single-spot check limit will be found on either surface.

6.3 Weldability

The product is suitable for welding if appropriate welding conditions are selected; however, because of its excellent solderability, welding is seldom performed.

6.4 Fabrication qualities

ITeH STANDARD PREVIEW
(standards.iteh.ai)

6.4.1 Commercial-quality electrolytic tin-coated sheet (quality 01) is intended for general fabricating purposes where sheet is used in the flat state, or for bending or moderate forming.

<https://standards.iteh.ai/catalog/standards/sist/cdf0b83d-2c63-49cf-bd03-f91406cc4ac/iso-5950-2012>

6.4.2 Drawing quality electrolytic tin-coated sheet (qualities 02, 03, 04) is intended for drawing or severe forming. It is furnished according to the requirements of this International Standard or, with agreement where ordered, to fabricate an identified part, in which case, the mechanical properties in Table 5 do not apply. Drawing qualities are identified as follows:

- 02 Drawing quality
- 03 Deep drawing quality
- 04 Deep drawing quality aluminium killed (non-ageing)

6.4.3 Interstitial free steel (IF Steel) can be applied in orders of 02, 03 and 04, provided that the customer is informed of the substitution and that related shipping documents reflect the actual material shipped.

6.5 Mill passivation

A passivating chemical or electrochemical treatment is applied to the surface of electrolytic tin-coated sheet to stabilize the plate surface characteristics compatible with a specific application.

6.6 Coating condition

The as-produced tin-coated sheet has a dull (matt) appearance (Clause 4 and 6.9). If it is heated to the melting point of tin, the tin reflows and has a bright (fused, melted) appearance. Some iron-tin alloy will also form at the steel surface interface during this heating process.

Normally “matt” finish sheet is produced from cold-reduced sheet having a “shot-blasted” surface, and “bright” finish sheet is produced from cold-reduced sheet having “ground” roll surfaces (6.9). All tinning lines have strip thickness limits on bright finish sheet because of melting limitations.

6.7 Application

Tin-coated steel shall be identified for fabrication by the name of the part or by the intended application. Steel sheet of drawing qualities (02, 03 and 04) may be produced to make an identified part, which shall be previously agreed between the manufacturer and purchaser. In this case, the part name, the details of fabrication and special requirements (freedom from stretcher strains or fluting, coating performance requirements) shall be specified and the mechanical properties of Table 5 do not apply.

6.8 Mechanical properties

Except when ordering an identified part, as explained in 6.7, at the time that the steel is made available for shipment, the mechanical properties shall be as stated in Table 5 when they are determined on test pieces obtained according to the requirements of 8.1 (mechanical tests). Prolonged storing of the sheet can cause changes in mechanical properties (increase in hardness and decrease in elongation), leading to a decrease in drawability. To minimize this effect, quality 04 should be specified.

Table 5 — Mechanical properties

Quality		R_m max. ^a	A min. ^b %	
Designation	Name	MPa	$L_0 = 50$ mm	$L_0 = 80$ mm
01	Commercial ^c			
02	Drawing	370	31	30
03	Deep drawing	350	35	34
04	Deep drawing aluminum killed (non-ageing)	340	37	36

R_m tensile strength
 A percentage elongation after fracture
 L_0 gauge length of original test piece
 1 MPa = 1 N/mm²

^a The minimum tensile strength for qualities 02, 03 and 04 would normally be expected to be 270 MPa. All tensile strength values are determined to the nearest 10 MPa.
^b For material up to and including 0,6 mm in thickness, the elongation values in this table shall be reduced by 1.
^c The hardness of quality 01 steel sheet is expected not to exceed the equivalent of Rockwell HRB65 at the time it is made available for shipment.

6.9 Surface finish

Normally two surface finishes are produced for electrolytic tin-coated sheet. These surfaces are obtained by skin passing the strip on either shot-blasted or ground rolls. Shot-blasted rolls impart a rough (SBF) finish produced for matt (dull, unmelted, not reflowed) finish tin-coated sheet, while ground rolls impart a smooth (BR) finish produced for bright (reflowed, melted, fused) electrolytic tin-coated sheet. The required finish shall be specified at the time of ordering.

6.10 Oiling

Electrolytic tin-coated sheet always has a lubricant film applied to both surfaces of the sheet as the last operation in the tinning line prior to shearing or coiling, to minimize abrasion. The oil is not intended as a drawing or forming lubricant and shall be easily removable with degreasing chemicals.

7 Dimensional tolerances

Dimensional and shape tolerances applicable to cold-reduced steel sheet shall be as given in ISO 16162.