



# SLOVENSKI STANDARD

## SIST EN 12697-18:2017

01-september-2017

Nadomešča:

SIST EN 12697-18:2005

---

**Bitumenske zmesi - Preskusne metode - 18. del: Odtekanje veziva**

Bituminous mixtures - Test methods - Part 18: Binder drainage

Asphalt - Prüfverfahren - Teil 18: Bestimmung des Ablaufens

Mélanges bitumineux - Méthodes d'essai - Partie 18: Egouttage du liant  
**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

**Ta slovenski standard je istoveten z: EN 12697-18:2017**

<https://standards.iteh.ai/catalog/standards/sist/0daa05b6-2557-4137-999a-33de1e8b0c68/sist-en-12697-18-2017>

---

**ICS:**

91.100.50	Veziva. Tesnilni materiali	Binders. Sealing materials
93.080.20	Materiali za gradnjo cest	Road construction materials

**SIST EN 12697-18:2017**

**en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 12697-18:2017](#)

<https://standards.iteh.ai/catalog/standards/sist/0daa05b6-2557-4137-999a-33de1c8b0c68/sist-en-12697-18-2017>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 12697-18**

June 2017

ICS 93.080.20

Supersedes EN 12697-18:2004

English Version

## Bituminous mixtures - Test methods - Part 18: Binder drainage

Mélanges bitumineux - Méthodes d'essai - Partie 18:  
Egouttage du liant

Asphalt - Prüfverfahren - Teil 18: Bestimmung des  
Ablaufens

This European Standard was approved by CEN on 24 April 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/0daa05b6-2557-4137-999a-33de1c8b0c68/sist-en-12697-18-2017>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

<b>Contents</b>	<b>Page</b>
European foreword.....	3
<b>1 Scope</b> .....	<b>7</b>
<b>2 Normative references</b> .....	<b>7</b>
<b>3 Terms and definitions</b> .....	<b>7</b>
<b>4 Basket method</b> .....	<b>7</b>
<b>4.1 Principle</b> .....	<b>7</b>
<b>4.2 Materials</b> .....	<b>8</b>
<b>4.3 Apparatus</b> .....	<b>8</b>
<b>4.4 Procedure</b> .....	<b>9</b>
<b>4.5 Calculation and expression of results</b> .....	<b>9</b>
<b>4.5.1 For each mixture, calculate the drained material <i>BD</i> from</b> .....	<b>9</b>
<b>4.6 Test report</b> .....	<b>10</b>
<b>4.7 Precision</b> .....	<b>10</b>
<b>5 Beaker method</b> .....	<b>11</b>
<b>5.1 Principle</b> .....	<b>11</b>
<b>5.2 Materials</b> .....	<b>11</b>
<b>5.3 Apparatus</b> .....	<b>11</b>
<b>5.4 Procedure</b> .....	<b>11</b>
<b>5.5 Calculation and expression of results</b> .....	<b>12</b>
<b>5.6 Test report</b> .....	<b>13</b>
<b>5.7 Precision</b> .....	<b>13</b>

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[SIST EN 12697-18:2017](https://standards.iteh.ai/catalog/standards/sist/0daa05b6-2557-4137-999a-33de1c8b0c68/sist-en-12697-18-2017)

<https://standards.iteh.ai/catalog/standards/sist/0daa05b6-2557-4137-999a-33de1c8b0c68/sist-en-12697-18-2017>

## European foreword

This document (EN 12697-18:2017) has been prepared by Technical Committee CEN/TC 227 “Road materials”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2017, and conflicting national standards shall be withdrawn at the latest by December 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12697-18:2004.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

Compared with EN 12697-18:2004, the following changes have been made:

- a) the standard title no longer makes the method exclusively for hot mix asphalt;
- b) the Schellenberg method renamed to the beaker method
- c) in the basket method number of trays reduced to two;
- d) in the basket test allowance for fibres made in the calculation;
- e) reference to EN 12697-35 in 4.4.1 and 5.4.1 addressed as “reference compaction temperature” as given in new edition of EN 12697-35;
- f) symbols has been amended in accordance with CEN-Regulations;
- g) [4.5.1] the symbol for drained material has been changed from *D* to *BD* in order to be consistent with latest versions of EN 13108-5:2016 and EN 13108-7:2016. NOTE 2 added for explanation;
- h) [5.5.1] the symbol for drained material has been changed from *D* to *BD* in order to be consistent with latest versions of EN 13108-5:2016 and EN 13108-7:2016.

This European standard is one of a series of standards as listed below:

- EN 12697-1, *Bituminous mixtures — Test methods for hot mix asphalt — Part 1: Soluble binder content*
- EN 12697-2, *Bituminous mixtures — Test methods — Part 2: Determination of particle size distribution*
- EN 12697-3, *Bituminous mixtures — Test methods for hot mix asphalt — Part 3: Bitumen recovery: Rotary evaporator*
- EN 12697-4, *Bituminous mixtures — Test methods — Part 4: Bitumen recovery: Fractionating column*

**EN 12697-18:2017 (E)**

- EN 12697-5, *Bituminous mixtures — Test methods for hot mix asphalt — Part 5: Determination of the maximum density*
- EN 12697-6, *Bituminous mixtures — Test methods for hot mix asphalt — Part 6: Determination of bulk density of bituminous specimens*
- EN 12697-7, *Bituminous mixtures — Test methods for hot mix asphalt — Part 7: Determination of bulk density of bituminous specimens by gamma rays*
- EN 12697-8, *Bituminous mixtures — Test methods for hot mix asphalt — Part 8: Determination of void characteristics of bituminous specimens*
- EN 12697-10, *Bituminous mixtures — Test methods for hot mix asphalt — Part 10: Compactability*
- EN 12697-11, *Bituminous mixtures — Test methods for hot mix asphalt — Part 11: Determination of the affinity between aggregate and bitumen*
- EN 12697-12, *Bituminous mixtures — Test methods for hot mix asphalt — Part 12: Determination of the water sensitivity of bituminous specimens*
- EN 12697-13, *Bituminous mixtures — Test methods for hot mix asphalt — Part 13: Temperature measurement*
- EN 12697-14, *Bituminous mixtures — Test methods for hot mix asphalt — Part 14: Water content*
- EN 12697-15, *Bituminous mixtures — Test methods for hot mix asphalt — Part 15: Determination of the segregation sensitivity*
- EN 12697-16, *Bituminous mixtures — Test methods — Part 16: Abrasion by studded tyres*
- EN 12697-17, *Bituminous mixtures — Test methods — Part 17: Particle loss of porous asphalt specimen*
- EN 12697-18, *Bituminous mixtures — Test methods — Part 18: Binder drainage*
- EN 12697-19, *Bituminous mixtures — Test methods for hot mix asphalt — Part 19: Permeability of specimen*
- EN 12697-20, *Bituminous mixtures — Test methods for hot mix asphalt — Part 20: Indentation using cube or cylindrical specimens (CY)*
- EN 12697-21, *Bituminous mixtures — Test methods for hot mix asphalt — Part 21: Indentation using plate specimens*
- EN 12697-22, *Bituminous mixtures — Test methods for hot mix asphalt — Part 22: Wheel tracking*
- EN 12697-23, *Bituminous mixtures — Test methods for hot mix asphalt — Part 23: Determination of the indirect tensile strength of bituminous specimens*
- EN 12697-24, *Bituminous mixtures — Test methods for hot mix asphalt — Part 24: Resistance to fatigue*
- EN 12697-25, *Bituminous mixtures — Test methods — Part 25: Cyclic compression test*

- EN 12697-26, *Bituminous mixtures — Test methods for hot mix asphalt — Part 26: Stiffness*
- EN 12697-27, *Bituminous mixtures — Test methods — Part 27: Sampling*
- EN 12697-28, *Bituminous mixtures — Test methods for hot mix asphalt — Part 28: Preparation of samples for determining binder content, water content and grading*
- EN 12697-29, *Bituminous mixtures — Test method for hot mix asphalt — Part 29: Determination of the dimensions of a bituminous specimen*
- EN 12697-30, *Bituminous mixtures — Test methods for hot mix asphalt — Part 30: Specimen preparation by impact compactor*
- EN 12697-31, *Bituminous mixtures — Test methods for hot mix asphalt — Part 31: Specimen preparation by gyratory compactor*
- EN 12697-32, *Bituminous mixtures — Test methods for hot mix asphalt — Part 32: Laboratory compaction of bituminous mixtures by vibratory compactor*
- EN 12697-33, *Bituminous mixtures — Test methods for hot mix asphalt — Part 33: Specimen prepared by roller compactor*
- EN 12697-34, *Bituminous mixtures — Test methods for hot mix asphalt — Part 34: Marshall test*
- EN 12697-35, *Bituminous mixtures — Test methods — Part 35: Laboratory mixing*
- EN 12697-36, *Bituminous mixtures — Test methods for hot mix asphalt — Part 36: Determination of the thickness of a bituminous pavement*
- EN 12697-37, *Bituminous mixtures — Test methods for hot mix asphalt — Part 37: Hot sand test for the adhesivity of binder on precoated chippings for HRA*
- EN 12697-38, *Bituminous mixtures — Test methods for hot mix asphalt — Part 38: Common equipment and calibration*
- EN 12697-39, *Bituminous mixtures — Test methods for hot mix asphalt — Part 39: Binder content by ignition*
- EN 12697-40, *Bituminous mixtures — Test methods for hot mix asphalt — Part 40: In situ drainability*
- EN 12697-41, *Bituminous mixtures — Test methods for hot mix asphalt — Part 41: Resistance to de-icing fluids*
- EN 12697-42, *Bituminous mixtures — Test methods for hot mix asphalt — Part 42: Amount of foreign matter in reclaimed asphalt*
- EN 12697-43, *Bituminous mixtures — Test methods for hot mix asphalt — Part 43: Resistance to fuel*
- EN 12697-44, *Bituminous mixtures — Test methods for hot mix asphalt — Part 44: Crack propagation by semi-circular bending test*
- EN 12697-45, *Bituminous mixtures — Test methods for hot mix asphalt — Part 45: Saturation Ageing Tensile Stiffness (SATS) conditioning test*

**EN 12697-18:2017 (E)**

- EN 12697-46, *Bituminous mixtures — Test methods for hot mix asphalt — Part 46: Low temperature cracking and properties by uniaxial tension tests*
- EN 12697-47, *Bituminous mixtures — Test methods for hot mix asphalt — Part 47: Determination of the ash content of natural asphalts*
- prEN 12697-48, *Bituminous mixtures — Test methods for hot mix asphalt — Part 48: Interlayer Bonding*
- EN 12697-49, *Bituminous mixtures — Test methods for hot mix asphalt — Part 49: Determination of friction after polishing*
- CEN/TS 12697-50, *Bituminous mixtures — Test methods — Part 50: Resistance to scuffing*
- prCEN/TS 12697-51, *Bituminous mixtures — Test methods — Part 51: Surface shear strength test*
- prCEN/TS 12697-52, *Bituminous mixtures — Test methods — Part 52: Conditioning to address oxidative ageing*
- prEN 12697-53, *Bituminous mixtures — Test methods — Part 53: Cohesion increase by spreadability-meter method*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

[SIST EN 12697-18:2017](https://standards.iteh.ai/catalog/standards/sist/0daa05b6-2557-4137-999a-33de1c8b0c68/sist-en-12697-18-2017)

<https://standards.iteh.ai/catalog/standards/sist/0daa05b6-2557-4137-999a-33de1c8b0c68/sist-en-12697-18-2017>



## 1 Scope

This European Standard describes two test methods:

- **basket method** (see Clause 4);
- **beaker method** (see Clause 5).

The basket method describes a method for determining binder drainage of bituminous mixtures. This method directly measures binder drainage, but when carried out on bituminous mixtures with fibres or mixtures whose mortar content is higher than in porous asphalt some clogging of the holes in the drainage baskets can occur, limiting the drainage of the binder. The basket method can be used either for determining the binder drainage for different binder content, or with a single binder content, eliminating the successive repetitions. It also enables the effects of varying fine aggregate types or including any anti-draining additive to be quantified.

The beaker method describes a method for determining binder drainage of bituminous mixtures. It is applicable to asphalt materials that are not porous asphalt or for porous asphalt incorporating fibres. It can be used either for determining the binder drainage for different binder content, or with a single binder content, eliminating the successive repetitions. It also enables the effects of varying fine aggregate types or including any anti-draining additive to be quantified.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12697-27, *Bituminous mixtures - Test methods* — Part 27: Sampling

<https://standards.iteh.ai/catalog/standards/sist/0daa05b6-2557-4137-999a->

EN 12697-35, *Bituminous mixtures - Test methods* — Part 35: Laboratory mixing

EN 14023, *Bitumen and bituminous binders* — Specification framework for polymer modified bitumens

ISO 3310-1, *Test sieves* — Technical requirements and testing — Part 1: Test sieves of metal wire cloth

ISO 3310-2, *Test sieves* — Technical requirements and testing — Part 2: Test sieves of perforated metal plate

## 3 Terms and definitions

For the purposes of this document, the following term and definition applies.

### 3.1

#### **binder drainage**

binder, fine particles and additives, if any, separated from the mixture after the mixing process or during transport of the mixture to the site

## 4 Basket method

### 4.1 Principle

The quantity of material lost by drainage, after 3 h at the test temperature (see 4.4.1) is measured in mixtures placed on baskets made out of perforated metal plates.