DRAFT INTERNATIONAL STANDARD ISO/DIS 17697



ISO/TC 216

Secretariat: **AENOR**

Voting begins on 2013-01-17

Voting terminates on 2013-06-17

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • MEXIZYHAPOQHAR OPFAHU3ALURI TIO CTAHDAPTU3ALURI • ORGANISATION INTERNATIONALE DE NORMALISATION

Footwear — Test methods for uppers, lining and insocks — Seam strength

Chaussures — Méthodes d'essai relatives aux tiges, doublures et premières de propreté — Résistance des piqûres

[Revision of first edition (ISO 17697:2003)]

ICS 61.060

ISO/CEN PARALLEL PROCESSING

EN PARA This draft has been developed within the European Committee for Standardization (CEN), and processed under the CEN-lead mode of collaboration as defined in the Vienna Agreement.

This draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel five-month enquiry.

Should this draft be accepted, a final draft, established on the basis of comments received, will be submitted to a parallel two-month approval vote in ISO and formal vote in CEN.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

Pour accélérer la distribution, le présent document est distribué tel qu'il est parvenu du secrétariat du comité. Le travail de rédaction et de composition de texte sera effectué au Secrétariat central de l'ISO au stade de publication.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.



Copyright notice

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.

Foreword



ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17697 was prepared by Technical Committee ISO/TC 216, *Footwear*, Subcommittee SC, and by Technical Committee CEN/TC 309, *Footwear* in collaboration.

20

Logistandarus

FLOR STANDARD FREENAND STANDARD STANDAR \bigcirc

Footwear — Test methods for uppers, lining and insocks — Seam strength

1 Scope

This document specifies two test methods for determining the seam strength of uppers, lining or insocks, irrespective of the material, in order to assess the suitability for the end use.

These methods are:

- Method A: Needle perforations. For determining the force required to pull a row of needles through an upper material, in a direction perpendicular to the row.
- Method B: Stitched seams. For determining the breaking strength of stitched seams in shoe upper and lining materials. This method is applicable to seams cut from shoes or made up to simulate footwear constructions.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ogistand?

ISO 18454, Footwear — Standard atmospheres for conditioning and testing of footwear and components for footwear

ISO 17709, Footwear — Sampling location, preparation and duration of conditioning of samples and test pieces

ISO 7500-1, Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system (ISO 7500-1:2004)

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

seam strength

breaking strength of a stitched seam as determined under specified conditions using a tensile testing machine

3.2

upper

materials forming the outer face of the footwear which is attached to the sole assembly and covers the upper dorsal surface of the foot. In the case of boots this also includes the outer face of the material covering the leg. Only the materials that are visible are included, no account should be made of underlying materials

3.3

complete upper assembly

finished upper, fully seamed, joined or laminated as appropriate, comprising the centre material and any lining(s) together with all components such as interlinings, adhesives, membranes, foams or reinforcements, but excluding toe puffs and stiffeners

NOTE The complete upper assembly can be flat, 2-dimensional or comprise lasted upper in the final footwear.

4 Apparatus and material

The following apparatus and material shall be used:

4.1 Method A

4.1.1 Tensile testing machine with a jaw separation rate of (100 ± 10) mm/min, a force range appropriate to the specimen under test (this will usually be less than 500 N for footwear upper materials), capable of measuring forces to an accuracy greater than 2 % as specified by Class 2 in ISO 7500-1.

4.1.2 Needle holding jig, see Figure 1, including the following:

4.1.2.1 Two rectangular rigid plates each of minimum width 30 mm and maximum thickness 6 mm. Each of the two plates is drilled with seventeen holes of diameter $(1,1 \pm 0,1)$ mm. The holes shall be in a straight line parallel to and approximately 5 mm from one end of the plate. The holes should be evenly spaced so that the centres of the two extreme holes are $(26,5 \pm 0,5)$ mm apart.

4.1.2.2 One spacing plate of width similar to the drilled plates and of thickness (3,5 ± 0,5) mm.

4.1.2.3 Means of securing the spacing plate to the surface of one of the drilled plates such that the distance between the end of the spacing plate and the centre line of the row of holes in the other plate can be adjusted and set at $(3,0 \pm 0,1)$ mm and $(6,0 \pm 0,2)$ mm. The combination will be referred to as the lower plate.

4.1.2.4 Means of securing the other drilled plate, which will be referred to as the upper plate, to the exposed surface of the spacing plate so that the holes in both of the drilled plates are aligned.

The end of one of the plates furthest from the row of holes should have means of attachment to one of the jaws of the tensile testing machine so that the rows of holes are perpendicular to the axis of the machine.



- 4 Spacing plate
- 5 Drilled plate
- 6 Distance (see 4.1.2.3)







4.1.3 Seventeen needles, normal round point (R), Metric size 90 (Singer size 14)

4.1.4 Press knife or other cutting device capable of cutting a T shaped test specimen of the dimensions shown in Figure 2.

4.2 Method B

4.2.1 Tensile testing machine with, a jaw separation rate of $(100 \pm 10 \text{ mm/min})$, a force range appropriate to the specimen under test (this will usually be up to 2 kN), capable of measuring forces to an accuracy greater than 2 % as specified by class 2 in ISO 7500-1.

4.2.2 Small sharp hand knife or scissors for cutting test specimens.

4.2.3 If made up seams are to be tested, **a press knife** capable of cutting test specimens, $(50 \pm 2) \text{ mm} \times (50 \pm 2) \text{ mm}$, is useful.

4.2.4 If made up seams are to be tested, a sewing machine and accessories.

5 Sampling and conditioning

5.1 Method A

5.1.1 Store the shoes or the uncut sheet material or uppers in a controlled standard atmosphere specified in ISO 18454 for a minimum of 24 h prior to testing and carry out the test in this atmosphere.

5.1.2 Cut six test specimens with the dimensions specified in Figure 2. Three shall be cut with the base edge of the T parallel to the along direction of the material [backbone direction for leather and selvage (warp) or machine direction for non-leather materials], and three shall be cut perpendicular to this.

Prepare test pieces from complete upper assemblies when the lining material is permanently attached to the upper material.

For materials cut test specimens from a range of positions across the full usable width and length of the sheet material. For a material with a woven structure this will ensure that no two test specimens contain the same warp or weft threads.

For test specimens cut from footwear uppers avoid any areas containing perforations, cut three test specimens with the base edge of the T parallel to the *X* axis of the upper as defined in ISO 17709 and three with the base edge perpendicular to the *X* axis.

It can be impossible to cut a test specimen of sufficient size from certain types of footwear especially children's and the test specimen size shall not be reduced. If it is not possible to cut the correct size test specimen from a shoe upper the materials themselves shall be tested.

5.1.3 Mark the along direction on each of the test specimens

5.2 Method B

5.2.1 Store the shoes or the uncut sheet material or uppers in a controlled standard atmosphere specified in ISO 18454 for a minimum of 48 h prior to testing and carry out the test in this atmosphere.

5.2.2 Test specimens cut from shoes or uppers?

5.2.2.1 Where possible use the knife (see 4.2.2) to cut two rectangular test specimens of dimensions $(90 \pm 10) \text{ mm} \times (50 \pm 2) \text{ mm}$ from the upper, including any lining materials, such that the seam is approximately mid-way between the two ends of the test specimen, see Figure 3.



If the shoe upper is too small to allow this, then the size of test specimen may be reduced but the 5.2.2.2 width of the central portion, see 5.2.2 3 and Figure 3, shall not be less than 10 mm.

Make cuts in each test specimen parallel to the longer edges from points 3 mm from the seam to 5.2.2.3 the edges of the material, to provide a test specimen having a central portion of width (25 ± 0.5) mm and two edge pieces of width $(12,5 \pm 0,5)$ mm, see Figure 3.

Test specimens prepared by making up seams: 5.2.3

Use either the hand knife or scissors (see 4.2.2) or press knife (see 4.2.3) to cut pieces, 5.2.3.1 (50 ± 2) mm × (50 ± 2) mm, of each material to be used in the construction. The number of pieces of material required will vary according to the construction of the seam. This may consist of two pieces of the same or different upper materials stitched together and may include one or more lining materials. Reinforcing tapes may also be included. Cut sufficient pieces to allow the preparation of three seamed test specimens for each direction of test. If required materials may be skived before seaming.

The test direction, along or across, is at 90° to the direction of the seam. The number of directions of test will vary according to the upper construction. Separate tests in the along and across directions can be sufficient but in some cases test specimens can need to be prepared with along and across directions combined or with material cut on the bias.

For non-leather materials cut test specimens from a range of positions across the full usable width and length of the sheet material. For a material with a woven structure this shall prevent any two test specimens containing the same warp or weft threads.

Key

a)

b)