DRAFT INTERNATIONAL STANDARD ISO/DIS 10751



ISO/TC 216

Secretariat: **AENOR**

Voting begins on 2013-01-17

Voting terminates on 2013-06-17

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • MEXIZYHAPOQHAR OPFAHU3ALURI TIO CTAHDAPTU3ALURI • ORGANISATION INTERNATIONALE DE NORMALISATION

Footwear — Test methods for slide fasteners — Resistance to repeated opening and closing

Chaussures — Méthodes d'essai pour les fermetures éclair — Résistance aux ouvertures et fermetures répétées

ICS 61.060

ISO/CEN PARALLEL PROCESSING

PEN PARA STANDARD PRETINITION CEN PARA Oped with ad mr This draft has been developed within the European Committee for Standardization (CEN), and processed under the CEN-lead mode of collaboration as defined in the Vienna Agreement.

This draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel five-month enquiry.

Should this draft be accepted, a final draft, established on the basis of comments received, will be submitted to a parallel two-month approval vote in ISO and formal vote in CEN.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

Pour accélérer la distribution, le présent document est distribué tel qu'il est parvenu du secrétariat du comité. Le travail de rédaction et de composition de texte sera effectué au Secrétariat central de l'ISO au stade de publication.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.



Copyright notice

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.

Foreword



ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards) Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10751 was prepared by Technical Committee ISO/TC 216, *Footwear*, Subcommittee SC, and by Technical Committee CEN/TC 309, *Footwear* in collaboration.

This second/third/... edition cancels and replaces the first/second/... edition (), [clause(s) / subclause(s) / table(s) / figure(s) / annex(es)] of which [has/ have] been technically revised.

14.97



Footwear — Test method for slide fasteners — Resistance to repeated opening and closing

1 Scope

This standard describes a method intended to determine the resistance of a slide fastener to repeated opening and closing. The method is applicable to all types of slide fastener with a teeth length greater than 80 mm.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 19952, Footwear — Vocabulary

ISO 18454, Footwear — Standard atmospheres for conditioning and testing of footwear and components of footwear

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 19952 and the following apply.

3.1

slide fastener

a means of securing two flexible materials consisting of interlockable teeth each attached to one of the opposing edges of two tapes and movable slider that spans the interlocking teeth which when moved in one direction causes the teeth of one tape to interlock with the teeth of the other tape; when the slider is moved in the opposite direction it causes the teeth to disengage (see Figure 1)

Key

- a) Top stop
- Slider C)
- Tape e)
- Bottom stop g)

b) Teeth Puller d)

С

h

f

f) Teeth

andard Figure 1 Slide Fastener

0

e

Sortor

3.2

Tape

fabric panels to support other teeth of the slide tasterier iten

3.3

slider means of drawing the two interlocking teeth together or apart as it traverses the length of the teeth

3.4

puller

piece of plastic or metal attached to the slider as a means of manual grip for the user to operate

3.5

teeth

individual component of the slide fastener which interlocks with an opposing element

3.6

end stop/top stop

terminal components of the teeths to prevent the slider from disengaging from the teeth and tape

3.7

stringer

Textile tape with an attached row of teeth designed to interact with a row of similarly attached to another tape.

4 Principle

The free tapes at the open end of a test fastener are clamped together so that they are parallel. The fastener is held under tension along its length and across its width while it is repeatedly opened and closed. The test is stopped when the fastener has either failed or been subjected to a set number of cycles.

5 Apparatus and materials

5.1 A test machine with one or more stations each having:

5.1.1 A fixed clamp capable of firmly holding the closed end of the test fastener without causing damage to the teeth or teeth.

5.1.2 A free clamp capable of holding the open end of the test fastener without causing damage to the teeth or teeth and with the two free tapes held so that they are together, see Figure 2

5.1.3 A clamping system capable of holding a (25 ± 2) mm length of both edges of the test fastener tapes so that:

5.1.3.1 The centre of the clamped length is a point $(82,5 \pm 2,0)$ mm from the free clamp (5.1.2).

5.1.3.2 The lateral movement of each clamp is restricted, by stops, to (6 ± 1) mm.

5.1.4 A means of applying a force F_1 as specified in Table 1 to the free clamp (5.1.2) in a direction at 90° to and away from the clamping edge of clamp (5.1.1), see Figure 2.

5.1.5 A means of applying a force F_2 as specified in Table 1 to each of the clamps (5.1.3) in direction parallel to the clamping edge of clamp (5.1.1).

5.1.6 A device for holding the slider of the test fastener

5.1.7 A method of applying a regular harmonic reciprocating motion to the device (5.1.6) with – Stroke: $(63,5 \pm 1,5)$ mm, speed: (60 ± 6) cycles per minute (cycle min):

5.1.8 A method of counting the number of cycles of the device (5.1.6) up to failure of the test specimen.

5.2 A device for measuring distances up to 300 mm to an accuracy of 1 mm. A steel rule is suitable.



c) Clamp (4.1.1)

Figure 2 — Clamping arrangement for test specimens



6 Preparation of test specimens

6.1 The test may be conducted with any number of test specimens, but a minimum of three is recommended. Condition the test specimens according to ISO 18454 for 24 h before testing and carry out the test in this environment.

6.2 If the test fastener is shorter than the minimum distance between the two clamps (5.1.1) and (5.1.2) then sew strips of either leather or fabric, minimum width 25 mm, to the closed ends of both tapes. The exact length of the strips will depend on the clamping system of the machine being used but they should enable the fastener to be clamped in a position such that its slider does not make contact with the end stops during the test.

6.3 Mark a line across the width of each tape of the test fastener which is (4 ± 2) mm on the outer side of the end stops at the open end.

6.4 Mark a second line across the width of each tape, or attached strip (5.2), which is $[D] \pm 1$ mm from, and parallel to the line (6.3). If this second line passes close to an end stop which is sufficiently thick to make clamping difficult, then move the line towards the centre of the fastener until it is over the teeth and clear of the end stop. Then move the line (6.3) until it is $[D] \pm 1$ mm from this second line.

6.5 For each test fastener make a mark on the edge of both tapes that is $(82,5 \pm 2,0)$ mm from the line (6.3).

6.6 If the test fastener is narrower than the minimum distance between the two clamps (5.1.3) then for each test fastener:

6.6.1 Cut two tabs of leather or fabric, minimum width 25 mm. The exact length of the strips will depend on the clamping system of the machine being used.

6.6.2 Sew a tab (6.6.1) to the reverse edge of each tape so that the longitudinal centre line of the tab is at 90° to the edge of the teeth and is coincident with the point made in clause 6.5. Use two rows of stitching which are parallel to the edge of the test fastener teeth with one row (7,0 ± 0,5) mm and the other (9,0 ± 0,5) mm from the teeth. Both rows of stitching should be continued for at least 25 mm beyond either end of the tab.

7 Procedure

7.1 Secure the closed end of a test fastener, or any attached strip (6.2), in the clamp (5.1.1) so that the line (6.4) is aligned with the edge of the clamp.

7.2 Grip the open end of the test fastener with the clamp (5.1.2) so that the line (6.3) is aligned with the edge of the clamp.

7.3 Apply the longitudinal force [F1] specified in Table 1 to the clamp (5.1.2) so that the fastener is held under tension along its length.

7.4 If a tab was attached to the edge of each tape in clause 6.6 then grip a tab with each clamp (5.1.3). Otherwise grip the edge of the tape in the clamp (5.1.3) ensuring that the point (6.5) is at the centre of the clamp, and the edge of the clamp is parallel to, and at least 5 mm from the edge of the teeth.

7.5 Tension the test fastener across its width by applying a force of F_2 , as specified in Table 2, to each of the two clamps (5.1.3) in a direction that is parallel to the clamping edge of clamp (5.1.1).

Ensure that the distance from the rear of each clamp (5.1.3) to the stop (5.1.3.2) with the test fastener closed is (6 ± 1) mm.

Table 1 — longitudinal and lateral forces applied to test fastener

F ₁ Longitudinal force (N)	F ₂ Lateral force (N)		
22	18	$\overline{\ }$	
Tolerance on all forces ± 1 N			

7.6 Clamp the test fastener slider in the device (5.1.6) and ensure that the stroke of the device is $(63,5 \pm 1,5)$ mm.

7.7 Repeat the procedure in clauses 7.1 to 7.6 for any remaining test fasteners up to the number of test stations.

7.8 Reset the counter (5.1.8) and run the test machine (5.1) at a speed of (60 \pm 6) cycles per minute (cycles/min).

7.9 When the test fastener(s) have either failed or been subjected to a specified number of cycles, remove them from the machine and record any damage such as:

- Detachment of slider from one track.
- Breakage of the puller.
- Jamming or wear of the teeth.
- Detachment or breakage of the teeth
- Stitch abrasion (sewn-on nylon teeth)
- Tearing of the tape.

Record the corresponding number(s) of cycles.

7.10 Repeat the procedure in clauses 7.1 to 7.9 for any remaining test fasteners.

8 Test report

The test report shall include the following information:

- 8.1 Reference to this standard.
- 8.2 Description of the fasteners tested.
- 8.3 Date of testing.
- **8.4** For each test slide fastener:
- a) the number of cycles as recorded in 7.9; and