



# SLOVENSKI STANDARD

## kSIST FprEN 13249:2016

01-februar-2016

---

**Geotekstilije in geotekstilijam sorodni izdelki - Značilnosti, ki se zahtevajo pri gradnji cest in drugih prometnih površin (železnice so izključene, asfaltne površine so vključene)**

Geotextiles and geotextile-related products - Characteristics required for use in the construction of roads and other trafficked areas (excluding railways and asphalt inclusion)

Geotextilien und geotextilverwandte Produkte - Geforderte Eigenschaften für die Anwendung beim Bau von Straßen und sonstigen Verkehrsflächen (mit Ausnahme von Eisenbahnbau und Asphaltoberbau)

**Ta slovenski standard je istoveten z: FprEN 13249**

---

**ICS:**

59.080.70	Geotekstilije	Geotextiles
93.080.20	Materiali za gradnjo cest	Road construction materials

**kSIST FprEN 13249:2016** en,fr,de



EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**FINAL DRAFT**  
**FprEN 13249**

December 2015

ICS 59.080.70

Will supersede EN 13249:2014+A1:2015

English Version

Geotextiles and geotextile-related products -  
Characteristics required for use in the construction of  
roads and other trafficked areas (excluding railways and  
asphalt inclusion)

Geotextilien und geotextilverwandte Produkte -  
Geforderte Eigenschaften für die Anwendung beim Bau  
von Straßen und sonstigen Verkehrsflächen (mit  
Ausnahme von Eisenbahnbau und Asphaltoberbau)

This draft European Standard is submitted to CEN members for unique acceptance procedure. It has been drawn up by the Technical Committee CEN/TC 189.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

**Warning** : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

<b>Contents</b>	<b>Page</b>
European foreword.....	4
Introduction .....	5
<b>1 Scope .....</b>	<b>6</b>
<b>2 Normative references.....</b>	<b>6</b>
<b>3 Terms, definitions and abbreviations .....</b>	<b>7</b>
<b>3.1 Terms and definitions .....</b>	<b>7</b>
<b>3.2 Abbreviations .....</b>	<b>8</b>
<b>4 Required characteristics and corresponding methods of test.....</b>	<b>8</b>
<b>4.1 General.....</b>	<b>8</b>
<b>4.2 Selection of the appropriate standard in a specific application .....</b>	<b>8</b>
<b>4.3 Characteristics relevant to specific conditions of use .....</b>	<b>11</b>
<b>4.3.1 Stiffness at 2 %, 5 % and 10 % .....</b>	<b>11</b>
<b>4.3.2 Tensile strength of seams and joints.....</b>	<b>11</b>
<b>4.3.3 Static puncture .....</b>	<b>11</b>
<b>4.3.4 Friction characteristics .....</b>	<b>11</b>
<b>4.3.5 Tensile creep.....</b>	<b>11</b>
<b>4.3.6 Resistance to damage during installation.....</b>	<b>11</b>
<b>4.3.7 Water permeability normal to the plane.....</b>	<b>11</b>
<b>4.4 Release of dangerous substances.....</b>	<b>11</b>
<b>5 Assessment and verification of constancy of performance (AVCP) .....</b>	<b>12</b>
<b>5.1 General.....</b>	<b>12</b>
<b>5.2 Presentation of characteristics .....</b>	<b>12</b>
<b>5.3 Product type determination (PTD).....</b>	<b>12</b>
<b>5.4 Factory production control (FPC) .....</b>	<b>13</b>
<b>5.5 Verification of values .....</b>	<b>13</b>
<b>5.6 Initial inspection of factory and of FPC .....</b>	<b>13</b>
<b>5.7 Continuous surveillance of FPC.....</b>	<b>14</b>
<b>6 Marking.....</b>	<b>14</b>
<b>Annex A (normative) Factory production control.....</b>	<b>15</b>
<b>A.1 Factory production control scheme .....</b>	<b>15</b>
<b>A.1.1 General.....</b>	<b>15</b>
<b>A.1.2 Product design .....</b>	<b>15</b>
<b>A.1.3 Production .....</b>	<b>15</b>
<b>A.1.4 Finished products .....</b>	<b>15</b>
<b>A.1.5 Provisions applicable to A.1.2, A.1.3 and A.1.4 (to be used where appropriate).....</b>	<b>16</b>
<b>A.2 Assessment of a factory production control (FPC) system.....</b>	<b>17</b>
<b>A.2.1 General.....</b>	<b>17</b>
<b>A.2.2 Checklist .....</b>	<b>17</b>

<b>A.2.3</b>	<b>Test frequency</b> .....	<b>20</b>
<b>Annex B</b>	<b>(normative) Durability aspects</b> .....	<b>22</b>
<b>B.1</b>	<b>General</b> .....	<b>22</b>
<b>B.1.1</b>	<b>Service life</b> .....	<b>22</b>
<b>B.1.2</b>	<b>Initial and repeat testing of durability</b> .....	<b>22</b>
<b>B.1.3</b>	<b>Use of rework material</b> .....	<b>23</b>
<b>B.2</b>	<b>Weathering (all products)</b> .....	<b>23</b>
<b>B.3</b>	<b>Products used in non-reinforcing applications and with service lives up to 5 years</b> .....	<b>23</b>
<b>B.4</b>	<b>Other applications and service lives up to 25 years, 50 years and 100 years</b> .....	<b>24</b>
<b>B.4.1</b>	<b>General</b> .....	<b>24</b>
<b>B.4.2</b>	<b>Tests for specific materials</b> .....	<b>24</b>
<b>Annex C</b>	<b>(informative) Guidelines for the selection of the appropriate standard in a specific application</b> .....	<b>28</b>
<b>Annex D</b>	<b>(informative) Significant technical changes to superseded versions of this standard</b> .....	<b>30</b>
<b>Annex ZA</b>	<b>(informative) Clauses of this European Standard addressing the provisions of the EU Construction Products Regulation</b> .....	<b>31</b>
<b>ZA.1</b>	<b>Scope and relevant characteristics</b> .....	<b>31</b>
<b>ZA.2</b>	<b>Procedure for AVCP of Geotextiles and geotextiles-related products for the use in the construction of roads and other trafficked areas</b> .....	<b>34</b>
<b>ZA.2.1</b>	<b>Systems of AVCP</b> .....	<b>34</b>
<b>ZA.2.2</b>	<b>Declaration of performance (DoP)</b> .....	<b>37</b>
<b>ZA.3</b>	<b>CE marking and labelling</b> .....	<b>41</b>
<b>Bibliography</b>	.....	<b>43</b>

**FprEN 13249:2015 (E)****European foreword**

This document (FprEN 13249:2015) has been prepared by Technical Committee CEN/TC 189 “Geosynthetics”, the secretariat of which is held by NBN.

This document is currently submitted to the Unique Acceptance Procedure.

This document will supersede EN 13249:2014+A1:2015.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Regulation No 305/2011.

For relationship with Regulation (EU) Nr. 305/2011, see informative Annex ZA, which is an integral part of this document.

Annex D provides details of significant technical changes between this European Standard and the previous edition.

## Introduction

This European Standard allows manufacturers to describe geotextiles and geotextile-related products on the basis of declared values for characteristics relevant to the intended use and if tested to the specified method. It also includes procedures for the assessment and verification of constancy of performance and factory production control.

This European Standard may also be used by designers, end-users and other interested parties to define which functions and conditions of use are relevant.

The term “product” used in this European Standard refers to a geotextile or geotextile-related product.

This European Standard is part of a series of standards, addressing the requirements for geotextiles and geotextile-related products when used in a specific application. Annex C provides guidance on how to select the appropriate standard.

## 1 Scope

This European Standard specifies the relevant characteristics of geotextiles and geotextile-related products used in the construction of roads and other trafficked areas (excluding railways and asphaltic inclusion), and the appropriate test methods to determine these characteristics.

The intended use of these geotextiles or geotextile-related products is to fulfil one or more of the following functions: filtration, separation, and reinforcement. The separation function will always occur in conjunction with filtration or reinforcement, and hence will not be specified alone.

This European Standard is not applicable to geosynthetic barriers, as defined in EN ISO 10318-1.

This European Standard provides for the assessment and verification of constancy of performance of the product to this European Standard and for factory production control procedures.

Particular application cases may contain requirements regarding additional properties and – preferably standardized – test methods, if they are technically relevant.

This European Standard may be used to derive design values by taking into account factors within the context of the definitions given in EN 1997-1 (Eurocode 7), e.g. factors of safety. The design life of the product should be determined, since its function may be temporary, as a construction expediency, or permanent, for the lifetime of the structure.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12224, *Geotextiles and geotextile-related products — Determination of the resistance to weathering*

EN 12226, *Geosynthetics — General tests for evaluation following durability testing*

EN 12447, *Geotextiles and geotextile-related products — Screening test method for determining the resistance to hydrolysis in water*

EN ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics (ISO 1043-1)*

EN ISO 3696, *Water for analytical laboratory use — Specification and test methods (ISO 3696)*

EN ISO 9862, *Geosynthetics — Sampling and preparation of test specimens (ISO 9862)*

EN ISO 10318-1, *Geosynthetics — Part 1: Terms and definitions (ISO 10318-1)*

EN ISO 10319, *Geosynthetics — Wide-width tensile test (ISO 10319)*

EN ISO 10320, *Geotextiles and geotextile-related products — Identification on site (ISO 10320)*

EN ISO 10321, *Geosynthetics — Tensile test for joints/seams by wide-width strip method (ISO 10321)*

EN ISO 10722, *Geosynthetics — Index test procedure for the evaluation of mechanical damage under repeated loading — Damage caused by granular material (ISO 10722)*

EN ISO 11058, *Geotextiles and geotextile-related products — Determination of water permeability characteristics normal to the plane, without load (ISO 11058)*