

# **SLOVENSKI STANDARD**

## **oSIST prEN ISO 22825:2016**

**01-november-2016**

---

### **Neporušitveno preskušanje zvarnih spojev - Ultrazvočno preskušanje - Preskušanje zvarnih spojev iz avstenitnih jekel in nikljevih zlitin (ISO/DIS 22825:2016)**

Non-destructive testing of welds - Ultrasonic testing - Testing of welds in austenitic steels and nickel-based alloys (ISO/DIS 22825:2016)

Zerstörungsfreie Prüfung von Schweißverbindungen - Ultraschallprüfung - Prüfung von Schweißverbindungen in austenitischen Stählen und Nickellegierungen (ISO/DIS 22825:2016)

*SIST EN ISO 22825:2018*

Contrôle non destructif des assemblages soudés - Contrôle par ultrasons - Contrôle des soudures en aciers austénitiques et en alliages à base nickel (ISO/DIS 22825:2016)

**Ta slovenski standard je istoveten z: prEN ISO 22825**

---

#### **ICS:**

25.160.40	Varjeni spoji in vari	Welded joints and welds
77.080.20	Jekla	Steels
77.120.40	Nikelj, krom in njune zlitine	Nickel, chromium and their alloys

**oSIST prEN ISO 22825:2016**

**en,fr,de**



# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 22825

ISO/TC 44/SC 5

Secretariat: **AFNOR**Voting begins on:  
**2016-09-13**Voting terminates on:  
**2016-12-05**

### Non-destructive testing of welds — Ultrasonic testing — Testing of welds in austenitic steels and nickel-based alloys

*Contrôle non destructif des assemblages soudés — Contrôle par ultrasons — Contrôle des soudures en aciers austénitiques et en alliages à base nickel*

ICS: 25.160.40

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 22825:2018

<https://standards.iteh.ai/catalog/standards/sist/2bde2647-cbd1-4fde-837c-29783b5cb0a5/sist-en-iso-22825-2018>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

### ISO/CEN PARALLEL PROCESSING



Reference number  
ISO/DIS 22825:2016(E)

© ISO 2016

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 22825:2018

<https://standards.iteh.ai/catalog/standards/sist/2bde2647-cbd1-4fde-837c-29783b5cb0a5/sist-en-iso-22825-2018>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
[copyright@iso.org](mailto:copyright@iso.org)  
[www.iso.org](http://www.iso.org)

# Contents

Page

<b>Foreword</b>	<b>iv</b>
<b>Introduction</b>	<b>v</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>2</b>
<b>4 Information required prior to testing</b>	<b>2</b>
4.1 Items to be defined by specification	2
4.2 Specific information required by the operator prior to testing	2
<b>5 Personnel</b>	<b>3</b>
<b>6 Test equipment</b>	<b>3</b>
<b>7 Range setting for compression waves</b>	<b>3</b>
<b>8 Sensitivity setting</b>	<b>4</b>
8.1 General	4
8.2 Use of side-drilled holes	5
8.3 Use of other reference reflectors	5
<b>9 Test procedure and ultrasonic techniques</b>	<b>5</b>
9.1 Development of the test procedure	5
9.2 Content of the procedure	5
9.3 Selection of ultrasonic technique(s)	7
9.4 Optimization of test technique and draft of test procedure	7
9.5 Practical implications of the use of refracted compression waves	7
<b>10 Classification and sizing of indications</b>	<b>8</b>
<b>11 Testing of welds</b>	<b>8</b>
11.1 General	8
11.2 Surface condition and couplant fluid	8
11.3 Parent metal testing	8
11.4 Scanning	9
11.5 Evaluation of indications	9
<b>12 Test report</b>	<b>9</b>
12.1 General data	9
12.2 Information related to the test equipment	10
12.3 Information related to the testing technique	10
12.4 Results of testing	10
<b>Annex A (informative) Compression wave angle-beam techniques</b>	<b>11</b>
<b>Annex B (informative) Stainless steel calibration blocks for range setting</b>	<b>17</b>
<b>Annex C (informative) Reference blocks for sensitivity setting</b>	<b>19</b>
<b>Bibliography</b>	<b>22</b>

## ISO/DIS 22825:2016(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

The committee responsible for this document is ISO/TC 44/SC 5.

ISO 22825 was prepared by the European Committee for Standardization (CEN) Technical Committee TC 121, *Welding*, Sub-committee SC 5, *Testing of welds*, in collaboration with Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5, *Testing and inspection of welds*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 22825:2012), which has been technically revised.

The main changes are:

- correction of an incorrect equation;
- update of the references;
- compression wave angle-beam techniques,
- stainless steel calibration blocks for range setting;
- examples of reference blocks.

## Introduction

Welds in austenitic steel components and dissimilar metal welds are widely regarded as very difficult to test by ultrasound. The problems are mainly associated with unfavourable structure and grain size, as well as with different material properties which result in inhomogeneous and anisotropic mechanical and acoustic properties that contrast with the relatively homogeneous and isotropic behaviour in low-alloy steel welds.

Austenitic weld metal and other coarse-grained, anisotropic materials can significantly affect the propagation of ultrasound. In addition, beam distortion, unexpected reflections and wave mode conversions on the fusion line and/or columnar grains can occur. Therefore it can be difficult and sometimes impossible for ultrasonic waves to penetrate the weld metal.

Ultrasonic testing of these metals may require techniques that differ from conventional testing techniques. These special techniques often include the use of dual-element probes designed for refracted compression (longitudinal) waves or creeping waves rather than for conventional shear (transverse) waves.

In addition, it is necessary to produce representative reference blocks with welds in order to develop a testing procedure, set a preliminary sensitivity level, assess the procedure and demonstrate effectiveness before a definitive procedure is written. Material, weld preparation and welding procedure, as well as the geometry and surface condition of reference blocks are the same as for the component being tested.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 22825:2018

<https://standards.iteh.ai/catalog/standards/sist/2bde2647-cbd1-4fde-837c-29783b5cb0a5/sist-en-iso-22825-2018>





# Non-destructive testing of welds — Ultrasonic testing — Testing of welds in austenitic steels and nickel-based alloys

## 1 Scope

This International Standard specifies the approach to be followed when developing procedures for the ultrasonic testing of the following welds:

- welds in stainless steels;
- welds in nickel-based alloys;
- welds in duplex steels;
- dissimilar metal welds;
- austenitic welds.

The purposes of the testing can be very different, e.g.:

- for the assessment of quality level (manufacturing);
- for the detection of specific discontinuities indications induced in service.

Acceptance levels are not included in this International Standard, but can be applied in accordance with the scope of the testing (see [Clause 5](#)).

The requirements of this International Standard are applicable to both manual and mechanized testing.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5577, *Non-destructive testing — Ultrasonic inspection — Vocabulary*

ISO 7963, *Non-destructive testing — Ultrasonic testing --- Specification for calibration block No. 2*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

ISO 17635, *Non-destructive testing of welds — General rules for metallic materials*

ISO 17640, *Non-destructive testing of welds — Ultrasonic testing — Techniques, testing levels, and assessment*

EN 12668-1, *Non-destructive testing — Characterization and verification of ultrasonic examination equipment — Part 1: Instruments*

EN 12668-2, *Non-destructive testing — Characterization and verification of ultrasonic examination equipment — Part 2: Probes*

EN 12668-3, *Non-destructive testing — Characterization and verification of ultrasonic examination equipment — Part 3: Combined equipment*

## ISO/DIS 22825:2016(E)

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 5577, ISO 17635 and the following apply.

#### 3.1 dual-element probe

ultrasonic probe in which the transmit and receive transducers are separate and are electrically and acoustically isolated from each other

#### 3.2 focal distance

⟨dual element probes⟩ distance between probe and focal point on the acoustical axis where the acoustic pressure is at its maximum

#### 3.3 focal curve

⟨dual element probes⟩ curve, representing the relationship between sound path and sensitivity of a probe on a specified material containing specified reflectors

### 4 Information required prior to testing

#### 4.1 Items to be defined by specification

Information on the following items is required:

- a) material type and grade;
- b) purpose and extent of testing, including testing for transverse discontinuities, if required;
- c) testing levels (see [Clause 10](#));
- d) manufacturing or operation stage at which the testing shall be carried out;
- e) requirements for access, the surface condition (see [11.2](#)) and temperature;
- f) whether or not parent metal testing shall be carried out prior to and/or after welding (see [11.3](#));
- g) reference blocks (see [Clauses 6](#) and [7](#));
- h) personnel qualifications (see [Clause 5](#));
- i) reporting requirements (see [Clause 12](#));
- j) acceptance criteria and/or recording level.

#### 4.2 Specific information required by the operator prior to testing

Before any testing of a welded joint, the operator shall have access to all the information as specified in [4.1](#), together with the following additional information:

- a) the written testing procedure (see [Clause 9](#));
- b) type(s) of parent material and product form (i.e. cast, forged, rolled);
- c) the joint preparation and dimensions;
- d) the welding procedure or relevant information on the welding process;
- e) the time of the testing with regard to any post-weld heat treatment;

- f) the result of any parent metal testing carried out prior to and/or after welding;
- g) reference points and details of co-ordinate systems for the test object.

## 5 Personnel

Personnel performing testing in accordance with this International Standard shall be qualified to an appropriate level in accordance with ISO 9712 or equivalent in the relevant industrial sector.

In addition to a general knowledge of ultrasonic weld testing, the operators shall be familiar with and have practical experience in testing problems specifically associated with the type of materials and weld joints to be tested. Specific training and examination of personnel should be performed on representative pieces (duplex, austenitic, stainless steel) containing welds and using dual-element longitudinal wave probes. This training and the examination results should be documented.

If this is not the case, specific training and examination should be performed with the finalized ultrasonic testing procedures and selected ultrasonic testing equipment on representative samples containing natural or artificial reflectors similar to those expected. This training and the examination results should be documented.

## 6 Test equipment

The equipment used for testing shall fulfil the requirements of EN 12668-1 and EN 12668-2. The verification of the combined equipment shall be done in accordance with EN 12668-3, with the exception of dual-element compression wave angle-beam probes, which can be verified on appropriate reference blocks other than the blocks mentioned in EN 12668-3.

Focal curves shall be available for the dual-element probes to be used, determined on a material representative of the material to be tested.

## 7 Range setting for compression waves

Range setting shall be carried out on appropriate calibration blocks, e.g. on blocks which are designed to be similar to block No. 2 (see ISO 7963) as shown in [Annex B](#). The dimension of at least one of the radii of the block used shall be close to the focal distance of the probes.

The index point of each probe shall be marked on the probe's side, after having optimized the echo amplitude on the radius closest to its focal distance. Since echo optimization can be difficult for high-angle probes and creeping wave probes, the shear wave component may be used for optimization instead. In that case, the calibration methodology shall be included in the test procedure.

Optimization of the echoes shall be done on the two radii separately, and by iteration until the signals from the smaller and the larger radius are on their correct positions.

Alternatively, the time base may be set with the aid of a single-element straight-beam probe on the width of the calibration block, and subsequent zero point adjustment with the angle-beam probe placed on the calibration block, on the radius which is closest to the probe's focal distance.

Range setting shall be carried out prior to each testing. Checks to confirm these settings shall be performed at least every 4 h and on completion of testing.

Checks shall also be carried out whenever a system parameter is changed or whenever changes in the equivalent settings are suspected.

If deviations are found during these checks, corrective actions shall be carried out as specified in [Table 1](#).

**Table 1 — Range deviations**

1	Deviations $\leq 5$ % of the range	No correction is needed, test can be continued
2	Deviations $> 5$ % of the range	The setting shall be corrected and all tests carried out over the previous period shall be repeated

## 8 Sensitivity setting

### 8.1 General

Sensitivity setting shall be performed on a reference block with a weld. [Annex C](#) shows examples for reference blocks. The wall thickness of the reference block shall be similar to the wall thickness of the object to be tested within 10 % or 3 mm, whichever is the larger.

Reference reflectors may be side-drilled holes in the weld centre and/or on the fusion line. Alternatively, flat-bottomed holes on the fusion line may be used, having the flat bottom in the plane of the fusion line (weld bevel). Surface notches shall be used as references for near-surface defects. See [Figures C.1, C.2, and C.3](#).

Zone coverage related to wall thickness shall be established on the basis of the focal curves as shown in [A.6](#) when dual-element probes are used. Zone overlap shall be documented in the procedure.

Setting of sensitivity shall be carried out prior to each testing in accordance with this International Standard.

The gap,  $g$ , between test surface and bottom of the probe shoe shall not be greater than 0,5 mm.

For cylindrical or spherical surfaces, this requirement can be checked with [Equation \(1\)](#):

$$g = \frac{a^2}{4D} \quad (1)$$

SIST EN ISO 22825:2018  
<https://standards.iteh.ai/catalog/standards/sist/2bde2647-cbd1-4fde-837c-29783b5cb0a5/sist-en-iso-22825-2018>

where

$D$  is the diameter, in millimetres, of the test object;

$a$  is the dimension, in millimetres, of the probe shoe in the direction of testing.

If a value for  $g$  larger than 0,5 mm results from [Equation \(1\)](#), the probe shoe shall be adapted to the surface, and the sensitivity and range shall be set accordingly.

Checks to confirm these settings shall be performed at least every 4 h and on completion of testing. Checks shall also be carried out if a system parameter is changed or if changes in the equivalent settings are suspected.

If deviations are found during these checks, corrective actions shall be carried out as specified in [Table 2](#).

**Table 2 — Sensitivity deviations**

1	Deviations $\leq 2$ dB	No correction is needed, test can be continued
2	Deviations between 2 dB and 4 dB	The setting shall be corrected before testing is continued
3	Reduction in sensitivity $> 4$ dB	The setting shall be corrected and all tests carried out since the last valid test shall be repeated
4	Increase in sensitivity $> 4$ dB	The setting shall be corrected and all indications recorded since the last valid test shall be re-evaluated