



SLOVENSKI STANDARD SIST EN 50290-2-29:2016

01-november-2016

Nadomešča:

SIST EN 50290-2-29:2002

Komunikacijski kabli - 2-29. del: Skupna pravila za snovanje in konstruiranje - Zamrežene polietilenske izolacijske zmesi: kabli za instrumente, krmiljenje in zunanja vodila

Communication cables - Part 2-29: Common design rules and construction - Crosslinked polyethylene insulation compounds: instrumentation, control and field bus cables

iTeh STANDARD PREVIEW

Kommunikationskabel - Teil 2-29: Gemeinsame Regeln für Entwicklung und Konstruktion - Vernetzte PE-Isolier-Mischungen

[SIST EN 50290-2-29:2016](#)

Câbles de communication - Partie 2-29: Règles de conception communes et construction - PE réticulé pour enveloppes isolantes

Ta slovenski standard je istoveten z: EN 50290-2-29:2016

ICS:

29.035.20	Plastični in gumeni izolacijski materiali	Plastics and rubber insulating materials
33.120.10	Koaksialni kabli. Valovodi	Coaxial cables. Waveguides

SIST EN 50290-2-29:2016

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 50290-2-29:2016](https://standards.iteh.ai/catalog/standards/sist/0939e160-a3f2-443d-975a-f8aa8a498a37/sist-en-50290-2-29-2016)

<https://standards.iteh.ai/catalog/standards/sist/0939e160-a3f2-443d-975a-f8aa8a498a37/sist-en-50290-2-29-2016>

EUROPEAN STANDARD

EN 50290-2-29

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2016

ICS 29.035.20; 33.120.10

Supersedes EN 50290-2-29:2002

English Version

Communication cables - Part 2-29: Common design rules and construction - Crosslinked polyethylene insulation compounds: instrumentation, control and field bus cables

Câbles de communication - Partie 2-29: Règles de conception communes et construction - PE réticulé pour enveloppes isolantes

Kommunikationskabel - Teil 2-29: Gemeinsame Regeln für Entwicklung und Konstruktion - Vernetzte PE-Isoliermischungen

This European Standard was approved by CENELEC on 2016-07-22. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword	3
1 Scope	4
2 Normative references	4
3 Compound test requirements	5
4 Cable test requirements	5
5 Health, Safety and Environmental Regulations	5
Bibliography	9

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 50290-2-29:2016](https://standards.iteh.ai/catalog/standards/sist/0939e160-a3f2-443d-975a-f8aa8a498a37/sist-en-50290-2-29-2016)

<https://standards.iteh.ai/catalog/standards/sist/0939e160-a3f2-443d-975a-f8aa8a498a37/sist-en-50290-2-29-2016>

European foreword

This document (EN 50290-2-29:2016) has been prepared by a joint working group of the Technical Committees CENELEC TC 46X, "Communication cables", and CENELEC TC 86A, "Optical fibres and optical fibre cables".

The following dates are fixed:

- latest date by which this document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2017-07-22
- latest date by which the national standards conflicting with this document have to be withdrawn (dow) 2019-07-22

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 50290-2-29:2002.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 50290-2-29:2016](https://standards.iteh.ai/catalog/standards/sist/0939e160-a3f2-443d-975a-f8aa8a498a37/sist-en-50290-2-29-2016)

<https://standards.iteh.ai/catalog/standards/sist/0939e160-a3f2-443d-975a-f8aa8a498a37/sist-en-50290-2-29-2016>

EN 50290-2-29:2016 (E)

1 Scope

This Part 2-29 of EN 50290 gives specific requirements for Crosslinked Polyethylene (XLPE) compounds to be used for the insulation of instrumentation, control and field bus cables. There are several routes used for manufacture of XLPE insulated cables and as a consequence a number of different types of polyethylene compound may be specified. The compounds required for the different manufacturing processes are described (Table 1). The unstabilised materials require antioxidant to be added during the cable extrusion process.

Table 1 — XLPE Materials

Material	Stabilisation	Manufacturing process
PE	None	Base polymer for irradiation/one step silane
PE-S	Yes	Stabilised compound for irradiation/one step silane
SXPE	None	Silane grafted compound or copolymer for two step process
SXPE-S	Yes	Stabilised silane grafted compound or copolymer for two step process

It is essential to read this European Standard in conjunction with Part 2-20 of EN 50290, the product standards EN 50288-7 and EN 61158 and other applicable product standards.

Using raw material and type test data as outlined in this standard, the raw material supplier will have sufficient data to demonstrate compliance and warrant that the material is suitable for the specified application.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 50288-7, *Multi-element metallic cables used in analogue and digital communication and control — Part 7: Sectional specification for instrumentation and control cables*

EN 60216 (all parts), *Electrical insulating materials — Thermal endurance properties (IEC 60216)*

EN 60811-401, *Electric and optical fibre cables — Test methods for non-metallic materials — Part 401: Miscellaneous tests — Thermal ageing methods — Ageing in an air oven (IEC 60811-401)*

EN 60811-501, *Electric and optical fibre cables — Test methods for non-metallic materials — Part 501: Mechanical tests — Tests for determining the mechanical properties of insulating and sheathing compounds (IEC 60811-501)*

EN 60811-502, *Electric and optical fibre cables — Test methods for non-metallic materials — Part 502: Mechanical tests — Shrinkage test for insulations (IEC 60811-502)*

EN 60811-507, *Electric and optical fibre cables — Test methods for non-metallic materials — Part 507: Mechanical tests — Hot set test for cross-linked materials (IEC 60811-507)*

EN 60811-510, *Electric and optical fibre cables — Test methods for non-metallic materials — Part 510: Mechanical tests — Methods specific to polyethylene and polypropylene compounds — Wrapping test after thermal ageing in air (IEC 60811-510)*

EN 61158 (all parts), *Industrial communication networks — Fieldbus specifications (IEC 61158)*

EN ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness) (ISO 868)*

EN ISO 1133 (all parts), *Plastics — Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics (ISO 1133)*

EN ISO 1183 (all parts), *Plastics — Methods for determining the density of non-cellular plastics (ISO 1183)*

EN ISO 11357-6, *Plastics — Differential scanning calorimetry (DSC) — Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT) (ISO 11357-6)*

ISO 6502, *Rubber — Guide to the use of curemeters*

ISO 974, *Plastics — Determination of the brittleness temperature by impact*

3 Compound test requirements

The tests are to be carried out on granules or moulded plaques produced from granules of compound. This data shall be provided by the compound supplier. Relevant test methods, requirements and limits shall be included in any supply specification of the compound.

Specific requirements are shown in Table 2. In the case of special applications, additional requirements could be specified.

4 Cable test requirements

The anticipated performance assumes standard cable design and conventional process technology and is specified (Table 3). To achieve the indicated values, the addition of antioxidant and/or catalyst is necessary for materials PE, PES, SXPE & SXPES. Using type test data the compound supplier is expected to demonstrate compliance and warrant that the material is suitable for the specified application.

In the case of special applications, additional requirements could be specified.

5 Health, Safety and Environmental Regulations

The compounds are subject to Health, Safety and Environmental requirements as defined in EN 50290-2-20. Any deviations or compliance failures must be identified by the compound supplier.

EN 50290-2-29:2016 (E)

Table 2 — Insulation compounds - physical properties of granules

Characteristics ^a	Test method	Unit	Value	Applicability
1 Density ^b	EN ISO 1183	g/cm ³	≤ 0,950	All
2 Melt flow index ^c (190°C/2,16 kg)	EN ISO 1133	g/10 min	D	PE, PE-S, SXPE & SXPE-S
3 Storage stability Retention of melt flow index (190°C/2,16 kg) after storage 1 month at 20°C, RH 50%	EN ISO 1133	%	>TBD ^c	SXPE and SXPE-S
4 Elastograph	ISO 6502	N*m	>0,5 ^c	VXPE-S
5 Hardness Shore D (1s)	EN ISO 868	[-]	TBD ^d	All
6 Low temperature brittleness	ISO 974	°C	< -70	All
7 Oxidative Induction Time (200 °C)	EN ISO 11357-6 ^e	min	>TBD	PE-S, SXPE-S & VXPE-S

^a All values of Table 2 shall be provided by the compound supplier, see Clause 3.

^b Tolerance for the nominal value of a specific compound is +/- 0,003 g/cm³.

^c Tolerance for the nominal value of a specific compound is +/- 25%.

^d Tolerance for the nominal value of a specific compound is +/- 3.

^e Alternative methods which correlate with the antioxidant content are permitted.

SIST EN 50290-2-29:2016

<https://standards.iteh.ai/catalog/standards/sist/0939e160-a3f2-443d-975a-f8aa8a498a37/sist-en-50290-2-29-2016>

Table 3 — Wire insulation properties

Characteristics	Test method	Unit	Values	
1	Maximum rated temperature of cable for which the compound can be used	EN 60216 ^a	°C	90
2	Mechanical characteristics	EN 60811-501		
2.1	Before ageing			
2.1.1	Tensile strength- median,min.		MPa	12,5
2.1.2	Elongation at break- median,min		%	250
2.2	Mechanical characteristics after ageing	EN 60811-401 and -501		
2.2.1	Ageing conditions			
2.2.2	- Temperature		°C	135 ± 2
2.2.3	- Duration		h	10 x 24
	Tensile strength			
	- Median, minimum value		MPa	12,5
	Elongation at break			
	- Median, minimum value		%	200
	Retention of Mechanical properties after ageing ^b		%	>75
3	Wrapping after ageing ^c - temperature - duration Result to be obtained	EN 60811-510	°C h	150 ± 2 7 x 24 No crack
4	Ageing test on complete cable (compatibility test) ^d	EN 60811-501		
4.1	Before ageing			
4.1.1	Tensile strength- median,min.		MPa	12,5
4.1.2	Elongation at break- median,min.		%	250
4.2	Mechanical characteristics after ageing	EN 60811-401 and -501		
4.2.1	Ageing conditions			
4.2.2	- Temperature		°C	100 ± 2
4.2.3	- Duration		h	7 x 24
	Tensile strength - Median, minimum value		MPa	12,5
	Elongation at break - Median, minimum value		%	200
	Retention of Mechanical properties after ageing ^b		%	>75
5	Hot set Test conditions - Temperature - Time under load - Mechanical stress Results to be obtained	EN 60811-507	°C min N/mm ²	200 ± 2 15 0,2