

---

---

**Stainless steels — Chemical  
composition**

*Aciers inoxydables — Composition chimique*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 15510:2014](https://standards.iteh.ai/catalog/standards/sist/236d6cd2-1263-4121-88e3-b254ab743b87/iso-15510-2014)

[https://standards.iteh.ai/catalog/standards/sist/236d6cd2-1263-4121-88e3-  
b254ab743b87/iso-15510-2014](https://standards.iteh.ai/catalog/standards/sist/236d6cd2-1263-4121-88e3-b254ab743b87/iso-15510-2014)



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 15510:2014

<https://standards.iteh.ai/catalog/standards/sist/236d6cd2-1263-4121-88e3-b254ab743b87/iso-15510-2014>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword .....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Chemical composition</b> .....	<b>1</b>
<b>5 Designation of comparable steels</b> .....	<b>1</b>
<b>Annex A (informative) Designation of the steels given in Table 1 and of comparable grades covered in various designation systems</b> .....	<b>17</b>
<b>Annex B (informative) Designation of the steels given in Table 1 and of comparable grades covered in various International Standards</b> .....	<b>42</b>
<b>Annex C (informative) Classification of grades</b> .....	<b>52</b>
<b>Annex D (informative) Density values for stainless steels</b> .....	<b>55</b>
<b>Bibliography</b> .....	<b>61</b>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 15510:2014](https://standards.iteh.ai/catalog/standards/sist/236d6cd2-1263-4121-88e3-b254ab743b87/iso-15510-2014)

<https://standards.iteh.ai/catalog/standards/sist/236d6cd2-1263-4121-88e3-b254ab743b87/iso-15510-2014>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 17, *Steel*, Subcommittee SC 4, *Heat treatable and alloy steels*.

This second edition cancels and replaces the first edition (ISO 15510:2010), which has been technically revised.

# Stainless steels — Chemical composition

## 1 Scope

This International Standard lists the chemical compositions of stainless steels agreed by ISO/TC 17/SC 4, mainly on the basis of a composition of the specifications in existing ISO, ASTM, EN, JIS, and GB (Chinese) standards. They apply to all wrought product forms including ingots and semi-finished material.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/TS 4949, *Steel names based on letter symbols*

ISO 6929, *Steel products — Vocabulary*

## 3 Terms and definitions

For the purposes of this document, the terms and definition given in ISO 6929 and the following apply.

### 3.1

#### stainless steel

steel with at least 10,5 % (mass fraction) Cr and maximum 1,2 % (mass fraction) C

Note 1 to entry: For the classification of stainless steels according to their structure, composition and application, see [Annex C](#).

## 4 Chemical composition

The chemical composition of stainless steels approved by ISO/TC 17/SC 4 is given in Table 1.

**WARNING — Due to hazardous effects to health and environmental problems of lead (Pb), it is recommended to use steels with sulfur additions instead. These steels generally have comparable properties relating to machinability.**

NOTE If, in special cases, for example, an ISO committee charged with the establishment or revision of a standard for a specific product or application of stainless steels sees the necessity of deviating from the specifications in Table 1, it should inform ISO/TC 17/SC 4 (Secretariat's address: FES/DIN, Postfach 10 51 45, 40042 Dusseldorf, Germany) of the reasons for this and try, before such deviations are considered, to achieve consensus for a corresponding modification to Table 1.

## 5 Designation of comparable steels

For the steel grades covered by this International Standard, the steel names as given in the tables are allocated in accordance with ISO/TS 4949.

For the steel grades covered by this International Standard, the steel numbers as given in the tables are based on a 10-digit code presented in 4 subgroups of digits: 4 digits-3 digits-2 digits-1 digit.

XXXX-YYY-ZZ-A

The steel number of each grade is based on a decision of the ISO/TC 17/SC 4 group, taking into account several commonly used existing standards and designations.

In particular, the principles below have been used for the steel numbers.

- The first subgroup contains four digits and is comparable to the European designation (EN numbers): keeping the number on the right side and dropping the “1”.
- The second subgroup contains three digits and refers, in most cases, to the three middle digits of the UNS number used by ASTM. In the case of the ISO designation, contrary to the UNS system, no letter (an S or an N in the case of stainless steels) is used as a start. This 3-digit subgroup allows reference to the obsolete AISI numbers or to the numerical part of the standard designations used in other countries, such as Japan (JIS) and China (GB).
- The third subgroup contains two digits. In most cases, similar principles to those used in the UNS have been adopted. Care should be taken because some differences can exist among UNS, Chinese, and ISO designations (see Table 2). The principles stated in Table 2 apply within each YYY series.
- The last digit is a single letter that allows the reader to identify, in a simple way, if the grade composition corresponds exactly to that included in one or more of the four existing standard practices from Europe, the USA, Japan, or China. If the composition is a compromise between several standards, it is then a new and genuine ISO composition. The last digit of the ISO designation is then I (see Table 3).

Table 4 gives complementary explanations for the use of the ISO numbering system through examples.

Tables A.1, A.2, and A.3 in [Annex A](#) give the designations of stainless steels which are listed in other designation systems and are identical or comparable to the grades in Table 1. In Table A.1, the sequence of steels is the same as in Table 1. In Table A.2, the sequence is given in the order of the three middle digits defined by the first three UNS numbers. In Table A.3, the sequence is given in the order of the European system.

<https://standards.iteh.ai/catalog/standards/sist/236d6cd2-1263-4121-88e3->

Table B.1 in [Annex B](#) gives a list where the steel grades of Table 1 are to be found in other International Standards.

Table D.1 in [Annex D](#) comprises density values for the steels given in Table 1.

NOTE 1 To compare similar grades, it is necessary to check each element before making a substitution.

NOTE 2 Steels in this International Standard and in ISO 16143-1 to ISO 16143-3 are listed according to a line number (see Table A.1) with the following rules. The primary rule is ordering by austenitic steels (without Mo), austenitic steels with Mo, austenitic steels with Ni/Co as the main alloying elements, austenitic-ferritic (duplex) steels first without Mo then with Mo, ferritic steels first without Mo then with Mo, martensitic steels first without Mo then with Mo and precipitation-hardening steels without and with Mo. The secondary rule is ordering by the line numbers as given in Table A.1. The line number consists of two letters, two digits, and a last letter. For the first letter ‘a’ means for austenitic steels, ‘d’ for duplex steels, ‘f’ for ferritic steels, ‘m’ for martensitic steels and ‘p’ for precipitation-hardening steels. The second letter means ‘P’ for pure without Mo, ‘M’ for molybdenum and ‘N’ for Ni/Co as the main alloying element. The next two digits are the sum of the main alloying elements of Cr, Mo and Ni/Mn/Co (for the ferritic and martensitic steels it is only the sum of Cr and Mo). The last digit stands for the relative C-content (‘A’ means low carbon and ‘Z’ means high carbon). Although, for example, for the first some 25 austenitic steels are strictly ordered by this criteria it is not consequently applied when grouping of steel grades with the same characteristics seems to be beneficial, like austenitic-manganese-alloyed steels or steels of the AISI 316 series. The line number is by no means a steel designation and it is not for commercial purposes.

Table 1 — International agreed specifications for the composition of stainless steels (applicable for cast analysis)

Steel designation		% (mass fraction) <sup>a</sup>										
ISO name	ISO number	Line number	C	Si	Mn	P	S	Cr	Mo	Ni	N	Others
a) Austenitic steels												
X5CrNi17-7	4319-301-00-1	AP24H	0,07	1,00	2,00	0,045	0,030 <sup>b</sup>	16,0 to 18,0	—	6,0 to 8,0	0,10	—
X12CrNi17-7	4310-301-09-X	AP24N	0,15	1,00	2,00	0,045	0,030	16,0 to 18,0	—	6,0 to 8,0	—	—
X2CrNi18-7	4318-301-53-1	AP25A	0,030	1,00	2,00	0,045	0,015	16,0 to 18,5	—	6,0 to 8,0	0,10 to 0,20	—
X6CrNiCu17-8-2	4567-304-76-1	AP25J	0,08	1,70	3,00	0,045	0,030	15,0 to 18,0	—	6,0 to 9,0	—	Cu: 1,00 to 3,0
X10CrNi18-8	4310-301-00-1	AP26L	0,05 to 0,15	2,00	2,00	0,045	0,030 <sup>b</sup>	16,0 to 19,0	0,80	6,0 to 9,5	0,10	—
X2CrNi18-9	4307-304-03-1	AP27B	0,030	1,00	2,00	0,045	0,030 <sup>b</sup>	17,5 to 19,5	—	8,0 to 10,5 <sup>c</sup>	0,10	—
X7CrNi18-9	4948-304-09-1	AP27L	0,04 to 0,10	1,00	2,00	0,045	0,030 <sup>b</sup>	17,5 to 19,5	—	8,0 to 11,0	0,10	—
X9CrNi18-9	4325-302-00-E	AP27N	0,030 to 0,15	1,00	2,00	0,045	0,030	17,0 to 19,0	—	8,0 to 10,0	0,10	—
X10CrNiSi18-9	4305-303-00-1	AP27M	0,12	1,00	2,00	0,060	≥0,15	17,0 to 19,0	—	8,0 to 10,0	0,10	Cu: <sup>e</sup>
X12CrNiSe18-9	4625-303-23-X	AP27O	0,15	1,00	2,00	0,20	0,060	17,0 to 19,0	—	8,0 to 10,0	—	Se: ≥0,15
X12CrNiSi18-9-3	4326-302-15-1	AP27P	0,15	2,00 to 3,00	2,00	0,045	0,030	17,0 to 19,0	—	8,0 to 10,0	—	—
X2CrNi18-9	4311-304-53-1	AP27A	0,030	1,00	2,00	0,045	0,030 <sup>b</sup>	17,5 to 19,5	—	8,0 to 11,0	0,12 to 0,22	—
X6CrNiCu18-9-2	4567-304-98-X	AP27J	0,08	1,00	2,00	0,045	0,030	17,0 to 19,0	—	8,0 to 10,5	—	Cu: 1,00 to 3,0
X3CrNiCu18-9-4	4567-304-30-1	AP27F	0,04	1,00	2,00	0,045	0,030 <sup>b</sup>	17,0 to 19,0	—	8,0 to 10,5	0,10	Cu: 3,0 to 4,0
X6CrNiCuSi18-9-2	4570-303-31-1	AP27I	0,08	1,00	2,00	0,045	≥0,15	17,0 to 19,0	0,60	8,0 to 10,0	0,10	Cu: 1,40 to 1,80
X12CrNiCuSi18-9-3	4667-303-76-1	AP27Q	0,15	1,00	3,00	0,20	≥0,15	17,0 to 19,0	—	8,0 to 10,0	—	Cu: 1,50 to 3,5
X5CrNi19-9	4315-304-51-1	AP28F	0,08	1,00	2,50	0,045	0,030	18,0 to 20,0	—	7,0 to 10,5	0,10 to 0,30	— <sup>f</sup>
X3CrNiCu19-9-2	4560-304-75-E	AP28D	0,035	1,00	1,50 to 2,00	0,045	0,015	18,0 to 19,0	—	8,0 to 9,0	0,10	Cu: 1,50 to 2,00
X6CrNiCu19-9-1	4649-304-76-1	AP28I	0,08	1,00	2,00	0,045	0,030	18,0 to 20,0	—	8,0 to 10,5	—	Cu: 0,70 to 1,30
X5CrNiCu19-6-2	4640-304-76-E	AP28L	0,030 to 0,08	0,50	1,50 to 4,0	0,045	0,015	18,0 to 19,0	—	5,5 to 6,9	0,03 to 0,11	Cu: 1,30 to 2,00
X5CrNi18-10	4301-304-00-1	AP28E	0,07	1,00	2,00	0,045	0,030 <sup>b</sup>	17,5 to 19,5	—	8,0 to 10,5 <sup>c</sup>	0,10	—
X6CrNiTi18-10	4541-321-00-1	AP28G	0,08	1,00	2,00	0,045	0,030 <sup>b</sup>	17,0 to 19,0	—	9,0 to 12,0 <sup>c</sup>	—	Ti: 5 × C to 0,70
X7CrNiTi18-10	4940-321-09-1	AP28O	0,04 to 0,10	1,00	2,00	0,045	0,030 <sup>b</sup>	17,0 to 19,0	—	9,0 to 12,0 <sup>c</sup>	—	Ti: 5 × C to 0,80
X6CrNiTiB18-10	4941-321-09-1	AP28J	0,04 to 0,08	1,00	2,00	0,035	0,015	17,0 to 19,0	—	9,0 to 12,0	—	Ti: 5 × C to 0,70 B: 0,001 5 to 0,005 0

Table 1 (continued)

Steel designation			% (mass fraction) <sup>a</sup>										
ISO name	ISO number	Line number	C	Si	Mn	P	S	Cr	Mo	Ni	N	Others	
X6CrNiNb18-10	4550-347-00-I	AP28H	0,08	1,00	2,00	0,045	0,030 <sup>b</sup>	17,0 to 19,0	—	9,0 to 12,0 <sup>c</sup>	—	Nb: 10 × C to 1,00	
X7CrNiNb18-10	4912-347-09-I	AP28K	0,04 to 0,08	1,00	2,00	0,045	0,030 <sup>b</sup>	17,0 to 19,0	—	9,0 to 12,0 <sup>c</sup>	—	Nb: 10 × C to 1,00	
X2CrNiCu19-10	4650-304-75-E	AP29A	0,030	1,00	2,00	0,045	0,015	18,5 to 20,0	—	9,0 to 10,0	0,08	Cu: 1,00	
X2CrNi19-11	4306-304-03-I	AP30A	0,030	1,00	2,00	0,045	0,030 <sup>b</sup>	18,0 to 20,0	—	10,0 to 12,0 <sup>c</sup>	0,10	—	
X6CrNi18-12	4303-305-00-I	AP30I	0,08	1,00	2,00	0,045	0,030 <sup>b</sup>	17,0 to 19,0	—	10,5 to 13,0	0,10	—	
X8CrNiNb16-13	4961-347-77-E	AP29L	0,04 to 0,10	0,30 to 0,60	1,50	0,035	0,015	15,0 to 17,0	—	12,0 to 14,0	—	Nb: 10 × C to 1,20	
X6CrNiSiNINCe19-10	4818-304-15-E	AP29J	0,04 to 0,08	1,00 to 2,00	1,00	0,045	0,015 <sup>b</sup>	18,0 to 20,0	—	9,0 to 11,0	0,12 to 0,20	Ce: 0,03 to 0,08	
X40CrNiWSi15-14-3-2	4867-316-77-J	AP29P	0,35 to 0,45	1,50 to 2,50	0,60	0,040	0,030	14,0 to 16,0	—	13,0 to 15,0	—	W: 2,00 to 3,00	
X6CrNiSi18-13-4	4884-305-00-X	AP31H	0,08	3,0 to 5,0	2,00	0,045	0,030	15,0 to 20,0	—	11,5 to 15,0	—	—	
X7CrNiSiNINCe21-11	4835-308-15-U	AP32N	0,05 to 0,10	1,40 to 2,00	0,80	0,040	0,030	20,0 to 22,0	—	10,0 to 12,0	0,14 to 0,20	Ce: 0,03 to 0,08	
X15CrNiSi20-12	4828-305-09-I	AP32R	0,20	1,50 to 2,50	2,00	0,045	0,030	19,0 to 21,0	—	11,0 to 13,0	0,10	—	
X1CrNiSi18-15-4	4361-306-00-E	AP33A	0,015	3,7 to 4,5	2,00	0,025	0,010	16,5 to 18,5	0,20	14,0 to 16,0	0,10	—	
X8CrMnCuN17-8-3	4597-204-76-I	AP25L	0,10	2,00	6,5 to 9,0	0,040	0,030	15,0 to 18,0	1,00	3,00	0,10 to 0,30	Cu: 2,00 to 3,5	
X8CrMnNi19-6-3	4376-201-00-E	AP28P	0,10	1,00	5,0 to 8,0	0,045	0,015	17,0 to 20,5	—	2,00 to 4,5	0,30	—	
X3CrMnNiCu15-8-5-3 <sup>l</sup>	4615-201-75-E <sup>l</sup>	AP28C	0,030	1,00	7,0 to 9,0	0,040	0,010	14,0 to 16,0	0,80	4,5 to 6,0	0,02 to 0,06	Cu: 2,0 to 4,0	
X12CrMnNiN17-7-5	4372-201-00-I	AP29O	0,15 <sup>g</sup>	1,00	5,5 to 7,5	0,045	0,030 <sup>b</sup>	16,0 to 18,0	—	3,5 to 5,5	0,05 to 0,25	—	
X2CrMnNiN17-7-5	4371-201-53-I	AP29B	0,030	1,00	6,0 to 8,0	0,045	0,015	16,0 to 17,5	—	3,5 to 5,5	0,15 to 0,25	Cu: 1,00	
X6CrNiMnCu17-8-4-2	4617-201-76-J	AP29I	0,08	1,70	3,0 to 5,0	0,045	0,030	15,0 to 18,0	—	6,0 to 9,0	—	Cu: 1,00 to 3,0	
X9CrMnNiCu17-8-5-2	4618-201-76-E	AP30L	0,10	1,00	5,5 to 9,5	0,070	0,010	16,5 to 18,5	—	4,5 to 5,5	0,15	Cu: 1,00 to 2,50	
X12CrMnNiN18-9-5	4373-202-00-I	AP32O	0,15	1,00	7,5 to 10,0	0,060	0,030	17,0 to 19,0	—	4,0 to 6,0	0,15 to 0,30	—	
X11CrNiMnN19-8-6	4369-202-91-I	AP33L	0,07 to 0,15	0,50 to 1,00	5,0 to 7,5	0,030	0,015	17,5 to 19,5	—	6,5 to 8,5	0,20 to 0,30	—	
X13CrMnNiN18-13-2	4020-241-00-X	AP33M	0,15	1,00	11,0 to 14,0	0,045	0,030	16,5 to 19,0	—	0,5 to 2,5	0,20 to 0,45	—	
X6CrMnNiCuN18-12-4	4646-240-76-E	AP34H	0,02 to 0,10	1,00	10,5 to 12,5	0,050	0,015	17,0 to 19,0	0,50	3,5 to 4,5	0,20 to 0,30	Cu: 1,50 to 3,0	
X6CrMnNiN18-13-3	4378-240-00-X	AP34I	0,08	1,00	11,5 to 14,5	0,060	0,030	17,0 to 19,0	—	2,3 to 2,7	0,20 to 0,40	—	



Table 1 (continued)

Steel designation		% (mass fraction) <sup>a</sup>										
ISO name	ISO number	Line number	C	Si	Mn	P	S	Cr	Mo	Ni	N	Others
X53CrMnNiN21-9-4	4890-202-09-X	AP34V	0,48 to 0,58	0,35	8,0 to 10,0	0,040	0,030	20,0 to 22,0	—	3,25 to 4,5	0,35 to 0,50	—
X20CrNiN22-11	4824-308-09-I	AP33Q	0,15 to 0,25	1,00	1,00 to 1,60	0,040	0,030	20,5 to 22,5	—	10,0 to 12,0	0,15 to 0,30	—
X6CrNi23-13	4950-309-08-E	AP36J	0,04 to 0,08	0,70	2,00	0,035	0,015	22,0 to 24,0	—	12,0 to 15,0	0,10	—
X18CrNi23-13	4833-309-08-I	AP36R	0,20	1,00	2,00	0,045	0,030	22,0 to 24,0	—	12,0 to 15,0	0,10	—
X6CrNi25-20	4951-310-08-I	AP45L	0,04 to 0,10	0,70	2,00	0,035	0,015	24,0 to 26,0	—	19,0 to 22,0	0,10	—
X1CrNi25-21	4335-310-02-I	AP46A	0,020	0,25	2,00	0,025	0,010	24,0 to 26,0	0,20	20,0 to 22,0	0,10	—
X8CrNi25-21	4845-310-08-E	AP46L	0,10	1,50	2,00	0,045	0,030	24,0 to 26,0	—	19,0 to 22,0	0,10	—
X23CrNi25-21	4845-310-09-X	AP46O	0,25	1,50	2,00	0,040	0,030	24,0 to 26,0	—	19,0 to 22,0	—	—
X15CrNiSi25-21	4841-314-00-E	AP46R	0,20	1,50 to 2,50	2,00	0,045	0,015	24,0 to 26,0	—	19,0 to 22,0	0,10	—
<b>b) Austenitic steels with Mo</b>												
X10CrNiMoMnNbV15-10-1	4982-215-00-E	AM32P	0,06 to 0,15	0,20 to 1,00	5,50 to 7,00	0,035	0,015	14,0 to 16,0	0,80 to 1,20	9,0 to 11,0	0,10	V: 0,15 to 0,40 Nb: 0,75 to 1,25 B: 0,003 to 0,009
X6CrNiCuSiMo19-10-3-2	4660-315-77-I	AM30J	0,08	0,50 to 2,50	2,00	0,045	0,030	17,0 to 20,5	0,50 to 1,50	8,5 to 11,5	—	Cu: 1,50 to 3,5
X6CrNiSiCuMo19-13-3-3-1	4648-315-77-I	AM33I	0,08	2,50 to 4,0	2,00	0,045	0,030	17,0 to 20,5	0,50 to 1,50	11,0 to 14,0	—	Cu: 1,50 to 3,5
X2CrNiMoN17-11-2	4406-316-53-I	AM30B	0,030	1,00	2,00	0,045	0,030 <sup>b</sup>	16,5 to 18,5	2,00 to 3,00	10,0 to 12,5 <sup>c</sup>	0,12 to 0,22	—
X3CrNiCuMo17-11-3-2	4578-316-76-E	AM30F	0,04	1,00	2,00	0,045	0,015	16,5 to 17,5	2,00 to 2,50	10,0 to 11,0	0,10	Cu: 3,0 to 3,5
X2CrNiMo17-12-2	4404-316-03-I	AM31A	0,030	1,00	2,00	0,045	0,030 <sup>b</sup>	16,5 to 18,5	2,00 to 3,00	10,0 to 13,0 <sup>c</sup>	0,10	—
X5CrNiMo17-12-2	4401-316-00-I	AM31I	0,08	1,00	2,00	0,045	0,030 <sup>b</sup>	16,0 to 18,0	2,00 to 3,00	10,0 to 13,0 <sup>c</sup>	0,10	—
X6CrNiMoTi17-12-2	4571-316-35-I	AM31F	0,08	1,00	2,00	0,045	0,030 <sup>b</sup>	16,5 to 18,5	2,00 to 2,50	10,5 to 13,5 <sup>c</sup>	—	Ti: 5 × C to 0,70
X6CrNiMoNb17-12-2	4580-316-40-I	AM31G	0,08	1,00	2,00	0,045	0,030 <sup>b</sup>	16,5 to 18,5	2,00 to 2,50	10,5 to 13,5	—	Nb: 10 × C to 1,00
X6CrNiMoCu18-12-2-2	4665-316-76-I	AM32I	0,08	1,00	2,00	0,045	0,030	17,0 to 19,0	1,20 to 2,75	10,0 to 14,0	—	Cu: 1,00 to 2,50

Table 1 (continued)

Steel designation			% (mass fraction) <sup>a</sup>										
ISO name	ISO number	Line number	C	Si	Mn	P	S	Cr	Mo	Ni	N	Others	
X2CrNiMo17-12-3	4432-316-03-I	AM32A	0,030	1,00	2,00	0,045	0,030 <sup>b</sup>	16,5 to 18,5	2,50 to 3,00	10,5 to 13,0 <sup>c</sup>	0,10	—	
X3CrNiMo17-12-3	4436-316-00-I	AM32F	0,05	1,00	2,00	0,045	0,030 <sup>b</sup>	16,5 to 18,5	2,50 to 3,00	10,5 to 13,0 <sup>c</sup>	0,10	—	
X2CrNiMoN17-12-3	4429-316-53-I	AM32B	0,030	1,00	2,00	0,045	0,030 <sup>b</sup>	16,5 to 18,5	2,50 to 3,00	10,5 to 13,0 <sup>c</sup>	0,12 to 0,22	—	
X6CrNiMoN17-12-3	4495-316-51-I	AM32H	0,08	1,00	2,00	0,045	0,030	16,0 to 18,0	2,00 to 3,0	10,0 to 14,0	0,10 to 0,22	—	
X6CrNiMoS17-12-3	4494-316-74-I	AM32K	0,08	1,00	2,00	0,045	≥0,10	16,0 to 18,0	2,00 to 3,0	10,0 to 14,0	—	—	
X3CrNiMo18-12-3	4449-316-76-E	AM33F	0,035	1,00	2,00	0,045	0,015	17,0 to 18,2	2,25 to 2,75	11,5 to 12,5	0,08	Cu: 1,00	
X3CrNiMoBN17-13-3	4910-316-77-E	AM33G	0,04	0,75	2,00	0,035	0,015	16,0 to 18,0	2,00 to 3,0	12,0 to 14,0	0,10 to 0,18	B: 0,001 5 to 0,005 0	
X2CrNiMoCu18-14-2-2	4647-316-75-X	AM34A	0,030	1,00	2,00	0,045	0,030	17,0 to 19,0	1,20 to 2,75	12,0 to 16,0	—	Cu: 1,00 to 2,50	
X2CrNiMo17-14-3	4435-316-03-X	AM34C	0,030	1,00	2,00	0,045	0,030	16,0 to 18,0	2,0 to 3,0	12,0 to 15,0	—	—	
X2CrNiMo18-14-3	4435-316-91-I	AM35A	0,030	1,00	2,00	0,045	0,030	17,0 to 19,0	2,50 to 3,00	12,5 to 15,0	0,10	—	
X30CrCrNiMoPB20-11-2	4879-317-77-I	AM33R	0,25 to 0,35	1,00	1,20	0,18 to 0,25	0,030	19,0 to 21,0	1,8 to 2,50	10,0 to 12,0	—	B: 0,001 to 0,010	
X2CrNiMoN18-12-4	4434-317-53-I	AM34B	0,030	1,00	2,00	0,045	0,030 <sup>b</sup>	17,5 to 20,0	3,00 to 4,0	11,0 to 14,0 <sup>c</sup>	0,10 to 0,20	—	
X2CrNiMoN17-13-5	4439-317-26-E	AM35B	0,030	1,00	2,00	0,045	0,015	16,5 to 18,5	4,0 to 5,0	12,5 to 14,5	0,12 to 0,22	—	
X6CrNiMo19-13-4	4445-317-00-U	AM36I	0,08	1,00	2,00	0,045	0,030	18,0 to 20,0	3,0 to 4,0	11,0 to 15,0	0,10	—	
X2CrNiMo19-14-4	4438-317-03-I	AM37A	0,030	1,00	2,00	0,045	0,030 <sup>b</sup>	17,5 to 20,0	3,0 to 4,0	12,0 to 15,0	0,10	—	
X2CrNiMoN18-15-5	4483-317-26-I	AM38A	0,030	1,00	2,00	0,045	0,030	17,0 to 20,0	4,0 to 5,0	13,5 to 17,5	0,10 to 0,20	—	
X3CrNiMo18-16-5	4476-317-92-X	AM39F	0,04	1,00	2,50	0,045	0,030	16,0 to 19,0	4,0 to 6,0	15,0 to 17,0	—	—	
X4CrNiMoN25-14-1	4496-309-51-I	AM40F	0,06	1,50	2,00	0,045	0,030	23,0 to 26,0	0,50 to 1,20	12,0 to 16,0	0,25 to 0,40	—	
X1CrNiMoCuN20-18-7	4547-312-54-I	AM45A	0,020	0,70	1,00	0,035	0,015	19,5 to 20,5	6,0 to 7,0	17,5 to 18,5	0,18 to 0,25	Cu: 0,50 to 1,00	
X1CrNiMoN25-22-2	4466-310-50-E	AM49A	0,020	0,70	2,00	0,025	0,010	24,0 to 26,0	2,00 to 2,50	21,0 to 23,0	0,10 to 0,16	—	

Table 1 (continued)

Steel designation		% (mass fraction) <sup>a</sup>										
ISO name	ISO number	Line number	C	Si	Mn	P	S	Cr	Mo	Ni	N	Others
X1CrNiMoCuNW24-22-6	4659-312-66-I	AM52B	0,020	0,70	2,0 to 4,0	0,030	0,010	23,0 to 25,0	5,5 to 6,5	21,0 to 23,0	0,35 to 0,50	Cu: 1,00 to 2,00 W: 1,50 to 2,50
X1CrNiMoCuN24-22-8	4652-326-54-I	AM54A	0,020	0,50	2,0 to 4,0	0,030	0,005	23,0 to 25,0	7,0 to 8,0	21,0 to 23,0	0,45 to 0,55	Cu: 0,30 to 0,60
X2CrNiMnMoN25-18-6-5	4565-345-65-I	AM54B	0,030	1,00	5,0 to 7,0	0,030	0,015	24,0 to 26,0	4,0 to 5,0	16,0 to 19,0	0,30 to 0,60	Nb: 0,15
<b>c) Austenitic steels with Ni/Co as main alloying elements</b>												
X3NiCr18-16	4389-384-00-I	AN34F	0,04	1,00	2,00	0,045	0,030 <sup>b</sup>	15,0 to 17,0	—	17,0 to 19,0	0,10	—
X1NiCrMoCu22-20-5-2	4656-089-04-I	AN47A	0,020	1,00	2,00	0,040	0,030	19,0 to 21,0	4,0 to 5,0	21,0 to 23,0	0,10	Cu: 1,00 to 2,00
X1NiCrMoCu25-20-5	4539-089-04-I	AN50A	0,020	0,75	2,00	0,035	0,015	19,0 to 22,0	4,0 to 5,0	23,5 to 26,0	0,15	Cu: 1,00 to 2,00
X1NiCrMoCuN25-20-7	4529-089-26-I	AN52A	0,020	0,75	2,00	0,035	0,015	19,0 to 21,0	6,0 to 7,0	24,0 to 26,0	0,15 to 0,25	Cu: 0,50 to 1,50
X2NiCrMoN25-21-7	4478-083-67-U	AN53A	0,030	1,00	2,00	0,040	0,030	20,0 to 22,0	6,0 to 7,0	23,5 to 25,5	0,18 to 0,25	Cu: 0,75
X1CrNiMoCuN25-25-5	4537-310-92-E	AN55A	0,020	0,70	2,00	0,030	0,010	24,0 to 26,0	4,7 to 5,7	24,0 to 27,0	0,17 to 0,25	Cu: 1,00 to 2,00
X5NiCrAlTi31-20	4958-088-77-E	AN51J	0,03 to 0,08	0,70	1,50	0,015	0,010	19,0 to 22,0	—	30,0 to 32,5	0,030	Al: 0,20 to 0,50 Co: 0,50 Cu: 0,50 Nb: 0,10 Ti: 0,20 to 0,50 Al+Ti: 0,70 Ni+Co: 30,0 to 32,5
X2NiCrAlTi32-20	4558-088-90-E	AN52B	0,030	0,70	1,00	0,020	0,015	20,0 to 23,0	—	32,0 to 35,0	—	Al: 0,15 to 0,45 Ti: [8 × (C+N)] to 0,60
X8NiCrAlTi32-20	4959-088-77-E	AN52L	0,05 to 0,10	0,70	1,50	0,015	0,010	19,0 to 22,0	—	30,0 to 34,0	0,030	Al: 0,20 to 0,65 Co: 0,50 Cu: 0,50 Ti: 0,20 to 0,65 Ni+Co: 30,0 to 34,0
X8NiCrAlTi32-21	4876-088-00-I	AN53L	0,10	1,00	1,50	0,015	0,015	19,0 to 23,0	—	30,0 to 34,0	—	Al: 0,15 to 0,60 Ti: 0,15 to 0,60 Cu: 0,70
X7NiCrAlTi33-21	4959-088-10-U	AN54L	0,05 to 0,10	1,00	1,50	0,045	0,015	19,0 to 23,0	—	30,0 to 35,0	—	Cu: 0,75 Fe: ≥39,5 Ti: 0,15 to 0,60 Al: 0,15 to 0,60

Table 1 (continued)

Steel designation		% (mass fraction) <sup>a</sup>										
ISO name	ISO number	Line number	C	Si	Mn	P	S	Cr	Mo	Ni	N	Others
X8NiCrAlTi33-21	4959-088-11-U	AN54M	0,06 to 0,10	1,00	1,50	0,040	0,015	19,0 to 23,0	—	30,0 to 35,0	—	Cu: 0,75 Fe: ≥39,5 Ti: 0,15 to 0,60 Al: 0,15 to 0,60 Al+Ti: 0,85 to 1,2
X13NiCr35-16	4864-083-77-X	AN510	0,15	1,50	2,00	0,040	0,030	14,0 to 17,0	—	33,0 to 37,0	—	—
X4NiCrCuMo35-20-4-3	4657-080-20-U	AN58F	0,07	1,00	2,00	0,045	0,035	19,0 to 21,0	2,00 to 3,00	32,0 to 38,0	—	Cu: 3,0 to 4,0 Nb: (8 × C) to 1,00
X6NiCrSiNc35-25	4854-353-15-E	AN60J	0,04 to 0,08	1,20 to 2,00	2,00	0,040	0,015	24,0 to 26,0	—	34,0 to 36,0	0,12 to 0,20	Ce: 0,03 to 0,08
X1NiCrMoCu31-27-4	4563-080-28-I	AN62A	0,020	0,70	2,00	0,030	0,010	26,0 to 28,0	3,0 to 4,0	30,0 to 32,0	0,10	Cu: 0,70 to 1,50
X12CrNiCoMoWmNb21-20-3-3-2	4971-314-79-1	AN64R	0,08 to 0,16	1,00	1,00 to 2,00	0,035	0,015	20,0 to 22,5	2,50 to 3,5	19,0 to 21,0	0,10 to 0,20	Co:18,5 to 21,0 W: 2,00 to 3,0 Nb: 0,75 to 1,25
X1NiCrMoMn34-27-6-5 <sup>1</sup>	4479-089-36-U <sup>1</sup>	AN72A	0,020	0,50	4,0 to 6,0	0,025	0,010	26,0 to 28,0	5,0 to 6,0	33,0 to 35,0	0,30 to 0,50	Cu: 0,50
<b>d) Austenitic-ferritic (duplex) steels</b>												
X2CrNiN22-2 <sup>1</sup>	4062-322-02-U <sup>1</sup>	DP24A	0,030	1,00	2,00	0,040	0,010	21,5 to 24,0	0,45	1,00 to 2,90	0,16 to 0,28	—
X2CrCuNiN23-2-2 <sup>1</sup>	4669-322-76-E <sup>1</sup>	DP25A	0,045	1,00	1,00 to 3,00	0,040	0,030	21,5 to 24,0	0,50	1,00 to 3,00	0,12 to 0,20	Cu: 1,60 to 3,00
X2CrMnNiN21-5-1 <sup>1</sup>	4162-321-01-E <sup>1</sup>	DP27F	0,040	1,00	4,0 to 6,0	0,040	0,015	21,0 to 22,0	0,10 to 0,80	1,35 to 1,90	0,20 to 0,25	Cu: 0,10 to 0,80
X2CrNiN23-4	4362-323-04-I	DP27B	0,030	1,00	2,00	0,035	0,015	22,0 to 24,5	0,10 to 0,60	3,5 to 5,5	0,05 to 0,20	Cu: 0,10 to 0,60
<b>e) Austenitic-ferritic (duplex) steels with Mo</b>												
X2CrMnNiMoN21-5-3	4482-320-01-X	DM29A	0,030	1,00	4,0 to 6,0	0,035	0,030	19,5 to 21,5	0,10 to 0,60	1,50 to 3,50	0,05 to 0,20	Cu: 1,00
X2CrNiMoSiMnN19-5-3-2-2	4424-315-00-I	DM29B	0,030	1,40 to 2,00	1,20 to 2,00	0,035	0,030	18,0 to 19,0	2,50 to 3,0	4,3 to 5,2	0,05 to 0,10	—
X2CrNiMoN22-5-3 <sup>b</sup>	4462-318-03-I	DM30A	0,030	1,00	2,00	0,035	0,015	21,0 to 23,0	2,50 to 3,5	4,5 to 6,5	0,10 to 0,22	—
X6CrNiMo26-4-2	4480-329-00-U	DM32F	0,08	0,75	1,00	0,040	0,030	23,0 to 28,0	1,00 to 2,00	2,5 to 5,0	—	—
X2CrNiMnMoCuN24-4-3-2 <sup>1</sup>	4662-824-41-X <sup>1</sup>	DM33A	0,030	0,70	2,50 to 4,0	0,035	0,005	23,0 to 25,0	1,00 to 2,00	3,0 to 4,5	0,20 to 0,30	Cu: 0,10 to 0,80

Table 1 (continued)

Steel designation			% (mass fraction) <sup>a</sup>										
ISO name	ISO number	Line number	C	Si	Mn	P	S	Cr	Mo	Ni	N	Others	
X3CrNiMoN27-5-2	4460-312-00-I	DM34F	0,050	1,00	2,00	0,035	0,030 <sup>b</sup>	25,0 to 28,0	1,30 to 2,00	4,5 to 6,5	0,05 to 0,20	—	
X2CrNiMoCuN25-6-3	4507-325-20-I	DM34A	0,030	0,70	2,00	0,035	0,015	24,0 to 26,0	3,0 to 4,0	6,0 to 8,0	0,20 to 0,30	Cu: 1,00 to 2,50	
X3CrNiMoCuN26-6-3-2	4507-325-50-X	DM35F	0,04	1,00	1,50	0,040	0,030	24,0 to 27,0	2,9 to 3,9	4,5 to 6,5	0,10 to 0,25	Cu: 1,50 to 2,50	
X2CrNiMoN25-7-3	4481-312-60-J	DM35A	0,030	1,00	1,50	0,040	0,030	24,0 to 26,0	2,50 to 3,5	5,5 to 7,5	0,08 to 0,30	—	
X2CrNiMoN25-7-4	4410-327-50-E	DM36A	0,030	1,00	2,00	0,035	0,015	24,0 to 26,0	3,0 to 4,5	6,0 to 8,0	0,24 to 0,35	—	
X2CrNiMoCuWN25-7-4	4501-327-60-I	DM36B	0,030	1,00	1,00	0,030	0,010	24,0 to 26,0	3,0 to 4,0	6,0 to 8,0	0,20 to 0,30	Cu: 0,50 to 1,00 W: 0,50 to 1,00	
X2CrNiMoN29-7-2 <sup>1</sup>	4477-329-06-E <sup>1</sup>	DM38A	0,030	0,80	0,80 to 1,50	0,030	0,030	28,0 to 30,0	1,50 to 2,60	5,8 to 7,5	0,30 to 0,40	Cu: 0,80	
X2CrNiMoCoN28-8-5-1 <sup>1</sup>	4658-327-07-U <sup>1</sup>	DM42A	0,030	0,50	1,50	0,035	0,010	26,0 to 29,0	4,0 to 5,0	5,5 to 9,5	0,30 to 0,50	Cu: 1,00 Co: 0,50 to 2,00	
X2CrNiMoN31-8-4 <sup>1</sup>	4485-332-07-U <sup>1</sup>	DM43A	0,030	0,80	1,50	0,035	0,010	29,0 to 33,0	3,0 to 5,0	6,0 to 9,0	0,40 to 0,60	Cu: 1,00	
<b>f) Ferritic steels</b>													
X2Cr12	4030-410-90-X	FP12A	0,030	1,00	1,00	0,040	0,030	11,0 to 13,5	—	—	—	—	
X2CrTi12 <sup>mn</sup>	4512-409-10- <sub>1mn</sub>	FP12B	0,030	1,00	1,00	0,040	0,030 <sup>b</sup>	10,5 to 12,5	—	0,50	0,030	Ti: 6 × (C+N) to 0,65	
X2CrNi12	4003-410-77-I	FP12C	0,030	1,00	2,00	0,040	0,015	10,5 to 12,5	—	0,30 to 1,10	0,030	—	
X2CrMnNiTi12	4600-410-70-E	FP12D	0,030	1,00	1,00 to 2,50	0,015	0,015	11,0 to 13,0	—	0,30 to 1,00	0,025	Ti: 6 × C to 0,35	
X6CrNiTi12	4516-409-75-I	FP12F	0,08	1,00	2,00	0,040	0,015	10,5 to 12,5	—	0,50 to 1,50	0,030	Ti: 0,05 to 0,35	
X6Cr13	4000-410-08-I	FP13G	0,08 <sup>i</sup>	1,00	1,00	0,040	0,030 <sup>b</sup>	11,5 to 14,0	—	0,75	—	—	
X6CrAl13	4002-405-00-I	FP13H	0,08	1,00	1,00	0,040	0,030 <sup>b</sup>	11,5 to 14,0	—	—	—	Al: 0,10 to 0,30	
X10CrAlSi13	4724-405-77-I	FP13L	0,12	0,70 to 1,40	1,00	0,040	0,015	12,0 to 14,0	—	1,00	—	Al: 0,70 to 1,20	
X10Cr15	4012-429-00-X	FP15L	0,12	1,00	1,00	0,040	0,030	14,0 to 16,0	—	—	—	—	
X1CrNb15	4595-429-71-I	FP15A	0,020	1,00	1,00	0,035	0,015	14,0 to 16,0	—	—	0,020	Nb: 0,20 to 0,60	
X6Cr17	4016-430-00-I	FP17I	0,08 <sup>i</sup>	1,00	1,00	0,040	0,030 <sup>b</sup>	16,0 to 18,0	—	—	—	—	
X7CrS17	4004-430-20-I	FP17L	0,09	1,50	1,50	0,040	≥0,15	16,0 to 18,0	0,60	—	—	—	
X2CrTi17	4520-430-70-I	FP17A	0,025	0,50	0,50	0,040	0,015	16,0 to 18,0	—	—	0,015	Ti: 8 × (C+N) to 0,60 <sup>d</sup>	

Table 1 (continued)

Steel designation		% (mass fraction) <sup>a</sup>										
ISO name	ISO number	Line number	C	Si	Mn	P	S	Cr	Mo	Ni	N	Others
X2CrNb17	4510-430-36-X	FP17B	0,030	0,75	1,00	0,040	0,030	16,0 to 19,0	—	—	—	Nb or Ti: 0,10 to 1,00
X3CrTi17	4510-430-35-I	FP17F	0,05	1,00	1,00	0,040	0,030 <sup>b</sup>	16,0 to 19,0	—	—	0,030	Ti: 0,15 to 0,75 <sup>d</sup>
X3CrNb17	4511-430-71-I	FP17G	0,05	1,00	1,00	0,040	0,015	16,0 to 18,0	—	—	0,030	Nb: 12 × C to 1,00
X6CrNi17-1	4017-430-91-E	FP17H	0,08	1,00	1,00	0,040	0,015	16,0 to 18,0	—	1,20 to 1,60	—	—
X2CrCuTi18	4664-430-75-J	FP18A	0,025	1,00	1,00	0,040	0,030	16,0 to 20,0	—	—	0,025	Ti: 8 × (C+N) to 0,80 <sup>d</sup> Cu: 0,30 to 0,80
X2CrTiNb18	4509-439-40-X	FP18B	0,030	1,00	1,00	0,040	0,015	17,5 to 18,5	—	—	—	Ti: 0,10 to 0,60 Nb: 0,30+3 × C to 1,00
X10CrAlSi18	4742-430-77-I	FP18N	0,12	0,70 to 1,40	1,00	0,040	0,015	17,0 to 19,0	—	1,00	—	Al: 0,70 to 1,20
X8CrAl19-3	4764-442-72-J	FP19N	0,10	1,50	1,00	0,040	0,030	17,0 to 21,0	—	—	—	Al: 2,00 to 4,0
X2CrNbTi20	4607-445-00-E	FP20A	0,030	1,00	1,00	0,040	0,015	18,5 to 20,5	—	—	0,030	Nb: 1,00 Ti: [4 × (C+N)+0,15] to 0,80 <sup>d</sup>
X2CrTi21	4611-445-70-E <sup>1</sup>	FP21A	0,030	1,00	1,00	0,050	0,050	19,0 to 22,0	0,50	0,50	—	Cu: 0,50, Al: 0,05 Ti: [4 × (C+N)+0,20] to 1,00 <sup>d</sup>
X2CrNbCu21	4621-445-00-E	FP21B	0,030	1,00	1,00	0,040	0,015	20,0 to 21,5	—	—	0,030	Cu: 0,10 to 1,00 Nb: 0,20 to 1,00
X2CrTiCu22	4621-443-30-J	FP22A	0,025	1,00	1,00	0,040	0,030	20,0 to 23,0	—	—	0,025	Cu: 0,30 to 0,80 Ti: 8 × (C+N) to 0,80 <sup>d</sup>
X2CrTi24	4613-446-70-E <sup>1</sup>	FP24A	0,030	1,00	1,00	0,050	0,050	22,0 to 25,0	0,50	0,50	—	Cu: 0,50, Al: 0,05 Ti: [4 × (C+N)+0,20] to 1,00 <sup>d</sup>
X10CrAlSi25	4762-445-72-I	FP25N	0,12	0,70 to 1,40	1,00	0,040	0,015	23,0 to 26,0	—	1,00	—	Al: 1,20 to 1,70
X15CrN26	4749-446-00-I	FP26R	0,20	1,00	1,00	0,040	0,030	24,0 to 28,0	—	1,00	0,15 to 0,25	—
<b>g) Ferritic steels with Mo</b>												
X5CrNiMoTi15-2	4589-429-70-E	FM16H	0,08	1,00	1,00	0,040	0,015	13,5 to 15,5	0,20 to 1,20	1,00 to 2,50	—	Ti: 0,30 to 0,50
X6CrMoS17	4105-430-20-X	FM17K	0,08	1,50	1,50	0,040	0,15 to 0,35	16,0 to 18,0	0,20 to 0,60	—	—	—

Table 1 (continued)

Steel designation		% (mass fraction) <sup>a</sup>										
ISO name	ISO number	Line number	C	Si	Mn	P	S	Cr	Mo	Ni	N	Others
X6CrMo17-1	4113-434-00-I	FM18I	0,08	1,00	1,00	0,040	0,030 <sup>b</sup>	16,0 to 18,0	0,75 to 1,40	—	—	—
X6CrMoNb17-1	4526-436-00-I	FM18J	0,08	1,00	1,00	0,040	0,015	16,0 to 18,0	0,80 to 1,40	—	0,040	Nb: 5x C to 1,00
X2CrMo19	4609-436-77-J	FM19B	0,025	1,00	1,00	0,040	0,030	17,0 to 20,0	0,40 to 0,80	—	0,025	Ti+Nb+Zr: 8x(C+N) to 0,80
X2CrMoNbTi18-1	4513-436-00-J	FM19A	0,025	1,00	1,00	0,040	0,030	16,0 to 19,0	0,75 to 1,50	—	0,025	Ti+Nb+Zr: 8x(C+N) to 0,80
X2CrMoTi18-2	4521-444-00-I	FM20B	0,025	1,00	1,00	0,040	0,015	17,0 to 20,0	1,75 to 2,50	—	0,030	Ti: ≥ 4x (C+N) and 0,15 ≤ Ti ≤ 0,80 d
X2CrMoTiS18-2	4523-182-35-I	FM20C	0,030	1,00	0,50	0,040	0,15 to 0,35	17,5 to 19,0	2,00 to 2,50	—	—	Ti: 0,30 to 0,80 (C+N) ≤ 0,040
X2CrMo23-1	4128-445-92-J	FM24B	0,025	1,00	1,00	0,040	0,030	21,0 to 24,0	0,70 to 1,50	—	0,025	—
X2CrMo23-2	4129-445-92-J	FM25A	0,025	1,00	1,00	0,040	0,030	21,0 to 24,0	1,50 to 2,50	—	0,025	—
X1CrMo26-1	4131-446-92-C	FM27A	0,010	0,40	0,40	0,030	0,020	25,0 to 27,5	0,75 to 1,50	—	0,015	—
X2CrMoNi27-4-2	4750-446-60-U	FM31A	0,030	1,00	1,00	0,040	0,030	25,0 to 28,0	3,0 to 4,0	1,00 to 3,5	0,040	(Ti + Nb): 0,20 + 6 × (C+N) to 1,00
X1CrMo30-2	4135-447-92-C	FM32A	0,010	0,40	0,40	0,030	0,020	28,5 to 32,0	1,50 to 2,50	—	0,015	—
<b>h) Martensitic steels</b>												
X12Cr13	4006-410-00-I	MP13B	0,08 to 0,15	1,00	1,50	0,040	0,030 <sup>b</sup>	11,5 to 13,5	—	0,75	—	—
X12CrS13	4005-416-00-I	MP13C	0,08 to 0,15	1,00	1,50	0,040	≥ 0,15	12,0 to 14,0	0,60	—	—	—
X13CrPb13	4642-416-72-J	MP13A	0,15	1,00	1,00	0,040	0,030	11,5 to 13,5	—	—	—	Pb: 0,05 to 0,30
X15Cr13	4024-410-09-E	MP13F	0,12 to 0,17	1,00	1,00	0,040	0,015	12,0 to 14,0	—	—	—	—
X20Cr13	4021-420-00-I	MP13I	0,16 to 0,25	1,00	1,50	0,040	0,030 <sup>b</sup>	12,0 to 14,0	—	—	—	—
X30Cr13	4028-420-00-I	MP13M	0,26 to 0,35	1,00	1,50	0,040	0,030 <sup>b</sup>	12,0 to 14,0	—	—	—	—
X33CrS13	4029-420-20-I	MP13N	0,25 to 0,40	1,00	1,50	0,060	≥ 0,15	12,0 to 14,0	0,60	0,60	—	—
X33CrPb13	4643-420-72-J	MP13O	0,26 to 0,40	1,00	1,00	0,040	0,030	12,0 to 14,0	—	—	—	Pb: 0,05 to 0,30
X39Cr13	4031-420-00-I	MP13P	0,36 to 0,42	1,00	1,00	0,040	0,030 <sup>b</sup>	12,5 to 14,5	—	—	—	—
X46Cr13	4034-420-00-I	MP13Q	0,43 to 0,50	1,00	1,00	0,040	0,030 <sup>b</sup>	12,5 to 14,5	—	—	—	—