



SLOVENSKI STANDARD
oSIST prEN 16354:2016
01-januar-2016

Laminatne talne obloge - Podlage - Specifikacije, zahteve in preskusne metode

Laminate floor coverings - Underlays - Specification, requirements and test methods

Laminatböden - Verlegeunterlage - Spezifikationen, Anforderungen und Prüfverfahren

Revêtements de sol stratifiés - Sous-couches - Spécifications, exigences et méthodes d'essai

Ta slovenski standard je istoveten z: prEN 16354

ICS:

97.150

Netekstilne talne obloge

Non-textile floor coverings

oSIST prEN 16354:2016

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 16354

January 2016

ICS 97.150

Will supersede CEN/TS 16354:2013

English Version

**Laminate floor coverings - Underlays - Specification,
requirements and test methods**

Revêtements de sol stratifiés - Sous-couches -
Spécifications, exigences et méthodes d'essai

Laminatböden - Verlegeunterlage - Spezifikationen,
Anforderungen und Prüfverfahren

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 134.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

| | |
|---|----|
| European Foreword..... | 3 |
| 1 Scope | 4 |
| 2 Normative references | 4 |
| 3 Terms and definitions | 5 |
| 4 Technical characteristics and requirements | 6 |
| 4.1 General..... | 6 |
| 4.2 General characteristics | 7 |
| 4.3 Additional technical characteristics | 8 |
| 4.4 Testing..... | 8 |
| 4.4.1 General..... | 8 |
| 4.4.2 Thickness (t) | 8 |
| 4.4.3 Punctual conformability (PC) | 9 |
| 4.4.4 Compressive strength (CS)..... | 9 |
| 4.4.5 Compressive Creep (CC) resistance..... | 9 |
| 4.4.6 Dynamic load (DL ₂₅) resistance | 9 |
| 4.4.7 Thermal resistance (R) | 9 |
| 4.4.8 Water vapour resistance (SD) | 9 |
| 4.4.9 Alkaline resistance (AR) | 10 |
| 4.4.10 Area weight (AW) | 10 |
| 4.4.11 Reaction to fire (RTF) | 10 |
| 4.4.12 Resistance to impact by large diameter ball (RLB)..... | 10 |
| 4.4.13 Electrostatic behaviour (EB) | 10 |
| 4.4.14 Emission of formaldehyde | 10 |
| 4.4.15 Emission of VOCs | 10 |
| 4.4.16 Impact sound (IS) | 10 |
| 4.4.17 Airborne sound (AS) | 11 |
| 5 Marking and labelling..... | 11 |
| Annex A (normative) Determination of thickness, length, width, squareness, flatness, punctual conformability, compressive strength, compressive creep resistance, dynamic load resistance and area weight | 12 |
| A.1 Sampling..... | 12 |
| A.2 Conditions..... | 12 |
| A.3 Procedure..... | 12 |
| Annex B (informative) Proposed performance classes..... | 19 |
| B.1 General..... | 19 |
| B.2 Proposed classes | 19 |
| Bibliography..... | 20 |

European Foreword

This document (prEN 16354:2015) has been prepared by Technical Committee CEN/TC 134 “Resilient, textile and laminate floor coverings”, the secretariat of which is held by NBN.

This document is currently submitted to the CEN Enquiry.

This document will supersede CEN/TS 16354:2013.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 16354:2019

<https://standards.iteh.ai/catalog/standards/sist/bce02f53-60d3-489b-9050-3a0f45f42b45/sist-en-16354-2019>

1 Scope

This European Standard specifies test methods for the determination of the technical characteristics of underlays under laminate floor coverings. It includes minimum performance requirements for the underlay-flooring system to give satisfactory service and to encourage the consumer to make an informed choice. It also specifies requirements for marking and packaging.

Underlays pre-attached to the laminate flooring coverings are not covered by this European Standard.

Underlays for laminate floor coverings intended for use in electrostatically sensitive areas like computer rooms, etc., are not covered by this European Standard.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 717-1, *Wood-based panels - Determination of formaldehyde release - Part 1: Formaldehyde emission by the chamber method*

EN 717-2, *Wood-based panels - Determination of formaldehyde release - Part 2: Formaldehyde release by the gas analysis method*

EN 822:2013, *Thermal insulating products for building applications - Determination of length and width*

EN 823, *Thermal insulating products for building applications - Determination of thickness*

EN 824, *Thermal insulating products for building applications - Determination of squareness*

EN 825, *Thermal insulating products for building applications - Determination of flatness*

EN 826, *Thermal insulating products for building applications - Determination of compression behaviour*

EN 1264-3, *Water based surface embedded heating and cooling systems - Part 3: Dimensioning*

EN 1606, *Thermal insulating products for building applications - Determination of compressive creep*

EN 1815, *Resilient and textile floor coverings - Assessment of static electrical propensity*

EN 12086, *Thermal insulating products for building applications - Determination of water vapour transmission properties*

EN 12311-2, *Flexible sheets for waterproofing - Determination of tensile properties - Part 2: Plastic and rubber sheets for roof waterproofing*

EN 12664, *Thermal performance of building materials and products - Determination of thermal resistance by means of guarded hot plate and heat flow meter methods - Dry and moist products of medium and low thermal resistance*

EN 12667, *Thermal performance of building materials and products - Determination of thermal resistance by means of guarded hot plate and heat flow meter methods - Products of high and medium thermal resistance*

EN 13238, *Reaction to fire tests for building products - Conditioning procedures and general rules for selection of substrates*

EN 13329, *Laminate floor coverings - Elements with a surface layer based on aminoplastic thermosetting resins - Specifications, requirements and test methods*

EN 13501-1:2007+A1:2009, *Fire classification of construction products and building elements - Part 1: Classification using data from reaction to fire tests*

EN 13793, *Thermal insulating products for building applications - Determination of behaviour under cyclic loading*

EN 14909, *Flexible sheets for waterproofing - Plastic and rubber damp proof courses - Definitions and characteristics*

EN 14978, *Laminate floor coverings - Elements with acrylic based surface layer, electron beam cured - Specifications, requirements and test methods*

EN 15468, *Laminate floor coverings - Elements with directly applied printing and resin surface layer - Specifications, requirements and test methods*

EN ISO 717-1, *Acoustics - Rating of sound insulation in buildings and of building elements - Part 1: Airborne sound insulation (ISO 717-1:2013)*

EN ISO 717-2, *Acoustics - Rating of sound insulation in buildings and of building elements - Part 2: Impact sound insulation (ISO 717-2:2013)*

EN ISO 868:2003, *Plastics and ebonite - Determination of indentation hardness by means of a durometer (Shore hardness) (ISO 868:2003)*

EN ISO 1923, *Cellular plastics and rubbers - Determination of linear dimensions (ISO 1923)*

EN ISO 10140-2, *Acoustics - Laboratory measurement of sound insulation of building elements - Part 2: Measurement of airborne sound insulation (ISO 10140-2)*

EN ISO 10140-3, *Acoustics - Laboratory measurement of sound insulation of building elements - Part 3: Measurement of impact sound insulation (ISO 10140-3)*

EN ISO 10140-5:2010, *Acoustics - Laboratory measurement of sound insulation of building elements - Part 5: Requirements for test facilities and equipment (ISO 10140-5:2010)*

EN ISO 11925-2:2010, *Reaction to fire tests - Ignitability of products subjected to direct impingement of flame - Part 2: Single-flame source test (ISO 11925-2:2010)*

EN ISO 16000-9, *Indoor air - Part 9: Determination of the emission of volatile organic compounds from building products and furnishing - Emission test chamber method (ISO 16000-9)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13329, EN 15468 and EN 14978 and the following apply.

prEN 16354:2015 (E)**3.1****underlay**

resilient layer between the substrate and floor covering added to obtain specific properties

Note 1 to entry: It is also possible to have combinations of the above underlays and underlay materials as underlay, as well as combinations of the above underlays with films or coatings (e.g. vapor barriers).

3.2**vapour control layer**

underlay and/or an additional layer that offers a resistance against the passage of water vapour

3.3**floor covering system**

laid floors consisting of laminate floor covering and underlay

3.4**reference floor covering**

monolithic seamless panel with no pre-attached underlay, having a nominal thickness of $(7,0 \pm 0,2)$ mm and a size of $(2,0 \pm 0,1)$ m x $(2,4 \pm 0,1)$ m in accordance with EN 13329, class 23/31 and produced by the DPL method with melamine backing, and with an HDF core board with a density of (850 ± 50) kg/m³

Note 1 to entry: The reference floor covering referred to in this European Standard is identical with the one specified in the reflected walking sound test according to bibliographical entries [1] and [2]. This reference floor covering can be retrieved from EPLF (<http://www.eplf.com>).

3.5**substrate**

structural layer on which the floor covering system is installed

4 Technical characteristics and requirements**4.1 General**

The following tables give an overview of the important key characteristics and requirements for the underlay, depending on the exact application and products used. They have been determined for defined scenarios (e.g. dynamic load by walking persons, moving castor chair, structural floor unevenness) and by practical trials and measurements (e.g. 100 Pa is the approx. pressure of an unloaded laminate onto the underlay). Where needed, existing methods have been adapted.

4.2 General characteristics

All underlays shall fulfil the requirements of Table 1, if the tests are done by the described test methods.

Table 1 — General requirements

| No. | Characteristic | Requirements/Tolerances | Test method | Subclause |
|---|--|--|-------------------------|-----------|
| 1-1 | Thickness, (t) | Measured thickness in mm. Tolerance of declared thickness (t_d): $\pm 15\%$ or $\pm 0,5\text{ mm}^a$ | EN 823 + A.3.1 | 4.4.2 |
| 1-2 | Length, (l) | Measured length. Tolerance of declared length (l_d): boards: $-1\% + 5\%$ rolls: $-0\% + 5\%$ | EN 822:2013 + A.3.3 | |
| 1-3 | Width, (w) | Measured width. Tolerance of declared width (w_d): $-1\% + 2,5\%$ and of width variation $w_{\max} - w_{\min} \leq 10\text{ mm}$ | EN 822:2013 + A.3.2 | |
| 1-4 | Squareness, (q) | $q_{\max} < 5\text{ mm/m}$ | EN 824 + A.3.4 | |
| 1-5 | Flatness, (S) | $S_{\max} < 2\text{ mm/m}$ | EN 825 + A.3.5 | |
| 1-6 | Punctual conformability (PC) | $PC \geq 0,5\text{ mm}$ | EN ISO 868:2003 + A.3.6 | 4.4.3 |
| 1-7 | Compressive strength (CS) | $CS \geq 10\text{ kPa}$ | EN 826 + A.3.7 | 4.4.4 |
| 1-8 | Dynamic load (DL₂₅) resistance | $DL \geq 10\ 000\text{ cycles}$ | EN 13793 + A.3.9 | 4.4.6 |
| ^a Whichever gives the smallest numerical tolerances. | | | | |

4.3 Additional technical characteristics

When reference is made to this standard, the characteristics declared shall be determined according to the test methods specified in Table 2.

Table 2 — Additional technical characteristics

| No. | Characteristic | Note | Test method | Subclause |
|------|--|--|---|-----------|
| 2-1 | Compressive Creep resistance (CC) | in kPa | EN 1606 + A.3.8 | 4.4.5 |
| 2-2 | Thermal resistance (R) | in m ² K/W | EN 12667 or EN 12664 at 24 °C mean temperature | 4.4.7 |
| 2-3 | Water vapour diffusion resistance (SD) | in m | EN 12086, method A, at 23 °C and 0 %-50 % rel. humidity | 4.4.8 |
| 2-4 | Impact sound (IS) | Weighted reduction of impact sound pressure level ΔL_w in dB | EN ISO 10140-3 and EN ISO 717-2 | 4.4.16 |
| 2-5 | Air borne sound (AS) | Weighted apparent sound reduction index R_w' in dB | EN ISO 10140-2 and EN ISO 717-1 | 4.4.17 |
| 2-6 | Resistance to impact by large diameter ball (RLB) | Product (underlay plus laminate in end-use conditions) | EN 13329 | 4.4.12 |
| 2-7 | Electrostatic behaviour (EB) | Product (underlay plus laminate in end-use conditions) | EN 1815, method A | 4.4.13 |
| 2-8 | Alkaline resistance (AR) | | EN 14909 | 4.4.9 |
| 2-9 | Emission of formaldehyde | | EN 717-1 or EN ISO 16000-9 | 4.4.14 |
| 2-10 | Emission of VOCs | | EN ISO 16000-9 | 4.4.15 |
| 2-11 | Area weight (AW) | | A.3.10 | 4.4.10 |
| 2-12 | Reaction-to-fire (RTF) | | EN ISO 11925-2:2010 Classification according to EN 13501-1:2007+A1:2009 – Table 2 | 4.4.11 |

4.4 Testing

4.4.1 General

The tests specified in this clause are based on existing standards used for other building applications and adapted to the specific application conditions of laminate flooring underlays where needed.

4.4.2 Thickness (t)

Thickness is the main property of an underlay to ensure functionality such as acoustic performance or conformability.

The thickness d shall be determined according to EN 823 plus the details given in A.3.1 under a measurement load of 100 Pa (= typical load of a laminate).

4.4.3 Punctual conformability (PC)

Punctual conformability is the ability of the underlay to smoothen small local defects of the subfloor (e.g. small protruding particles) and/or small particles laying on the subfloor when installed under a laminate floor covering.

The punctual conformability of the underlay shall be determined by measuring the Shore-A-hardness (SH) according to EN ISO 868:2003 plus the details defined in A.3.6. The punctual conformability shall be declared as PC-value (mm).

4.4.4 Compressive strength (CS)

To ensure the integrity of the joints of a laminate floor covering element, the compressive strength at 0,5 mm deformation shall be determined according to EN 826 plus the details defined in A.3.7 and with a pre-load of 100 Pa. The compressive strength shall be declared as CS-value (in kPa).

4.4.5 Compressive Creep (CC) resistance

To ensure sufficient resistance of the underlay against static load applied by e.g. furniture feet, the resistance to compressive load shall be determined according to EN 1606 plus the details defined in A.3.8 and with a pre-load of 100 Pa.

Compressive creep resistance shall be determined as the maximum applicable load in kPa resulting in a thickness loss $X_t = X_0 + X_{ct}$ of $\leq 0,5$ mm after extrapolation to 10 years. The compressive creep resistance shall be declared as CC-value in kPa.

When CC is determined at temperatures other than the standard conditions as defined under A.2, the conditions shall be reported (e.g. CC (35 °C)).

4.4.6 Dynamic load (DL₂₅) resistance

To ensure sufficient resistance of the underlay against long-term dynamic loads applied by e.g. people walking or sitting on a castor chair the resistance to dynamic load shall be determined according to EN 13793 plus the details defined in A.3.9.

The dynamic load resistance shall be declared as DL₂₅-value (number of cycles). The value is determined as the maximum number of load cycles which can be applied to the underlay that results in a maximum loss in thickness of $\leq 0,5$ mm.

4.4.7 Thermal resistance (R)

If the laminate floor coverings is going to be installed over underfloor heating according to EN 1264-3 the thermal resistance R of the floor covering system shall not exceed 0,15 m²K/W when tested according to EN 12667 or EN 12664 at 24 °C mean temperature.

The heat resistance R of the materials laid onto the heated floor such as underlay and floor covering, etc., shall be summed up. Because of the weight of the floor covering itself and the weight of furniture, air gaps may not be expected and can be neglected in this respect.

4.4.8 Water vapour resistance (SD)

In situations where slight rising dampness or occasional condensation can be expected because of differences in temperature, wet conditions in underneath rooms or in case of an underfloor heating, a vapour control layer shall be installed to protect the floor covering system from swelling or other negative effects. The minimum SD value of the vapour control layer in these situations should be $SD \geq 75$ m measured using EN 12086, method A, with the test conditions 23 °C, 0/50 % relative humidity.

The vapour control properties may be provided by the underlay itself (e.g. multilayer) or by a separate layer. For underlays known to be sensitive to humidity, suitable precautions shall be taken to prevent