INTERNATIONAL STANDARD

ISO 18086

First edition 2015-06-01

Corrosion of metals and alloys — Determination of AC corrosion — Protection criteria

Corrosion des métaux et alliages — Détermination de la corrosion occasionnée par les courants alternatifs — Critères de protection

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 18086:2015</u> https://standards.iteh.ai/catalog/standards/sist/3ee8821f-33de-45b8-bd5f-5007bef057e9/iso-18086-2015



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 18086:2015 https://standards.iteh.ai/catalog/standards/sist/3ee8821f-33de-45b8-bd5f-5007bef057e9/iso-18086-2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Contents						
Fore	word		v			
Intr	oductio	n	vi			
1	Scon	e	1			
2	Normative references					
		ms and definitions				
3						
4	Cathodic protection persons competence					
5	Assessment of the AC influence					
	5.1	General				
	5.2	Assessment of the level of interference				
6	Evaluation of the AC corrosion likelihood					
	6.1	Prerequisite				
		6.1.2 AC voltage on the structure				
	6.2	AC and DC current density				
		6.2.1 General	7			
		6.2.2 AC current density				
		6.2.3 High cathodic DC current density	7			
		6.2.4 Low cathodic DC current density 6.2.5 Current ratio #1a.c./Id.c./A.R.D. P.R.E.VIE.W.				
		6.2.6 Soil resistivity	8 8			
	6.3	6.2.6 Soil resistivity Corrosion rate (Standards.iteh.ai)	8			
	6.4	Pipeline coatings				
	6.5	Evaluation of the metal loss _{ISO-18086-2015}				
7	Acce	ptable interference levelstalog/standards/sist/3ee8821f-33de-45b8-bd5f-	8			
8	Meas	5007bef057e9/iso-18086-2015 surement techniques	9			
	8.1	Measurements	9			
		8.1.1 General				
		8.1.2 Selection of test sites				
		8.1.3 Selection of measurement parameter				
		8.1.4 Sampling rate for the recording of interference levels				
		8.1.6 Installation of coupons or probes to calculate current densities				
	8.2	DC potential measurements				
	8.3	AC voltage measurements				
	8.4	Measurements on coupons and probes				
		8.4.1 Installation of coupons or probes				
		8.4.2 Current measurements				
	8.5	Pipeline metal loss techniques				
0						
9	9.1	gation measures General				
	9.2	Construction measures				
	7.2	9.2.1 Modification of bedding material				
		9.2.2 Installation of isolating joints				
		9.2.3 Installation of mitigation wires	13			
		9.2.4 Optimization of pipeline and/or powerline route				
	0.2	9.2.5 Power line or pipeline construction				
	9.3	Operation measures 9.3.1 Earthing				
		9.3.2 Adjustment of cathodic protection level				
		9.3.3 Repair of coating defects				

ISO 18086:2015(E)

10	Commissioning				
	10.1	l issioning		16	
	10.2	Preliminary checking		16	
		10.2.1	General	16	
		10.2.2	Coupon AC voltage and current startup	17	
		10.2.3	Verification of effectiveness	17	
		10.2.4	Installation and commissioning documents	17	
11	Monit	toring an	d maintenance	17	
Annex			Simplified description of the AC corrosion phenomenon		
Annex B (informative) Coupons and probes					
Annex	C (info	ormative)	Coulometric oxidation	26	
Annex	D (inf	ormative) Influence of soil characteristics on the AC corrosion process	27	
Annex	E (info	ormative)	Other criteria that have been used in the presence of AC influence	28	
Annex	F (info	ormative)	Parameters to take into account to choose a DC decoupling device	32	
Annex	G (info	ormative]	Method to determine the reference electrode location to remote earth	34	
Annex	H (inf	ormative) Simultaneous measurement on coupon current densities with high rate	36	
Biblio	graphy	v		38	

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 18086:2015 https://standards.iteh.ai/catalog/standards/sist/3ee8821f-33de-45b8-bd5f-5007bef057e9/iso-18086-2015

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: Foreword — Supplementary information.

The committee responsible for this document is ISO/TC 156, Corrosion of metal and alloys.

ISO 18086:2015 https://standards.iteh.ai/catalog/standards/sist/3ee8821f-33de-45b8-bd5f-5007bef057e9/iso-18086-2015

Introduction

This International Standard has incorporated criteria and thresholds together with experience gained from the most recent data. Various countries have a very different approach to the prevention of AC corrosion depending primarily on the DC interference situation. These different approaches are taken into account in two different ways

- either in presence of "low" on-potentials, which allows a certain level of AC voltage (up to 15 V), or
- in presence of "high" on-potentials (with DC stray current interference on the pipeline for instance) which requires the reduction of the AC voltage towards the lowest possible levels.

This International Standard also gives some parameters to consider when evaluating the AC corrosion likelihood, as well as detailed measurement techniques, mitigation measures, and measurements to carry out for commissioning of any AC corrosion mitigation system. Note that Annex E proposes other parameters and thresholds that require further validation based on practical experiences.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 18086:2015 https://standards.iteh.ai/catalog/standards/sist/3ee8821f-33de-45b8-bd5f-5007bef057e9/iso-18086-2015

Corrosion of metals and alloys — Determination of AC corrosion — Protection criteria

1 Scope

This International Standard is applicable to buried cathodically-protected pipeline that is influenced by AC traction systems and/or AC power lines.

In the presence of AC interference, the protection criteria given in ISO 15589-1 are not sufficient to demonstrate that the steel is being protected against corrosion.

This International Standard provides limits, measurement procedures, mitigation measures, and information to deal with long term AC interference for AC voltages at frequencies between 16,7 and 60 Hz and the evaluation of AC corrosion likelihood.

This International Standard deals with the possibility of AC corrosion of metallic pipelines due to AC interferences caused by inductive, conductive or capacitive coupling with AC power systems and the maximum tolerable limits of these interference effects. It takes into account the fact that this is a long-term effect, which occurs during normal operating conditions of the AC power system.

This International Standard does not cover the safety issues associated with AC voltages on pipelines. These are covered in national standards and regulations (see e.g. EN 50443).

(standards.iteh.ai)

2 Normative references

ISO 18086:2015

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 15589-1, Petroleum, petrochemical and natural gas industries — Cathodic protection of pipeline systems — Part 1: On-land pipelines

ISO 8044, Corrosion of metals and alloys — Basic terms and definitions

IEC 61010-1, Safety requirements for electrical equipment for measurements, control, and laboratory use — Part 1: General requirements

EN 13509, Cathodic protection measurement techniques

EN 15257, Cathodic protection — Competence levels and certification of cathodic protection personnel

EN 50443, Effects of electromagnetic interference on pipelines caused by high voltage AC electric traction systems and/or high voltage AC power supply systems

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8044 and the following apply.

3.1

AC electric traction system

AC railway electrical distribution network used to provide energy for rolling stock

Note 1 to entry: The system can comprise the following:

contact line systems;

ISO 18086:2015(E)

- return circuit of electric railway systems;
- running rails of non-electric railway systems, which are in the vicinity of and conductively connected to the running rails of an electric railway system.

3.2

AC power supply system

AC electrical system devoted to electrical energy transmission and includes overhead lines, cables, substations and all apparatus associated with them

3.3

AC power system

AC electric traction system or AC power supply system

Note 1 to entry: Where it is necessary to differentiate, each interfering system is clearly indicated with its proper term.

3.4

copper/copper sulfate reference electrode

reference electrode consisting of copper in a saturated solution of copper sulfate

3.5

AC voltage

voltage measured to earth between a metallic structure and a reference electrode

3.6 interfering system

iTeh STANDARD PREVIEW

general expression encompassing an interfering high voltage AC electric traction system and/or high voltage AC power supply system

ISO 18086:2015

interfered system

https://standards.iteh.ai/catalog/standards/sist/3ee8821f-33de-45b8-bd5f-

system on which the interference effects appear

Note 1 to entry: In this International Standard, it is the pipeline system.

3.8

pipeline system

system of pipe network with all associated equipment and stations

Note 1 to entry: In this International Standard, pipeline system refers only to metallic pipeline system.

Note 2 to entry: The associated equipment is the equipment electrically connected to the pipeline.

3.9

conductive mass of the earth, whose electric potential at any point is conventionally taken as equal to zero

[SOURCE: IEC 60050 826]

operating condition

fault-free operation of any system

Note 1 to entry: Transients are not to be considered as an operating condition.

3.11

fault condition

non-intended condition caused by short-circuit to earth, the fault duration being the normal clearing time of the protection devices and switches

Note 1 to entry: The short circuit is an unintentional connection of an energized conductor to earth or to any metallic part in contact with earth.

3.12

conductive coupling

coupling which occurs when a proportion of the current belonging to the interfering system returns to the system earth via the interfered system or when the voltage to the reference earth of the ground in the vicinity of the influenced object rises because of a fault in the interfering system and the results of which are conductive voltages and currents

3.13

inductive coupling

phenomenon whereby the magnetic field produced by a current carrying circuit influences another circuit

Note 1 to entry: The coupling being quantified by the mutual impedance of the two circuits, and the results of which are induced voltages and hence currents that depend on, for example, the distances, length, inducing current, circuit arrangement, and frequency.

3.14

phenomenon whereby the electric field produced by an energized conductor influences another conductor (standards.iteh.ai)

Note 1 to entry: The coupling being quantified by the capacitance between the conductors and the capacitances between each conductor and earth, and the results of which are interference voltages into conductive parts or conductors insulated from earth, these voltages depends for example on the voltage of the influencing system, distances, and circuit arrangement.

5007bef057e9/iso-18086-2015

3.15

interference

phenomenon resulting from conductive, capacitive, inductive coupling between systems and which can cause malfunction, dangerous voltages, damage, etc.

3.16

disturbance

malfunction of an equipment losing its capability to work properly for the duration of the interference

Note 1 to entry: When the interference disappears, the interfered system starts working properly again without any external intervention.

3.17

damage

permanent reduction in the quality of service which can be suffered by the interfered system

Note 1 to entry: A reduction in the quality of service could also be the complete cancellation of service.

EXAMPLE Coating perforation, pipe pitting, pipe perforation, permanent malfunction of the equipment connected to the pipes, etc.

3.18

danger

state of the influenced system which is able to produce a threat to human life

3.19

interference situation

maximum distance between the pipeline system and AC power system for which an interference is to be considered

3.20

interference voltage

voltage caused on the interfered system by the conductive, inductive, and capacitive coupling with the nearby interfering system between a given point and the earth or across an insulating joint

3.21

IR drop

voltage due to any current, developed in an electrolyte such as the soil, between the reference electrode and the metal of the structure, in accordance with Ohm's Law $(U = I \times R)$

3.22

IR-free potential

 $E_{IR\text{-free}}$

pipe to electrolyte potential measured without the voltage error caused by the IR drop due to the protection current or any other current

3.23

off-potential

 $E_{\rm off}$

pipe to electrolyte potential measured after interruption of all sources of applied cathodic protection current with the aim of approaching an *IR*-free potential **D P R F V IF W**

Note 1 to entry: The delay before measurement varies according to circumstances.

3.24

on-potential

ISO 18086:2015

 E_{on}

https://standards.iteh.ai/catalog/standards/sist/3ee8821f-33de-45b8-bd5f-

pipe to electrolyte potential measured while the cathodic protection system is continuously operating

3.25

spread resistance

ohmic resistance through a coating defect to earth or from the exposed metallic surface of a coupon towards earth

Note 1 to entry: This is the resistance which controls the DC or AC current through a coating defect or an exposed metallic surface of a coupon for a given DC or AC voltage.

3.26

coupon

metal sample of defined dimensions made of a metal equivalent to the metal of the pipeline

3.27

probes

device incorporating a coupon that provides measurements of parameters to assess the effectiveness of cathodic protection and/or corrosion risk

4 Cathodic protection persons competence

Persons who undertake the design, supervision of installation, commissioning, supervision of operation, measurements, monitoring, and supervision of maintenance of cathodic protection systems shall have the appropriate level of competence for the tasks undertaken.

EN 15257 or NACE Cathodic Protection Training and Certification Programme constitute suitable methods of assessing and certifying competence of cathodic protection personnel.

Competence of cathodic protection persons to the appropriate level for tasks undertaken should be demonstrated by certification in accordance with prequalification procedures such as EN 15257, NACE Cathodic Protection Training and Certification Programme, or any other equivalent scheme.

5 Assessment of the AC influence

5.1 General

This International Standard is applicable to all metallic pipelines and all high voltage AC traction systems and high voltage AC power supply systems and all major modifications that can significantly change the AC interference effect.

The effects are the following:

- danger to people who come in direct contact or contact through conductive parts with the metallic pipeline or the connected equipment;
- damage of the pipeline or to the connected equipment;
- disturbance of electrical/electronic equipment connected to the pipeline.

Electrical/electronic systems installed on a pipeline network shall be chosen, such that they will neither become dangerous nor interfere with normal operating conditions because of short-term voltages and currents, which appear during short circuits on the AC power system.

Long term AC interference on a buried pipeline can cause corrosion due to an exchange of AC current between the exposed metal of the pipeline and the surrounding electrolyte.

This exchange of current depends on an AC voltage whose amplitude is related to various parameters such as the following:

<u>ISO 180862015</u>

- https://standards.iteh.ai/catalog/standards/sist/3ee8821f-33de-45b8-bd5fconfiguration of AC power line phase conductors;86-2015
- presence and configuration of the earthing conductor;
- distance between the AC power line/traction system and the pipeline;
- current flowing in the AC power line/traction system phase conductors;
- average coating resistance of the pipeline;
- thickness of the coating;
- soil resistivity;
- presence of earthing systems;
- voltage of the AC railway system or the AC power line system.

5.2 Assessment of the level of interference

Calculations can be carried out (e.g. according to EN 50443) by mathematical modelling to determine the earthing requirements necessary to maintain touch voltages within acceptable safe levels. Their results can also be used to determine voltages necessary to reduce the AC corrosion likelihood.

During the design phase of new influencing systems (electricity power line or railway line) or a new influenced system (pipelines), an estimation of the level of AC voltage on the pipeline should be calculated. Calculations can be carried out by mathematical modelling to determine the level of voltage produced on the pipeline. In the case of existing structures, field measurements can also be used as an option to calculation.

ISO 18086:2015(E)

According to the results of calculations or field measurements, relevant mitigation measures should be installed on the influencing systems and/or the influenced system to achieve the relevant AC voltage to reduce the AC corrosion likelihood (see <u>Clause 7</u>.).

Guidance on calculating the AC voltage on a structure caused by an AC power system was published in Reference [6] The algorithm determines the worst case conditions for the input parameters used for the calculation.

Due to inconsistent load demands on AC power systems, the magnitude of operating currents in power lines varies. The fluctuations depend on daily and seasonal changes. Input data for calculation purposes should be based on the realistic operating conditions or the maximum power load of the influencing system.

NOTE Carrying out calculations with input data based on both approaches is a help to estimate the range between both results and to choose the right method.

6 Evaluation of the AC corrosion likelihood

6.1 Prerequisite

6.1.1 General

The AC voltage on a pipeline is the driving force for the AC corrosion processes taking place on the steel surface at coating defects. Among other things, corrosion damage depends on AC current density, level of DC polarization, defect geometry, local soil composition and resistivity (see Annex D).

Basically, there are three different approaches to prevent AC corrosion: to limit the AC current flowing through a defect, to control cathodic protection level, and to ensure that any coating remains defect free. These approaches are not mutually exclusive. ISO 180862015

https://standards.iteh.ai/catalog/standards/sist/3ee8821f-33de-45b8-bd5fThe evaluation of AC corrosion likelihood should be performed by evaluation of some or all of the following parameters:

- AC voltage on the structure;
- on-potential;
- IR-free potential;
- AC current density;
- DC current density;
- AC/DC current density ratio;
- soil resistivity;
- corrosion rate.

<u>Annex B</u>, <u>Annex C</u>, and <u>Annex E</u> provide further information.

6.1.2 AC voltage on the structure

The acceptable AC voltage thresholds (see <u>Clause 7</u> and <u>Annex E</u>) depend on the chosen strategy to prevent AC corrosion. Hence, a given interference situation on the pipeline can influence the decision regarding the applicable strategy.

6.2 AC and DC current density

6.2.1 General

The AC and DC current density on a coating defect controls both the cathodic protection level and AC corrosion process. Therefore, it is a more reliable parameter for the evaluation of the AC corrosion likelihood than the on-potential or the AC voltage. However, in contrast to the voltages present on the pipeline, the current density cannot be readily determined. In principle, the current density can be calculated from the spread resistance and the geometry of the coating defect and the AC voltage. This calculation is generally not possible since the geometry of the coating fault and its surface area are generally not known. Moreover, the application of cathodic protection can significantly change the spread resistance and therefore, the current density at a given voltage.

The current density can only be estimated by means of coupons or probes. When evaluating the AC corrosion likelihood by means of a coupon or probe, it is important to consider the limitations of this technique. The calculation of the current density based upon the metallic coupon or probe surface area and on the current measured on a coupon or probe, the current is averaged over the entire coupon or probe surface. However, the current distribution on the coupon or probe can vary depending on its geometry. Typically, current densities at the edges of the coupon or probe are larger than the current averaged over the entire surface. Moreover, the often observed formation of chalk layers can decrease the effective coupon or probe surface area. Again, this effect results in an under estimation of the current density.

6.2.2 AC current density 1Teh STANDARD PREVIEW

The AC current density results in anodic and cathodic charge transfer. A detailed explanation of the charge transfer process is given in Annex A. This current can be consumed in charging of the double layer capacitance at the steel surface, in the oxidation of hydrogen (resulting in a decreasing pH), in the oxidation of corrosion products, and in the oxidation of the metal. The oxidation of the metal results in corrosion. Generally, an increasing AC current density results in a larger amount of metal oxidation and higher corrosion rates. However, the anodic current is not the only current that can affect the corrosion process. Cathodic current can reduce oxide layers formed and increase the pH on the metal surface.

High AC current densities do not necessarily cause AC corrosion if the charge passed through the metal surface can be consumed in reactions other than metal oxidation and oxide film reduction. This is the case in the presence of low cathodic DC current densities. As a consequence, the judgment of the AC corrosion likelihood based on the AC current density requires the additional consideration of the cathodic DC current density.

Nevertheless, there is an empirically determined lower limit for the AC current density below which the probability for AC corrosion is extremely low (see <u>Clause 7</u>).

6.2.3 High cathodic DC current density

A high DC current density results in more negative cathodic protection levels and the formation of a high pH at the pipeline surface. However, the formation of a high pH-value, the decrease of the spread resistance, and the increased reduction of surface oxide films can result in an acceleration of the corrosion rate under simultaneous AC interference. Nevertheless, a sufficiently high DC current density can prevent any anodic metal oxidation and therefore, the occurrence of AC corrosion.

Annex A and Annex E give detailed explanations about this process.

6.2.4 Low cathodic DC current density

A low DC current density results in a limited increase of the pH value at the metal surface, does not significantly change the spread resistance, and has less reductive effect on metal oxides on the pipeline surface. Therefore, the AC corrosion likelihood significantly decreases with decreasing DC current densities. However, low DC current densities can result in an insufficient level of cathodic polarization of the metal surface as stated in ISO 15589-1.