
Lepila na osnovi mavca za toplotno/zvočno izolacijo kompozitnih panelov in mavčne plošče - Definicije, zahteve in preskusne metode

Gypsum based adhesives for thermal/acoustic insulation composite panels and gypsum boards - Definitions, requirements and test methods

Kleber auf Gipsbasis für Verbundplatten zur Wärme- und Schalldämmung und Gipsplatten - Begriffe, Anforderungen und Prüfverfahren

Adhésifs à base de plâtre pour complexes d'isolation thermique/acoustique en plaques de plâtre et isolant - Définitions, exigences et méthodes d'essai

Ta slovenski standard je istoveten z: FprEN 14496

ICS:

| | | |
|-----------|---|--|
| 83.180 | Lepila | Adhesives |
| 91.100.10 | Cement. Mavec. Apno. Malta | Cement. Gypsum. Lime. Mortar |
| 91.100.60 | Materiali za toplotno in zvočno izolacijo | Thermal and sound insulating materials |

kSIST FprEN 14496:2016

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

FINAL DRAFT
FprEN 14496

January 2016

ICS 91.100.10; 91.120.10; 91.120.20

Will supersede EN 14496:2005

English Version

**Gypsum based adhesives for thermal/acoustic insulation
composite panels and gypsum boards - Definitions,
requirements and test methods**

Adhésifs à base de plâtre pour complexes d'isolation
thermique/acoustique en plaques de plâtre et isolant -
Définitions, exigences et méthodes d'essai

Kleber auf Gipsbasis für Verbundplatten zur Wärme-
und Schalldämmung und Gipsplatten - Begriffe,
Anforderungen und Prüfverfahren

This draft European Standard is submitted to CEN members for unique acceptance procedure. It has been drawn up by the Technical Committee CEN/TC 241.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

| Contents | Page |
|---|-------------|
| Foreword | 3 |
| 1 Scope | 4 |
| 2 Normative references | 4 |
| 3 Symbols and abbreviations | 4 |
| 3.1 Symbols and abbreviations | 4 |
| 4 Requirements | 5 |
| 4.1 Fire behaviour..... | 5 |
| 4.2 Bond strength..... | 5 |
| 4.3 Dangerous substances..... | 5 |
| 4.4 Calcium sulfate content..... | 5 |
| 4.5 End of utilisation time | 5 |
| 5 Test methods | 5 |
| 5.1 General..... | 5 |
| 5.2 Determination of the calcium sulfate content | 6 |
| 5.3 Determination of the water/adhesive ratio..... | 6 |
| 5.4 Preparation of the paste for the tests | 6 |
| 5.5 Determination of the end of utilisation time | 6 |
| 5.6 Determination of the bond strength | 7 |
| 6 Assessment and verification of constancy of performance – AVCP | 10 |
| 6.1 General..... | 10 |
| 6.2 Type testing..... | 10 |
| 6.3 Factory production control (FPC) | 11 |
| 7 Designation | 12 |
| 8 Marking, labelling and packaging | 13 |
| Annex A (informative) Sampling procedure for testing | 14 |
| A.1 General..... | 14 |
| A.2 Sampling procedure..... | 14 |
| Annex ZA (informative) Relationship of this European Standard with Regulation (EU) No.305/2011 | 15 |
| ZA.1 Scope and relevant characteristics..... | 15 |
| ZA.2 System of Assessment and Verification of Constancy of Performance (AVCP) | 15 |
| ZA.3 Assignment of AVCP tasks | 16 |
| Bibliography | 17 |

European foreword

This document (FprEN 14496:2016) has been prepared by Technical Committee CEN/TC 241 “Gypsum and gypsum based products”, the secretariat of which is held by AFNOR.

This document is currently submitted to the Unique Acceptance Procedure.

This document will supersede EN 14496:2005.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of Regulation (EU) No. 305/2011.

For relationship with Regulation (EU) No. 305/2011, see informative Annex ZA, which is an integral part of this document.

The main technical changes that have been made in this new edition of EN 14496 are the following:

- a) normative references have been updated;
- b) new clause symbols and abbreviations has been introduced;
- c) Annex ZA and Clause 6 have been revised to be in line with the Construction Products Regulation (CPR);
- d) document has been editorially revised.

1 Scope

This European standard specifies the characteristics and performances of gypsum based adhesives which are composed of gypsum plasters defined in EN 13279-1 and of additives. These adhesives are used for fixing to walls and partitions, gypsum board thermal/acoustic insulation composite panels according to EN 13950, gypsum plasterboard linings according to EN 520, gypsum boards with mat reinforcement according to EN 15283-1, gypsum fibre boards according to EN 15283-2 and other suitable products as reprocessed boards according to EN 14190 and cornices according to EN 14209. They assist in the construction of systems which provide thermal and acoustic performance.

It covers the following performance characteristics: reaction to fire, fire resistance and bond strength to be measured according to the corresponding European test methods.

It provides the assessment and verification of constancy of performance of the products.”

This standard covers also additional technical characteristics that are of importance for the use and acceptance of the product by the construction Industry and the reference tests for these characteristics.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 196-1:2005, *Methods of testing cement - Part 1: Determination of strength*

EN 13279-2:2014, *Gypsum binders and gypsum plasters - Part 2: Test methods*

EN 13501-1, *Fire classification of construction products and building elements — Part 1: Classification using test data from reaction to fire tests*

EN 13501-2, *Fire classification of construction products and building elements — Part 2: Classification using data from fire resistance tests, excluding ventilation services*

EN 13823, *Reaction to fire tests for building products — Building products excluding floorings exposed to the thermal attack by a single burning item*

3 Symbols and abbreviations

3.1 Symbols and abbreviations

Table 1 — Symbols and abbreviations

| Requirement | Sub-clause | Symbol or abbreviation |
|----------------------|------------|------------------------|
| Reaction to fire | 4.1 | R2F |
| Bond strength | 4.2 | F |
| Dangerous substances | 4.3 | DS |

4 Requirements

4.1 Fire behaviour

4.1.1 Reaction to fire

Gypsum building plaster is the main component of gypsum based adhesives. Therefore, gypsum based adhesives are classified A.1 (no contribution to fire) without testing when they contain less than 1 % by weight or volume (whichever is the more onerous) of organic material (Commission Decision 96/603/EEC as amended).

If they contain 1 % or more by weight or volume of organic material, they shall be determined and classified in accordance with EN 13501-1.

When testing in EN 13823 is required, gypsum based adhesives shall be tested in their end use conditions.

4.1.2 Fire resistance

NOTE Resistance to fire is a characteristic dependant on an assembled system and not of the product in isolation.

When required, the fire resistance of a system including gypsum based adhesives for thermal/acoustic insulation composite panels shall be determined and classified according to EN 13501-2.

4.2 Bond strength

The bond strength of the adhesive determined as described in 5.6 shall not be less than 0,06 MPa.

4.3 Dangerous substances

National regulations on dangerous substances may require verification and declaration on release, and sometimes content, when construction products covered by this standard are placed on those markets.

In the absence of European harmonized test methods, verification and declaration on release/content should be done taking into account national provisions in the place of use.

NOTE An informative database covering European and national provisions on dangerous substances is available at the Construction website on EUROPA accessed through:

<http://ec.europa.eu/enterprise/construction/cpd-ds/>

4.4 Calcium sulfate content

The calcium sulfate content of the powder as a percentage by mass of the product shall not be less than 30 % when calculated from the result of the test carried out in accordance with 5.2.

4.5 End of utilization time

The end of utilization time is determined as described in 5.5 shall be greater than the time declared by the producer.

5 Test methods

5.1 General

This standard describes the specific test methods for gypsum based adhesives for thermal/acoustic insulation composite panels and gypsum boards.

FprEN 14496:2016 (E)

General conditions of tests as well as test method which are common to gypsum plaster and gypsum based adhesives are described in EN 13279-2.

Those test methods which enable the requirements of this European Standard to be evaluated are given below; test methods for other properties, for example particle size, may be used by agreement.

5.2 Determination of the calcium sulfate content

Test method is described in 4.2 of EN 13279-2:2014.

5.3 Determination of the water/adhesive ratio

Test method is described in EN 13279-2:2014, 4.3.2.

5.4 Preparation of the paste for the tests

The paste used for the tests and for the preparation of test pieces is prepared as described in EN 13279-2:2014, 4.3.2.

5.5 Determination of the end of utilization time**5.5.1 Principle**

The depth of penetration of the conical penetrator (cone) into a gypsum based adhesive/water paste as the set progresses shall be measured.

5.5.2 Apparatus

- a) Vicat apparatus: see EN 13279-2:2014, Figures 2 and 3;
- b) conical penetrator (cone): see EN 13279-2:2014, Figure 4;
- c) glass plate: about 150 mm long and 150 mm wide;
- d) Vicat ring: see EN 13279-2:2014, 4.3.2.3 item b);
- e) straight edge: 140 mm length;
- f) chronometer;
- g) mixer and paddle: see EN 196-1:2005, 4.4 (description in Annex A).

5.5.3 Procedure

The Vicat ring shall be placed on the glass plate with the larger opening in contact with the glass plate. The gypsum based adhesive shall be mixed with the amount of water determined according to 5.3. The time at which the adhesive is first added to the water is noted t_0 . An excess of adhesive shall be transferred to the ring. Using a sawing motion the vertically held straight edge is used to strike off the excess material. Lower the cone to the surface of the adhesive using the spring plate of the release mechanism.

The guide bar shall be opened for testing using the release mechanism. The time between successive cone penetration should be not greater than $1/20$ of the utilization time. The cone shall be cleaned and dried between each penetration and there should be at least 12 mm between each penetration mark. The time at which the depth of penetration achieved (35 ± 2) mm above the glass plate shall be noted t_1 .