

SLOVENSKI STANDARD kSIST FprEN 14353:2016

01-marec-2016

Pomožni in dodatni kovinski profili za mavčne plošče - Definicije, zahteve in preskusne metode

Metal beads and feature profiles for use with gypsum plasterboards - Definitions, requirements and test methods

Hilfs- und Zusatzprofile aus Metall zur Verwendung mit Gipsplatten - Begriffe, Anforderungen und Prüfverfahren

Cornières et profilés métalliques pour plaques de plâtre - Définitions, exigences et méthodes d'essai

Ta slovenski standard je istoveten z: FprEN 14353

ICS:

91.100.10 Cement. Mavec. Apno. Malta Cement. Gypsum. Lime. Mortar

kSIST FprEN 14353:2016 en,fr,de

kSIST FprEN 14353:2016

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

FINAL DRAFT FprEN 14353

January 2016

ICS 91.100.10

Will supersede EN 14353:2007+A1:2010

English Version

Metal beads and feature profiles for use with gypsum plasterboards - Definitions, requirements and test methods

Cornières et profilés métalliques pour plaques de plâtre - Définitions, exigences et méthodes d'essai Hilfs- und Zusatzprofile aus Metall zur Verwendung mit Gipsplatten - Begriffe, Anforderungen und Prüfverfahren

This draft European Standard is submitted to CEN members for unique acceptance procedure. It has been drawn up by the Technical Committee CEN/TC 241.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning: This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

FprEN 14353:2016 (E)

Contents		Page
Euroj	European forewordIntroduction	
Intro		
1	Scope	
2	Normative references	
3	Terms, definitions, symbols and abbreviations	6
3.1	Terms and definitions	
3.2	Symbols and abbreviations	
4	Requirements	7
4.1	Reaction to fire	
4.2	Flexural strength (expressed as bending behaviour)	
4.3	Release of dangerous substances	
4.4	Additional technical requirements	
4.5	Protective coating	
4.6 4.7	Functional requirements Dimensions and tolerances	
4.7		
5	Test methods	
5.1	Sampling	
5.2	Dimensional measurements	
5.3	Profile dimensions	
5.4	Wing width	
5.5 5.6	Determination of expansion and movement	
5.6 5.7	Determination of breaking strength of paper tape Determination of bending behaviour	
6 6.1	Assessment and verification of constancy of performance — AVCP	17
6.2	GeneralType testing	
6.3	Factory production control (FPC)	
7	Designation	
8	Marking, labelling and packaging	20
Anne	x A (informative) Sampling procedure for testing	21
A.1	General	21
A.2	Sampling procedure	21
Anne	x ZA (informative) Relationship of this European Standard with Regulation (EU) No.305/2011	22
ZA.1	Scope and relevant characteristics	22
ZA.2	System of Assessment and Verification of Constancy of Performance (AVCP)	22
ZA.3	Assignment of AVCP tasks	
Rihlia	ography	25
	/ 🛌 × 🛊 / × · · · · · · · · · · · · · · · · · ·	

European foreword

This document (FprEN 14353:2016) has been prepared by Technical Committee CEN/TC 241 "Gypsum and gypsum based products", the secretariat of which is held by AFNOR.

This document is currently submitted to the Unique Acceptance Procedure.

This document will supersede EN 14353:2007+A1:2010.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of Regulation (EU) No. 305/2011.

For relationship with Regulation (EU) No. 305/2011, see informative Annex ZA, which is an integral part of this document.

The main technical changes that have been made in this new edition of EN 14353 are the following:

- a) Normative references have been updated;
- b) Annex ZA and Clause 6 have been revised to be in line with the Construction Products Regulation (CPR);
- c) document has been editorially revised.

FprEN 14353:2016 (E)

Introduction

Metal beads and feature profiles are produced in wide variety of sizes and shapes. They are cold formed from mild steel sheets with various protective coatings or extruded or cold formed from aluminium. Some of the beads are faced with paper tape to enable them to be jointed. The materials, design and mechanical properties make them particularly suitable to provide improved physical properties and/or enhanced decorative solutions to gypsum board assemblies.

Metal beads and feature profiles may be fixed by various methods to the gypsum board and may be featured self-finished, featured with decoration or concealed by finishing with jointing compounds to receive decoration.

1 Scope

This European Standard specifies the characteristics and performance of metal beads, metal beads combined with paper tape and metal feature profiles designed for use in systems made with gypsum plasterboards according to EN 520, gypsum boards with fibrous reinforcement according to EN 15283-1 and EN 15283-2 and products from secondary processing according to EN 14190, gypsum board thermal/acoustic insulation composite panels according to EN 13950 and prefabricated gypsum board panels with a cellular paperboard core according to EN 13915, intended to be used in building construction works. Metal beads and feature profiles, depending upon their material and type, can be featured without decoration, decorated or finished with jointing compounds to receive decoration.

It covers the following performance characteristics: reaction to fire and flexural strength (bending behaviour) to be measured according to the corresponding European test methods.

It provides the assessment and verification of constancy of performance of the products

This European Standard covers also additional technical characteristics that are of importance for the use and acceptance of the product by the construction industry and the reference tests for these characteristics.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 485-2, Aluminium and aluminium alloys - Sheet, strip and plate - Part 2: Mechanical properties

EN 485-4, Aluminium and aluminium alloys - Sheet, strip and plate - Part 4: Tolerances on shape and dimensions for cold-rolled products

EN 520, *Gypsum plasterboards* — *Definitions, requirements and test methods*

EN 10131, Cold rolled uncoated and zinc or zinc-nickel electrolytically coated low carbon and high yield strength steel flat products for cold forming - Tolerances on dimensions and shape

EN 10139, Cold rolled uncoated mild steel narrow strip for cold forming - Technical delivery conditions

EN 10140, Cold rolled narrow steel strip - Tolerances on dimensions and shape

EN 10143, Continuously hot-dip coated steel sheet and strip - Tolerances on dimensions and shape

EN 10152, Electrolytically zinc coated cold rolled steel flat products for cold forming - Technical delivery conditions

EN 10346, Continuously hot-dip coated steel flat products for cold forming - Technical delivery conditions

EN 13501-1, Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests

EN 13963, Jointing materials for gypsum boards - Definitions, requirements and test methods

EN 15283-1, Gypsum boards with fibrous reinforcement — Definitions, requirements and test methods — Part 1: Gypsum boards with mat reinforcement

FprEN 14353:2016 (E)

EN 15283-2, Gypsum boards with fibrous reinforcement — Definitions, requirements and test methods — Part 2: Gypsum fibre boards

EN ISO 1924-2, Paper and board - Determination of tensile properties - Part 2: Constant rate of elongation method (20 mm/min) (ISO 1924-2)

EN ISO 9227, Corrosion tests in artificial atmospheres - Salt spray tests (ISO 9227)

3 Terms, definitions, symbols and abbreviations

For the purposes of this document, the following terms, definitions, symbols and abbreviations apply.

3.1 Terms and definitions

3.1.1

metal bead

profiled narrow section formed in steel or aluminium with a cross section to suit its application

Note 1 to entry: Beads may incorporate a variety of profiles and one or more wings depending upon their function. The wings can be perforated or expanded to facilitate fixing using mechanical and/or jointing compound methods.

3.1.2

angle bead

profiled section used to enhance and protect external angles

3.1.3

edge bead

profiled section engaged to enclose and enhance and protect the edge of the gypsum board

3.1.4

feature bead

profiled section used to enhance the finish to the edge of the gypsum board

3.1.5

stop bead

profiled section used to provide a straight edge to receive the finish to the edge

3.1.6

corner tape

paper tape incorporating one or more metal or other strips to give added protection to external angles

3.1.7

profile

surface or edge with a cross section to suit the application

3.1.8

wing

area adjoining the bead face or edge, usually perforated or expanded, used for support or fixing

3.1.9

movement bead

profiled section, composed of three parts, with flexibility to allow movement in both its length and width