



SLOVENSKI STANDARD
SIST EN 12467:2013+A1:2016

01-september-2016

Nadomešča:
SIST EN 12467:2013

Vlaknato-cementne ravne plošče - Specifikacija za izdelek in preskusne metode

Fibre-cement flat sheets - Product specification and test methods

Faserzement-Tafeln - Produktspezifikation und Prüfverfahren

Plaques planes en fibres-ciment - Spécifications du produit et méthodes d'essai
iTeh STANDARD PREVIEW
(standards.iteh.ai)

Ta slovenski standard je istoveten z: EN 12467:2012+A1:2016

<https://standards.iteh.ai/catalog/standards/sist/8bfdfc31-359b-47af-a9fa-3d0914235761/sist-en-12467-2013a1-2016>

ICS:

91.100.40	Cementni izdelki, ojačani z vlakni	Products in fibre-reinforced cement
-----------	------------------------------------	-------------------------------------

SIST EN 12467:2013+A1:2016

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 12467:2013+A1:2016](#)

<https://standards.iteh.ai/catalog/standards/sist/8bfdfc31-359b-47af-a9fa-3d0914235761/sist-en-12467-2013a1-2016>

EUROPEAN STANDARD

EN 12467:2012+A1

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2016

ICS 91.100.40

Supersedes EN 12467:2012

English Version

Fibre-cement flat sheets - Product specification and test methods

Plaques planes en fibres-ciment - Spécifications du produit et méthodes d'essai

Faserzement-Tafeln - Produktspezifikation und Prüfverfahren

This European Standard was approved by CEN on 4 August 2012 and includes Amendment 1 approved by CEN on 24 November 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions.....	6
4 Symbols and abbreviations.....	8
5 Requirements.....	9
5.1 General.....	9
5.1.1 Composition.....	9
5.1.2 Appearance and finish.....	9
5.2 Classification.....	9
5.2.1 General.....	9
5.2.2 Category A.....	9
5.2.3 Category B.....	10
5.2.4 Category C.....	10
5.2.5 Category D.....	10
5.2.6 Groups of sizes.....	10
5.3 Dimensions and tolerances.....	10
5.3.1 General.....	10
5.3.2 Nominal length and width.....	10
5.3.3 Thickness.....	10
5.3.4 Tolerances on nominal dimensions.....	11
5.3.5 Tolerances on shape.....	12
5.4 Physical requirements and characteristics.....	12
5.4.1 General.....	12
5.4.2 Apparent density.....	12
5.4.3 Moisture movement.....	12
5.4.4 Mechanical characteristics – Bending strength (<i>MOR</i>) – Modulus of elasticity (<i>MOE</i>).....	13
5.4.5 Water impermeability for Categories A, B and D.....	13
5.4.6 Water vapour permeability for Category D.....	13
5.5 Durability requirements.....	14
5.5.1 General.....	14
5.5.2 Freeze-thaw for Categories A, B and D.....	14
5.5.3 Heat-rain for Categories A and B.....	14
5.5.4 Warm water for Categories A, B, C and D.....	14
5.5.5 Soak-dry for Categories A, B, C and D.....	14
5.6 Fire and safety.....	14
5.6.1 Reaction to fire.....	14
5.6.2 Release of dangerous substances.....	14
5.7 Product information.....	15
6 Ⓐ Assessment and verification of constancy of performance — AVCP.....	15
6.1 General.....	15
6.2 Type testing.....	15
6.2.1 General.....	15
6.2.2 Test samples, testing and compliance criteria.....	17
6.2.3 Test reports.....	17

6.3	Factory production control (FPC).....	17
6.3.1	General	17
6.3.2	Requirements.....	17
6.3.3	Product specific requirements	20
6.3.4	Initial inspection of factory and of FPC.....	20
6.3.5	Continuous surveillance of FPC	21
6.3.6	Procedure for modifications.....	21
6.4	Inspection of a consignment of finished products $\langle A_1 \rangle$	21
7	Test methods.....	21
7.1	General	21
7.2	Dimensional and geometrical tests.....	21
7.2.1	Preparation of specimen.....	21
7.2.2	Apparatus	22
7.2.3	Procedure	22
7.2.4	Expression and interpretation of results.....	24
7.3	Tests for physical performance and characteristics.....	25
7.3.1	Apparent density	25
7.3.2	Mechanical characteristics - Bending strength - Modulus of elasticity (Bending modulus).....	25
7.3.3	Water impermeability	30
7.3.4	Water vapour permeability	31
7.3.5	Warm water	31
7.3.6	Soak-dry	32
7.3.7	Moisture movement test	33
7.4	Tests for climatic performance	33
7.4.1	Freeze-thaw	33
7.4.2	Heat-rain.....	35
7.5	Test for reaction to fire performance.....	36
7.5.1	Sheets satisfying the requirements for the fire reaction Class A1 without the need for testing	36
7.5.2	Other sheets.....	36
8	Marking, labelling and packaging.....	44
Annex A	(normative) Consignment inspection sampling.....	45
Annex B	(normative) Statistical method for determining the corresponding wet values or revised dry specifications for the <i>MOR</i> when carrying out the dry method of test or when tested prior to coating for quality control purposes	46
B.1	Procedure	46
B.2	Determination of the correlation between the results of testing wet and dry specimens.....	46
B.3	Determination of the regression line	47
B.4	Determination of a value for wet testing from an obtained value for dry testing	47
B.5	Determination of the minimum value specified for dry testing x_{std} corresponding to the minimum value specified for wet testing in this document y_{std}	48
Annex C	(normative) Test method for the determination of moisture movement characteristic of fibre-cement sheets.....	49
C.1	General	49
C.2	Principle.....	49
C.3	Apparatus	49
C.4	Specimen preparation	49
C.5	Test procedure	49
C.6	Calculation of results.....	50
C.7	Test report	50

EN 12467:2012+A1:2016 (E)

Annex ZA (informative) A1 Clauses of this European Standard addressing the provisions of the EU Construction Products Regulation	51
ZA.1 Scope and relevant characteristics.....	51
ZA.2 Procedure for AVCP of fibre cement flat sheets.....	52
ZA.2.1 Systems of AVCP.....	52
ZA.2.2 Declaration of performance (DoP)	56
ZA.3 CE marking and labelling A1	60
Bibliography.....	63

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 12467:2013+A1:2016](https://standards.iteh.ai/catalog/standards/sist/8bfdfc31-359b-47af-a9fa-3d0914235761/sist-en-12467-2013a1-2016)

<https://standards.iteh.ai/catalog/standards/sist/8bfdfc31-359b-47af-a9fa-3d0914235761/sist-en-12467-2013a1-2016>

European foreword

This document (EN 12467:2012+A1:2016) has been prepared by Technical Committee CEN/TC 128 “Roof covering products for discontinuous laying and products for wall cladding”, the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2017, and conflicting national standards shall be withdrawn at the latest by April 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1 approved by CEN on 24 November 2015.

This document supersedes A1 EN 12467:2012 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

A1 In comparison with EN 12467:2004, the following sections in EN 12467:2012 had been changed or added: A1 3.9, 3.10, 4, 5.1.1, 5.4.3, 5.4.4, Table 7, Table 8, 7.3.2, 7.3.2.4.2, 7.3.3.3, 7.3.3.4, 7.3.7, 7.5.2.2 and Annex C. Annex ZB concerning the EC Directive 76/769/EEC A1 had been deleted A1.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of A1 EU Regulation No 305/2011 A1. <https://standards.iteh.ai/catalog/standards/sist/8bdfd31-359b-47af-a9fa-3d0914235761/sist-en-12467-2013a1-2016>

For relationship with A1 EU Regulation No 305/2011 A1, see informative Annex ZA, which is an integral part of this document.

A distinction A1 had been made A1 between product appraisal (type tests) and factory production control requirements (acceptance tests).

The performance of a building part constructed with these sheets depends not only on the properties of the product as required by this document, but also on the design, construction and installation of the component as a whole in relation to the environment and conditions of use.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 12467:2012+A1:2016 (E)**1 Scope**

This European Standard specifies the technical requirements and establishes methods of inspection and test as well as acceptance conditions for fibre-cement flat sheets, siding shingles and planks (referred to as sheets later in this document) for one or more of the following uses:

- internal wall and ceiling finishes;
- external wall and ceiling finishes.

Products covered by this European Standard can be used for other purposes provided they comply with the relevant application standard, e.g. rigid underlays.

This European Standard covers sheets reinforced with fibres of different types as specified in 5.1.1.

This European Standard does not cover sheets for fire protection purposes.

This European Standard does not include calculations with regard to works, design requirements, installation techniques, wind uplift or rain proofing of the installed sheets.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 197-1, *Cement — Part 1: Composition, specifications and conformity criteria for common cements*

EN 13501-1, *Fire classification of construction products and building elements — Part 1: Classification using test data from reaction to fire tests*

EN 13823, *Reaction to fire tests for building products — Building products excluding floorings exposed to the thermal attack by a single burning item*

EN ISO 1716, *Reaction to fire tests for building products — Determination of the gross heat of combustion (calorific value) (ISO 1716)*

EN ISO 12572, *Hygrothermal performance of building materials and products — Determination of water vapour transmission properties (ISO 12572)*

ISO 2602, *Statistical interpretation of test results — Estimation of the mean — Confidence interval*

ISO 2859-1, *Sampling procedures for inspection by attributes — Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection*

ISO 3951-1, *Sampling procedures for inspection by variables — Part 1: Specification for single sampling plans indexed by acceptance quality limit (AQL) for lot-by-lot inspection for a single quality characteristic and a single AQL*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1**acceptance test**

test to establish whether a batch of sheets conforms to a specification and which is performed on samples drawn either from continuous production or from a consignment

Note 1 to entry: Test methods, specifications and limit values are specified in this document. Sampling levels and acceptance criteria are specified in 6.3.2.

3.2**initial type test**

test carried out to demonstrate conformity with the requirements of this document or for the approval of a new product and/or when a fundamental change is made in formulation and/or method of manufacture, the effects of which cannot be predicted on the basis of previous experience

Note 1 to entry: The test is performed on the as delivered product, but is not required for each production batch.

3.3**acceptable quality level (AQL)**

quality level which in a sampling plan corresponds to a specified, relatively high probability of acceptance

Note 1 to entry: It is the maximum percent defective (or maximum number of defects per 100 units) that for purposes of sampling inspection can be considered satisfactory as a process average.

Note 2 to entry: A sampling scheme with an AQL of 4 % means that batches containing up to 4 % defective items have a high probability of acceptance.

3.4**apparent density**

density based on the external dimensions of the sample to calculate the volume

Note 1 to entry: This is an average density of material and pores.

3.5**as delivered**

same condition as the producer intends to supply the product after completing all aspects of the process including maturing and, when appropriate, painting

3.6**upper face**

face normally exposed

3.7**under face**

reverse of upper face

3.8**textured sheets**

sheets which have a relief pattern embossed or applied as a coating on their upper face before delivery

3.9**NT**

type of fibre-cement flat sheets which cover products made using a non-asbestos technology

EN 12467:2012+A1:2016 (E)

3.10

ambient laboratory conditions

ambient laboratory conditions which are a temperature of $(23 \pm 5) ^\circ\text{C}$ and a relative humidity of $(50 \pm 20) \%$

4 Symbols and abbreviations

a	nominal length or width of the sheet
b	1. dimension of the specimen (length or width) measured parallel to the test machine supports, in millimetres 2. one of the coefficients of the regression line (see Annex B)
d	apparent density of the sheet in grams per cubic centimetre
e	thickness of the sheet, in millimetres
F	breaking load, in newtons
l	length, in millimetres
l_s	span between the centres of the test machine supports in the bending strength test, in millimetres
m	mass of the specimen after drying, in grams
n	number of paired specimens
MOE	modulus of elasticity, in Gigapascals or megapascals
MOR	modulus of rupture, in megapascals
MOR_{fi}	modulus of rupture of the i^{th} exposed specimen after the type test
MOR_{fci}	modulus of rupture of the i^{th} unexposed reference specimen
MR_i	individual ratio of the modulus of rupture of the i^{th} pair of exposed and unexposed specimens
R	average ratio of the modulus of rupture of exposed and unexposed specimens
R_L	lower estimate of the mean of the ratios at 95 % confidence level of the modulus of rupture of exposed and unexposed specimens
s	standard deviation of the values in the appropriate calculation
μ	water vapour resistance value
V	volume of the specimen, in cubic centimetres
w	width, in millimetres
x_i	individual value of the i^{th} specimen tested dry
x_{std}	minimum value to be used as the specification for the dry method of test. This value is calculated at the 97,5 % lower confidence level from the value specified for the wet method of test in this document (see B.5)
y_{std}	minimum value specified in the standard for wet testing (see B.5)
x_0	actual result obtained when dry testing (see B.4)
\bar{x}	mean of the values of x_i for $i = 1$ to n
y_i	individual value of the i^{th} specimen tested wet

y_0	value calculated from the value obtained from a specimen tested dry, which is the estimate at the 97,5 % lower confidence level of the value expected from a specimen tested wet (see B.4)
\bar{y}	mean of the values of y_i for $i = 1$ to n

5 Requirements

5.1 General

5.1.1 Composition

Sheets shall consist essentially of cement or a calcium silicate formed by a chemical reaction of a siliceous and a calcareous material, reinforced by fibres. The cement shall comply with EN 197-1 or with technical specifications relevant in the country of use.

This European Standard covers fibre-reinforced cement flat sheets of type NT. The reinforcing fibres shall be one or more of the following forms:

- discrete elements randomly dispersed;
- continuous strands or tapes;
- nets or webs.

Process aids, fillers, aggregates and pigments may be added.

5.1.2 Appearance and finish

The exposed face of the sheets can be with or without texture. The sheets can be coloured or left in their natural colour. The sheets can also receive adherent coloured or uncoloured coatings on their surface. Variations of the surface appearance which do not impair the fitness for purpose of the sheets are permitted.

The sheets may be supplied with holes for fixing and/or cut to size.

5.2 Classification

5.2.1 General

Sheets covered by this document are divided into:

- four categories in accordance with their weather resistance (see 5.2.2 to 5.2.5);
- five classes in accordance with their bending strength (see 5.4.3);
- two groups of sizes in accordance with their method of installation (see 5.2.6);
- two levels in accordance with their dimensional tolerances (see 5.3.4).

Type tests for each category are specified in Table 7.

5.2.2 Category A

Sheets which are intended for applications where they may be subjected to heat, high moisture and severe frost.

EN 12467:2012+A1:2016 (E)**5.2.3 Category B**

Sheets which are intended for applications where they may be subjected to heat, moisture and occasional frost, e.g. where they are either protected from or not subjected to severe weathering conditions.

5.2.4 Category C

Sheets which are intended for internal applications, where they may be subjected to heat and moisture, but not to frost.

5.2.5 Category D

Sheets for rigid underlayer applications.

5.2.6 Groups of sizes**5.2.6.1 Small size sheets**

Sheets for which the method of installation includes horizontal overlap. Their dimensions are generally such that their area is $< 0,4 \text{ m}^2$ and have a length/width relation ≤ 3 .

5.2.6.2 Large size sheets

Sheets which do not correspond to indicators for small size sheets. Large sheets may be declared as "small size sheets" provided tolerances for small size sheets apply and are specified in the manufacturer's literature.

5.3 Dimensions and tolerances

SIST EN 12467:2013+A1:2016

5.3.1 General

<https://standards.iteh.ai/catalog/standards/sist/8bdfc31-359b-47af-a9fa-3d0914235761/sist-en-12467-2013a1-2016>

There are two levels of tolerances for length, width, straightness and squareness of edges. Sheets shall comply with the requirements of the same level for the four sets of tolerances.

5.3.2 Nominal length and width

The manufacturer shall specify the nominal length and width of the sheets.

NOTE Sheets are normally available in nominal lengths up to 3 000 mm and nominal width up to 1 250 mm. Greater nominal lengths and widths can be supplied.

5.3.3 Thickness

The manufacturer shall specify the nominal thickness of the sheets.

For non-textured sheets, the nominal thickness refers to the average thickness. For textured sheets, the nominal thickness refers to the maximum thickness.

NOTE 1 The nominal thickness of textured sheets cannot be used for the calculation of mechanical performance.

Sheets are normally available in thickness from 3 mm to 30 mm.

NOTE 2 Thicker sheets can be supplied.

5.3.4 Tolerances on nominal dimensions¹⁾

5.3.4.1 Tolerances on length and width

Tolerances on length and width shall be in accordance with Table 1, for the appropriate level.

Table 1 — Tolerances on nominal dimensions in accordance with value and level

Nominal dimension a^a	Level I	Level II
$a \leq 600$ mm	± 3 mm	± 4 mm
600 mm $< a \leq 1\ 000$ mm	± 3 mm	± 5 mm
$1\ 000$ mm $< a \leq 1\ 600$ mm	$\pm 0,3\%$ a	$\pm 0,5\%$ a
$1\ 600$ mm $< a$	± 5 mm	± 8 mm
^a a is the nominal width or length.		

These tolerances are not applicable to oversize sheets.

The method of measurement is given in 7.2.3.1.

5.3.4.2 Tolerances on thickness

For non-textured sheets, tolerances shall be in accordance with Table 2.

Table 2 — Tolerances on thickness for non-textured sheets

$e \leq 6$ mm	$\pm 0,6$ mm
6 mm $< e \leq 20$ mm	$\pm 10\%$ e
$e > 20$ mm	± 2 mm

For sheets without texture, the maximum difference between extreme values of the thickness measurements within one sheet shall not exceed 10 % of the maximum measured value.

For textured sheets, tolerances shall be in accordance with Table 3.

Table 3 — Tolerances on thickness for textured sheets

$e \leq 6$ mm	- 0,6 mm + 0,9 mm
6 mm $< e \leq 20$ mm	- 10 % e + 15 % e
$e > 20$ mm	- 2 mm + 3 mm

For textured sheets, the maximum difference between extreme values of the eight thickness measurements within one sheet shall not exceed 15 % of the maximum measured value.

The method of measurement is given in 7.2.3.2.

1) For certain applications, tighter tolerances could be demanded.

EN 12467:2012+A1:2016 (E)

5.3.5 Tolerances on shape²⁾

5.3.5.1 Straightness of edges

Tolerances are applicable only to large size sheets.

The tolerances on the straightness of edges are defined as a percentage of the length of the edge of the relevant dimensions (length or width), and shall be in accordance with Table 4 for the appropriate level.

Table 4 — Tolerances on straightness of edges

Level I	Level II
0,1 %	0,3 %

The method of measurement is given in 7.2.3.3. These tolerances are not applicable for oversize sheets.

5.3.5.2 Squareness of edges

The tolerances on squareness of sheets shall be in accordance with Table 5 for the appropriate level.

Table 5 — Tolerances on squareness of edges

Level I	Level II
2 mm/m	4 mm/m

The method of measurement is given in 7.2.3.4.

These tolerances are not applicable for oversize sheets.

5.4 Physical requirements and characteristics

5.4.1 General

Mechanical and material properties are normally determined on sheets as delivered. The results shall be identified as applying to coated or uncoated material.

NOTE See Annex B for statistic interpretation.

5.4.2 Apparent density

The manufacturer shall specify in his literature the minimum apparent density for each category and each class of sheet. When tested in accordance with the method specified in 7.3.1, the density shall be not less than this value.

5.4.3 Moisture movement

The manufacturer's literature shall state the percentage value of linear sheet moisture movement measured when the sheet is exposed to a relative humidity change from 30 % to 90 %. The stated value shall be determined in accordance with 7.3.7 using the test method given in Annex C.

2) For certain applications, tighter tolerances are demanded and should be agreed on between the manufacturer and the purchaser.

5.4.4 Mechanical characteristics – Bending strength (*MOR*) – Modulus of elasticity (*MOE*)

When tested as specified in 7.3.2, the minimum modulus of rupture of the sheets, expressed in megapascals, shall be as specified in Table 6. The *MOR* shall be the average of the values obtained from testing the samples in both directions.

NOTE For non-homogeneous e.g. coated sheets, Table 6 refers to the apparent *MOR*.

Category A and B sheet strengths are specified in the wet condition (see Table 10).

Category C and D sheet strengths are specified in the ambient condition (see Table 10).

The manufacturer shall specify the characteristic value for mechanical strength. Characteristic values of bending strength are based on statistical data on results of tests in ambient conditions. The statistical interpretation of test results is based on the procedure prescribed in EN 1990:2002, *Eurocode — Basis of structural design*, Table D.1, $V_{x, \text{unknown}}$).

If a correlation has been established (see Annex B) between the *MOR* from production control and the *MOR* from products as delivered, the *k*-value of $V_{x, \text{known}}$ can be used. The minimum modulus of rupture of the sheets in the weaker direction shall be not less than 70 % of the specified value in Table 6 for the average of the two directions. This requirement does not apply to textured sheets.

The modulus of elasticity of the sheets, expressed in Giga- or Megapascals, shall be specified on test results of tests in ambient conditions. The *MOE* shall be the average of the values obtained from testing the sampling in both directions with indication of the standard deviation.

It is up to the manufacturer to determine the *MOE* for information purposes, i.e. with type testing.

Table 6 — Minimum modulus of rupture (*MOR*)

min. <i>MOR</i> in the wet condition MPa		min. <i>MOR</i> in the ambient laboratory conditions MPa	
<i>Classes</i>	Category A & B	<i>Classes</i>	Category C & D
1	4	1	4
2	7	2	7
3	13	3	10
4	18	4	16
5	24	5	22

Where manufacturers state minimum product *MOR* this should be at the 4 % acceptable quality level (AQL).

NOTE For textured sheets, the *MOR* cannot be used for calculating mechanical performance.

5.4.5 Water impermeability for Categories A, B and D

When tested in accordance with 7.3.3, traces of moisture may appear on the under face of the sheet, but in no instance shall there be any formation of drops of water.

5.4.6 Water vapour permeability for Category D

For flat sheets used as rigid underlays, the water vapour resistance value μ shall be determined according to 7.3.4 and shall be specified in the manufacturer's literature.

The μ value obtained from the test shall not be higher than the value specified by the manufacturer.