



SLOVENSKI STANDARD SIST EN ISO 11357-1:2016

01-december-2016

Nadomešča:

SIST EN ISO 11357-1:2010

Polimerni materiali - Diferenčna dinamična kalorimetrija (DSC) - 1. del: Splošna načela (ISO 11357-1:2016)

Plastics - Differential scanning calorimetry (DSC) - Part 1: General principles (ISO 11357-1:2016)

Kunststoffe - Dynamische Differenz-Thermoanalyse (DSC) - Teil 1: Allgemeine Grundlagen (ISO 11357-1:2016)

Plastiques - Analyse calorimétrique différentielle (DSC) - Partie 1: Principes généraux (ISO 11357-1:2016) <https://standards.iteh.ai/catalog/standards/sist/75a63c46-6c9f-467e-b14f-632112346e70/sist-en-iso-11357-1-2016>

Ta slovenski standard je istoveten z: EN ISO 11357-1:2016

ICS:

17.200.10	Toplota. Kalorimetrija	Heat. Calorimetry
83.080.01	Polimerni materiali na splošno	Plastics in general

SIST EN ISO 11357-1:2016

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11357-1:2016](https://standards.iteh.ai/catalog/standards/sist/75a63c46-6c9f-467e-b14f-632112346e70/sist-en-iso-11357-1-2016)

<https://standards.iteh.ai/catalog/standards/sist/75a63c46-6c9f-467e-b14f-632112346e70/sist-en-iso-11357-1-2016>

EUROPEAN STANDARD

EN ISO 11357-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2016

ICS 83.080.01

Supersedes EN ISO 11357-1:2009

English Version

Plastics - Differential scanning calorimetry (DSC) - Part 1: General principles (ISO 11357-1:2016)

Plastiques - Analyse calorimétrique différentielle (DSC)
- Partie 1: Principes généraux (ISO 11357-1:2016)

Kunststoffe - Dynamische Differenz-Thermoanalyse
(DSC) - Teil 1: Allgemeine Grundlagen (ISO 11357-
1:2016)

This European Standard was approved by CEN on 13 August 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 11357-1:2016
<https://standards.iteh.ai/catalog/standards/sist/75a63c46-6c9f-467e-b14f-632112346e70/sist-en-iso-11357-1-2016>

European foreword

This document (EN ISO 11357-1:2016) has been prepared by Technical Committee ISO/TC 61 “Plastics” in collaboration with Technical Committee CEN/TC 249 “Plastics” the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2017, and conflicting national standards shall be withdrawn at the latest by April 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11357-1:2009.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

STANDARD PREVIEW

(standards.iteh.ai)

Endorsement notice

The text of ISO 11357-1:2016 has been approved by CEN as EN ISO 11357-1:2016 without any modification.

SIST EN ISO 11357-1:2016
<https://standards.iteh.ai/catalog/standards/sist/75a63c46-6c9f-467e-b14f-632112346e70/sist-en-iso-11357-1-2016>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11357-1:2016](#)

<https://standards.iteh.ai/catalog/standards/sist/75a63c46-6c9f-467e-b14f-632112346e70/sist-en-iso-11357-1-2016>

INTERNATIONAL
STANDARD

ISO
11357-1

Third edition
2016-09-15

**Plastics — Differential scanning
calorimetry (DSC) —**

**Part 1:
General principles**

Plastiques — Analyse calorimétrique différentielle (DSC) —

Partie 1: Principes généraux
iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 11357-1:2016

<https://standards.iteh.ai/catalog/standards/sist/75a63c46-6c9f-467e-b14f-632112346e70/sist-en-iso-11357-1-2016>



Reference number
ISO 11357-1:2016(E)

© ISO 2016

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 11357-1:2016

<https://standards.iteh.ai/catalog/standards/sist/75a63c46-6c9f-467e-b14f-632112346e70/sist-en-iso-11357-1-2016>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Basic principles	8
4.1 General.....	8
4.2 Heat-flux DSC.....	8
4.3 Power-compensation DSC.....	8
5 Apparatus and materials	9
6 Specimen	10
7 Test conditions and specimen conditioning	11
7.1 Test conditions.....	11
7.2 Conditioning of specimens.....	11
8 Calibration	11
8.1 General.....	11
8.2 Calibration materials.....	12
8.3 Temperature calibration.....	12
8.3.1 General.....	12
8.3.2 Procedure.....	12
8.3.3 Accuracy of calibration.....	13
8.4 Heat calibration.....	13
8.4.1 General.....	13
8.4.2 Procedure.....	14
8.4.3 Accuracy of calibration.....	14
8.5 Heat flow rate calibration.....	15
8.5.1 General.....	15
8.5.2 Procedure.....	15
9 Procedure	17
9.1 Setting up the apparatus.....	17
9.1.1 Switching on.....	17
9.1.2 Purge gas.....	17
9.1.3 Experimental conditions.....	17
9.1.4 Baseline determination.....	17
9.2 Loading the specimen into the crucible.....	17
9.2.1 General.....	17
9.2.2 Selection of crucibles.....	18
9.2.3 Weighing the specimen crucible.....	18
9.2.4 Loading the specimen.....	18
9.2.5 Determination of the mass of the specimen.....	18
9.3 Insertion of crucibles into the instrument.....	18
9.4 Performing measurements.....	18
9.4.1 General.....	18
9.4.2 Scanning mode.....	18
9.4.3 Isothermal mode.....	19
9.5 Post-run checks.....	20
9.5.1 Check for loss in mass.....	20
9.5.2 Inspection of specimens.....	20
9.5.3 Checking of crucibles and crucible holder.....	20
10 Test report	20

ISO 11357-1:2016(E)

Annex A (normative) Extended, high-precision, temperature calibration ^[12]	22
Annex B (normative) Extended, high-precision, heat calibration	24
Annex C (informative) Recommended calibration materials	26
Annex D (informative) Interaction of calibration materials with different crucible materials	29
Annex E (informative) General recommendations	31
Bibliography	33

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11357-1:2016](https://standards.iteh.ai/catalog/standards/sist/75a63c46-6c9f-467e-b14f-632112346e70/sist-en-iso-11357-1-2016)

<https://standards.iteh.ai/catalog/standards/sist/75a63c46-6c9f-467e-b14f-632112346e70/sist-en-iso-11357-1-2016>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*

This third edition cancels and replaces the second edition (ISO 11357-1:2009), 3.7.2 of which has been technically revised.

ISO 11357 consists of the following parts, under the general title *Plastics — Differential scanning calorimetry (DSC)*:

- *Part 1: General principles*
- *Part 2: Determination of glass transition temperature and glass transition step height*
- *Part 3: Determination of temperature and enthalpy of melting and crystallisation*
- *Part 4: Determination of specific heat capacity*
- *Part 5: Determination of characteristic reaction-curve temperatures and times, enthalpy of reaction and degree of conversion*
- *Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT)*
- *Part 7: Determination of crystallization kinetics*

ISO 11357-1:2016(E)**Introduction**

ISO 11357 describes thermoanalytical DSC test methods which can be used for quality assurance purposes, for routine checks of raw materials and finished products or for the determination of comparable data needed for data sheets or databases. The procedures given in ISO 11357 apply as long as product standards or standards describing special atmospheres for conditioning of specimens do not specify otherwise.

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

[SIST EN ISO 11357-1:2016](https://standards.iteh.ai/catalog/standards/sist/75a63c46-6c9f-467e-b14f-632112346e70/sist-en-iso-11357-1-2016)

<https://standards.iteh.ai/catalog/standards/sist/75a63c46-6c9f-467e-b14f-632112346e70/sist-en-iso-11357-1-2016>

Plastics — Differential scanning calorimetry (DSC) —

Part 1: General principles

SAFETY STATEMENT — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any regulatory requirements.

1 Scope

ISO 11357 specifies several differential scanning calorimetry (DSC) methods for the thermal analysis of polymers and polymer blends, such as

- thermoplastics (polymers, moulding compounds and other moulding materials, with or without fillers, fibres or reinforcements),
- thermosets (uncured or cured materials, with or without fillers, fibres or reinforcements), and
- elastomers (with or without fillers, fibres or reinforcements).

ISO 11357 is intended for the observation and measurement of various properties of, and phenomena associated with, the above-mentioned materials, such as

- physical transitions (glass transition, phase transitions such as melting and crystallization, polymorphic transitions, etc.),
- chemical reactions (polymerization, crosslinking and curing of elastomers and thermosets, etc.),
- the stability to oxidation, and
- the heat capacity.

This part of ISO 11357 specifies a number of general aspects of differential scanning calorimetry, such as the principle and the apparatus, sampling, calibration and general aspects of the procedure and test report common to all following parts.

Details on performing specific methods are given in subsequent parts of ISO 11357 (see Foreword).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 80000-5, *Quantities and units — Part 5: Thermodynamics*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472 and ISO 80000-5 and the following apply.