



Designation: ~~C1071-00~~ Designation: **C 1071 – 05<sup>ε1</sup>**

## Standard Specification for Fibrous Glass Duct Lining Insulation (Thermal and Sound Absorbing Material)<sup>1</sup>

This standard is issued under the fixed designation C 1071; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

---

<sup>ε1</sup> NOTE—Sections 2.2 and 12.9 were editorially updated in June 2008.

---

### 1. Scope

1.1 This specification covers fibrous glass insulation used as a thermal and sound absorbing liner for interior surfaces of ducts, plenums, and other air handling equipment that handle air up to 250°F (121°C).

1.2 The values stated in inch-pound units are the standard. The SI values in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

C 167 Test Methods for Thickness and Density of Blanket or Batt Thermal Insulations

C 168 ~~Terminology Relating to Thermal Insulating Materials<sup>2</sup>~~ Terminology Relating to Thermal Insulation

C 177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus

C 390 ~~Criteria Practice for Sampling and Acceptance of Preformed Thermal Insulation Lots~~

C 411 Test Method for Hot-Surface Performance of High-Temperature Thermal Insulation

C 423 Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method

C 518 ~~Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus~~

C 665 Specification for Mineral-Fiber Blanket Thermal Insulation for Light Frame Construction and Manufactured Housing

C 1104/C 1104M Test Method for Determining the Water Vapor Sorption of Unfaced Mineral Fiber Insulation

C 1114 Test Method for Steady-State Thermal Transmission Properties by Means of the Thin-Heater Apparatus

C 1304 Test Method for Assessing the Odor Emission of Thermal Insulation Materials

C 1338 Test Method for Determining Fungi Resistance of Insulation Materials and Facings

E 84 Test Method for Surface Burning Characteristics of Building Materials

E 795 ~~Practices for Mounting Test Specimens During Sound Absorption Tests<sup>2</sup>~~ Practices for Mounting Test Specimens During Sound Absorption Tests

E 2231 Practice for Specimen Preparation and Mounting of Pipe and Duct Insulation Materials to Assess Surface Burning Characteristics

G 21 Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi

G 22 Practice for Determining Resistance of Plastics to Bacteria

#### 2.2 Other Standards:

NAIMA Fibrous Glass Duct Liner Standard<sup>3</sup>

---

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.23 on Blanket and Loose Fill Insulation.

Current edition approved Dec. 10, 2000. Published January 2001. Originally published as C1071-86. Last previous edition C1071-98.

Current edition approved April 1, 2005. Published April 2005. Originally approved in 1986. Last previous edition approved in 2000 as C 1071 – 00.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards*, Vol 04.06, volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 04.07.

<sup>3</sup> Available from North American Insulation Manufacturers Association, 44 Canal Center Plaza, Suite 310, Alexandria, VA 22314.

SMACNA HVAC Duct Construction Standards <sup>4</sup>

UL 723 Test for Surface Burning Characteristics of Building Materials <sup>5</sup>

NFPA 255 Standard—Method of Test of Surface Burning Characteristics of Building Materials <sup>6</sup>

NFPA 259 Standard—Test Method for Potential Heat of Building Materials <sup>6</sup>

~~CAN/ULC-S102-M88 Standard~~ CAN/ULC-S102 Method of Test for Surface Burning Characteristics of Building Materials and Assemblies <sup>7</sup>

### 3. Terminology

3.1 For definitions of terms used in this specification, see Terminology C 168.

### 4. Classification

4.1 The insulation covered by this specification shall be of the following types:

4.1.1 *Type I*—Blanket in roll form up to 200 ft (61 m) in length, 36 to 72 in. (914 to 1829 mm) in width, and thicknesses of ½ to 3 in. (13 to 76 mm), in ½-in. (13-mm) increments.

4.1.2 *Type II*—Board in sheet form, up to 120 in. (3048 mm) in length, up to 48 in. (1219 mm) in width, and thicknesses of ½ to 3 in. (13 to 76 mm) in ½-in. (13-mm) increments.

### 5. Ordering Information

5.1 Purchasers ~~should~~shall select the preferred options permitted herein and include the following information in procurement documents:

5.1.1 Title, designation, and year of this specification.

5.1.2 Type of insulation (see 4.1).

5.1.3 Length, width, and thickness required (see 4.1).

5.1.4 Packaging required (see 16.1).

5.1.5 Marking required (see 16.2 and 16.3).

5.1.6 ~~Material weight should be obtained from supplier.~~

### 6. Materials and Manufacture

6.1 *Basic Material*— The basic material shall be made from glass processed from the molten state into fibrous form with a binder added to form dimensionally stable insulation. Asbestos shall not be used as an ingredient or component part of the product.

6.2 *Air Stream Surface*—Depending on the insulation surface characteristics and service air velocity, the air stream surface ~~may~~be plain or coated with a temperature resistant coating or faced with a plain or coated fibrous mat or fabric.

### 7. Physical Requirements

7.1 *Corrosiveness*— When tested in accordance with 12.3, the ~~metal plate~~steel plates in contact with the ~~back side (non-air surface side)~~both sides of the insulation shall show no corrosion greater than the comparative plates in contact with sterile cotton which has been tested in the same manner.

7.2 *Water Vapor Sorption*—When tested in accordance with 12.4, the water vapor sorption of the insulation shall not be more than 3 % by weight.

7.3 *Fungi Resistance*— When tested in accordance with 12.5, the insulation shall be observed as having no fungal growth.

7.4 *Temperature Resistance*—When tested in accordance with 12.6, the air stream surface shall have no evidence of flaming, glowing, smoldering, visible smoke, or delamination, cracking, deformation or reduction in thickness.

7.5 *Erosion Resistance*—When tested in accordance with 12.7, the insulation shall not break away, crack, peel, flake off, or show evidence of delamination or continued erosion when air is passed through typical duct sections at a velocity specified in 12.7.

7.6 *Odor Emission*— When tested in accordance with 12.8, a detectable odor of objectionable nature recorded by more than two of the five panel members shall constitute failure of the material.

7.7 *Surface Burning Characteristics* —When tested in accordance with 12.9, the air stream surface of the insulation shall have a maximum flame spread index of 25 and a maximum smoke developed index of 50.

7.8 *Apparent Thermal Conductivity* —When tested in accordance with 12.10, the apparent thermal conductivity (*k*) of the insulation, expressed as Btu-in/h-ft<sup>2</sup>·°F or W/m·K for the specified thickness shall not exceed the values shown in Table 1.

<sup>4</sup> Annual Book of ASTM Standards, Vol 14.04.

<sup>4</sup> Available from Sheet Metal and Air Conditioning Contractors National Association, Inc., 4201 Lafayette Center Drive, Chantilly, VA 22021-1209.

<sup>6</sup> Available from North American Insulation Manufacturers Association, 44 Canal Center Plaza, Suite 310, Alexandria, VA 22314.

<sup>5</sup> Available from Underwriters Laboratories Inc., 333 Pfingsten Road, Northbrook, Illinois 60062-2096.

<sup>6</sup> Available from Sheet Metal and Air Conditioning Contractors National Association, Inc., 4201 Lafayette Center Drive, Chantilly, VA 22021-1209.

<sup>6</sup> Available from National Fire Protection Association, 1 Batterymarch Park, PO Box 9101, Quincy, MA 02269-9101.

<sup>7</sup> Available from Underwriters Laboratories Inc., 333 Pfingsten Road, Northbrook, Illinois 60062-2096.

<sup>7</sup> Available from Underwriters Laboratories of Canada, 7 Crouse Road, Scarborough, Ontario, Canada M1R 3A9.