



SLOVENSKI STANDARD
SIST EN 479:2000

01-maj-2000

Profili iz trdega polivinilklorida (PVC-U) za izdelavo oken in vrat - Ugotavljanje preostale deformacije po toplotni obremenitvi

Unplasticized polyvinylchloride (PVC-U) profiles for the fabrication of windows and doors - Determination of heat reversion

Profile aus weichmacherfreiem Polyvinylchlorid (PVC-U) zur Herstellung von Fenstern und Türen - Bestimmung des Wärmeschumpfes

Profilés de polychlorure de vinyle non plastifié (PVC-U) pour la fabrication des fenetres et des portes - Détermination du retrait a chaud

<https://standards.iteh.ai/catalog/standards/sist/b5c06a2b-0d07-4287-b479-9190cfc39ea/sist-en-479-2000>

Ta slovenski standard je istoveten z: EN 479:1995

ICS:

83.140.99	Drugi izdelki iz gume in polimernih materialov	Other rubber and plastics products
91.060.50	Vrata in okna	Doors and windows

SIST EN 479:2000

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 479:2000

<https://standards.iteh.ai/catalog/standards/sist/b5c06a2b-0d07-4287-b479-9190cfec39ea/sist-en-479-2000>

EUROPEAN STANDARD

EN 479

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 1995

ICS 83.140; 91.060.50

Descriptors: buildings, windows, non-metallic sections, unplasticized polyvinylchloride, high temperature tests, determination, shrinkage

English version

**Unplasticized polyvinylchloride (PVC-U) profiles for
the fabrication of windows and doors -
Determination of heat reversion**

Profils de polychlorure de vinyle non
plastifié (PVC-U) pour la fabrication des
fenêtres et des portes - Détermination du
retrait à chaud

Profile aus weichmacherfreiem Polyvinylchlorid
(PVC-U) zur Herstellung von Fenstern und Türen
- Bestimmung des Wärmeschrumpfes

STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 479:2000](https://standards.iteh.ai/catalog/standards/sist/b5c06a2b-0d07-4287-b479-9190cfec39ea/sist-en-479-2000)

<https://standards.iteh.ai/catalog/standards/sist/b5c06a2b-0d07-4287-b479-9190cfec39ea/sist-en-479-2000>

This European Standard was approved by CEN on 1995-05-02. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

© 1995

All rights of reproduction and communication in any form and by any means reserved in all countries to CEN and its members.

Ref. No. EN 479:1995 E

Foreword

This European Standard has been prepared by the Technical Committee CEN/TC 33 "Windows, doors, shutters, building hardware and curtain walling" of which the secretariat is held by AFNOR.

The requirements are incorporated in the Product standards concerned.

This European Standard will result in one of a series of standards on test methods which supports a product standard for PVC-U profiles for the fabrication of windows and doors.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1995, and conflicting national standards shall be withdrawn at the latest by November 1995.

According to the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 479:2000

<https://standards.iteh.ai/catalog/standards/sist/b5c06a2b-0d07-4287-b479-9190cfec39ea/sist-en-479-2000>



1 Scope

This European Standard specifies a method for the determination of the heat reversion of unplasticized polyvinylchloride (PVC-U) profiles for the fabrication of windows and doors by a test at 100 °C in an oven.

2 Principle

A test piece of a specified length of profile is maintained in an oven at 100 °C for 1 h.

A marked length of this test piece is measured under identical conditions, before and after heating in the oven.

The heat reversion is calculated as the percentage change of the final length relative to the initial length per pair of marks.

For main profiles the differential heat reversion is calculated as the difference between the heat reversion of opposite sight surfaces of each test piece.

3 Definitions

For the purpose of this European Standard the following definitions apply :

3.1 main profile

A profile, which has a load bearing function in the construction of windows and doors.

3.2 auxiliary profile

A profile, which has no load bearing function in the construction of windows and doors.

3.3 sight surface

A face surface of a profile, that is exposed to view, when the window or door is closed.

4 Apparatus

4.1 Air oven, thermostatically controlled, with forced air circulation, in which the test pieces can be exposed to a temperature of 100 °C.

The oven shall be equipped with a thermostat capable of maintaining the temperature at (100 ± 2) °C.

4.2 Thermometer, graduated in 0,5 °C.

4.3 Heat resistant glass plate and talc or stainless steel plate and talc.

4.4 Measuring device, to measure the length of the test piece to an accuracy of 0,1 mm.

5 Test pieces

5.1 The test piece shall be of a minimum length of 250 mm of profile.

5.2 Prepare three similar test pieces per length of profile.

6 Conditioning

Condition the test pieces for at least 1 h at room temperature.

In cases of dispute the test pieces shall be conditioned at $(23 \pm 2) ^\circ\text{C}$.

7 Procedure

7.1 Using, a scribe or similar implement, trace on each test piece two marks, perpendicular to the profile axis, 200 mm apart, so that one of them is approximately 25 mm from one end of the test piece.

On the main profiles one pair of marks shall be made on each of the two sight surfaces.

On the auxillary profiles only one pair of marks is made

7.2 Measure for every test piece at room temperature the distance between the two marks in one pair with an accuracy of 0,1 mm.

7.3 Set the oventemperature to 100 °C.

7.4 When the oven has reached 100 °C, place the test pieces horizontally in the oven on a glass or steel plate sprinkled with talc.

7.5 Maintain the test pieces in the oven for $(60 + \frac{3}{0})$ min, after the temperature has regained to 100 °C.

7.6 Remove the glass or steel plate with the test pieces from the oven and let them cool down in air to room temperature.

Under identical conditions to those used in 7.2, measure the distance between the two marks per pair.

7.7 In cases of dispute the cooling of the profiles and the measuring of the distance between the marks shall be performed at $(23 \pm 2) ^\circ\text{C}$.

8 Expression of results

8.1 For each test piece, calculate the heat reversion R for each pair of marks, as a percentage using the following equation

$$R = \frac{\Delta l}{L_0} \times 100$$

where :

$$\Delta l = L_0 - L_1;$$

L_0 is the distance between the marks before heating in the oven in millimetres ;

L_1 is the distance, between the marks, after heating in the oven in millimetres.

8.2 For the main profiles, take as the heat reversion R the value for each sight surface for each test piece.

For the main profiles take as the differential heat reversion ΔR the difference between the heat reversions of opposite sight surfaces of each test piece.

9 Test report

The test report shall include the following information :

- a) reference to this European Standard ;
- b) the test laboratory ;
- c) full identification of the profile ;
- d) the date of testing ;

- e) the distance between the marks before heating in the oven (L_0) for each pair of marks of each test piece ;
- f) the distance between the marks after heating in the oven (L_1) for each pair of marks of each test piece ;
- g) the value R for each pair of marks for each test piece and for the main profiles the differential heat reversion ΔR for each test piece ;
- h) all operating details not specified in this European Standard, as well as any incidents likely to have influenced the results.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 479:2000

<https://standards.iteh.ai/catalog/standards/sist/b5c06a2b-0d07-4287-b479-9190cfec39ea/sist-en-479-2000>