



Designation: C 936 – 08

## Standard Specification for Solid Concrete Interlocking Paving Units<sup>1</sup>

This standard is issued under the fixed designation C 936; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers the requirements for interlocking concrete pavers manufactured for the construction of paved surfaces.

1.2 When particular features are desired, such as weight classification, higher compressive strength, surface textures, finish, color, or other special features, such properties should be specified by the purchaser. Local sellers, however, should be consulted as to availability of units having the desired features.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

- C 33 Specification for Concrete Aggregates
- C 140 Test Methods for Sampling and Testing Concrete Masonry Units and Related Units
- C 150 Specification for Portland Cement
- C 207 Specification for Hydrated Lime for Masonry Purposes
- C 260 Specification for Air-Entraining Admixtures for Concrete
- C 331 Specification for Lightweight Aggregates for Concrete Masonry Units
- C 418 Test Method for Abrasion Resistance of Concrete by Sandblasting

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C27 on Precast Concrete Products and is the direct responsibility of Subcommittee C27.20 on Architectural and Structural Products.

Current edition approved June 1, 2008. Published June 2008. Originally approved in 1982. Last previous edition approved in 2007 as C 936 – 07.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- C 494/C 494M Specification for Chemical Admixtures for Concrete
- C 595 Specification for Blended Hydraulic Cements
- C 618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- C 979 Specification for Pigments for Integrally Colored Concrete
- C 989 Specification for Ground Granulated Blast-Furnace Slag for Use in Concrete and Mortars
- C 1157 Performance Specification for Hydraulic Cement
- C 1240 Specification for Silica Fume Used in Cementitious Mixtures
- C 1645 Test Method for Freeze-thaw and De-icing Salt Durability of Solid Concrete Interlocking Paving Units

### 3. Terminology

#### 3.1 Definitions:

3.1.1 *architectural finishes*—surface modified by mechanical means such as blasting, hammering, polishing, tumbling, washing, or other methods.

### 4. Materials

4.1 *Cementitious Materials* shall conform to the following applicable ASTM specifications:

4.1.1 *Portland Cements*—Specification C 150.

4.1.2 *Blended Cements*—Specification C 595, Types IS or IP.

4.1.3 *Hydraulic Cement*—Specification C 1157.

4.1.4 *Hydrated Lime, Type S*—Specification C 207.

4.1.5 *Fly Ash*—Specification C 618.

4.1.6 *Ground Slag*—Specification C 989.

4.1.7 *Silica Fume*—Specification C 1240.

4.2 *Aggregates* shall conform to the following ASTM specifications, except that grading requirements shall not necessarily apply:

4.2.1 *Normal Weight*—Specification C 33.

4.2.2 *Lightweight*—Specification C 331.