



Designation: ~~F1091-02~~ Designation: **F 1091 - 08**

## Standard Specification for Wrought Cobalt-20Chromium-15Tungsten-10Nickel Alloy Surgical Fixation Wire [~~UNS R30605~~](**UNS R30605**)<sup>1</sup>

This standard is issued under the fixed designation F 1091; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 This specification covers the chemical, mechanical, and metallurgical requirements for the manufacture of wrought cobalt-20chromium-15tungsten-10nickel surgical fixation wire.

1.2 The values stated in SI units are to be regarded as the standard. The inch-pound equivalents of the SI units may be approximate—values given in parentheses are for information only.

### 2. Referenced Documents

#### 2.1 *ASTM Standards:*<sup>2</sup>

E 8 Test Methods for Tension Testing of Metallic Materials

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

F 86 Practice for Surface Preparation and Marking of Metallic Surgical Implants

F 90 Specification for Wrought Cobalt-20Chromium-15Tungsten-10Nickel Alloy for Surgical Implant Applications (UNS R30605)

#### 2.2 *USP Standards:*<sup>3</sup>

Nonabsorbable Surgical Suture, *U.S. Pharmacopeia*

#### 2.3 *ISO Standard:*<sup>4</sup>

ISO 9001 Quality Management Systems—Requirements

#### 2.4 *American Society for Quality Standard:*<sup>5</sup>

ASQ C1 Specification of General Requirements for a Quality Program

### 3. General Requirements for Delivery

3.1 In addition to the requirements of this specification, all requirements of the current editions of Specification F 90 shall apply.

3.2 In cases where a conflict exists between this specification and the standards listed in Section 2, this specification shall take precedence.

### 4. Ordering Information

~~4.1 Inquiries and orders for material under this specification shall include the following information:~~

~~4.1.1 Quantity;~~

~~4.1.2 ASTM designation and date of issue;~~

~~4.1.3 Material requirements;~~

~~4.1.4 Mechanical properties;~~

~~4.1.5 Form;~~

~~4.1.6 Dimensional requirements, including diameter and diameter tolerance;~~

~~4.1.7 Surface condition and handling;~~

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.12 on Metallurgical Materials.

Current edition approved Apr. 10, 2002. Published June 2002. Originally published as F1091-91. Last previous edition F1091-91 (2000).

Current edition approved May 1, 2008. Published June 2008. Originally approved 1991. Last previous edition approved in 2002 as F 1091 - 02.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards*, Vol 03.01, volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 13.01.

<sup>4</sup> Available from U.S. Pharmacopeia (USP), 12601 Twinbrook Pkwy., Rockville, MD 20852-1790, <http://www.usp.org>.

<sup>5</sup> Available from U.S. Pharmacopeia, 12601 Twinbrook Pkwy., Rockville, MD 20852.

<sup>6</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

<sup>7</sup> Available from American Society for Quality (ASQ), 600 N. Plankinton Ave., Milwaukee, WI 53203, <http://www.asq.org>.

\*A Summary of Changes section appears at the end of this standard.

4.1.8 Special tests (if applicable), and

4.1.9 Other requirements. Terminology

4.1 Definitions of Terms Specific to This Standard:

4.1.1 *lot, n*—the total number of mill products produced from the same melt heat under the same conditions at essentially the same time.

## 5. Material Requirements

5.1 The starting material used to make fixation wire must meet Specification F90 Ordering Information

5.1 Inquiries and orders for material under this specification shall include the following information:

5.1.1 Quantity,

5.1.2 ASTM designation and date of issue,

5.1.3 Material requirements (Section 6),

5.1.4 Mechanical properties (7),

5.1.5 Form,

5.1.6 Dimensional requirements, including diameter and diameter tolerance,

5.1.7 Surface condition and handling,

5.1.8 Special tests (if applicable), and

5.1.9 Other requirements.

## 6. Material Requirements

6.1 The starting material used to make fixation wire must meet Specification F 90.

6.2 Surgical fixation wire shall conform to the specified chemical requirements of Specification F 90.

6:

## 7. Mechanical Requirements

7.1 Surgical fixation wire shall conform to the appropriate mechanical properties specified in Table 1.

7.2 Mechanical testing shall be performed in accordance with Test Methods E8 using a 254-mm (10-in.) gage length and crosshead speed of 254 mm/min (10 in./min).

7.3 The wire shall meet the requirements of USP for Nonabsorbable Surgical Sutures

7.2 Perform tension tests in accordance with Test Methods E 8 using a 254-mm (10-in.) gage length and crosshead speed of 254 mm/min (10 in./min). Should any of the test specimens not meet the specified requirements, test two additional test pieces representative of the same lot, in the same manner, for each failed test piece. The lot shall be considered in compliance only if all additional test pieces meet the specified requirements.

ASTM F1091-08

**TABLE 1 Mechanical and Dimensional Requirements for Wrought Cobalt-20 Chromium-15 Tungsten-10 Nickel Alloy Surgical Fixation Wire**

Range of Sizes Diameter, mm (in.)	USP Size <sup>A</sup>	Diameter Tolerance <sup>B,C</sup>	Tensile Strength max, MPa (ksi) <sup>D</sup>	Elong. min, % <sup>E</sup>
0.010 to under 0.020 (0.0004 to 0.0008)	...	0.0015 (0.000 06)	1730 (250)	20
0.020 to under 0.030 (0.0008 to 0.0012)	10-0	0.0015 (0.000 06)	1660 (240)	20
0.030 to under 0.040 (0.0012 to 0.0016)	9-0	0.0025 (0.0001)	1590 (230)	25
0.040 to under 0.050 (0.0016 to 0.0020)	8-0	0.0025 (0.0001)	1555 (225)	30
0.050 to under 0.070 (0.0020 to 0.0028)	7-0	0.0025 (0.0001)	1520 (220)	30
0.070 to under 0.100 (0.0028 to 0.0039)	6-0	0.0025 (0.0001)	1385 (215)	35
0.100 to under 0.150 (0.0039 to 0.0059)	5-0	0.0050 (0.0002)	1450 (210)	35
0.150 to under 0.200 (0.0059 to 0.0079)	4-0	0.0050 (0.0002)	1415 (205)	35
0.200 to under 0.250 (0.0079 to 0.0098)	3-0	0.0075 (0.0003)	1380 (200)	40
0.250 to under 0.300 (0.0098 to 0.0118)	...	0.0075 (0.0003)	1380 (200)	40
0.300 to under 0.340 (0.0118 to 0.0134)	2-0	0.0100 (0.0004)	1310 (190)	40
0.340 to under 0.350 (0.0134 to 0.0138)	...	0.0100 (0.0004)	1310 (190)	40
0.350 to under 0.400 (0.0138 to 0.0158)	1-0	0.0100 (0.0004)	1275 (185)	40
0.400 to under 0.500 (0.0158 to 0.0197)	1	0.0100 (0.0004)	1275 (185)	40
0.500 to under 0.600 (0.0197 to 0.0236)	2	0.0100 (0.0004)	1275 (185)	45
0.600 to under 0.700 (0.0236 to 0.0276)	3 and 4	0.0130 (0.0005)	1240 (180)	45
0.700 to under 0.800 (0.0276 to 0.0315)	5	0.0130 (0.0005)	1240 (180)	45
0.800 to under 0.900 (0.0315 to 0.0354)	6	0.0200 (0.0008)	1240 (180)	45
0.900 to under 1.000 (0.0354 to 0.0394)	7	0.0200 (0.0008)	1170 (170)	45
1.000 to under 1.100 (0.0394 to 0.0433)	...	0.0200 (0.0008)	1170 (170)	45
1.100 to under 1.600 (0.0433 to 0.0630)	...	0.0250 (0.0010)	1140 (165)	45

<sup>A</sup> For reference purposes only (*U.S. Pharmacopeia*).

<sup>B</sup> Diameter tolerances are over and under as given in this table. When required by the purchaser, round wire tolerances may be specified all plus and nothing minus, or all minus and nothing plus, or any combination of plus and minus if the total spread in size tolerance is not less than the total spread shown in this table.

<sup>C</sup> The maximum out-of-round tolerance for round wire is one half of the total size tolerance given in this table.

<sup>D</sup> Maximum tensile strength in ksi (1 ksi = 1000 psi) is specified to assure proper wire-handling characteristics.

<sup>E</sup> Minimum elongation for spooled wire is six percentage points lower than values given in this table.