
Profili iz trdega polivinilklorida (PVC-U) za izdelavo oken in vrat - Videz po izpostavi temperaturi 150 °C - Preskusna metoda

Unplasticized polyvinylchloride (PVC-U) profiles for the fabrication of windows and doors - Appearance after exposure at 150 °C - Test method

Profile aus weichmacherfreiem Polyvinylchlorid (PVC-U) zur Herstellung von Fenstern und Türen - Bestimmung des Verhaltens nach Lagerung bei 150 °C - Prüfverfahren

Profilés de polychlorure de vinyle non plastifié (PVC-U) pour la fabrication des fenetres et des portes - Caractérisation de l'aspect apres conditionnement a 150 °C - Méthode d'essai

<https://standards.iteh.ai/catalog/standards/sist/7c817455-01cf-40e0-ba13-71f1bd464db/sist-en-478-2000>

Ta slovenski standard je istoveten z: EN 478:1995

ICS:

83.140.99	Drugi izdelki iz gume in polimernih materialov	Other rubber and plastics products
91.060.50	Vrata in okna	Doors and windows

SIST EN 478:2000**en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 478:2000

<https://standards.iteh.ai/catalog/standards/sist/7c817455-01cf-40e0-ba13-71ff1bd464db/sist-en-478-2000>

EUROPEAN STANDARD

EN 478

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 1995

ICS 83.140; 91.060.50

Descriptors: buildings, windows, non-metallic sections, unplasticized polyvinylchloride, high temperature tests, macroscopic analysis, appearance

English version

**Unplasticized polyvinylchloride (PVC-U) profiles for
the fabrication of windows and doors -
Appearance after exposure at 150 °C - Test
method**

Profilés de polychlorure de vinyle non
plastifié (PVC-U) pour la fabrication des
fenêtres et des portes - Caractérisation de
l'aspect après conditionnement à 150 °C -
Méthode d'essai

Profile aus weichmacherfreiem Polyvinylchlorid
(PVC-U) zur Herstellung von Fenstern und Türen
- Bestimmung des Verhaltens nach Lagerung bei
150 °C - Prüfverfahren

SIST EN 478:2000

<https://standards.iteh.ai/catalog/standards/sist/7c817455-01cf-40e0-ba13-71ff1bd464db/sist-en-478-2000>

This European Standard was approved by CEN on 1995-05-02. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

© 1995

All rights of reproduction and communication in any form and by any means reserved in all countries to CEN and its members.

Ref. No. EN 478:1995 E

Foreword

This European Standard has been prepared by the Technical Committee CEN/TC 33 "Windows, doors, shutters, building hardware and curtain walling" of which the secretariat is held by AFNOR.

The requirements are incorporated in the product standards concerned.

This European Standard will result in one of a series of standards on test methods which supports a product standard for PVC-U profiles for the fabrication of windows and doors.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1995, and conflicting national standards shall be withdrawn at the latest by November 1995.

According to the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 478:2000](https://standards.iteh.ai/catalog/standards/sist/7c817455-01cf-40e0-ba13-71f1bd464db/sist-en-478-2000)

<https://standards.iteh.ai/catalog/standards/sist/7c817455-01cf-40e0-ba13-71f1bd464db/sist-en-478-2000>



1 Scope

This European Standard specifies two methods for the determination of the effect of heat on unplasticized polyvinylchloride (PVC-U) profiles for the fabrication of windows and doors. The oven method is considered as the reference method.

2 Principle

A test piece of a specified length of profile is maintained in an oven or liquid bath at 150 °C for 30 min. and is inspected visually on the inside, outside and the cross-section of the wall for defects after heating.

3 Definition

For the purpose of this European Standard the following definition applies.

defect : The visual appearance of blisters, cavities or cracks on any of the surfaces (inner and outer) of the profile and of any delamination in the cross section.

4 Apparatus

4.1 Ventilated oven, thermostatically controlled, with air circulation, in which the test pieces can be exposed to a temperature of 150 °C.

The oven shall be equipped with a thermostat capable of maintaining the temperature at (150 ± 2) °C.

The capacity of the oven shall be such that, after insertion of the test piece, the test temperature is regained within 15 min.

4.2 Liquid bath, thermostatically controlled, in which the test pieces can be exposed to a temperature of 150 °C.

The bath shall be equipped with a thermostat capable of maintaining the temperature at (150 ± 2) °C.

The capacity of the bath shall be such that after insertion of the test piece, the test temperature is regained within 5 min.

The liquid to be used shall be glycerine or an aromatic-free hydrocarbon. This liquid shall be free of substances which may affect the properties of the PVC-U.

4.3 Thermometer, graduated in 0,5°C.

5 Test piece

The test piece shall be as follows :

- a) for testing in an oven, a minimum length of 200 mm of profile ;
- b) for testing in a liquid bath, a minimum length of 300 mm of profile.

6 Test procedure

6.1 Oven method

6.1.1 Set the oven temperature to 150 °C.

6.1.2 When the oven has reached 150 °C, place the test piece horizontally in the oven.

NOTE: The use of a glass sheet dusted with talcum can be convenient.

iTeh STANDARD PREVIEW

6.1.3 Maintain the test piece in the oven for $(30 + \frac{3}{0})$ min, measuring from the time when the oven temperature has returned to 150 °C.

[SIST EN 478:2000](https://standards.iteh.ai/catalog/standards/sist/7c817455-01cf-40e0-ba13-7310b1454d/sist-en-478-2000)

[https://standards.iteh.ai/catalog/standards/sist/7c817455-01cf-40e0-ba13-](https://standards.iteh.ai/catalog/standards/sist/7c817455-01cf-40e0-ba13-7310b1454d/sist-en-478-2000)

6.1.4 Remove the test piece from the oven, taking care not to distort or otherwise damage it.

6.1.5 Allow the test piece to cool in air. When the test piece is cool enough for handling, examine it for defects.

6.2 Liquid bath method

6.2.1 Set the liquid bath temperature to 150 °C.

6.2.2 When the liquid bath has reached 150 °C, hang the test piece vertically in the test liquid, so that the upper part does not protrude more than 100 mm out of the fluid.

The means of suspending a test piece shall be such that it does not touch either the floor or the wall of the bath.

6.2.3 Keep the test piece in the liquid bath for $(30 + \frac{3}{0})$ min measuring from the time when the liquid bath temperature has returned to 150 °C.

6.2.4 Remove the test piece from the bath, taking care not to distort or otherwise damage it.

6.2.5 Allow the test piece to cool in air. When the test piece is cool enough for handling, examine it for defects.

7 Expression of results

The nature and the location of any defects shall be noted.

8 Test report

The test report shall include the following information :

- a) reference to this European Standard ;
- b) the test laboratory ;
- c) full identification of the profile ;
- d) the date of testing ;
- e) the apparatus used and, for the liquid bath method, the type of liquid ;
- f) the results of the examination of the test piece ;
- g) all operating details not specified in this European Standard, as well as any incidents likely to have influenced the results.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 478:2000
<https://standards.iteh.ai/catalog/standards/sist/7c817455-01cf-40e0-ba13-71f1bd464db/sist-en-478-2000>