



~~Designation: A 36/A 36M-05~~ Designation: A 36/A 36M – 08

## Standard Specification for Carbon Structural Steel<sup>1</sup>

This standard is issued under the fixed designation A 36/A 36M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification<sup>2</sup> covers carbon steel shapes, plates, and bars of structural quality for use in riveted, bolted, or welded construction of bridges and buildings, and for general structural purposes.

1.2 Supplementary requirements are provided for use where additional testing or additional restrictions are required by the purchaser. Such requirements apply only when specified in the purchase order.

1.3 When the steel is to be welded, a welding procedure suitable for the grade of steel and intended use or service is to be utilized. See Appendix X3 of Specification A 6/A 6M for information on weldability.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system is to be used independently of the other, without combining values in any way.

1.5 The text of this specification contains notes or footnotes, or both, that provide explanatory material. Such notes and footnotes, excluding those in tables and figures, do not contain any mandatory requirements.

1.6 For structural products produced from coil and furnished without heat treatment or with stress relieving only, the additional requirements, including additional testing requirements and the reporting of additional test results, of A 6/A 6M apply.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>3</sup>

A 6/A 6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling

A 27/A 27M Specification for Steel Castings, Carbon, for General Application

A 307 Specification for Carbon Steel Bolts and Studs, ~~60000 psi~~ 60 000 PSI Tensile Strength

A 325 Specification for Structural Bolts, Steel, Heat Treated, 120/105 ksi Minimum Tensile Strength

A 325M Specification for Structural Bolts, Steel, Heat Treated 830 MPa Minimum Tensile Strength [Metric]

A 500 Specification for Cold-Formed Welded and Seamless Carbon Steel Structural Tubing in Rounds and Shapes

A 501 Specification for Hot-Formed Welded and Seamless Carbon Steel Structural Tubing

A 502 Specification for Rivets, Steel, Structural

A 563 Specification for Carbon and Alloy Steel Nuts

A 563M Specification for Carbon and Alloy Steel Nuts [~~Metric~~](Metric)

~~A1011/A1011M Specification for Steel, Sheet and Strip, Hot-Rolled, Carbon, Structural High-Strength Low-Alloy, and High-Strength Low-Alloy with Improved Formability~~

~~A 668/A 668M Specification for Steel Forgings, Carbon and Alloy, for General Industrial Use~~ Specification for Steel Forgings, Carbon and Alloy, for General Industrial Use

A 1011/A 1011M Specification for Steel, Sheet and Strip, Hot-Rolled, Carbon, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability, and Ultra-High Strength

A 1018/A 1018M Specification for Steel, Sheet and Strip, Heavy-Thickness Coils, Hot-Rolled, Carbon, Commercial, Drawing, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability, and Ultra-High Strength

~~F 568M Specification for Carbon and Alloy Steel Externally Threaded Metric Fasteners~~ Specification for Carbon and Alloy Steel Externally Threaded Metric Fasteners (Metric)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys, and is the direct responsibility of Subcommittee A01.02 on Structural Steel for Bridges, Buildings, Rolling Stock, and Ships.

Current edition approved March 1, 2005; May 15, 2008. Published March 2005; June 2008. Originally approved in 1960. Last previous edition approved in 2004/2005 as A 36/A 36M – 04 $\epsilon$ .

<sup>2</sup> For ASME Boiler and Pressure Vessel Code Applications, see related Specifications SA-36 in Section II of that Code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard.

**F 1554 Specification for Anchor Bolts, Steel, 36, 55, and 105-ksi Yield Strength**
**3. Appurtenant Materials**

3.1 When components of a steel structure are identified with this ASTM designation but the product form is not listed in the scope of this specification, the material shall conform to one of the standards listed in Table 1 unless otherwise specified by the purchaser.

**4. General Requirements for Delivery**

4.1 Structural products furnished under this specification shall conform to the requirements of the current edition of Specification A 6/A 6M, for the specific structural product ordered, unless a conflict exists in which case this specification shall prevail.

4.2 Coils are excluded from qualification to this specification until they are processed into a finished structural product. Structural products produced from coil means structural products that have been cut to individual lengths from a coil. The processor directly controls, or is responsible for, the operations involved in the processing of a coil into a finished structural product. Such operations include decoiling, leveling or straightening, hot-forming or cold-forming (if applicable), cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

NOTE 1—For structural products produced from coil and furnished without heat treatment or with stress relieving only, two test results are to be reported for each qualifying coil. Additional requirements regarding structural products produced from coil are described in Specification A 6/A 6M.

**5. Bearing Plates**

5.1 Unless otherwise specified, plates used as bearing plates for bridges shall be subjected to mechanical tests and shall conform to the tensile requirements of Section 8.

5.2 Unless otherwise specified, mechanical tests shall not be required for plates over 1½ in. [40 mm] in thickness used as bearing plates in structures other than bridges, subject to the requirement that they shall contain 0.20 to 0.33 % carbon by heat analysis, that the chemical composition shall conform to the requirements of Table 2 in phosphorus and sulfur content, and that a sufficient discard shall be made to secure sound plates.

**6. Materials and Manufacture**

6.1 The steel for plates and bars over ½ in. [12.5 mm] in thickness and shapes with flange or leg thicknesses over 1 in. [25 mm] shall be semi-killed or killed.

**7. Chemical Composition**

7.1 The heat analysis shall conform to the requirements prescribed in Table 2, except as specified in 5.2.

7.2 The steel shall conform on product analysis to the requirements prescribed in Table 2, subject to the product analysis tolerances in Specification A 6/A 6M.

**8. Tension Test**

8.1 The material as represented by the test specimen, except as specified in 5.2 and 8.2, shall conform to the requirements as

**TABLE 1 Appurtenant Material Specifications**

NOTE 1—The specifier should be satisfied of the suitability of these materials for the intended application. Chemical composition and/or mechanical properties may be different than specified in A 36/A 36M.

Material	ASTM Designation
Steel rivets	A 502, Grade 1
Bolts	A 307, Grade A or F 568M, Class 4.6
High-strength bolts	A 325 or A 325M
Steel nuts	A 563 or A 563M
Cast steel	A 27/A 27M, Grade 65–35 [450–240]
Cast steel	A 27/A 27M, Grade 65–35 [450–240]
Forgings (carbon steel)	A 668, Class D
Forgings (carbon steel)	A 668/A 668M, Class D
Hot-rolled sheets and strip	A 1011/A 1011M, SS Grade 36 [250] Type 1 or Type 2 or A 1018/A 1018M-SS Grade 36 [250]
Hot-rolled sheets and strip	A 1011/A 1011M, SS Grade 36 [250] Type 1 or Type 2 or A 1018/A 1018M, SS Grade 36 [250]
Cold-formed tubing	A 500, Grade B
Hot-formed tubing	A 501
Anchor bolts	F 1554
Anchor bolts	F 1554, Grade 36