



SLOVENSKI STANDARD
oSIST prEN ISO 10350-2:2018
01-november-2018

Polimerni materiali - Pridobitev in predstavitev primerljivih značilnih enotočkovnih podatkov - 2. del: Z dolgimi vlakni ojačeni polimerni materiali (ISO/DIS 10350-2:2018)

Plastics - Acquisition and presentation of comparable single-point data - Part 2: Long-fibre-reinforced plastics (ISO/DIS 10350-2:2018)

Kunststoffe - Ermittlung und Darstellung vergleichbarer Einpunktkennwerte - Teil 2: Langfaserverstärkte Kunststoffe (ISO/DIS 10350-2:2018)

Plastiques - Acquisition et présentation de caractéristiques intrinsèques comparables - Partie 2: Plastiques renforcés par de longues fibres (ISO/DIS 10350-2:2018)

Ta slovenski standard je istoveten z: prEN ISO 10350-2

ICS:

83.120 Ojačani polimeri Reinforced plastics

oSIST prEN ISO 10350-2:2018 **en,fr,de**

DRAFT INTERNATIONAL STANDARD

ISO/DIS 10350-2

ISO/TC 61/SC 2

Secretariat: **KATS**Voting begins on:
2018-08-21Voting terminates on:
2018-11-13

Plastics — Acquisition and presentation of comparable single-point data —

Part 2: Long-fibre-reinforced plastics

*Plastiques — Acquisition et présentation de caractéristiques intrinsèques comparables —
Partie 2: Plastiques renforcés par de longues fibres*

ICS: 83.120

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 10350-2:2020

<https://standards.iteh.ai/catalog/standards/sist/f43c2616-29a8-4ad4-ae9b-7079991fc191/sist-en-iso-10350-2-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 10350-2:2018(E)

© ISO 2018

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 10350-2:2020

<https://standards.iteh.ai/catalog/standards/sist/f43c2616-29a8-4ad4-ae9b-7079991fc191/sist-en-iso-10350-2-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	2
4 Specimen preparation and conditioning.....	3
5 Test requirements.....	3
6 Presentation of results.....	4
Bibliography.....	9

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 10350-2:2020](https://standards.iteh.ai/catalog/standards/sist/f43c2616-29a8-4ad4-ae9b-7079991fc191/sist-en-iso-10350-2-2020)

<https://standards.iteh.ai/catalog/standards/sist/f43c2616-29a8-4ad4-ae9b-7079991fc191/sist-en-iso-10350-2-2020>

ISO/DIS 10350-2:2018(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10350-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 2, *Mechanical properties*.

This third edition cancels and replaces the second edition (ISO 10350-2:2001), which has been technically revised.

ISO 10350 consists of the following parts, under the general title *Plastics — Acquisition and presentation of comparable single-point data*:

— *Part 1: Moulding materials*

— *Part 2: Long-fibre-reinforced plastics*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 10350-2:2020

<https://standards.iteh.ai/catalog/standards/sist/f43c2616-29a8-4ad4-ae9b-7079991fc191/sist-en-iso-10350-2-2020>

Introduction

This part of ISO 10350 has been prepared because users of long-fibre-reinforced plastics find that available data cannot always be readily used to compare the properties of similar materials, especially when the data have been supplied by different sources. Even when the same standard tests have been used, they may allow the adoption of a wide range of alternative test conditions, and the data obtained are not necessarily comparable. The purpose of this part of ISO 10350 is to identify specific methods and conditions of test to be used for the acquisition and presentation of data in order that valid comparisons between materials can be made.

This part of ISO 10350 is concerned with tests employed to present “single-point” data on the limited range of properties commonly included in data sheets and used for the preliminary selection of materials. Such data represent the most basic approach to the specification of properties of materials and this part of ISO 10350 thus facilitates the first steps towards more efficient selection and use of plastics in the many applications to which they are suited.

Many properties of long-fibre-reinforced plastics are anisotropic. The test method standards for these properties have been produced with different procedures for specific types of reinforcement. In this part of ISO 10350, use of the appropriate procedure is specified rather than the use of a specific specimen geometry as adopted in Part 1 for moulding materials. This is necessary for the recording of meaningful material property values.

Complementary International Standards (ISO 11403-1, ISO 11403-2 and ISO 11403-3) (see the Bibliography) are concerned with the standardized acquisition and presentation of multipoint data, to demonstrate how properties vary with important factors such as time, temperature and the presence of particular natural and chemical environments. In these standards, some additional properties are included. Their use will provide a more substantial database than one containing only single-point data, and so will enable improved assessment of the fitness of a material for any particular application. In addition, ISO 11403-1, which deals with mechanical properties, assists predictions of the performance of components and ISO 11403-2, covering thermal and processing properties, aids predictions of melt-flow behaviour during manufacturing. ISO 11403-3 is concerned with environmental influences on properties, and other parts may be prepared to cover additional properties. The various parts of ISO 11403 were written primarily for moulding materials. The test methods and test conditions referred to might not therefore be ideally suited to the acquisition of data for all long-fibre-reinforced plastics.

Plastics — Acquisition and presentation of comparable single-point data —

Part 2: Long-fibre-reinforced plastics

1 Scope

ISO 10350 identifies specific test procedures for the acquisition and presentation of comparable data for certain basic properties of plastics. In general, each property is specified by a single experimental value, although in certain cases properties are represented by two values obtained under different test conditions or along different directions in the material. The properties included are those presented conventionally in manufacturers' data sheets. This part of ISO 10350 applies to reinforced thermoplastic and thermosetting materials where the reinforcement fibres are either discontinuous with a fibre length prior to processing greater than 7,5 mm or continuous (e.g. fabric, continuous-strand mat or unidirectional). Part 1 of this International Standard deals specifically with unreinforced and filled plastics, including those using fibres less than 7,5 mm in length.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 62, *Plastics — Determination of water absorption*

ISO 75-3, *Plastics — Determination of temperature of deflection under load — Part 3: High-strength thermosetting laminates and long-fibre-reinforced plastics*

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 179-2, *Plastics — Determination of Charpy impact properties — Part 2: Instrumented impact test*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 527-4, *Plastics — Determination of tensile properties — Part 4: Test conditions for isotropic and orthotropic fibre-reinforced plastic composites*

ISO 527-5, *Plastics — Determination of tensile properties — Part 5: Test conditions for unidirectional fibre-reinforced plastic composites*

ISO 1172, *Textile-glass-reinforced plastics — Prepregs, moulding compounds and laminates — Determination of the textile-glass and mineral-filler content — Calcination methods*

ISO 1183 (all parts), *Plastics — Methods for determining the density of non-cellular plastics*

ISO 1268 (all parts), *Fibre-reinforced plastics — Methods of producing test plates*

ISO 2577, *Plastics — Thermosetting moulding materials — Determination of shrinkage*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 3915, *Plastics — Measurement of resistivity of conductive plastics*

ISO/DIS 10350-2:2018(E)

ISO 4589-2, *Plastics — Determination of burning behaviour by oxygen index — Part 2: Ambient-temperature test*

ISO 6603-2, *Plastics — Determination of puncture impact behaviour of rigid plastics — Part 2: Instrumented impact testing*

ISO 7822, *Textile glass reinforced plastics — Determination of void content — Loss on ignition, mechanical disintegration and statistical counting methods*

ISO 11357-2, *Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature and glass transition step height*

ISO 11357-3, *Plastics — Differential scanning calorimetry (DSC) — Part 3: Determination of temperature and enthalpy of melting and crystallization*

ISO 11359-2, *Plastics — Thermomechanical analysis (TMA) — Part 2: Determination of coefficient of linear thermal expansion and glass transition temperature*

ISO 14125:1998, *Fibre-reinforced plastic composites — Determination of flexural properties*

ISO 14127, *Carbon-fibre-reinforced composites — Determination of the resin, fibre and void contents*

ISO 14130, *Fibre-reinforced plastic composites — Determination of apparent interlaminar shear strength by short-beam method*

ISO 15310, *Fibre-reinforced plastic composites — Determination of the in-plane shear modulus by the plate twist method*

IEC 60112, *Method for the determination of the proof and the comparative tracking indices of solid insulating materials*

IEC 60243-1, *Electrical strength of insulating materials — Test methods — Part 1: Tests at power frequencies*

IEC 60250, *Recommended methods for the determination of the permittivity and dielectric dissipation factor of electrical insulating materials at power, audio and radio frequencies including metre wavelengths*

IEC 60296, *Fluids for electrotechnical applications — Unused mineral insulating oils for transformers and switchgear*

IEC 60695-11-10, *Fire hazard testing — Part 11-10: Test flames — 50 W horizontal and vertical flame test methods*

IEC 60695-11-20, *Fire hazard testing — Part 11-20: Test flames — 500 W flame test methods*

IEC 62631-3-1, *Dielectric and resistive properties of solid insulating materials - Part 3-1: Determination of resistive properties (DC methods) - Volume resistance and volume resistivity - General method*

IEC 62631-3-2, *Dielectric and resistive properties of solid insulating materials - Part 3-2: Determination of resistive properties (DC methods) - Surface resistance and surface resistivity*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 single-point data

data characterizing a plastics material by means of those property tests in which important aspects of performance can be described with single-value results