

INTERNATIONAL
STANDARD

ISO
18218-1

IULTCS/IUC 28-1

First edition
2015-06-15

**Leather — Determination of
ethoxylated alkylphenols —**

**Part 1:
Direct method**

Cuir — Détermination des alkylphénols éthoxylés —

Partie 1: Méthode directe

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

ISO 18218-1:2015

<https://standards.iteh.ai/catalog/standards/sist/1e2e78a9-32c8-4c7f-8870-0af5b41f54ef/iso-18218-1-2015>



Reference numbers
ISO 18218-1:2015(E)
IULTCS/IUC 28-1:2015(E)

© ISO 2015

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 18218-1:2015

<https://standards.iteh.ai/catalog/standards/sist/1e2e78a9-32c8-4c7f-8870-0af5b41f54ef/iso-18218-1-2015>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Principle.....	1
4 Apparatus and materials.....	1
5 Chemicals.....	2
6 Sampling.....	2
7 Sample preparation and analysis.....	3
7.1 Extraction.....	3
7.2 Analysis.....	3
7.3 Calibration.....	3
7.4 Calculation.....	3
8 Test report.....	3
Annex A (informative) Chromatographic analysis operating parameters.....	5
Bibliography.....	7

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 18218-1:2015](https://standards.iteh.ai/catalog/standards/sist/1e2e78a9-32c8-4c7f-8870-0af5b41f54ef/iso-18218-1-2015)

<https://standards.iteh.ai/catalog/standards/sist/1e2e78a9-32c8-4c7f-8870-0af5b41f54ef/iso-18218-1-2015>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

ISO 18218-1 was prepared by the Chemical Test Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, Leather, the secretariat of which is held by UNI, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

ISO 18218 consists of the following parts, under the general title *Leather — Determination of ethoxylated alkylphenols*:

- *Part 1: Direct method*
- *Part 2: Indirect method*

Introduction

Nonylphenol ethoxylate belongs to the non-ionic surfactants. The biodegradation of nonylphenol ethoxylate releases the persistent pollutant, the branched nonylphenol. Nonylphenol is a hormonal acting substance that is toxic for waterborne organisms and many other organisms. For this reason the release of nonylphenol ethoxylate into the environment should be avoided.

In 2003 the European Directive 2003/53/EC restricted the sale and use of nonylphenol and nonylphenol ethoxylate in product preparations for industries with discharges to waste water. Preparations containing concentrations equal or higher than 0,1 % of nonylphenol ethoxylate or nonylphenol were forbidden. This Directive is included as part of the EU Regulation 1907/2006 (REACH).

No detailed composition of the chemical substance nonylphenol ethoxylate can be given, it is assigned the general structural formula:



To cover the group of ethoxylates of 4-nonylphenol, branched and linear, the European Chemical Agency (ECHA) has assigned the substance the following definition: *4-nonylphenol, branched and linear, ethoxylated [substances with a linear and/or branched alkyl chain with a carbon number of 9 covalently bound in position 4 to phenol, ethoxylated covering UVCB and well-defined substances, polymers and homologues, which include any of the individual isomers and/or combinations thereof].*

In the leather industry nonylphenol ethoxylate and octylphenol ethoxylate surfactants have been used. However, the water insoluble substances, nonylphenol and octylphenol, have not been used. For this reason two different analytical procedures have been prepared for analysing leather samples.

This part of ISO 18218 is a method that directly determines the ethoxylated alkylphenol. It is an efficient procedure for the analysing of a larger number of leather samples. This procedure requires HPLC with triple quadrupole mass spectrometer (MSMS) to identify the nonylphenol ethoxylate and octylphenol ethoxylate.

ISO 18218-2 is a procedure for analysing the alkylphenol. The ethoxylated alkylphenol is cleaved to form the alkylphenol, which is identified using high-performance liquid chromatography (HPLC) or gas chromatography-mass spectrometry (GC-MS) equipment. This method can also be used to indirectly determine the alkylphenol ethoxylate content in leather and process auxiliaries.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 18218-1:2015

<https://standards.iteh.ai/catalog/standards/sist/1e2e78a9-32c8-4c7f-8870-0af5b41f54ef/iso-18218-1-2015>

Leather — Determination of ethoxylated alkylphenols —

Part 1: Direct method

1 Scope

This part of ISO 18218 is a method for determining ethoxylated alkylphenols (nonyphenol ethoxylate [NPEO_n with 1 ≤ n ≤ 16] and octylphenol ethoxylate [OPEO_n with 1 ≤ n ≤ 16]) in leather. This direct method is especially suitable where a larger number of leather samples are to be checked for the presence of ethoxylated alkylphenols.

This method requires the use of high-performance liquid chromatography (HPLC) with triple quadrupole mass spectrometer (MSMS) to identify and quantify the ethoxylated alkylphenols.

NOTE 1 In the leather industry, the most commonly used commercial ethoxylated alkylphenol is the NPEO with an average of 9 EO. It has an optimum cloud point in water for the typical leather processing temperatures of 40 °C to 55 °C.

NOTE 2 ISO 18218-1 and ISO 18218-2 use different solvents for the extraction of the ethoxylated alkylphenols from leather. Consequently, the two analytical methods are expected to give similar trends but not necessarily the same absolute result for the ethoxylated alkylphenol content in leather.

2 Normative references

ISO 18218-1:2015

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 4044, *Leather — Chemical tests — Preparation of chemical test samples*

3 Principle

The leather sample is extracted in methanol using an ultrasonic bath. Subsequently, an aliquot of the solution can, after filtering, be directly analysed without further cleaning of the sample using high-performance liquid chromatography (HPLC) with a triple quadrupole mass spectrometer (MSMS).

4 Apparatus and materials

Normal laboratory apparatus and, in particular, the following:

4.1 **Ultrasonic bath**, with controllable heating capable of maintaining a temperature of (70 ± 5) °C.

4.2 **Glass container with a screw cap** (22 ml has been found suitable).

4.3 **Polypropylene or polyethylene syringe**, 2 ml.

4.4 **Syringe membrane filters**, pore size 0,2 µm, for use with syringe (4.3).

4.5 **Volumetric flasks**, 10 ml and 100 ml.

4.6 **Analytical balance**, weighing to 1 mg.

4.7 **Pipettes**, various sizes, 1 ml to 5 ml.

4.8 **Instrumental equipment**, high-performance liquid chromatograph with gradient elution and triple quadrupole mass spectrometer (HPLC-MSMS).

5 Chemicals

If not otherwise defined, analytical reagent grade chemicals shall be used.

5.1 Methanol.

5.2 **Nonylphenol ethoxylate**, NPEO_n with n = 9 – 10, CAS No. 68412-54-4, Sigma-Aldrich® Product No. T9284 (IGEPAL® CO-630)¹⁾, technical grade.

NOTE The brand name is given to improve the comparability of test results amongst laboratories. The commercial nonylphenol ethoxylate contains groups of ethoxylates of nonylphenol with linear and branched structures, so use of another reference can lead to different results. Only technical grade references are currently available from laboratory chemical suppliers.

5.3 **Octylphenol ethoxylate**, OPEO_n with n = 9 – 10, CAS No. 9002-93-1, Sigma-Aldrich® Product No. 542334 (Triton™ X-100)¹⁾, technical grade.

NOTE The brand name is given to improve the comparability of test results amongst laboratories. The commercial octylphenol ethoxylate contains groups of ethoxylates of octylphenol with linear and branched structures, so use of another reference can lead to different results. Only technical grade references are currently available from laboratory chemical suppliers.

5.4 **Stock solution of nonylphenol ethoxylate and octylphenol ethoxylate**, $\rho = 250 \mu\text{g/ml}$.

25 mg of the respective alkylphenol ethoxylate (5.2 and 5.3) are dissolved in different 100 ml volumetric flasks (4.5) with methanol (5.1) and filled up to the mark.

5.5 **Calibration solutions of nonylphenol ethoxylate and octylphenol ethoxylate**

Four calibration solutions of $\rho = 2,5 \mu\text{g/ml}$, $\rho = 5 \mu\text{g/ml}$ and $\rho = 10 \mu\text{g/ml}$ and $\rho = 50 \mu\text{g/ml}$ for each alkylphenol ethoxylate are prepared using the respective stock solution (5.4).

5.6 **Formic acid**.

5.7 **Water**, deionised or distilled water, grade 3 according to ISO 3696.

6 Sampling

The sampling shall be made according to ISO 2418. If a sampling according to ISO 2418 is not possible (e.g. in case of leather from finished products like shoes, clothing, etc.) the details of the sampling shall be given in the test report. Glue residuals shall be mechanically removed from leather samples.

1) Sigma-Aldrich® Product No. T9284 (IGEPAL® CO-630) and Sigma-Aldrich® Product No. 542334 (Triton™ X-100) are examples of suitable products available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO or IDF of these products.

The leather samples shall be cut into small pieces or ground according to ISO 4044. The dimensions of the pieces shall not be larger than 2 to 3 mm in size.

7 Sample preparation and analysis

7.1 Extraction

Approximately 1 g of the leather sample is weighed accurately to 10 mg in a screw-top glass container (4.2). 10 ml methanol (5.1) is added, the container closed and the sample extracted for (60 ± 5) min in an ultrasonic bath (4.1) at (70 ± 5) °C.

NOTE This method can also be used for analysing leather auxiliaries by the addition of the auxiliary to the screw-top container (4.2) instead of the leather sample. The auxiliary ought to be soluble in methanol or, if not, then the extraction solution ought to be centrifuged to give a clear extract.

7.2 Analysis

After cooling down to room temperature, an aliquot of the extraction solution is removed using a disposable syringe (4.3) and transferred into an HPLC sample vial using a syringe filter (4.4). The aliquot is now ready for the HPLC analysis.

The detection of the alkylphenol ethoxylate is made using an HPLC with gradient elution and triple quadrupole mass spectrometer (4.8). Guidelines for suitable chromatographic conditions are given in Annex A.

7.3 Calibration

The four calibration solutions (5.5) shall be transferred to an HPLC vial and analysed along with each batch of test samples. The peak areas of the four analysed calibration solutions (5.5) are used to prepare a calibration graph.

<https://standards.iteh.ai/catalog/standards/sist/1e2e78a9-32c8-4c7f-8870-0af5b41f54ef/iso-18218-1-2015>

7.4 Calculation

The content of alkylphenol ethoxylates is calculated as mass portion, w , in milligrams per kilogram (mg/kg) of the leather sample according to the following formula:

$$w = \frac{(A_s - b) \times V}{a \times m_E} \quad (1)$$

where

A_s is the peak area of alkylphenol ethoxylate in the extraction solution;

b is the intercept of the calibration graph;

a is the slope of the calibration graph;

V is the final volume used according to 7.1 in millilitres (ml); here 10 ml;

m_E is the weight of the leather sample in grams (g).

8 Test report

The test report shall include at least the following information:

- a) a reference to this part of ISO 18218, i.e. ISO 18218-1;
- b) type, origin, and denomination of the sample (aliquot, as far as relevant);