

SLOVENSKI STANDARD

SIST EN ISO 294-4:2019

01-april-2019

Nadomešča:

SIST EN ISO 294-4:2003

SIST EN ISO 294-4:2003/AC:2011

Polimerni materiali - Preskušanci iz plastomerov, oblikovani z injekcijskim vbrizgavanjem - 4. del: Določitev skrčka pri oblikovanju (ISO 294-4:2018)

Plastics - Injection moulding of test specimens of thermoplastic materials - Part 4: Determination of moulding shrinkage (ISO 294-4:2018)

Kunststoffe - Spritzgießen von Probekörpern aus Thermoplasten - Teil 4: Bestimmung der Verarbeitungsschwindung (ISO 294-4:2018)

Plastiques - Moulage par injection des éprouvettes de matériaux thermoplastiques - Partie 4: Détermination du retrait au moulage (ISO 294-4:2018)

Ta slovenski standard je istoveten z: EN ISO 294-4:2019

ICS:

83.080.20 Plastomeri Thermoplastic materials

SIST EN ISO 294-4:2019 en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 294-4:2019

<https://standards.iteh.ai/catalog/standards/sist/87d3eed7-4563-4fd3-9f8d-8f4cb95d8cc9/sist-en-iso-294-4-2019>

EUROPEAN STANDARD

EN ISO 294-4

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2019

ICS 83.080.20

Supersedes EN ISO 294-4:2003

English Version

Plastics - Injection moulding of test specimens of thermoplastic materials - Part 4: Determination of moulding shrinkage (ISO 294-4:2018)

Plastiques - Moulage par injection des éprouvettes de matériaux thermoplastiques - Partie 4: Détermination du retrait au moulage (ISO 294-4:2018)

Kunststoffe - Spritzgießen von Probekörpern aus Thermoplasten - Teil 4: Bestimmung der Verarbeitungsschwindung (ISO 294-4:2018)

This European Standard was approved by CEN on 18 January 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

iTeh STANDARD PREVIEW

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 294-4:2019](https://standards.iteh.ai/catalog/standards/sist/87d3eed7-4563-4fd3-9f8d-8f4cb95d8cc9/sist-en-iso-294-4-2019)
<https://standards.iteh.ai/catalog/standards/sist/87d3eed7-4563-4fd3-9f8d-8f4cb95d8cc9/sist-en-iso-294-4-2019>

European foreword

This document (EN ISO 294-4:2019) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2019, and conflicting national standards shall be withdrawn at the latest by August 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 294-4:2003.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW Endorsement notice (standards.iteh.ai)

The text of ISO 294-4:2018 has been approved by CEN as EN ISO 294-4:2019 without any modification.

[SIST EN ISO 294-4:2019](https://standards.iteh.ai/catalog/standards/sist/87d3eed7-4563-4fd3-9fd-8f4cb95d8cc9/sist-en-iso-294-4-2019)

<https://standards.iteh.ai/catalog/standards/sist/87d3eed7-4563-4fd3-9fd-8f4cb95d8cc9/sist-en-iso-294-4-2019>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 294-4:2019

<https://standards.iteh.ai/catalog/standards/sist/87d3eed7-4563-4fd3-9f8d-8f4cb95d8cc9/sist-en-iso-294-4-2019>

INTERNATIONAL STANDARD

ISO 294-4

Third edition
2018-12

Plastics — Injection moulding of test specimens of thermoplastic materials —

Part 4: Determination of moulding shrinkage

iTeh STANDARD PREVIEW
(standards.iteh.ai)
*Plastiques — Moulage par injection des éprouvettes de matériaux
thermoplastiques —
Partie 4: Détermination du retrait au moulage*

[SIST EN ISO 294-4:2019](https://standards.iteh.ai/catalog/standards/sist/87d3eed7-4563-4fd3-9f8d-8f4cb95d8cc9/sist-en-iso-294-4-2019)

<https://standards.iteh.ai/catalog/standards/sist/87d3eed7-4563-4fd3-9f8d-8f4cb95d8cc9/sist-en-iso-294-4-2019>



Reference number
ISO 294-4:2018(E)

© ISO 2018

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 294-4:2019](https://standards.iteh.ai/catalog/standards/sist/87d3eed7-4563-4fd3-9fd-8f4cb95d8cc9/sist-en-iso-294-4-2019)

<https://standards.iteh.ai/catalog/standards/sist/87d3eed7-4563-4fd3-9fd-8f4cb95d8cc9/sist-en-iso-294-4-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Apparatus	2
5 Procedure	3
5.1 Conditioning of material.....	3
5.2 Injection moulding.....	3
5.3 Measurement of mould temperature.....	4
5.4 Measurement of melt temperature.....	4
5.5 Treatment of test specimens after demoulding.....	4
5.6 Measurement of moulding shrinkage.....	5
5.7 Treatment following measurement of moulding shrinkage.....	5
5.8 Measurement of post-moulding shrinkage.....	5
6 Expression of results	6
6.1 Moulding shrinkage.....	6
6.2 Post-moulding shrinkage.....	6
6.3 Total shrinkage.....	6
7 Precision	7
8 Test report	7
Annex A (informative) Reference points for length and width measurement	8
Bibliography	9

ISO 294-4:2018(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This third edition cancels and replaces the second edition (ISO 294-4:2001), of which it constitutes a minor revision to update the reference in [Clause 2](#). It also incorporates the Technical Corrigendum ISO 294-4:2001/Cor.1:2007.

A list of all parts in the ISO 294 series can be found on the ISO website.

Introduction

See ISO 294-1.

In the injection moulding of thermoplastics, the difference between the dimensions of the mould cavity and those of the moulded articles produced from it can vary with the design and operation of the mould. Such differences can depend on the size of the injection-moulding machine, the shape and dimensions of mouldings including any restrictive action this can have on the shrinkage, the degree and direction of flow or movement of the material in the mould, the sizes of the nozzle, sprue, runner and gate, the cycle on which the machine is operated, the temperature of the melt and the mould, and the magnitude and duration of the hold pressure. Moulding and post-moulding shrinkage are caused by crystallization, volume relaxation and orientation relaxation of the material and by thermal contraction of both the thermoplastic material and the mould. Post-moulding shrinkage can also be influenced by humidity uptake.

The measurement of moulding and post-moulding shrinkage is useful in making comparisons between thermoplastics and in checking uniformity of manufacture.

The method is not intended as a source of data for design calculations of components. Information on the typical behaviour of a material can be obtained, however, by carrying out measurements at different melt and mould temperatures, injection velocities and hold pressures, as well as at different values of other injection-moulding parameters. The information thus obtained is important in establishing the suitability of the moulding material for the production of moulded articles with accurate dimensions.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 294-4:2019](https://standards.iteh.ai/catalog/standards/sist/87d3eed7-4563-4fd3-9f8d-8f4cb95d8cc9/sist-en-iso-294-4-2019)

<https://standards.iteh.ai/catalog/standards/sist/87d3eed7-4563-4fd3-9f8d-8f4cb95d8cc9/sist-en-iso-294-4-2019>