

**SLOVENSKI STANDARD**  
**oSIST prEN ISO 15012-3:2016**  
**01-oktober-2016**

---

**Varnost in zdravje pri varjenju in sorodnih postopkih - Zahteve, preskušanje in označevanje opreme za filtriranje - 3. del: Ugotavljanje učinkovitosti zajema pri napravah za ekstrakcijo (odsosavanje) varilnega dima (ISO/DIS 15012-3:2016)**

Health and safety in welding and allied processes - Requirements, testing and marking of equipment for air filtration - Part 3: Determination of the capture efficiency of on-torch welding fume extraction devices (ISO/DIS 15012-3:2016)

**iTeh STANDARD PREVIEW**

(standards.iteh.ai)  
Arbeits- und Gesundheitsschutz beim Schweißen und bei verwandten Verfahren - Anforderungen, Prüfung und Kennzeichnung von Luftreinigungssystemen - Teil 3: Bestimmung des Erfassungsgrades von brennerintegrierten Absaugeinrichtungen für Schweißrauch (ISO/DIS 15012-3:2016) prEN ISO 15012-3:2016

<https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acce57d/osist-pren-iso-15012-3-2016>

Hygiène et sécurité en soudage et techniques connexes - Exigences, essais et marquage des équipements de filtration d'air - Partie 3: Détermination de l'efficacité de captage des systèmes d'extraction des fumées de soudage par torche aspirante (ISO/DIS 15012-3:2016)

**Ta slovenski standard je istoveten z: prEN ISO 15012-3**

---

**ICS:**

13.040.40	Emisije nepremičnih virov	Stationary source emissions
13.100	Varnost pri delu. Industrijska higiena	Occupational safety. Industrial hygiene
25.160.10	Varilni postopki in varjenje	Welding processes

**oSIST prEN ISO 15012-3:2016**

**en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[oSIST prEN ISO 15012-3:2016](https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acee57d/osist-pren-iso-15012-3-2016)

<https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acee57d/osist-pren-iso-15012-3-2016>

# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 15012-3

ISO/TC 44/SC 9

Secretariat: BSI

Voting begins on:  
2016-08-02Voting terminates on:  
2016-10-24

---

---

## Health and safety in welding and allied processes — Requirements, testing and marking of equipment for air filtration —

Part 3:

### Determination of the capture efficiency of on-gun welding fume extraction devices

*Hygiène et sécurité en soudage et techniques connexes — Exigences, essais et marquage des équipements  
de filtration d'air —*

*Partie 3: Détermination de l'efficacité de la prise des appareils d'extraction des fumées de soudage*

ICS: 25.160.30

iteh STANDARD PREVIEW  
(standards.iteh.ai)

[oSIST prEN ISO 15012-3:2016](https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acee57d/osist-pren-iso-15012-3-2016)

<https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acee57d/osist-pren-iso-15012-3-2016>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number  
ISO/DIS 15012-3:2016(E)

© ISO 2016

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 15012-3:2016](https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acce57d/osist-pren-iso-15012-3-2016)

<https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acce57d/osist-pren-iso-15012-3-2016>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
<b>5 Test equipment and materials</b> .....	<b>2</b>
5.1 General requirement.....	2
5.2 Test chamber.....	2
5.3 Isokinetic samplers.....	2
5.4 Total fume and isokinetic filters.....	2
5.5 Extraction fan.....	2
5.6 On-torch extraction unit.....	3
5.7 Equipment for measuring welding current, welding voltage, wire feed speed and arcing time.....	3
5.8 Equipment for direct-reading of fume concentration.....	3
5.9 Equipment for measuring the mass of fume collected.....	3
5.10 Equipment for measuring shielding gas volume flow rate.....	3
5.11 Device for automatic welding.....	3
5.12 Device for measuring contact tip to workpiece distance (CTWD).....	3
5.13 Device for measuring static pressure.....	4
5.14 Device for measuring the mass flow rate.....	4
5.15 Materials.....	4
<b>6 Test procedure</b> .....	<b>4</b>
6.1 Preliminary tests.....	4
6.1.1 Setting the shielding gas flow rate.....	4
6.1.2 Measuring the flow rates and determination of leakage.....	4
6.2 Setting up the test equipment.....	5
6.3 Capture efficiency tests.....	6
6.3.1 General.....	6
6.3.2 Test procedure.....	6
6.3.3 Calculation of the results.....	7
<b>7 Test parameters for generating comparable test report capture efficiency data</b> .....	<b>8</b>
<b>8 Test report</b> .....	<b>9</b>
<b>Annex A (informative) Examples of test chambers</b> .....	<b>10</b>
<b>Annex B (informative) Equipment notes</b> .....	<b>12</b>
<b>Annex C (informative) Trial tests</b> .....	<b>14</b>
<b>Annex D (normative) Test procedures</b> .....	<b>16</b>
<b>Annex E (informative) Data processing for test method 3</b> .....	<b>17</b>
<b>Annex F (normative) Test parameters form to be filled</b> .....	<b>19</b>
<b>Annex G (informative) Suggested parameters for testing</b> .....	<b>20</b>
<b>Annex H (informative) Information about the necessity to measure leakage</b> .....	<b>21</b>
<b>Bibliography</b> .....	<b>22</b>

## ISO/DIS 15012-3:2016(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

The committee responsible for this document is ISO/44/SC 9.

A list of all parts in the ISO 15012- series can be found on the ISO website.

<https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acce57d/osist-pren-iso-15012-3-2016>

## Introduction

Welding generates fumes and gases which, if inhaled, can be harmful to human health. Therefore, control of the fume and gases must be exercised to minimise worker exposure.

The most effective method of welding fume control is local exhaust ventilation (LEV) which captures the fumes at source before they enter the general environment and the breathing zone of workers.

One form of LEV used in welding is on-torch extraction in which the extraction system is either an integral part of the welding torch or is attached to it close to the arc area. Anecdotal evidence within the fabrication industry suggested that it is impossible to capture fume efficiently whilst maintaining weld metal integrity but research (see bibliography<sup>[4]</sup>) has shown this not to be the case, certainly as far as weld metal porosity is concerned.

This part of EN 15012 prescribes a method for measuring the capture efficiency of on-torch extraction systems. The procedure only prescribes a methodology, leaving selection of the test parameters to the user, so that the effect of different variables may be evaluated.

It has been presumed in the drafting of this standard that the executions of its provisions and the interpretation of the results obtained are entrusted to appropriately qualified and experienced people.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 15012-3:2016](https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acee57d/osist-pren-iso-15012-3-2016)

<https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acee57d/osist-pren-iso-15012-3-2016>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[oSIST prEN ISO 15012-3:2016](https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acce57d/osist-pren-iso-15012-3-2016)

<https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acce57d/osist-pren-iso-15012-3-2016>



# Health and safety in welding and allied processes — Requirements, testing and marking of equipment for air filtration —

## Part 3:

## Determination of the capture efficiency of on-gun welding fume extraction devices

### 1 Scope

This part of ISO 15012 defines a laboratory method for measuring the welding fume capture efficiency of on-torch extraction systems. It is applicable to integrated on-torch systems and to systems where a discrete extraction system is attached to the welding torch close to the arc area. The methodology is suitable for use with all continuous wire welding processes, all material types and all welding parameters.

The method can be used to evaluate the effects of variables such as extraction flow rate, extract nozzle position, shielding gas flow rate, welding geometry, welding torch angle, fume emission rate etc. on capture efficiency.

(standards.iteh.ai)

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 15767, *Workplace atmospheres — Controlling and characterizing uncertainty in weighing collected aerosols*

ISO/IEC Guide 98, *Uncertainty of measurement — All parts*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1

##### **test chamber**

semi-enclosed extracted chamber in which welding fume capture efficiency testing is performed

#### 3.2

##### **isokinetic sampler**

device for collecting aerosol samples at the same velocity as the air being sampled

#### 3.3

##### **test chamber sampling duct**

duct between the test chamber and an extraction fan in which all the fume generated can be collected or sampled isokinetically

## ISO/DIS 15012-3:2016(E)

### 3.4

#### **emission rate**

mass of the particles emitted by the welding fume source per unit time

Note 1 to entry: Emission rate is expressed in mg/s.

## 4 Principle

Automatic welding is performed using the on-torch extraction torch under test, on a test piece, inside a continuously extracted test chamber. Testing is carried out using identical welding parameters with and without the on-torch extraction activated. The ratio of measurements in the test chamber sampling duct is used to calculate the capture efficiency of the on-torch extraction torch.

Three methods of measuring the fume can be used. Two methods employ gravimetric measurement. The first method measures the total fume generated whilst second method employs isokinetic sampling in the test chamber sampling duct. The third method employs a direct reading measuring technique in the test chamber sampling duct.

## 5 Test equipment and materials

### 5.1 General requirement

The test setup shall enable containment of the fume generated in the arc area within the test chamber whilst ensuring the air velocity in the welding area below the torch does not exceed 0,2 m/s without welding and with the on-torch extraction off. See also [B.1](#).

NOTE It is possible that not all of the fume generated by spatter production will be contained within the test chamber.

[oSIST prEN ISO 15012-3:2016](https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acce57d/osist-pren-iso-15012-3-2016)

<https://standards.iteh.ai/catalog/standards/sist/e69cc94e-832e-4e61-939a-02927acce57d/osist-pren-iso-15012-3-2016>

### 5.2 Test chamber

A continuously extracted chamber of sufficient dimensions to enclose the welding operation. Either the chamber shall be constructed of materials that will withstand close proximity to the heat and spatter generated by the welding or the chamber shall be designed so that the materials used are sufficiently distant from the arc to avoid problems arising from heat and spatter generation. See Figures A.1 and A.2.

Compliance with the requirements of [clause 5.1](#) shall be verified.

### 5.3 Isokinetic samplers

The sample flow rate shall be such that the velocity through the sample inlet is the same as the surrounding air velocity. This ensures that the particle size distribution is unaffected by the sampling process and therefore the sample represents the particles present in the sampling duct. See also [C.3](#).

### 5.4 Total fume and isokinetic filters

Filters, manufactured from glass or quartz fibre, with particle retention properties down to approximately 1 µm to 2 µm. The filters shall not tear or perforate during testing (see [B.3](#)) and shall not be so friable that fibres can be lost from the filters during handling.

Filters shall be treated according to the procedures defined in ISO 15767.

### 5.5 Extraction fan

The extraction fan for the sampling chamber shall be capable of maintaining a constant flow rate ( $\pm 2\%$ ) in the test chamber sampling duct during testing when using during testing with iso-kinetic sampling or direct reading equipment.

The air flow generated by the fan shall be capable of retaining the entire fume generated within the test chamber.

### 5.6 On-torch extraction unit

The on-torch extraction unit shall be capable of maintaining a constant flow rate ( $\pm 2\%$ ) in the on-torch extraction line during testing.

### 5.7 Equipment for measuring welding current, welding voltage, wire feed speed and arcing time

Equipment capable of measuring the current, voltage, wire feed speed and the arcing time within  $\pm 1\%$ . Electronic integrating equipment with frequent sampling intervals and a logging capability is recommended. See also [Annex D](#).

In the absence of such equipment, current may be measured using a shunt or a Hall Effect probe connected to a moving coil meter. Voltage may be measured using a moving coil meter. Wire feed speed may be determined by measuring the length of wire exiting the welding torch in a measured time. The calibration of the equipment shall be traceable to national standards.

### 5.8 Equipment for direct-reading of fume concentration

The equipment shall have a reading that is directly proportional to the concentration with a maximum linearity error of 5% over the expected concentration range.

NOTE Equipment suitable for direct-reading of fume concentration is described for example in CEN/TR 16013.

### 5.9 Equipment for measuring the mass of fume collected

A balance, capable of measuring the mass of isokinetic sample filters and isokinetic sample filters plus fume with an accuracy of  $\pm 0,01$  mg or better.

A balance, capable of measuring the mass of total fume collection filters and total fume collection filters plus fume with an accuracy of  $\pm 1$  mg or better.

The balance calibrations shall be traceable to national standards.

### 5.10 Equipment for measuring shielding gas volume flow rate

Equipment calibrated for the shielding gas in use, capable of measuring the volume flow rate to within  $\pm 5\%$  or better. See [B.4](#).

The calibration of the equipment shall be traceable to national standards.

### 5.11 Device for automatic welding

A device that permits the capture efficiency test to be performed under automated conditions, capable of advancing the test piece under a stationary welding torch at an appropriate rate (welding speed). It shall be possible to secure the test piece to the device, such that it cannot bow during welding.

### 5.12 Device for measuring contact tip to workpiece distance (CTWD)

A gauge, made by machining a metal block to a thickness equivalent to the required CTWD to within  $\pm 5\%$  or better, or a metal wedge with distance markings at appropriate points.

## ISO/DIS 15012-3:2016(E)

### 5.13 Device for measuring static pressure

A device capable of measuring static air pressure in the on-torch extraction line with an uncertainty of measurement not exceeding  $\pm 1\%$  of the reading, traceable to national standards. See [B.8](#).

### 5.14 Device for measuring the mass flow rate

A device for measuring the mass flow rate to an accuracy of  $\pm 5\%$  or better, traceable to national standards (e.g. according to EN ISO 5167). See [B.9](#).

### 5.15 Materials

The same batch of filler wire and test pieces shall be used for each test series.

Test pieces, of a material and dimensions that are suitable for the capture efficiency test to be carried out, that allow a weld of sufficient length to be continuously deposited. See [B.6](#).

## 6 Test procedure

### 6.1 Preliminary tests

#### 6.1.1 Setting the shielding gas flow rate

Set the shielding gas flow rate using the equipment described in [5.10](#).

#### 6.1.2 Measuring the flow rates and determination of leakage

Measure the mass flow rate at two points shown in [Figure 1](#), without welding, by using appropriate devices and calculate the air volume flow rate. See also [B.7](#) and [Annex H](#).