



**SLOVENSKI STANDARD**  
**SIST EN 1017:2014/oprA1:2016**  
**01-junij-2016**

---

**Kemikalije, ki se uporabljajo za pripravo pitne vode - Polpraženi dolomit**

Chemicals used for treatment of water intended for human consumption - Half-burnt dolomite

Produkte zur Aufbereitung von Wasser für den menschlichen Gebrauch - Halbgebrannter Dolomit

**iTeh STANDARD PREVIEW**

(standards.itteh.ai)  
Produits chimiques pour le traitement de l'eau destinée à la consommation humaine - Dolomie semi-calcinée

[SIST EN 1017:2014/kprA1:2017](https://standards.itteh.ai/catalog/standards/sist/9809d512-eabb-4db8-9020-ca57099b6c0/sist-en-1017-2014-kpra1-2016)

Ta slovenski standard je istoveten z: **EN 1017:2014/prA1**

---

**ICS:**

13.060.20	Pitna voda	Drinking water
71.100.80	Kemikalije za čiščenje vode	Chemicals for purification of water

**SIST EN 1017:2014/oprA1:2016**

**en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 1017:2014/kprA1:2017](https://standards.iteh.ai/catalog/standards/sist/9809d512-cabb-4db8-9020-ca57f09bfe0/sist-en-1017-2014-kpra1-2017)

<https://standards.iteh.ai/catalog/standards/sist/9809d512-cabb-4db8-9020-ca57f09bfe0/sist-en-1017-2014-kpra1-2017>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**DRAFT**  
**EN 1017:2014**  
**prA1**

April 2016

ICS 71.100.80

English Version

## Chemicals used for treatment of water intended for human consumption - Half-burnt dolomite

Produits chimiques pour le traitement de l'eau destinée à la consommation humaine - Dolomie semi-calcinée

Produkte zur Aufbereitung von Wasser für den menschlichen Gebrauch - Halbgebrannter Dolomit

This draft amendment is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 164.

This draft amendment A1, if approved, will modify the European Standard EN 1017:2014. If this draft becomes an amendment, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for inclusion of this amendment into the relevant national standard without any alteration.

This draft amendment was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

**Warning** : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

<b>Contents</b>	<b>Page</b>
<b>European foreword</b> .....	<b>3</b>
<b>Introduction</b> .....	<b>4</b>
<b>1 Modification to 4.4, Chemical parameters</b> .....	<b>5</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 1017:2014/kprA1:2017](https://standards.iteh.ai/catalog/standards/sist/9809d512-cabb-4db8-9020-ca57f09bfe0/sist-en-1017-2014-kpra1-2017)  
[https://standards.iteh.ai/catalog/standards/sist/9809d512-cabb-4db8-9020-  
ca57f09bfe0/sist-en-1017-2014-kpra1-2017](https://standards.iteh.ai/catalog/standards/sist/9809d512-cabb-4db8-9020-ca57f09bfe0/sist-en-1017-2014-kpra1-2017)

## European foreword

This document (EN 1017:2014/prA1:2016) has been prepared by Technical Committee CEN/TC 164 “Water supply”, the secretariat of which is held by AFNOR.

This document is currently submitted to the CEN Enquiry.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 1017:2014/kprA1:2017](https://standards.iteh.ai/catalog/standards/sist/9809d512-cabb-4db8-9020-ca57f09bfe0/sist-en-1017-2014-kpra1-2017)

<https://standards.iteh.ai/catalog/standards/sist/9809d512-cabb-4db8-9020-ca57f09bfe0/sist-en-1017-2014-kpra1-2017>

**EN 1017:2014/prA1:2016 (E)****Introduction**

In respect of potential adverse effects on the quality of water intended for human consumption, caused by the product covered by this European Standard:

- a) this European Standard provides no information as to whether the product may be used without restriction in any of the Member States of the EU or EFTA;
- b) it should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of this product remain in force.

NOTE Conformity with this European Standard does not confer or imply acceptance or approval of the product in any of the Member States of the EU or EFTA. The use of the product covered by this European Standard is subject to regulation or control by National Authorities.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 1017:2014/kprA1:2017](https://standards.iteh.ai/catalog/standards/sist/9809d512-cabb-4db8-9020-ca57f09bfe0/sist-en-1017-2014-kpra1-2017)

<https://standards.iteh.ai/catalog/standards/sist/9809d512-cabb-4db8-9020-ca57f09bfe0/sist-en-1017-2014-kpra1-2017>

## 1 Modification to 4.4, Chemical parameters

Replace the whole Table 3 with the following one:

"

**Table 3 — Chemical parameters**

Parameter	Limit mg/kg of commercial product		
		Type 1	Type 2
Antimony (Sb) max.	3	3	5
Arsenic (As) max.	3	3	5
Cadmium (Cd) max.	2	2	2
Chromium (Cr) max.	10	10	20
Lead (Pb) max.	10	10	20
Mercury (Hg) max.	0,5	0,5	1
Nickel (Ni) max.	10	10	20
Selenium (Se) max.	3	3	5
NOTE Other chemical parameters and indicator parameters are not relevant in half-burnt dolomite because the raw materials used in the manufacturing process are free of them. For parametric values of half-burnt dolomite on trace metal content in drinking water, see [1].			

<https://standards.iso.org/standards/sist/9809d512-cabb-4db8-9020-ca57f09bfb0/sist-en-1017-2014-kpra1-2017>

"