



**SLOVENSKI STANDARD
SIST EN ISO 13479:1999**

01-julij-1999

7 Yj]]n`dc`]c`YZ]bcj `nUfUbgdcfhZi]Xcj `!`I [c]Uj `Ub`Y`cXdcfbcgh`dfch]`ý]f`Yb`f
fUdc`Y`!`A`YrcXU`nU`dfYg`_i`g`dc` UgbY[U`ý]f`Yb`U`fUdc`_Y`bU`nU`fYnUb]`Wj`j`fbc]W
hYgt`L`f]GC`%` (+`-`.%`-`+L`

Polyolefin pipes for the conveyance of fluids - Determination of resistance to crack propagation - Test method for slow crack growth on notched pipes (notch test) (ISO 13479:1997)

iTeh STANDARD PREVIEW

Rohre aus Polyolefinen für den Transport von Fluiden - Bestimmung des Widerstandes gegen Reißfortpflanzung - Prüfverfahren für langsames Reißwachstum an gekerbten Rohren (Kerbprüfung) (ISO 13479:1997)

[SIST EN ISO 13479:1999](https://standards.iteh.ai/catalog/standards/sist/2cd6594b-adeb-4c46-b0d2-13479-1999)

[https://standards.iteh.ai/catalog/standards/sist/2cd6594b-adeb-4c46-b0d2-](https://standards.iteh.ai/catalog/standards/sist/2cd6594b-adeb-4c46-b0d2-13479-1999)

Tubes en polyoléfines pour le transport des fluides - Résistance a la propagation de la fissure - Méthode d'essai de la propagation lente de la fissure d'un tube entaillé (essai d'entaille) (ISO 13479:1997)

Ta slovenski standard je istoveten z: EN ISO 13479:1997

ICS:

23.040.20 Cevi iz polimernih materialov Plastics pipes

SIST EN ISO 13479:1999

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 13479:1999](#)

<https://standards.iteh.ai/catalog/standards/sist/2cd6594b-adeb-4c46-b0d2-51385e80fc33/sist-en-iso-13479-1999>

EUROPEAN STANDARD

EN ISO 13479

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 1997

ICS 23.040.20

Descriptors: see ISO document

English version

**Polyolefin pipes for the conveyance of fluids -
Determination of resistance to crack propagation -
Test method for slow crack growth on notched
pipes (notch test) (ISO 13479:1997)**

Tubes en polyoléfines pour le transport des fluides - Résistance à la propagation de la fissure - Méthode d'essai de la propagation lente de la fissure d'un tube entaillé (essai d'entaille) (ISO 13479:1997)

Rohre aus Polyolefinen für den Transport von Fluiden - Bestimmung des Widerstandes gegen Ribfortpflanzung - Prüfverfahren für langsames Ribwachstum an gekerbten Rohren (Kerbprüfung) (ISO 13479:1997)

SIST EN ISO 13479:1999

<https://standards.iteh.ai/catalog/standards/sist/2cd6594b-adeb-4c46-b0d2-51385e80fc33/sist-en-iso-13479-1999>

This European Standard was approved by CEN on 1997-03-17. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
EN ISO 13479:1997

Foreword

The text of the International Standard ISO 13479:1997 has been prepared by Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids" in collaboration with Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1997, and conflicting national standards shall be withdrawn at the latest by November 1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 13479:1997 was approved by CEN as a European Standard without any modification.

SIST EN ISO 13479:1999

<https://standards.iteh.ai/catalog/standards/sist/2cd6594b-adeb-4c46-b0d2-51385e80fc33/sist-en-iso-13479-1999>



INTERNATIONAL
STANDARD

ISO
13479

First edition
1997-05-01

**Polyolefin pipes for the conveyance of
fluids — Determination of resistance to
crack propagation — Test method for slow
crack growth on notched pipes (notch test)**

*Tubes en polyoléfines pour le transport des fluides — Résistance à la
propagation de la fissure — Méthode d'essai de la propagation lente de la
fissure d'un tube entaillé (essai d'entaille)*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 13479:1999](https://standards.iteh.ai/catalog/standards/sist/2cd6594b-adeb-4c46-b0d2-51385e80fc33/sist-en-iso-13479-1999)

<https://standards.iteh.ai/catalog/standards/sist/2cd6594b-adeb-4c46-b0d2-51385e80fc33/sist-en-iso-13479-1999>



Reference number
ISO 13479:1997(E)

ISO 13479:1997(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 13479 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*.

SIST EN ISO 13479:1999

<https://standards.iteh.ai/catalog/standards/sist/2cd6594b-adeb-4c46-b0d2->

Annexes A and B of this International Standard are for information only.

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet central@iso.ch
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Polyolefin pipes for the conveyance of fluids — Determination of resistance to crack propagation — Test method for slow crack growth on notched pipes (notch test)

1 Scope

This International Standard specifies a method of test for determining the resistance to slow crack growth of polyolefin pipes, expressed in terms of time to failure in a hydrostatic pressure test on a pipe with machined longitudinal notches in the outside surface. The test is applicable to pipes of wall thickness greater than 5 mm.

2 Normative references

The following standards contain provisions which through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 161-1:1996, *Thermoplastics pipes for the conveyance of fluids — Nominal outside diameters and nominal pressures — Part 1: Metric series.*

ISO 1167:1996, *Thermoplastics pipes for the conveyance of fluids — Resistance to internal pressure — Test method.*

ISO 6108:1978, *Double equal angle cutters with plain bore and key drive.*

ISO 11922-1:1997, *Thermoplastics pipes for the conveyance of fluids — Dimensions and tolerances — Part 1: Metric series.*

3 Definitions

For the purposes of this International Standard, the definitions given in ISO 161-1 and ISO 11922-1 apply.

4 Principle

Lengths of pipe with four machined longitudinal external notches are subject to a constant-pressure hydrostatic pressure test whilst immersed in a water tank at 80 °C. The time to failure is recorded.

5 Apparatus

5.1 Pipe pressure-testing equipment, as specified in ISO 1167.

5.2 Notch-machining equipment, i.e. a milling machine with a horizontal mandrel rigidly fixed to the bed to enable the pipe to be securely clamped to give a straight test piece. The mandrel shall support the pipe bore beneath and along the full length of the notch to be machined. The milling cutter mounted on a horizontal arbor shall be a 60°-included-angle "V"-cutter conforming to ISO 6108, having a cutting rate of $(0,010 \pm 0,002)$ (mm/rev)/tooth (see example below).

The milling cutter shall be carefully protected against damage. The cutter shall be subject to a running-in treatment amounting to 10 m of notching prior to its first use for preparation of test pieces. It shall not be used for any other material or purpose and shall be replaced after 100 m of notching.

EXAMPLE

A cutter with 20 teeth rotating at 700 rpm, traversed at a speed of 150 mm/min, has a cutting rate of $150/(20 \times 700) = 0,011$ (mm/rev)/tooth.

6 Test piece preparation

6.1 Test pieces

Each test piece shall comprise a length of pipe sufficient to give a minimum free length of pipe of $(3d_n \pm 5)$ mm between the end caps, when fitted for pressure testing in accordance with ISO 1167, where d_n is the nominal outside diameter of the pipe. For pipes with a nominal outside diameter greater than 315 mm, a minimum free length of $(3d_n \pm 5)$ mm shall be used where practical; otherwise a minimum free length of greater than or equal to 1 000 mm shall be used.

SIST EN ISO 13479:1999

6.2 Notch location

<https://standards.iteh.ai/catalog/standards/sist/2cd6594b-adeb-4c46-b0d2-51385e80fc33/sist-en-iso-13479-1999>

Positions shall be marked for machining four notches equally spaced around the pipe circumference (see figure 1).

6.3 Machining the notches

6.3.1 If the wall thickness of the test piece is greater than 50 mm, the material shall be machined with a slot drill of 15 mm to 20 mm diameter to leave approximately 10 mm to be removed by the "V"-cutter used in accordance with 6.3.2.

6.3.2 Each notch shall be machined by climb milling to a depth so as to produce a pipe wall ligament of thickness between 0,78 and 0,82 times the minimum wall thickness, as specified in ISO 11922-1, for the diameter and pressure series of the pipe as shown in table 1 (see note). The ends of each notch shall be aligned circumferentially as shown in figures 1 and 2.

The length of each notch, at full depth, shall be equal to the pipe nominal outside diameter ± 1 mm. For pipes with a free length of pipe of less than $(3 d_n \pm 5)$ mm, the length of each notch, at full depth, shall be equal to the free length minus (500 ± 1) mm.

NOTE — To achieve a remaining ligament within the required tolerance range, it is advisable to aim for a remaining ligament at the top of the tolerance range. This is because the pipe wall can move due to release of residual stresses, resulting in a deeper than anticipated notch.

6.3.3 The test piece shall have end caps fitted which ensure that any longitudinal internal pressure load will act fully on the pipe (e.g. as shown for the type A arrangement in ISO 1167).

Table 1 — Remaining ligament thicknesses for pipe series

Dimensions in millimetres

Nominal outside diameter d_h	SDR6 S2,5		SDR7,4 S3,2		SDR9 S4		SDR11 S5		SDR13,6 S6,3		SDR17 S8		SDR17,6 S8,3		SDR21 S10		SDR26 S12,5		SDR33 S16		SDR41 S20	
	min.	max.	min.	max.	min.	max.	min.	max.	min.	max.	min.	max.	min.	max.	min.	max.	min.	max.	min.	max.	min.	max.
32	4,2	4,4																				
40	5,2	5,5	4,3	4,5																		
50	6,5	6,8	5,4	5,7	4,4	4,6																
63	8,2	8,6	6,7	7,1	5,5	5,8	4,5	4,8														
75	9,8	10,3	8,0	8,4	6,5	6,9	5,3	5,6	4,3	4,5												
90	11,7	12,3	9,6	10,1	7,9	8,3	6,4	6,7	5,1	5,4	4,2	4,4	4,0	4,2								
110	14,3	15,0	11,8	12,4	9,6	10,1	7,8	8,2	6,3	6,6	5,1	5,4	4,9	5,2	4,1	4,3						
125	16,2	17,1	13,3	14,0	10,9	11,5	8,9	9,3	7,2	7,5	5,8	6,1	5,5	5,8	4,7	4,9						
140	18,2	19,1	15,0	15,7	12,2	12,9	9,9	10,4	8,0	8,4	6,5	6,8	6,2	6,6	5,2	5,5	4,2	4,4				
160	20,7	21,8	17,1	18,0	14,0	14,7	11,4	12,0	9,2	9,7	7,4	7,8	7,1	7,5	6,0	6,3	4,8	5,1				
180	23,3	24,5	19,2	20,2	15,7	16,5	12,8	13,4	10,4	10,9	8,3	8,8	8,0	8,4	6,7	7,1	5,4	5,7				
200	25,9	27,2	21,4	22,5	17,5	18,4	14,2	14,9	11,5	12,1	9,3	9,8	8,9	9,3	7,5	7,9	6,0	6,3	4,3	4,5		
225	29,2	30,7	24,0	25,3	19,6	20,6	16,0	16,8	12,9	13,6	10,5	11,0	10,0	10,5	8,4	8,9	6,7	7,1	5,4	5,7	4,3	4,5
250	32,4	34,0	26,7	28,0	21,8	22,9	17,7	18,6	14,4	15,1	11,5	12,1	11,1	11,6	9,3	9,8	7,5	7,9	6,0	6,3	4,8	5,0
280	36,3	38,1	29,9	31,4	24,3	25,6	19,8	20,8	16,1	16,9	12,9	13,6	12,4	13,0	10,5	11,0	8,3	8,8	6,7	7,1	5,4	5,7
315	40,8	42,9	33,6	35,3	27,3	28,7	22,3	23,5	18,2	19,1	14,6	15,3	14,0	14,7	11,7	12,3	9,4	9,9	7,6	8,0	6,0	6,3
355	46,0	48,4	37,8	39,8	30,8	32,4	25,2	26,5	20,4	21,4	16,5	17,3	15,8	16,6	13,2	13,9	10,6	11,2	8,5	8,9	6,8	7,1
400			42,7	44,9	34,7	36,5	28,4	29,8	22,9	24,1	18,5	19,4	17,8	18,7	14,9	15,7	11,9	12,5	9,6	10,1	7,6	8,0
450			48,1	50,6	39,0	41,0	31,9	33,5	25,8	27,1	20,8	21,9	19,9	21,0	16,8	17,6	13,4	14,1	10,8	11,3	8,6	9,0
500					43,4	45,6	35,5	37,3	28,7	30,2	23,1	24,3	22,2	23,3	18,6	19,6	14,9	15,7	11,9	12,5	9,5	10,0
560							39,7	41,7	32,1	33,8	25,9	27,2	24,9	26,2	20,8	21,9	16,7	17,5	13,4	14,1	10,7	11,2
630							44,7	47,0	36,2	38,0	29,1	30,6	27,9	29,4	23,4	24,6	18,8	19,8	15,1	15,8	12,0	12,6
710									40,8	42,9	32,8	34,5	31,4	33,0	26,4	27,8	21,2	22,3	17,0	17,9	13,6	14,3
800									45,9	48,3	37,0	38,9	35,3	37,1	29,7	31,2	23,9	25,1	19,1	20,1	15,3	16,1
900											41,7	43,9	39,8	41,8	33,5	35,2	27,1	28,5	21,5	22,6	17,2	18,0
1 000											46,3	48,6	44,1	46,4	37,2	39,1	30,0	31,6	23,9	25,1	19,0	20,0
1 200														44,6	46,9	36,0	37,9	29,8	29,8	22,8	24,0	
1 400															42,0	44,2	42,0	44,2	33,1	34,8	26,7	28,0
1 600															48,0	50,4	48,0	50,4	37,8	39,8	30,5	32,1