



SLOVENSKI STANDARD
oSIST prEN ISO 11210:2016
01-junij-2016

Nakit - Določevanje platine v zlitinah za nakit iz platine - Gravimetrična metoda po obarjanju diamonijevega heksakloroplatinata (ISO 11210:2014)

Jewellery - Determination of platinum in platinum jewellery alloys - Gravimetric method after precipitation of diammonium hexachloroplatinate (ISO 11210:2014)

Schmuck - Bestimmung von Platin in Platin-Schmucklegierungen - Gravimetrische Bestimmung durch Fällung als Diammoniumhexachloroplatinat (ISO 11210:2014)

Joallerie, bijouterie - Dosage du platine dans les alliages de platine pour la bijouterie-joaillerie - Méthode gravimétrique après précipitation de l'hexachloroplatinate de diammonium (ISO 11210:2014)

Ta slovenski standard je istoveten z: prEN ISO 11210

ICS:

39.060

Nakit

Jewellery

oSIST prEN ISO 11210:2016

en

INTERNATIONAL STANDARD

**ISO
11210**

Second edition
2014-12-01

Jewellery — Determination of platinum in platinum jewellery alloys — Gravimetric method after precipitation of diammonium hexachloroplatinate

*Joannerie — Dosage du platine dans les alliages de platine pour la
bijouterie-joannerie — Méthode gravimétrique après précipitation de
l'hexachloroplatinate de diammonium*

iTeh STANDARDS (standards.iteh.ai)

SIST EN ISO 11210:2016

<https://standards.iteh.ai/catalog/standards/sist/7f6de3fa-61e3-46ad-860c-e1485bb622a1/sist-en-iso-11210-2016>



Reference number
ISO 11210:2014(E)

© ISO 2014

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 11210:2016

<https://standards.iteh.ai/catalog/standards/sist/7f6de3fa-61e3-46ad-860c-e1485bb622a1/sist-en-iso-11210-2016>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reagents	1
5 Apparatus	2
6 Sampling	2
7 Procedure	2
7.1 Platinum jewellery alloys with less than 5 % iridium, rhodium, ruthenium, or tungsten	2
7.2 Platinum jewellery alloys with more than 5 % iridium, rhodium, or ruthenium, or more than 0,5 % gold	3
8 Methods of calculation and expression of results	3
8.1 Calculation	3
8.2 Repeatability	4
9 Test report	4
Annex A (informative) Reduction apparatus according to Rose	5
Bibliography	6

IT-1 STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 11210:2016

<https://standards.iteh.ai/catalog/standards/sist/7f6de3fa-61e3-46ad-860c-e1485bb622a1/sist-en-iso-11210-2016>

ISO 11210:2014(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 174, *Jewellery*.

This second edition cancels and replaces the first edition (ISO 11210:1995), which has been technically revised with the following changes:

- addition of an analytical balance in [Clause 5](#);
- change of requirement for sampling in [Clause 6](#);
- addition in [7.1](#) to allow dissolution in a sealed container under pressure;
- addition in [7.1](#) to allow drying of the crucibles in a programmable furnace;
- deletion of the temperature for reduction in [7.1](#);
- International Standard editorially revised.

Introduction

The following definitions apply in understanding how to implement an ISO International Standard and other normative ISO deliverables (TS, PAS, IWA).

- “shall” indicates a requirement
- “should” indicates a recommendation
- “may” is used to indicate that something is permitted
- “can” is used to indicate that something is possible, for example, that an organization or individual is able to do something

ISO/IEC Directives, Part 2 (sixth edition, 2011), 3.3.1 defines a requirement as an “expression in the content of a document conveying criteria to be fulfilled if compliance with the document is to be claimed and from which no deviation is permitted.”

ISO/IEC Directives, Part 2 (sixth edition, 2011), 3.3.2 defines a recommendation as an “expression in the content of a document conveying that among several possibilities, one is recommended as particularly suitable, without mentioning or excluding others, or that a certain course of action is preferred but not necessarily required, or that (in the negative form) a certain possibility or course of action is deprecated but not prohibited.”

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 11210:2016

<https://standards.iteh.ai/catalog/standards/sist/7f6de3fa-61e3-46ad-860c-e1485bb622a1/sist-en-iso-11210-2016>

Jewellery — Determination of platinum in platinum jewellery alloys — Gravimetric method after precipitation of diammonium hexachloroplatinate

1 Scope

This International Standard specifies a gravimetric method for the determination of platinum in platinum jewellery alloys, preferably within the range of fineness stated in ISO 9202.

These alloys can contain palladium, iridium, rhodium, copper, cobalt, gold, ruthenium, gallium, chromium, indium, and less than 5 % tungsten. Some modifications are indicated where palladium, iridium, rhodium, gold, or ruthenium are present.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11596, *Jewellery — Sampling of precious metal alloys for and in jewellery and associated products*

3 Principle

The sample is dissolved in aqua regia. After converting the sample solution to a slightly acid medium, the platinum is precipitated as diammonium hexachloroplatinate. The precipitate is converted to metallic platinum. Coprecipitated alloying elements are tested in the re-dissolved platinum sponge and measured using, for example, an atomic absorption spectrometer (AAS) or an inductively coupled plasma optical emission spectrometer (ICP-OES), and a correction applied.

4 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

4.1 Hydrochloric acid (HCl), approximately 30 % to 37 % HCl (mass fraction).

4.2 Dilute hydrochloric acid, 18 % HCl (mass fraction).

4.3 Nitric acid (HNO₃), approximately 65 % to 69 % HNO₃ (mass fraction).

4.4 Ammonium chloride solution (NH₄Cl), cold saturated solution.

4.5 Reducing gas, such as hydrogen or a hydrogen/nitrogen mixture.

4.6 Inert gas, such as carbon dioxide or nitrogen.

4.7 Aqua regia, mix three volumes of hydrochloric acid ([4.1](#)) and one volume of nitric acid ([4.3](#)).

ISO 11210:2014(E)

5 Apparatus

- 5.1 Ordinary laboratory apparatus.
- 5.2 Reduction apparatus, see [Figure A.1](#).
- 5.3 AAS or ICP-OES, capable of determining traces of metals.
- 5.4 Muffle furnace, capable of attaining at least 1 000 °C.
- 5.5 Ashless filter paper, capable of retaining 3 µm particles.
- 5.6 Analytical balance, with a reading accuracy of 0,01 mg.

6 Sampling

The sampling procedure shall be performed in accordance with ISO 11596.

7 Procedure

WARNING — Suitable health and safety procedures should be followed.

7.1 Platinum jewellery alloys with less than 5 % iridium, rhodium, ruthenium, or tungsten

Weigh the sample containing approximately 250 mg to 300 mg of platinum, accurately to the nearest 0,01 mg, and transfer it to a 100 ml glass beaker. Dissolve the sample in 20 ml of aqua regia ([4.7](#)) in the glass beaker covered with a watch glass, while heating gently, or in a sealed container under pressure.

Any insoluble material remaining after this procedure shall be filtered off at this stage and its composition established for possible correction of the results.

Evaporate the solution five times without letting the residue become dry and without exceeding a temperature of 90 °C, each time adding 2 ml of dilute hydrochloric acid ([4.2](#)) before recommencing evaporation.

If this temperature is exceeded, the platinum can be reduced to Pt(II) or even Pt(I) and require re-oxidation with approximately 0,1 ml of nitric acid ([4.3](#)). After the last evaporation, dissolve the still moist platinum salt in 1 ml of dilute hydrochloric acid ([4.2](#)) and add 4 ml of water. Add 40 ml of saturated ammonium chloride solution ([4.4](#)) at (85 ± 5) °C to this clear solution. The platinum is precipitated as yellow $(\text{NH}_4)_2[\text{PtCl}_6]$. The solution with the precipitated $(\text{NH}_4)_2[\text{PtCl}_6]$ is evaporated almost to dryness at this temperature. Further gentle heating shall continue until hydrogen chloride is no longer emitted. Allow to cool. Add just sufficient water while agitating to dissolve the residual ammonium chloride crystals.

Immediately filter the $(\text{NH}_4)_2[\text{PtCl}_6]$ precipitate over a filter paper ([5.5](#)) which has been moistened with ammonium chloride solution ([4.4](#)). Thoroughly wash the precipitate with ammonium chloride solution. Wipe the glass beaker and watch glass with a second filter paper. Check the filtrate for residual platinum by suitable means, such as an AAS or ICP-OES ([5.2](#)).

The filter paper containing the precipitate is folded into the second one, transferred to a porcelain crucible and covered with a thin layer (2 mm) of ammonium chloride. This crucible is then placed inside a covered crucible. Cautiously dry the contents of the crucibles on a hotplate which can be gradually adjusted or in a programmable furnace. By drying initially at 50 °C to 70 °C and heating subsequently to 340 °C, all ammonium chloride is lost. Ash the filter paper ([5.5](#)) and $(\text{NH}_4)_2[\text{PtCl}_6]$ residue at a temperature of 500 °C to 600 °C without a flame. Finally, remove the cover of the crucible and calcine in a muffle furnace