

SLOVENSKI STANDARD

SIST EN ISO 13760:1999

01-julij-1999

Dc`ja YfbYWWj]nUlfUbgdcfhZi]Xcj `dcX'hU_ca 'l'A]bYfYj c`dfUj]c`fA'5 "A]bYfL!
FU i bg_Ua YlcXU'nU_i a i `Uhj Yb'i]bY`dcy_cXV

Plastics pipes for the conveyance of fluids under pressure - Miner's rule - Calculation method for cumulative damage (ISO 13760:1998)

Kunststoffrohre für den Transport von Fluiden unter Druck - Minersche Regel - Berechnungsverfahren für kumulative Schädigungen (ISO 13760:1998)

STANDARD REVIEW

(standards.iteh.ai)

Tubes en matieres plastiques pour le transport des fluides sous pression - Regle de Miner - Méthode de calcul du cumul des dommages (ISO 13760:1998)

<https://standards.iteh.ai/catalog/standards/sist/3a043eea-733c-4f19-bddf-5090e102baa7/sist-en-iso-13760-1999>

Ta slovenski standard je istoveten z: EN ISO 13760:1998

ICS:

23.040.20 Cevi iz polimernih materialov Plastics pipes

SIST EN ISO 13760:1999

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 13760:1999

<https://standards.iteh.ai/catalog/standards/sist/3a043eea-733c-4f19-bddf-5090e102baa7/sist-en-iso-13760-1999>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 13760

May 1998

ICS 23.040.00

Descriptors: see ISO document

English version

Plastics pipes for the conveyance of fluids under pressure -
Miner's rule - Calculation method for cumulative damage (ISO
13760:1998)

Tubes en matières plastiques pour le transport des fluides
sous pression - Règle de Miner - Méthode de calcul du
cumul des dommages (ISO 13760:1998)

Kunststoffrohre für den Transport von Flüssigkeiten unter Druck -
Minersche Regel - Berechnungsverfahren für kumulative
Schädigungen (ISO 13760:1998)

This European Standard was approved by CEN on 13 May 1998.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.
<https://standards-jean-avocat.org/standard/sist-en-iso-13760-1998>
 5090e102baa7/sist-en-iso-13760-1999



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITÉ FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
EN ISO 13760:1998

Foreword

The text of the International Standard ISO 13760:1998 has been prepared by Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids" in collaboration with Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1998, and conflicting national standards shall be withdrawn at the latest by November 1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

NOTE FROM CEN/CS: The foreword is susceptible to be amended on reception of the German language version. The confirmed or amended foreword, and when appropriate, the normative annex ZA for the references to international publications with their relevant European publications will be circulated with the German version.


iTeh STANDARD REVIEW

Endorsement notice

The text of the International Standard ISO 13760:1998 was approved by CEN as a European Standard without any modification.

[SIST EN ISO 13760:1999](#)

<https://standards.iteh.ai/catalog/standards/sist/3a043eea-733c-4f19-bdd5-5090e102baa7/sist-en-iso-13760-1999>



INTERNATIONAL STANDARD

ISO
13760

First edition
1998-05-15

Plastics pipes for the conveyance of fluids under pressure — Miner's rule — Calculation method for cumulative damage

*Tubes en matières plastiques pour le transport des fluides sous pression —
Règle de Miner — Méthode de calcul du cumul des dommages*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 13760:1999](#)
<https://standards.iteh.ai/catalog/standards/sist/3a043eea-733c-4f19-bddf-5090e102baa7/sist-en-iso-13760-1999>



Reference number
ISO 13760:1998(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

iTeh STANDARD PREVIEW

International Standard ISO 13760 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories* — ~~Test methods and basic specifications~~

<https://standards.iteh.ai/catalog/standards/sist/3a043eea-733c-4f19-bddf-5090e102baa7/sist-en-iso-13760-1999>

Annexes A, B and C of this International Standard are for information only.

© ISO 1998

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet iso@iso.ch
Printed in Switzerland

Plastics pipes for the conveyance of fluids under pressure — Miner's rule — Calculation method for cumulative damage

1 Scope

This International Standard specifies a method for calculating the maximum allowable hoop stress applicable to pipes exposed to varying internal pressures and/or temperatures during their expected lifetime. This method is generally known as Miner's rule.

It is necessary to apply Miner's rule to each failure mechanism separately. Thus, for mechanical failure due to internal pressure, other failure mechanisms, such as oxidative or dehydrochlorinative degradative failure mechanisms, are to be neglected (assuming, of course, no interaction). A material may be used only when it is proven to conform to all failure mechanism criteria.

iTeh STANDARD PREVIEW

NOTE — Miner's rule is an empirically based procedure, and is only a first approximation to reality.
(standards.iteh.ai)

2 Normative reference

[SIST EN ISO 13760:1999](https://standards.iteh.ai/catalog/standards/sist/3a043eea-733c-4f19-bddf)

The following standard contains provisions which, through reference in this text, constitute provisions of this International Standard. At the time of the publication, the edition indicated was valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent edition of the standard indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 10508:1995, *Thermoplastics pipes and fittings for hot and cold water systems*.

3 Symbols and abbreviated terms

For the purposes of this International Standard, the following symbols and abbreviations apply:

- a_i fraction of a year, expressed as a percentage, when referring to set of conditions " i ";
- t_i lifetime under a specified set of conditions " i " ($i = 1, 2, 3$, etc.) expressed in years;
- t_m lifetime at malfunction temperature T_m as defined in ISO 10508;
- t_{\max} lifetime at maximum operating temperature T_{\max} as defined in ISO 10508;
- t_0 lifetime at operating temperature T_0 as defined in ISO 10508;
- t_x maximum permissible time of use under varying conditions, expressed in years;
- TYD total yearly damage, expressed as a percentage.

4 Principle

Miner's rule is based on the following assumptions:

- a) The total damage a material or product is allowed to suffer from a certain type of attack is constant (100 %).
- b) Under constant conditions, the damage done is proportional to the duration of the attack. The material or product will last till the 100 % damage level has been reached. The time needed for this is called t_i , in this context expressed in years. Per year, the amount of damage done is $\frac{100}{t_i}$ %.

This is the **proportionality rule**.

NOTE — The amount of damage is not necessarily visible or measurable; it may, e.g., also be the passing of an induction time.

- c) If a material is exposed to attack for only part of a year (say a_i % of the year, instead of 100 % of the year), the yearly damage is not $\frac{100}{t_i}$ % but $\frac{a_i}{t_i}$ %. This follows from the proportionality rule.
- d) In the case of damage of the same type but under various sets of conditions (differing severity, temperature, pressure, stress, etc.), one after the other, the total damage per year will be the combined effect of the various sets of conditions. The **additivity rule** states that the separate amounts of damage may be added. The result is the **cumulative damage** under varying conditions.

5 Procedure

iTeh STANDARD PREVIEW (standards.iteh.ai)

Calculate the total yearly damage (TYD) using the following equation:

$$TYD = \sum \frac{a_i}{t_i} \quad \begin{matrix} \text{SIST EN ISO 13760:1999} \\ \text{https://standards.iteh.ai/catalog/standards/sist/3a043eea-733c-4f19-bddc-} \\ \text{5090e102baa7/sist-en-iso-13760-1999} \end{matrix} \quad (1)$$

expressed as a percentage of the total permissible damage.

Calculate the maximum permissible time of use t_x , in years, using the following equation:

$$t_x = \frac{100}{TYD} \quad (2)$$

NOTE — See annex A for example calculations and annex B for the assessment of oxidative stability.

Annex A

(informative)

Examples of the use of Miner's rule

A.1 Example of varying conditions

An illustrative example is provided by the calculation of the expected service life of hot-water pipes, viz: class 2 as defined in ISO 10508.

This International Standard specifies, during a 50-year service life, a temperature profile consisting of 49 years at the standard operating temperature T_0 of 70 °C, 1 year at the maximum operating temperature T_{max} of 80 °C and 100 h at the malfunction temperature T_m of 95 °C to allow for heater control faults.

To derive the proper wall thickness (or rather the ratio SDR, i.e. the diameter/wall thickness ratio), it is necessary to know the maximum permissible hoop stress in the pipe wall that will withstand the given conditions. However, the proposed class specifications state that, in the case of polybutylene for instance, a safety factor of 1,5 is to be applied to the stress at T_0 , a safety factor of 1,3 to the stress at T_{max} and a safety factor of 1,0 to the stress at T_m (this already being a safety factor in itself).

For the actual calculation, an educated guess is made of the acceptable design stress σ and the expected lifetime t_0 determined when the pipe is exposed continuously to $1,5 \times \sigma$ and a temperature T_0 of 70 °C, and likewise t_{max} determined at $1,3 \times \sigma$ and $T_{\text{max}} = 80$ °C and t_m at σ and $T_m = 95$ °C.

These expected lifetimes t_i are determined graphically or calculated from equations such as those given in ISO/TR 9080.

The factors a_i are 98 %, 2 % and 0,022 8 %, respectively. Substituting these and the values for t_i (the subscript "i" standing for the three components of the temperature curve) in equation (1) yields the TYD.

5090e102baa7/sist-en-iso-13760-1999

The maximum time that the pipe may be used is given by $t_x = \frac{100}{\text{TYD}}$ years.

If this time t_x is higher or lower than required (in this case 50 years), the operating stress σ may be chosen to be higher or lower. Selection of a new operating stress requires a complete recalculation, until by successive approximations the correct value of t_x has been found.

The practice of successive approximations is most easily carried out with a computer. A spreadsheet is a convenient tool, especially when the expected failure times at different temperatures and hoop stresses can be calculated with a model, such as that used in ISO/TR 9080.

$$\lg t = A + \frac{B}{T} \lg \sigma + \frac{C}{T} + D \lg \sigma$$

Using the coefficients that describe $\lg t$ as a function of σ and T , a spreadsheet algorithm will easily give t_x as a function of σ .

A.2 Example of an actual calculation

Using for an actual calculation the hoop stress data for polybutylene pipes (ISO 1167 and ISO 12230), start with e.g. $\sigma = 5,0$ MPa and change this value to a higher one if the resulting time t_x is too long, and vice versa. The values for t (t_0 , t_{max} and t_m) are obtained using the equations given in ISO 12230. The calculation is carried out using hours as the unit of time because that is the normal unit in hoop stress diagrams. The final result is converted into years.